

P.O.NO-28100320

313002-03 m.Boddy
313003-03 Corp



TC-1676



Unitech Laboratories Services LLP
16, Samrat Industrial Area, B/h. S. T. Workshop
Gondal Road, Rajkot - 360 004, Gujarat, INDIA
M+91 84600 60450, 99742 01090, 79901 74169
E unitech_lab@yahoo.com


You can always trust on our accuracy.

TEST REPORT

ULR -TC161762500080278F

Name of the Customer : METAL MECH ENGINEERING.		Lab No. : US/4472/0725
Plot No. 4246, Road E, GIDC Phase-III, Dared, Jamnagar(Guj.) INDIA		Date of Reporting : 31/07/2025 Date of Smp. Receipt : 31/07/2025
Group : Chemical Testing of Metals and Alloys		
Sub Group : Stainless Steel		
#Customer Reference No. : Letter Date-31/07/2025		
Condition of Sample : Cut Piece		
Material Specification : ASTM A276/A276M-24a Gr. 316L(S31603)		
#Identification of Sample : Size : 46.00 MM HEX		
#Type of Test : Chemical Analysis		
Instrument Utilized : Optical Emission Spectrometer-Bruker- German make-Q4 TASMAN		
Date of Testing : 31/07/2025		
Test Method : ASTM E1086-22, JIS G-1253-2002		
ELEMENTS	OBSERVATION	REQUIRED VALUE
% CARBON	0.014	0.03 max
% SILICON	0.488	1.00 max
% MANGANESE	1.670	2.00 max
% PHOSPHORUS	0.038	0.045 max
% SULFUR	0.005	0.030 max
% CHROMIUM	16.506	16.00-18.00
% MOLYBDENUM	2.063	2.00-3.00
% NICKEL	10.260	10.00-14.00
Conformity statement : The above result is conform to ASTM A276/A276M-24a Gr. 316L(S31603)		

End of Report



Authorized signatory:
Deepak Solanki
(Quality Manager)

Tested By :
Jaimini Vadodariya
(Technician)

Note : (1) Sample(s) not drawn by ULS. The results relate only to the sample(s) tested.
(2) This certificate shall not be reproduced, except in full, without the written approval of ULS.
(3) If balance material is available after testing, it will be retained for 15 days maximum. If customer wants to retain it for one month from this date, he has to inform in writing or he can collect the same.
(4) While "ULS" has made their best endeavors to provide accurate and reliable information.
(5) The conformity statement is given bases of decision rule documented in Quality Manual Annexure-3. "I" Information Given by Customer

