

Bansidhar Metals

Plot No. 16, R.S. NO - 89, Near-G.I.D.C., Phase-III, Beside Mahavir Circle, Vi. kansumara, Jamnagar.-361004

GSTIN : 24AAUFB1285E1ZG

EMAIL : bansidharmetals16@gmail.com

MOB. No. 9824080410


Test Certificate

Customer :	MTC No.	1432	Date :	27-02-2026
MetalMech Engineering Jamanagar GIDC Phase III Road E Plot No 4246 ,Jamnagar ,Gujrat,	Invoice No .	1300/25-26		
	Po.No	EX-PO25/25100984		
	Qty.Kgs	495.700		

Particular	As Required By Specification	Specification Of Supplied Material				
I. Chemical Composition	EN 12164 CW614N CuZn39Pb3	Size	Size	Size	Size	Size
		68.00 X 54.00 MM ROUND	70.00 X 48.00 MM HEX	85.00 X 70.00 MM HEX	74.00 X 54.00 MM HEX	
		HEAT NO.	HEAT NO.	HEAT NO.	HEAT NO.	
		4	4	4	4	
1. COPPER (Cu) %	57.00 - 59.00	57.60	57.60	57.60	57.60	
2. LEAD (Pb) %	2.50 - 3.50	2.94	2.94	2.94	2.94	
3. IRON (Fe)%	0.30 Max	0.28	0.28	0.28	0.28	
4. ZINC (Zn) %	Remainder	38.73	38.73	38.73	38.73	
5. ALUMINIUM (Al)%	0.05 Max	0	0	0	0	
6. MANGANESE (Mn)%	-	-	-	-	-	
7. NICKLE (Ni)%	0.30 Max	0.13	0.13	0.13	0.13	
8. TIN (Sn)%	0.30 Max	0.25	0.25	0.25	0.25	
9. SILICON (Si)%	-	-	-	-	-	
10. PHOSPHORUS (P)%	-	-	-	-	-	
11. SULPHAR (S) %	-	-	-	-	-	
12. TOTAL IMPURITIES %	0.20 Max	0.07	0.07	0.07	0.07	

1. UTS- MIIN (Mpa)	360 MIN	366	366	366	366	
2. ELONGATION %	20 MIN	24	24	24	24	
3. HARDNESS (HV5)	-	-	-	-	-	
4. IZOD	-	-	-	-	-	
5. 0.2% PROOF STRESS	350 MAX	340	340	340	340	

1. CONDUCTIVITY	-					
-----------------	---	--	--	--	--	--



For Banshidhar Metal

