

Bansidhar Metals

Plot No. 16, R.S. NO - 89, Near-G.I.D.C., Phase-III, Beside Mahavir Circle, Vi. kansumara, Jamnagar.-361004

GSTIN : 24AAUFB1285E1ZG

EMAIL : bansidharmetals16@gmail.com

MOB. No. 9824080410

Test Certificate

Customer :	MTC No.	54	Date :	16-04-2026
MetalMech Engineering Jamanagar GIDC Phase III Road E Plot No 4246 ,Jamnagar ,Gujrat,	Invoice No .	60/2026-27		
	Po.No	EX-PO26/26100020		
	Qty.Kgs	1103.550		

Particular	As Required By Specification	Specification Of Supplied Material				
1. Chemical Composition	EN 12164 CW614N CuZn39Pb3	Size	Size	Size	Size	Size
		74.00 X 54.00 MM HEX	80.00 X 64.00 MM HEX	77.00 X 61.00 MM ROUND	26.00 X 15.00 MM HEX	42.00 X 24.00 MM HEX
		HEAT NO.	HEAT NO.	HEAT NO.	HEAT NO.	HEAT NO.
		2	2	2	2	2
1. COPPER (Cu) %	57.00 - 59.00	57.83	57.83	57.83	57.83	57.83
2. LEAD (Pb) %	2.50 - 3.50	2.93	2.93	2.93	2.93	2.93
3. IRON (Fe)%	0.30 Max	0.28	0.28	0.28	0.28	0.28
4. ZINC (Zn) %	Remainder	38.22	38.22	38.22	38.22	38.22
5. ALUMINIUM (Al)%	0.05 Max	0	0	0	0	0
6. MANGANESE (Mn)%	-	-	-	-	-	-
7. NICKLE (Ni)%	0.30 Max	0.27	0.27	0.27	0.27	0.27
8. TIN (Sn)%	0.30 Max	0.29	0.29	0.29	0.29	0.29
9. SILICON (Si)%	-	-	-	-	-	-
10. PHOSPHORUS (P)%	-	-	-	-	-	-
11. SULPHAR (S) %	-	-	-	-	-	-
12. TOTAL IMPURITIES %	0.20 Max	0.18	0.18	0.18	0.18	0.18

1. UTS- MIIN (Mpa)	360 MIN	363	363	363	363	363
2. ELONGATION %	20 MIN	25	25	25	25	25
3. HARDNESS (HV5)	-	-	-	-	-	-
4. IZOD	-	-	-	-	-	-
5. 0.2% PROOF STRESS	350 MAX	336	336	336	336	336

1. CONDUCTIVITY

-



For Banshidhar Metal



Authorised Signature

Bansidhar Metals

Plot No. 16, R.S. NO - 89, Near-G.I.D.C., Phase-III, Beside Mahavir Circle, Vi. kansumara, Jamnagar.-361004

GSTIN : 24AAUFB1285E1ZG

EMAIL : bansidharmetals16@gmail.com

MOB. No. 9824080410

Test Certificate

Customer :	MTC No.	54	Date :	16-04-2026
MetalMech Engineering Jamanagar GIDC Phase III Road E Plot No 4246 ,Jamnagar ,Gujrat,	Invoice No .	60/2026-27		
	Po.No	EX-PO26/26100020		
	Qty.Kgs	393.450		

Particular	As Required By Specification	Specification Of Supplied Material				
I. Chemical Composition	EN 12164 CW614N CuZn39Pb3	Size	Size	Size	Size	Size
		36.00 X 24.00 MM HEX				
		HEAT NO.				
		2				
1. COPPER (Cu) %	57.00 - 59.00	57.83				
2. LEAD (Pb) %	2.50 - 3.50	2.93				
3. IRON (Fe)%	0.30 Max	0.28				
4. ZINC (Zn) %	Remainder	38.22				
5. ALUMINIUM (Al)%	0.05 Max	0				
6. MANGANESE (Mn)%	-	-				
7. NICKLE (Ni)%	0.30 Max	0.27				
8. TIN (Sn)%	0.30 Max	0.29				
9. SILICON (Si)%	-	-				
10. PHOSPHORUS (P)%	-	-				
11. SULPHAR (S) %	-	-				
12. TOTAL IMPURITIES %	0.20 Max	0.18				
1. UTS- MIIN (Mpa)	360 MIN	363				
2. ELONGATION %	20 MIN	25				
3. HARDNESS (HV5)	-	-				
4. IZOD	-	-				
5. 0.2% PROOF STRESS	350 MAX	336				
1. CONDUCTIVITY	-					



For Banshidhar Metal



Authorised Signature