

Bansidhar Metals

Plot No. 16, R.S. NO - 89, Near-G.I.D.C., Phase-III, Beside Mahavir Circle, Vi. kansumara, Jamnagar.-361004

GSTIN : 24AAUFB1285E1ZG

EMAIL : bansidharmetals16@gmail.com

MOB. No. 9824080410

Test Certificate

Customer :	MTC No.	610	Date :	18-07-2026
METALMECH ENGINEERING R/S NO. 580, PLOT NO.1, NEAR BHARAT PETROLEUM, SASOI DAM ROAD, KHOJABERAJA, JAMNAGAR - 361012	Invoice No .	504/2026-27		
	Po.No	EX-PO26/26100279		
	Qty.Kgs	2788.400		

Particular	As Required By Specification	Specification Of Supplied Material				
1. Chemical Composition	EN 12164 CW614N CuZn39Pb3	Size	Size	Size	Size	Size
		25.00 X 14.00 MM HEX	25.00 X 17.00 MM HEX	25.00 MM HEX	20.00 MM ROUND	18.50 MM ROUND
		HEAT NO. 3	HEAT NO. 3	HEAT NO. 3	HEAT NO. 3	HEAT NO. 3
1. COPPER (Cu) %	57.00 - 59.00	57.90	57.90	57.90	57.90	57.90
2. LEAD (Pb) %	2.50 - 3.50	2.79	2.79	2.79	2.79	2.79
3. IRON (Fe) %	0.30 Max	0.26	0.26	0.26	0.26	0.26
4. ZINC (Zn) %	Remainder	38.37	38.37	38.37	38.37	38.37
5. ALUMINIUM (Al) %	0.05 Max	0	0	0	0	0
6. MANGANESE (Mn) %	-	-	-	-	-	-
7. NICKLE (Ni) %	0.30 Max	0.23	0.23	0.23	0.23	0.23
8. TIN (Sn) %	0.30 Max	0.29	0.29	0.29	0.29	0.29
9. SILICON (Si) %	-	-	-	-	-	-
10. PHOSPHORUS (P) %	-	-	-	-	-	-
11. SULPHAR (S) %	-	-	-	-	-	-
12. TOTAL IMPURITIES %	0.20 Max	0.16	0.16	0.16	0.16	0.16

1. UTS- MIIN (Mpa)	360 MIN	366	366	366	366	366
2. ELONGATION %	20 MIN	23	23	23	23	23
3. HARDNESS (HV5)	-	-	-	-	-	-
4. IZOD	-	-	-	-	-	-
5. 0.2% PROOF STRESS	350 MAX	339	339	339	339	339

1. CONDUCTIVITY	-					
-----------------	---	--	--	--	--	--



For Banshidhar Metal

Signature
BANSIDHAR METALS
PARTNER

Authorised Signature