

Bansidhar Metals

Plot No. 16, R.S. NO - 89, Near-G.I.D.C., Phase-III, Beside Mahavir Circle, Vi. kansumara, Jamnagar.-361004

GSTIN : 24AAUFB1285E1ZG

EMAIL : bansidharmetals16@gmail.com

MOB. No. 9824080410


Test Certificate

Customer :	MTC No.	471	Date :	29-06-2026
METALMECH ENGINEERING R/S NO. 580, PLOT NO.1, NEAR BHARAT PETROLEUM, SASOI DAM ROAD, KHOJABERAJA, JAMNAGAR - 361012	Invoice No .	401/2026-27		
	Po.No	EX-PO26/26100222		
	Qty.Kgs	1192.750		

Particular	As Required By Specification	Specification Of Supplied Material				
		Size	Size	Size	Size	Size
I. Chemical Composition	EN 12164 CW614N CuZn39Pb3	35.50 X 24.00 MM ROUND	42.00 X 24.00 MM HEX	42.00 X 30.00 MM HEX		
		HEAT NO.	HEAT NO.	HEAT NO.		
		3	3	3		
1. COPPER (Cu) %	57.00 - 59.00	57.90	57.90	57.90		
2. LEAD (Pb) %	2.50 - 3.50	2.96	2.96	2.96		
3. IRON (Fe) %	0.30 Max	0.27	0.27	0.27		
4. ZINC (Zn) %	Remainder	38.23	38.23	38.23		
5. ALUMINIUM (Al) %	0.05 Max	0	0	0		
6. MANGANESE (Mn) %	-	-	-	-		
7. NICKLE (Ni) %	0.30 Max	0.21	0.21	0.21		
8. TIN (Sn) %	0.30 Max	0.26	0.26	0.26		
9. SILICON (Si) %	-	-	-	-		
10. PHOSPHORUS (P) %	-	-	-	-		
11. SULPHAR (S) %	-	-	-	-		
12. TOTAL IMPURITIES %	0.20 Max	0.17	0.17	0.17		
1. UTS- MIIN (Mpa)	360 MIN	366	366	366		
2. ELONGATION %	20 MIN	23	23	23		
3. HARDNESS (HV5)	-	-	-	-		
4. IZOD	-	-	-	-		
5. 0.2% PROOF STRESS	350 MAX	337	337	337		
1. CONDUCTIVITY	-					



For Banshidhar Metal



Authorised Signature