

Bansidhar Metals

Plot No. 16, R.S. NO - 89, Near-G.I.D.C., Phase-III, Beside Mahavir Circle, Vi. kansumara, Jamnagar.-361004

GSTIN : 24AAUFB1285E1ZG

EMAIL : bansidharmetals16@gmail.com

MOB. No. 9824080410

Test Certificate

Customer :		MTC No.	577	Date :	13-07-2026
METALMECH ENGINEERING R/S NO. 580, PLOT NO.1, NEAR BHARAT PETROLEUM, SASOI DAM ROAD, KHOJABERAJA, JAMNAGAR - 361012	Invoice No .		482/2026-27		
	Po.No		EX-PO26/26100271		
	Qty.Kgs		1587.800		

Particular	As Required By Specification	Specification Of Supplied Material				
1. Chemical Composition	EN 12164 CW614N CuZn39Pb3	Size	Size	Size	Size	Size
		31.00 X 19.00 MM HEX	31.00 X 22.00 MM HEX	23.00 MM ROUND SOLID		
		HEAT NO.	HEAT NO.	HEAT NO.		
		3	3	3		
1. COPPER (Cu) %	57.00 - 59.00	57.80	57.80	57.80		
2. LEAD (Pb) %	2.50 - 3.50	3.02	3.02	3.02		
3. IRON (Fe) %	0.30 Max	0.26	0.26	0.26		
4. ZINC (Zn) %	Remainder	38.23	38.23	38.23		
5. ALUMINIUM (Al) %	0.05 Max	0	0	0		
6. MANGANESE (Mn) %	-	-	-	-		
7. NICKLE (Ni) %	0.30 Max	0.22	0.22	0.22		
8. TIN (Sn) %	0.30 Max	0.27	0.27	0.27		
9. SILICON (Si) %	-	-	-	-		
10. PHOSPHORUS (P) %	-	-	-	-		
11. SULPHAR (S) %	-	-	-	-		
12. TOTAL IMPURITIES %	0.20 Max	0.20	0.20	0.20		

1. UTS- MIN (Mpa)	360 MIN	366	366	366		
2. ELONGATION %	20 MIN	22	22	22		
3. HARDNESS (HV5)	-	-	-	-		
4. IZOD	-	-	-	-		
5. 0.2% PROOF STRESS	350 MAX	340	340	340		

1. CONDUCTIVITY	-					
-----------------	---	--	--	--	--	--



For Banshidhar Metal



Authorised Signature