

# Bansidhar Metals

Plot No. 16, R.S. NO - 89, Near-G.I.D.C., Phase-III, Beside Mahavir Circle, Vi. kansumara, Jamnagar.-361004

GSTIN : 24AAUFB1285E1ZG

EMAIL : bansidharmetals16@gmail.com

MOB. No. 9824080410

## Test Certificate

|                                                                                                |              |         |                  |        |            |
|------------------------------------------------------------------------------------------------|--------------|---------|------------------|--------|------------|
| Customer :                                                                                     |              | MTC No. | 981              | Date : | 21-11-2025 |
| MetalMech Engineering<br>Jamanagar<br>GIDC Phase III Road E Plot No<br>4246 ,Jamnagar ,Gujrat, | Invoice No . |         | 940/2025-26      |        |            |
|                                                                                                | Po.No        |         | EX-PO25/25100744 |        |            |
|                                                                                                | Qty.Kgs      |         | 799.400          |        |            |

| Particular              | As Required By<br>Specification | Specification Of Supplied Material |                         |                            |                         |      |
|-------------------------|---------------------------------|------------------------------------|-------------------------|----------------------------|-------------------------|------|
| I. Chemical Composition | EN 12164<br>CW614N<br>CuZn39Pb3 | Size                               | Size                    | Size                       | Size                    | Size |
|                         |                                 | 45.00 MM HEX                       | 30.00 X 18.00<br>MM HEX | 36.00 X<br>18.00 MM<br>HEX | 50.00 X 32.00<br>MM HEX |      |
|                         |                                 | HEAT NO.                           | HEAT NO.                | HEAT NO.                   | HEAT NO.                |      |
|                         |                                 | 4                                  | 4                       | 4                          | 4                       |      |
| 1. COPPER (Cu) %        | 57.00 - 59.00                   | 57.90                              | 57.90                   | 57.90                      | 57.90                   |      |
| 2. LEAD (Pb) %          | 2.50 - 3.50                     | 2.90                               | 2.90                    | 2.90                       | 2.90                    |      |
| 3. IRON (Fe)%           | 0.30 Max                        | 0.26                               | 0.26                    | 0.26                       | 0.26                    |      |
| 4. ZINC (Zn) %          | Remainder                       | 38.36                              | 38.36                   | 38.36                      | 38.36                   |      |
| 5. ALUMINIUM (Al)%      | 0.05 Max                        | 0                                  | 0                       | 0                          | 0                       |      |
| 6. MANGANESE (Mn)%      | -                               | -                                  | -                       | -                          | -                       |      |
| 7. NICKLE (Ni)%         | 0.30 Max                        | 0.21                               | 0.21                    | 0.21                       | 0.21                    |      |
| 8. TIN (Sn)%            | 0.30 Max                        | 0.27                               | 0.27                    | 0.27                       | 0.27                    |      |
| 9. SILICON (Si)%        | -                               | -                                  | -                       | -                          | -                       |      |
| 10. PHOSPHORUS (P)%     | -                               | -                                  | -                       | -                          | -                       |      |
| 11. SULPHAR (S) %       | -                               | -                                  | -                       | -                          | -                       |      |
| 12. TOTAL IMPURITIES %  | 0.20 Max                        | 0.10                               | 0.10                    | 0.10                       | 0.10                    |      |
| 1. UTS- MIIN (Mpa)      | 360 MIN                         | 366                                | 366                     | 366                        | 366                     |      |
| 2. ELONGATION %         | 20 MIN                          | 24                                 | 24                      | 24                         | 24                      |      |
| 3. HARDNESS (HV5)       | -                               | -                                  | -                       | -                          | -                       |      |
| 4. IZOD                 | -                               | -                                  | -                       | -                          | -                       |      |
| 5. 0.2% PROOF STRESS    | 350 MAX                         | 345                                | 345                     | 345                        | 345                     |      |
| 1. CONDUCTIVITY         | -                               |                                    |                         |                            |                         |      |

For Banshidhar Metal

