



AMAR ENTERPRISE

Aarti Society, Street no-2, Opp. Parsana Industries, 80 Feet Road,
Dhebar Road, Rajkot-360002 Mo.9824172426, Gst No-24ANDPR2565D1Z6

ULR - TC457221000001104F

Issued to : M/s METALMECH ENGINEERING.,
Plot No.4246, Road Edared Phase-3,
G.I.D.C., Jamnagar-361004

Test Report No : MAEON/0322/234
Date : 30-03-2022

Contact Person: Mr. Gaurav Kothari

Page 1 of 1

Name of the sample	Silicon Rubber			
Batch No	NA	Date of Receipt	10-03-2022	
Type	Slab & Button	Test Start Date	21-03-2022	
Quantity	13 Nos	Date of Completion	29-03-2022	
Discipline	Mechanical Testing	Group	Rubber and Rubber Products	

Environmental Condition : 23±2°C, 50±5% R.H

S.No	Test Parameter	Unit	Test Method	Test Result
1	Hardness Shore A	-	ISO 48-4 : 2018	76
2	Density	g/cc	ISO 2781 Method A: 2018	1.196
3	Tensile Strength	MPa	ISO 37: 2017	10.28
4	Elongation at Break	%	ISO 37: 2017	467.68
5	Tear Strength : Die B, Nicked	kg/cm	ISO 34 Part 1: 2015	32.80
6	Compression Set : 175°C, 22h, 25% Compression	%	ISO 815 (Part 1): 2014	15.34
7	Heat Ageing : 225°C, 70h			
7.1	Hardness Change Shore A	-	ISO 188: 2011	+7
7.2	Tensile Strength Change	%	ISO 188: 2011	-48.38
7.3	Elongation at Break Change	%	ISO 188: 2011	-48.24
7.4	Weight Change	%	ISO 188: 2011	-2.65

- Note: 1. Test samples are received in good condition.
2. Test Method: As agreed with the customer.
3. This report shall not be reproduced except in full without the approval of the testing laboratory.
4. This test report is only for the sample tested as supplied by the customer.

Verified by :

Authorised by

K.S. Sabaris
Manager Testing
Work Order : 6774A

D.Sekar, LAB CHIEF
MAEON Laboratories