






**a****b****c****d**

flux- and spectrum-weighted round-trip loss

- Al / ITO 150 nm 15.6 %
- DBR / IZO 50 nm 11.5 %  
(3.0 absorbed + 8.5 leaked)
- Ag / Ag 10 nm 5.6 %
- Ag / ITO 150 nm 4.5 %
- Ag / IZO 50 nm 3.2 %

generic stack: substrate / electrode / 420 nm organics ( $n = 1.8$ ) / reflector, glass substrate, green emitter