

Natural Bahamian Oolitic Aragonite

Biogenic calcium carbonate for industrial, agricultural, and water-treatment evaluation

Representative technical data. Values on this sheet support preliminary material evaluation and product selection. They are not a shipment-specific Certificate of Analysis. Request current lot-specific documentation before procurement, formulation, or specification decisions.

MATERIAL DESCRIPTION

Naturally precipitated, biogenic calcium carbonate recovered from oolitic sands of the Great Bahama Bank. Composed of spherical ooids built from interlocking acicular aragonite crystals, giving the material naturally high surface area and internal microporosity. Mechanically collected, dried, and screened — no chemical synthesis or high-temperature calcination.

CHEMICAL COMPOSITION			PHYSICAL PROPERTIES			
CONSTITUENT	VALUE	STATUS	PROPERTY	VALUE	STATUS	
Calcium carbonate (CaCO ₃)	97.8%	REPRESENTATIVE	Crystal system	Orthorhombic	MINERAL PROPERTY	
			Polymorph	Aragonite	MINERAL PROPERTY	
Elemental calcium (Ca)	~39-40%	REPRESENTATIVE	Surface area	~1.8 m²/g	REPRESENTATIVE	
Iron oxide (Fe ₂ O ₃)	On request	PER LOT	Moisture (as shipped)	<0.3%	PER LOT	
Acid insolubles	On request	PER LOT	Bulk / tapped density	On request	PER GRADE	
Trace strontium (Sr)	Present*	REPRESENTATIVE		Brightness / whiteness	On request	PER GRADE
*Natural lattice substitution typical of biogenic aragonite. Confirm current-lot value if relevant to application.						

AVAILABLE SIZING

CATEGORY	RANGE	TYPICAL EVALUATION CONTEXT
Standard offering	20-325 U.S. mesh	Across agricultural, water-treatment, and industrial evaluation
Custom sizing	By request	Application-specific distributions discussed per program

Particle-size distribution (d10/d50/d98), top-cut, and sieve basis available as current-lot documentation on request. Distributions are grade- and lot-dependent.

APPLICATION NOTES

- Water treatment:** Higher reactivity than calcite suits calcite-contactor remineralization and pH adjustment. Confirm potable-water compliance requirements for the target system.
 - Agriculture:** Faster calcium delivery and liming value in acidic soils; OMRI Listed for organic use. Soil-test-driven, crop-specific.
- Glass:** Naturally high CaCO₃ purity; suitability for a given glass type depends on trace-metal (esp. iron) analysis — request per lot.
 - Cement / specialty concrete:** Aragonite polymorph shows differentiated cement-paste rheology vs. calcite; evaluate for specialty rather than bulk applications.

Certification. OMRI Listed for use in organic production. Other application-specific compliance (e.g., potable-water standards) is not implied and must be confirmed for the intended use.

SOURCING & SUPPLY

Source: Great Bahama Bank (natural oolitic aragonite sands). Distribution: Stockton, California, United States. Packaging formats and available quantities confirmed per program. Request current lead-time and logistics information for your delivery region.

Request current specifications & lot documentation

Samples · Technical data · Bulk pricing · Application support

sales@aragocorminerals.com

AragoCor Minerals LLC · Stockton, CA

REPRESENTATIVE

typical value, confirm current grade ·

PER LOT/GRADE

supplied with current documentation ·

MINERAL PROPERTY

intrinsic to aragonite