


Sound absorption rating

ISO 354 laboratory measurement of sound absorption. Rating per ISO 11654:1997.

Client:	Example client	Manufacturer:	Example acoustics
Description:	50 mm porous absorber over a 100 mm air gap	Sample area S [m ²]:	10.8
Mounting:	Type A (mounted directly against a rigid wall)	Test room:	Reverberation room (example)
Date of test:	2026-07-20	Temperature [°C]:	21.4
Relative humidity [%]:	54	Ambient pressure [kPa]:	101

One-third-octave α_s , octave α_p

Frequency f [Hz]	α_s	α_p
200	0.30	
250	0.35	0.35
315	0.40	
400	1.00	
500	1.00	1.00
630	1.00	
800	0.62	
1000	0.66	0.65
1250	0.67	
1600	0.58	
2000	0.60	0.60
2500	0.62	
3150	0.53	
4000	0.55	0.55
5000	0.57	



$\alpha_w = 0.60$ (M)

Absorption class: C
Shape indicator: M
Applied shift: 0.40

Result vs requirement: $\alpha_w = 0.60$, required $\geq 0.55 \rightarrow$ **PASS**

Laboratory: Phonometry reference example

Report no.: EXAMPLE-11654

Date: 2026-07-20

Operator: phonometry **Signature:** _____

■ The results relate only to the tested specimen.

Generated by phonometry.