CTL DECISION SHEET

Standard(s): IEC 60112/2003 Ed. 4.0	**Subclause(s):** 7.3	**No.** DSH 0724	**Year** 2008
Categories: Various, General		**Developed by:** WG4	
Subject: Measurement of conductivity	**Key words:** - Tracking solution - Conductivity - IEC 60589	**Decision approved at the 46th CTL Plenary Meeting, in 2009**	

Question:

Clause 7.3 requires that the conductivity of the tracking test solution *"be measured with alternating voltage at a frequency in the range 1 kHz to 2 kHz. The procedure is described in IEC 60589"*.

The procedure in IEC 60589 utilises conical flasks with reflux condensors, platinised platinum electrodes, a conductivity cell and a resistance bridge. This appears to be a chemical standard rather than an appropriate electrical test laboratory measurement technique.

Are CBTL:

- (a) expected to use this method of measurement for solution conductivity; or
- (b) can a suitable conductivity meter with a measurement frequency in the range 1 kHz to 2 kHz be used; or
- (c) can any suitable conductivity meter (different measurement range) be used.

Decision:

The Group decided that the *"use of any appropriate conductivity meter with sufficient accuracy and uncertainty including the probe"* is the only practical one - item (c) above.

Explanatory Notes: ---