CTL DECISION SHEET (DSH)

Standard(s) (incl. year)	Subclause(s)	Tracking No.	Year
IEC 60695-10-2/2014	4, 7, 9, Figure 2	DSH 0391D	2015
Category			
VARIOUS, GENERAL			
Subject	**Keywords**	**Developed by**	**Approved at**
Ball pressure test	- Diameter of indentation - Test specimen support - Air temperature	WG2 - WG4	2016 CTL Plenary Meeting

Question

To define the “best practice” test procedure for the ball pressure test based on the requirements of the standard.

Decision

IEC 60216-4-1 is a standard providing requirements for ovens for aging tests and requires forced gas ventilation. As the ball pressure test is not considered to be an ageing test such forced gas ventilation is not required and should not be confused with forced convection.

For the purpose of ball pressure testing chambers with or without forced convection may be used, provided all other requirements are fulfilled.

Following clause 5.2 of the standard and considering the note there, a separate thermocouple on or right below the surface of the test specimen support and as close as practical to the test sample shall be used to check that the temperature of the test specimen support does not significantly deviate from the test temperature.

In addition measure the air temperature as close as possible to the test specimen.

In case of non-round indentation obtained, report the biggest diameter measurement observed. The maximum difference between the longest and shortest measurement should not exceed 0,2 mm.

Where the product standard contains differing or conflicting requirements to IEC 60695-10-2 or to this decision sheet these product standard requirements override the requirements from IEC 60695-10-2 and this decision sheet.

Explanatory notes

DSH 0391D is an update to DSH 0391C to align with IEC 60695-10-2 ed.3.0 2014-02.