■ CTL Provisional DECISION SHEET (PDSH)
☐ CTL DECISION SHEET (DSH)

Standard(s) (incl. year)	**Subclause(s)**	**Tracking No.**
IEC 63056:2020	Clause 7.2	2266
Category		
BATT		
Subject	**Keywords**	**Developed by**
Maximum temperature rise of thermoplastic parts	Maximum temperature rise	ETF 13

Question

For harmonization of the approach for CB testing:

In clause 7.2 for the resistance to abnormal heat of non-metallic materials, it is asked to consider the ΔT for the temperature ((ΔT + Tmax + 15 °C) ± 2 °C) in the heating cabinet to perform the ball pressure test.

Q1: From where is this ΔT coming?

There is no reference to a test to be performed in this standard IEC 63056:2020 from where to take the data and what shall be considered the most adverse condition.

Q2: Is just taking a declaration from a manufacturer for the ΔT adequate for confirming compliance with the requirements in the CB scheme or must it be taken from another CB test report covering such temperature aspects?

Decision

A1: The most adverse condition is where the part carries the highest power or current.

$$P = I * V = I^2 * R$$

Since the warning after clause 6.1 requests the test facility to take precautions to prevent burn, CBTLs should measure the battery temperature, and measure the ΔT at clause 7.8 Overdischarge control of voltage.

A2: CBTLs should use the results in clause 7.8 test.

Explanatory notes

Enquiry:	
Date:	2024-08-06
PDSH:	
Year of publication:	2024
To be approved at CTL plenary:	2025
DSH	
Publication date:	

None.

Disclaimer: This document is controlled and has been released electronically.
Only the version on the IECEE Website is the current document version.