


캠페인 B 최종 후보의 (100) 표면 CO 활성 사이트 — 투시·평면·측면 (DFT)

(a) (Mo, Ti, Zr)C


(b) (Cr, Ti, V)C

(c) (Cr, Ti, Zr)C


투시(3D)



Mo 온톱 · CO 방출(약결합), $\Delta G_{CO} = +0.18$ eV






Cr 온톱(강결합), $\Delta G_{CO} = -0.20$ eV






Cr 온톱(약결합), $\Delta G_{CO} = +0.06$ eV

위에서(평면)



앞에서(측면)



Mo Cr Ti Zr V C O 활성 금속 자리