


Measurement Report

Surface Texture Measurement

Bearing Area/Firestone-Abbott Curve
of Roughness Dataset (Selection)

ZONA_4_1_1

$L_c = 800.000\mu\text{m}$



Measurement line

$BA(z) = 50.000\%$

$z = -0.257\mu\text{m}$

Name	Value	Unit	Description
Sk	7.271	μm	Core roughness depth, Height of the core material
Spk	3.345	μm	Reduced peak height, mean height of the peaks above the core material
Svk	5.013	μm	Reduced valley height, mean depth of the valleys below the core material
Smr1	10.830	%	Peak material component, the fraction of the surface which consists of peaks above the core material
Smr2	91.350	%	Peak material component, the fraction of the surface which will carry the load
Vmp	0.166	ml/m^2	Peak material volume of the topographic surface (ml/m^2)
Vmc	2.497	ml/m^2	Core material volume of the topographic surface (ml/m^2)
Vvc	3.547	ml/m^2	Core void volume of the surface (ml/m^2)
Vvv	0.405	ml/m^2	Valley void volume of the surface (ml/m^2)
Vvc/Vmc	1.421		Ratio of Vvc parameter to Vmc parameter
Lc	800.000	μm	LambdaC: cut off wavelength