


Measurement Report

Surface Texture Measurement

Bearing Area/Firestone-Abbott Curve
of Roughness Dataset (Selection)

ZONA_1_3

$L_c = 800.000\mu\text{m}$



Measurement line

$BA(z) = 50.000\%$

$z = -0.027\mu\text{m}$

Name	Value	Unit	Description
Sk	2.393	μm	Core roughness depth, Height of the core material
Spk	1.142	μm	Reduced peak height, mean height of the peaks above the core material
Svk	0.888	μm	Reduced valley height, mean depth of the valleys below the core material
Smr1	10.070	%	Peak material component, the fraction of the surface which consists of peaks above the core material
Smr2	90.540	%	Peak material component, the fraction of the surface which will carry the load
Vmp	0.057	ml/m^2	Peak material volume of the topographic surface (ml/m^2)
Vmc	0.829	ml/m^2	Core material volume of the topographic surface (ml/m^2)
Vvc	1.136	ml/m^2	Core void volume of the surface (ml/m^2)
Vvv	0.104	ml/m^2	Valley void volume of the surface (ml/m^2)
Vvc/Vmc	1.371		Ratio of Vvc parameter to Vmc parameter
Lc	800.000	μm	LambdaC: cut off wavelength