Heterogeneous & Homogeneous & Bio-
CHEMCATCHEM
CATALYSIS

Supporting Information

© Copyright Wiley-VCH Verlag GmbH & Co. KGaA, 69451 Weinheim, 2011

Statistical Analysis of Past Catalytic Data on Oxidative Methane Coupling for New Insights into the Composition of High-Performance Catalysts

Ulyana Zavyalova,[a] Martin Holena,[b, c] Robert Schlögl,[a] and Manfred Baerns*[a]

cctc_201100186_sm_miscellaneous_information.pdf

Übersicht

Description
Composition-Conditions-Results
References

Tabelle 1: *Description*

Description of columns

- Number of publication used for the data extraction (see corresponding References);
- Cation 1 – 4 – cation composition of catalysts in molar fractions;
- Anion 1 – 4 – anion composition of catalysts excluding oxygen in molar fractions;
- Support 1, 2 – cation composition of supports;
- Promoter – additional non-metals not belonging to catalyst compositions;
- Preparation – all techniques are divided into the 5 groups (n.a.- not available);
- Temperature – operating temperature in K;
- p(CH4) and p(O2)- partial pressures of methane and O2 in bar;
- p total - total pressure in reactor in bar;
- Contact time - relation between catalyst bed volume and volumetric flow in seconds;
- X(O2) – oxygen conversion in mole percentages;
- X(CH4) – methane conversion in mole percentages;
- S(COx) – selectivity to CO and CO2 in mole percentages;
- S(C2=) – selectivity to ethylene in mole percentages;
- S(C2-) – selectivity to ethane in mole percentages;
- S(C2) – selectivity to ethane and ethylene in mole percentages;
- Y(C2) – ethane and ethylene yield – methane conversion * selectivity to ethane and ethylene, in mole percentages.

Tabelle 2: *Composition-Conditions-Results*

Nr of publication	Cation 1 value	mol%	Cation 2 value	mol%	Cation 3 value	mol%	Cation 4 value	mol%	Anion 1 value	mol%	Anion 2 value	mol%	Pro-motor	Support 1 value	mol%	Support 2 value	mol%	Preparation	Temperature, K	p(CH4), bar	p(O2), bar	p(CH4)/p(O2)	P total, bar	Contact time, s	X(O2), %	X(CH4), %	S(COx), %	S(C2=), %	S(C2-), %	S(C2), %	Y(C2),%	Basicity	Acidity	Electro-negativity	Anion conductivity	p/n conductiv
	Mn	9,2												Al	90,8			Impregnation	1073	0,40	0,08	4,8	1,0	0,04		11,0				45,5	5,0					
	Cd	4,7												Al	95,3			Impregnation	1073	0,40	0,08	4,8	1,0	0,04		10,0				40,0	4,0					
	Sn	4,5												Al	95,5			Impregnation	1073	0,40	0,08	4,8	1,0	0,04		8,4				4,8	0,4					
	Ti	10,4												Al	89,6			Impregnation	1073	0,40	0,08	4,8	1,0	0,04		6,8				44,1	3,0					
	Pt	2,8												Al	97,2			Impregnation	1073	0,40	0,08	4,8	1,0	0,04		8,0				1,3	0,1					
	Ce	3,8												Al	96,2			Impregnation	1073	0,40	0,08	4,8	1,0	0,04		5,0				2,0	0,1					
1	Pb	2,6												Al	97,4			Impregnation	1073	0,40	0,08	4,8	1,0	0,04		4,6				43,5	2,0					
	Bi	2,6												Al	97,4			Impregnation	1073	0,40	0,08	4,8	1,0	0,04		4,4				9,1	0,4					
	Mo	5,5												Al	94,5			Impregnation	1073	0,40	0,08	4,8	1,0	0,04		4,0				2,5	0,1					
	Cu	8,0												Al	92,0			Impregnation	1073	0,40	0,08	4,8	1,0	0,04		4,0				0,0	0,0					
	Sb	4,4												Al	95,6			Impregnation	1073	0,40	0,08	4,8	1,0	0,04		3,5				42,9	1,5					
	Li	44,6												Al	55,4			Impregnation	1073	0,40	0,08	4,8	1,0	0,04		3,2				6,3	0,2					
	Mg	18,7												Al	81,3			Impregnation	1073	0,40	0,08	4,8	1,0	0,04		2,0				40,0	0,8					
	Pb	20,0												Al	80,0			Therm.decomp.	1023	0,50	0,05	10,0	1,0	1,03	90,0	12,1		11,2	41,1	52,3	6,3					
	Pb	10,0												Al	90,0			Impregnation	973	0,26	0,05	5,0	1,0	0,24		9,0		12,2	26,2	38,4	3,5					
2	Pb	10,0	Bi	90,0														Impregnation	973	0,25	0,04	6,1	1,0	10,00		8,0		14,4	31,8	46,2	3,7					
	Pb	10,0	Bi	10,0	Sb	80,00												Impregnation	973	0,47	0,03	14,2	1,0	8,70		12,0		5,1	39,7	44,8	5,4					
	Pb	50,0												Al	50,0			Impregnation	1023	0,51	0,05	9,8	1,0	4,30		7,0		11,2	41,1	52,3	3,7					
3	Li	30,3	Mg	69,7														n.a.	993	0,08	0,04	2,0	1,0	5,30	85,0	38,0				50,0	19,0					
	Be	100,0																n.a.	744	0,65	0,08	8,3	1,0	3,44	99,0	9,0		9,0	15,0	24,0	2,2					
	Be	50,0							S	50,0								Therm.decomp.	745	0,68	0,07	10,0	1,0	20,50	87,0	15,0		1,0	5,0	6,0	0,9					
	Mg	100,0																Therm.decomp.	607	0,64	0,08	8,0	1,0	1,27	93,0	8,0		0,2	1,7	1,9	0,2					
	Mg	100,0																n.a.	753	0,64	0,08	8,2	1,0	0,62	95,0	10,0		8,0	14,0	22,0	2,2					
	Mg	50,0							S	50,0								n.a.	745	0,65	0,08	8,4	1,0	9,64	38,0	3,0		20,0	39,0	59,0	1,8					
	Ca	50,0							C	50,0								Therm.decomp.	786	0,64	0,08	8,1	1,0	7,20	96,0	12,0		15,0	34,0	49,0	5,9					
	Ca	100,0																Therm.decomp.	771	0,07	0,08	0,8	1,0	3,90	94,0	14,0		18,0	34,0	52,0	7,3					
	Ca	50,0							S	50,0								Therm.decomp.	744	0,63	0,08	7,9	1,0	26,00	53,0	7,0		22,0	28,0	50,0	3,5					
	Sr	50,0							C	50,0								n.a.	741	0,65	0,08	8,6	1,0	18,20	64,0	7,0		12,0	28,0	40,0	2,8					
	Sr	100,0																n.a.	746	0,77	0,05	15,4	1,0	17,80	99,0	13,0		29,0	21,0	50,0	6,5					
	Sr	100,0																Therm.decomp.	850	0,63	0,08	8,1	1,0	4,40	100,0	8,0		53,0	37,0	90,0	7,2					
	Sr	50,0							S	50,0								n.a.	742	0,63	0,08	7,7	1,0	56,00	100,0	13,0		3,0	5,0	8,0	1,0					
	Ba	50,0							S	50,0								n.a.	740	0,65	0,08	8,2	1,0	42,10	21,0	2,0		10,0	24,0	34,0	0,7					
	Ba	100,0																Therm.decomp.	740	0,60	0,09	6,7	1,0	8,40	93,0	10,0		43,0	46,0	89,0	8,9					
	K	66,7							C	33,3								n.a.	743	0,64	0,08	8,0	1,0	3,50	97,0	12,0		13,0	25,0	38,0	4,6					
	Na	66,7							C	33,3								n.a.	747	0,65	0,08	8,1	1,0	8,50	71,0	10,0		28,0	19,0	47,0	4,7					
4	K	10,5	Sr	84,3					C	5,2								Therm.decomp.	740	0,67	0,07	9,6	1,0	25,60	96,0	7,0		52,0	36,0	88,0	6,2					
	K	5,3	Pb	92,1					C	2,6								Therm.decomp.	742	0,67	0,07	9,6	1,0	0,80	99,0	13,0		26,0	35,0	61,0	7,9					
	Mg	66,7							S	33,3								Impregnation	746	0,65	0,08	8,1	1,0	1,40	39,0	4,0		23,0	41,0	64,0	2,6					
	Mg	55,0							S	45,0								Impregnation	744	0,66	0,08	8,3	1,0	3,00	65,0	10,0		27,0	40,0	67,0	6,7					
	Na	7,0	Mg	33,0					S	60,0								Impregnation	744	0,64	0,08	8,0	1,0	0,19	39,0	3,0		23,0	19,0	42,0	1,3					
	Na	5,5	Ca	94,5														Impregnation	748	0,64	0,08	8,0	1,0	0,16	98,0	16,0		24,0	39,0	63,0	10,1					
	Na	7,0	Ca	93,0														Impregnation	750	0,65	0,08	8,1	1,0	38,40	97,0	15,0		25,0	44,0	69,0	10,4					
	Na	2,0	K	16,0	Ca	37,00	Sr	37,00	C	8,0								Therm.decomp.	744	0,67	0,07	9,6	1,0	0,20	94,0	6,0		50,0	39,0	89,0	5,3					
	Ca	56,0	Si	44,0														Sol-gel	771	0,67	0,07	9,6	1,0	1,30	100,0	11,0		12,0	30,0	42,0	4,6					
	Ca	66,2	Pb	33,8														Therm.decomp.	840	0,65	0,08	8,1	1,0	0,20	100,0	13,0		13,0	36,0	49,0	6,4					
	Pb	8,0	Ca	61,3	Si	30,70												Impregnation	740	0,66	0,08	8,3	1,0	9,90	94,0	9,0		9,0	36,0	45,0	4,1					
	Pb	3,8	Ca	48,1					S	48,1								Impregnation	777,0	0,64	0,08	8,0	1,0	30,70	99,0	12,0		26,0	29,0	55,0	6,6					
	Pb	82,0							S	18,0								Precipitation	754	0,64	0,08	8,0	1,0	49,50	63,0	8,0		32,0	23,0	55,0	4,4					
	Pb	77,0							P	23,0								Therm.decomp.	781	0,65	0,08	8,1	1,0	19,90	79,0	5,0		12,0	29,0	41,0	2,1					
	Pb	7,5	Ca	51,0					S	7,5	P	34,0						Therm.decomp.	747	0,67	0,07	9,6	1,0	2,40	89,0	12,0		25,0	32,0	57,0	6,8					
	Pb	9,0	Ca	41,0					S	50,0								Impregnation	741	0,67	0,07	9,6	1,0	11,60	33,0	4,0		23,0	37,0	60,0	2,4					
	Pb	1,0	Ca	49,0					S	50,0								Impregnation	746	0,65	0,08	8,1	1,0	14,20	100,0	6,0		23,0	48,0	71,0	4,3					

	Sr	4,6	Ca	95,4								Therm.decomp.	847	0,66	0,08	8,3	1,0	0,84	100,0	13,0		16,0	37,0	53,0	6,9
	Li	6,0	Ca	94,0								Impregnation	744	0,64	0,08	8,0	1,0	1,05	99,0	13,0		24,0	38,0	62,0	8,1
	K	62,0	Ca	38,0								Impregnation	743	0,64	0,08	8,0	1,0	0,38	86,0	10,0		14,0	40,0	54,0	5,4
	Na	3,6	Ca	94,6			S	1,8				Impregnation	745	0,65	0,08	8,1	1,0	0,25	92,0	16,0		26,0	45,0	71,0	11,4
	Li	5,8	Ca	94,2								Impregnation	754	0,67	0,07	9,6	1,0	0,50	97,0	14,0		24,0	40,0	64,0	9,0
	Na	9,8	Ca	85,3			C	4,9				Impregnation	743	0,67	0,07	9,6	1,0	0,49	98,0	13,0		20,0	41,0	61,0	7,9
	K	12,0	Ca	82,0			S	6,0				Impregnation	758	0,65	0,08	8,1	1,0	0,42	93,0	14,0		24,0	42,0	66,0	9,2
	K	8,0	Ca	92,0								Impregnation	783	0,66	0,08	8,3	1,0	0,47	93,0	11,0		18,0	37,0	55,0	6,1
	Na	7,0	Ca	93,0								Impregnation	753	0,64	0,08	8,0	1,0	0,47	95,0	10,0		16,0	36,0	52,0	5,2
	K	13,0	Ca	80,5			C	6,5				Impregnation	749	0,64	0,08	8,0	1,0	0,48	94,0	10,0		13,0	33,0	46,0	4,6
	Li	5,4	Ca	91,9			S	2,7				Impregnation	757	0,65	0,08	8,1	1,0	0,90	98,0	14,0		32,0	34,0	66,0	9,2
	Al	100,0										Therm.decomp.	752	0,67	0,07	9,6	1,0	1,10	99,0	11,0		14,0	31,0	45,0	5,0
	Na	36,0	Al	46,0			S	18,0				Impregnation	745	0,67	0,07	9,6	1,0	1,92	93,0	11,0		19,0	36,0	55,0	6,1
	Li	13,0	Al	87,0								Impregnation	751	0,65	0,08	8,1	1,0	6,88	100,0	11,0		24,0	26,0	50,0	5,5
	Na	3,8	Mn	3,8	Mg	92,40						Therm.decomp.	1123	0,68	0,33	2,0	1,0	6,00		14,2				81,8	11,6
5	Na	3,8	Mn	3,8	Mg	85,40					Si	7,0	Therm.decomp.	1123	0,68	0,33	2,0	1,0	6,00		20,5			65,6	13,4
	Si	100,0											n.a.	1173	0,91	0,09	9,6	1,0	3,00	98,0	12,0		51,0	5,0	56,0	6,7
	Al	100,0											n.a.	1218	0,96	0,04	24,0	1,0	2,10	57,0	3,9		25,0	37,0	62,0	2,4
	Al	2,0	Zr	98,0									n.a.	1173	0,91	0,09	9,6	1,0	3,00	98,0	8,0		4,0	0,0	4,0	0,3
	K	1,0	Si	98,0			Br	1,0					n.a.	1173	0,91	0,09	9,6	1,0	3,00	98,0	16,0		48,0	6,0	54,0	8,6
	Al	6,3	Mg	6,3			B	87,4					n.a.	1119	0,96	0,04	24,0	1,0	3,20	38,0	3,2		10,5	28,2	38,7	1,2
	Pb	20,0									Al	80,0	n.a.	1030	0,96	0,05	19,2	1,0	0,40	100,0	6,8		17,6	32,8	50,4	3,4
6	Pb	20,0									Si	80,0	n.a.	1103	0,96	0,05	19,2	1,0	0,55	44,1	18,7		18,7	20,5	39,2	7,3
	Na	2,0	Pb	20,0							Si	78,0	n.a.	1128	0,96	0,05	19,2	1,0	1,00	98,9	7,8		42,1	38,3	80,4	6,3
	Na	5,0	Pb	20,0							Si	75,0	n.a.	1062	0,97	0,03	32,3	1,0	2,10	99,4	9,5		27,3	8,8	36,1	3,4
	Mg	1,5	Pb	20,0							Si	78,5	n.a.	1062	0,97	0,03	32,3	1,0	2,10	99,5	3,6		10,9	19,1	30,0	1,1
	Pb	20,0					S	20,0			Si	60,0	n.a.	1123	0,97	0,03	32,3	1,0	1,20	94,2	7,3		32,9	47,6	80,5	5,9
	Pb	20,0	W	20,0							Si	60,0	n.a.	1123	0,97	0,03	32,3	1,0	1,20	99,1	7,3		5,4	21,4	26,8	2,0
	Pb	20,0	Mo	20,0							Si	60,0	n.a.	1123	0,97	0,03	32,3	1,0	1,20	99,4	3,6		2,6	24,6	27,2	1,0
	Mg	100,0											n.a.	1173	0,30	0,05	6,0	1,0	0,10	100,0	18,1		32,1	17,9	61,8	11,2
	Ca	100,0											n.a.	1023	0,30	0,05	6,0	1,0	0,10	100,0	15,3		15,1	26,1	62,8	9,6
	Sr	100,0											n.a.	1123	0,30	0,05	6,0	1,0	0,10	36,0	8,0		22,1	46,5	63,8	5,1
	Sc	100,0											n.a.	1173	0,30	0,05	6,0	1,0	0,10	100,0	17,6		30,7	16,5	64,8	11,4
	Y	100,0											n.a.	1073	0,30	0,05	6,0	1,0	0,10	100,0	18,0		26,8	27,4	65,8	11,8
	La	100,0											n.a.	1023	0,30	0,05	6,0	1,0	0,10	100,0	19,6		25,7	30,9	66,8	13,1
	Pr	100,0											n.a.	1123	0,30	0,05	6,0	1,0	0,10	100,0	11,3		8,7	16,6	67,8	7,7
	Nd	100,0											n.a.	1023	0,30	0,05	6,0	1,0	0,10	100,0	17,9		22,5	31,5	68,8	12,3
	Sm	100,0											n.a.	1023	0,30	0,05	6,0	1,0	0,10	100,0	17,9		23,5	29,5	69,8	12,5
	Eu	100,0											n.a.	973	0,30	0,05	6,0	1,0	0,10	100,0	18,2		24,4	28,2	70,8	12,9
	Gd	100,0											n.a.	1073	0,30	0,05	6,0	1,0	0,10	100,0	19,2		31,1	27,2	71,8	13,8
	La	100,0											n.a.	1023	0,30	0,05	6,0	1,0	0,10	100,0	19,6		25,7	30,9	72,8	14,3
	Li	10,0	La	90,0								Impregnation	1073	0,30	0,05	6,0	1,0	0,10	100,0	21,6		32,6	37,6	73,8	15,9
	Na	10,0	La	90,0								Impregnation	1073	0,30	0,05	6,0	1,0	0,10	100,0	20,0		31,4	33,2	74,8	15,0
	K	10,0	La	90,0								Impregnation	1073	0,30	0,05	6,0	1,0	0,10	100,0	20,6		30,1	30,3	75,8	15,6
	Mg	10,0	La	90,0								Impregnation	1023	0,30	0,05	6,0	1,0	0,10	100,0	20,7		28,0	32,1	76,8	15,9
	Ca	10,0	La	90,0								Impregnation	1023	0,30	0,05	6,0	1,0	0,10	100,0	19,4		28,6	31,1	77,8	15,1
	Sr	10,0	La	90,0								Impregnation	1023	0,30	0,05	6,0	1,0	0,10	100,0	20,9		28,7	34,9	78,8	16,5
	Ba	10,0	La	90,0								Impregnation	1073	0,30	0,05	6,0	1,0	0,10	100,0	20,3		30,5	33,6	79,8	16,2
7	Pb	10,0	La	90,0								Impregnation	1023	0,30	0,05	6,0	1,0	0,10	100,0	18,5		24,9	33,2	80,8	14,9
	Bi	10,0	La	90,0								Impregnation	1023	0,30	0,05	6,0	1,0	0,10	100,0	18,4		27,0	34,6	81,8	15,1
	Ar	10,0	La	90,0								Impregnation	1073	0,30	0,05	6,0	1,0	0,10	100,0	20,0		27,8	31,9	82,8	16,6
	Li	10,0	Mg	90,0								Impregnation	1123	0,30	0,05	6,0	1,0	0,10	100,0	21,1		38,0	29,1	83,8	17,7
	Na	10,0	Mg	90,0								Impregnation	1073	0,30	0,05	6,0	1,0	0,10	100,0	19,4		27,5	31,6	84,8	16,5
	K	10,0	Mg	90,0								Impregnation	1173	0,30	0,05	6,0	1,0	0,10	100,0	19,3		37,5	18,6	85,8	16,6
	Y	10,0	Mg	90,0								Impregnation	1173	0,30	0,05	6,0	1,0	0,10	100,0	16,5		35,6	20,2	86,8	14,3
	La	10,0	Mg	90,0								Impregnation	1123	0,30	0,05	6,0	1,0	0,10	100,0	18,0		28,8	23,1	87,8	15,8
	Ba	10,0	Mg	90,0								Impregnation	1123	0,30	0,05	6,0	1,0	0,10	100,0	17,4		27,6	28,5	88,8	15,5
	Sr	,5	La	99,5								Impregnation	1023	0,30	0,05	6,0	1,0	0,10	100,0	21,2		28,9	35,2	89,8	19,0
	Sr	,8	La	99,2								Impregnation	1023	0,30	0,05	6,0	1,0	0,10	100,0	21,4		29,0	36,2	90,8	19,4
	Sr	1,5	La	98,5								Impregnation	1023	0,30	0,05	6,0	1,0	0,10	100,0	20,9		28,7	34,9	91,8	19,2
	Sr	3,0	La	97,0								Impregnation	1023	0,30	0,05	6,0	1,0	0,10	100,0	21,0		28,9	35,8	92,8	19,5
	Sr	15,0	La	85,0								Impregnation	1023	0,30	0,05	6,0	1,0	0,10	100,0	19,6		28,0	35,2	93,8	18,4
	La	67,0	Ce	1,0	Re	32,00						Impregnation	1023	0,30	0,05	6,0	1,0	0,10	100,0	16,5		17,8	30,0	94,8	15,6
	La	60,0	Ce	10,0	Re	30,00						Impregnation	1023	0,30	0,05	6,0	1,0	0,10	100,0	15,5		18,4	31,8	95,8	14,8
	La	40,0	Ce	40,0	Re	20,00						Impregnation	1023	0,30	0,05	6,0	1,0	0,10	100,0	11,6		7,9	16,2	96,8	11,2
	Ce	100,0											n.a.	1023	0,30	0,05	6,0	1,0	0,10	100,0	9,3		0,3	1,6	97,8	9,1
	Pb	10,0									Si	90,0	Impregnation	1173	0,30	0,05	6,0	1,0	0,10	50,0	8,5		27,0	31,1	98,8	8,4
8	Pb	5,6									Si	94,4	Impregnation	1013	0,70	0,07	10,0	1,0	0,15	60,0	7,7		32,0	39,0	70,5	5,4
9	Na	14,9	Mg	85,1									n.a.	1073	0,03	0,01	1,9	1,0	2,40		39,0				57,0	22,2
10	Li	11,1	Sm	88,9									n.a.	1023	0,05	0,02	2,6	1,0	0,60	80,0	28,8		59,0	10,8	70,0	20,2
11	Li	12,5	Zn	87,5									n.a.	1013	0,11	0,06	1,9	1,0	2,40	90,0	40,0				62,1	24,8
12	Pb	4,3	Mg	95,7									Impregnation	1023	0,61	0,02	38,3	1,0	0,16	84,0	10,0	34,0	13,0	53,0	66,0	6,6
13	Li	14,3	Ca	85,7									n.a.	984	0,50	0,11	4,7	1,0	7,20		20,0		39,0	27,0	66,0	13,2
	Na	50,0	Ca	50,0									n.a.	980	0,50	0,11	4,7	1,0	7,20		15,0		36,0	37,0	73,0	11,0
14	Li	16,7	Ni	66,6			Br	16,7					Impregnation	1023	0,05	0,03	2,0	1,0	0,60	94,0	35,1		43,0	3,0	46,0	16,1
	Li	16,7	Ni	66,6			Cl	16,7					Impregnation	1023	0,05	0,03	2,0	1,0	0,60	57,0	25,9		56,0	16,0	72,0	18,6
15	La	50,0	Al	50,0									n.a.	983	0,51	0,11	4,8	1,0	0,45	94,7	25,3				48,4	12,2
16	Li	20,0	Sm	80,0									Impregnation	1023	0,05	0,02	2,5	1,0	0,60	90,0	41,2		26,0	28,0	54,1	22,3
17	Li	2,0	Ba	98,0									n.a.	1073	0,03	0,01	1,9	1,0	2,40		37,0				50,0	18,5
	Na	2,0	Ba	98,0									n.a.	1073	0,03	0,01	1,9	1,0	2,40		36,0				42,0	15,1
	K	2,0	Ba	98,0									n.a.	1073	0,03	0,01	1,9	1,0	2,40		48,0				42,0	20,2
	Rb	2,0	Ba	98,0									n.a.	1073	0,03	0,01	1,9	1,0	2,40		45,0				38,0	17,1
18	Pb	10,0									Al	90,0	n.a.	923	0,58	0,09	6,4	1,0	0,03		13,1				56,2	7,4
19	Bi	1,7	K	7,1							Al	91,2	Pyrolysis	913	0,51	0,25	2,0	1,0	0,01	87,0	6,6				23,9	1,6
	Li	2,4	Ca	96,4			C	1,2					Impregnation	1013	0,52	0,06	9,0	1,0	0,37	92,0	15,0				76,0	11,4
	Li	11,6	Ca	82,6			C	5,8					Impregnation	1013	0,52	0,06	9,0	1,0	0,44	93,0	16,0				77,0	12,3
	Na	7,0	Ca	89,5			C	3,5					Impregnation	1013	0,52	0,06	9,0	1,0	0,14	83,0	15,0				78,0	11,7
	Na	12,4	Ca	81,4			C	6,2					Impregnation	1013	0,52	0,06	9,0	1,0	0,81	91,0	12,0				70,0	8,4
	K	7,4	Ca	88,9			C	3,7					Impregnation	1013	0,52	0,06	9,0	1,0	0,14	91,0	14,0				71,0	9,9
20	K	14,2	Ca	78,7			C	7,1					Impregnation	1013	0,52	0,06	9,0	1,0	0,38	96,0	13,0				70,0	9,1
	Li	2,8	Ca	97,2									Impregnation	1013	0,52	0,06	9,0	1,0	0,37	92,0	14,0				75,0	10,5
	Li	6,0	Ca	94,0									Impregnation	1013	0,52	0,06	9,0	1,0	0,38	97,0	14,0				72,0	10,1
	Li	12,0	Ca	88,0									Impregnation	1013	0,52	0,06	9,0	1,0	0,36	99,0	14,0				72,0	10,1
	Na	2,6	Ca	97,4									Impregnation	1013	0,52	0,06	9,0	1,0	0,36	97,0	17,0				78,0	13,3
	Na	6,0	Ca	94,0									Impregnation	1013	0,52	0,06	9,0	1,0	0,36	95,0	16,0				76,0	12,2

	Na	17,4	Ca	82,6										Impregnation	1013	0,52	0,06	9,0	1,0	0,72	96,0	14,0				76,0	10,6
	K	2,2	Ca	97,8										Impregnation	1013	0,52	0,06	9,0	1,0	0,25	93,0	15,0				73,0	11,0
	K	5,8	Ca	94,2										Impregnation	1013	0,52	0,06	9,0	1,0	0,25	83,0	14,0				72,0	10,1
	K	12,0	Ca	88,0										Impregnation	1013	0,52	0,06	9,0	1,0	0,43	94,0	14,0				69,0	9,7
	Li	2,8	Ca	95,8			S	1,4						Impregnation	1013	0,52	0,06	9,0	1,0	0,91	100,0	16,0				76,0	12,2
	Li	6,8	Ca	89,8			S	3,4						Impregnation	1013	0,52	0,06	9,0	1,0	1,40	99,0	16,0				76,0	12,2
	Li	13,0	Ca	80,5			S	6,5						Impregnation	1013	0,52	0,06	9,0	1,0	0,95	93,0	14,0				74,0	10,4
	Na	2,8	Ca	95,8			S	1,4						Impregnation	1013	0,52	0,06	9,0	1,0	0,24	95,0	14,0				73,0	10,2
	Na	7,0	Ca	89,5			S	3,5						Impregnation	1013	0,52	0,06	9,0	1,0	0,19	92,0	16,0				78,0	12,5
	Na	10,4	Ca	84,4			S	5,2						Impregnation	1013	0,52	0,06	9,0	1,0	0,20	82,0	15,0				78,0	11,7
	K	2,4	Ca	96,4			S	1,2						Impregnation	1013	0,52	0,06	9,0	1,0	0,22	85,0	15,0				76,0	11,4
	K	6,8	Ca	89,8			S	3,4						Impregnation	1013	0,52	0,06	9,0	1,0	0,18	80,0	14,0				76,0	10,6
	K	10,4	Ca	84,4			S	5,2						Impregnation	1013	0,52	0,06	9,0	1,0	0,23	92,0	15,0				75,0	11,3
	Ca	100,0												Impregnation	1040	0,64	0,08	8,2	1,0	0,17	94,0	11,0	45,0			55,0	6,1
	Pb	7,5	Mg	92,5										Impregnation	1057	0,64	0,08	8,2	1,0	0,54	98,0	13,0	31,0			69,0	9,0
	Pb	1,4	Ca	49,3			S	49,3						Impregnation	1057	0,64	0,08	8,2	1,0	7,30	99,0	12,0	40,0			60,0	7,2
	Pb	,1	Si	33,3	Ca	66,60								Impregnation	1054	0,64	0,08	8,2	1,0	0,20	94,0	9,0	54,0			46,0	4,1
	Pb	1,9	K	65,4			C	32,7						Impregnation	1013	0,64	0,08	8,2	1,0	5,90	95,0	10,0	42,0			58,0	5,8
	Na	5,6	Ca	94,4										Impregnation	1013	0,35	0,14	2,4	1,0	0,30	84,0	30,0				56,0	16,8
	Li	4,5	Ca	95,5										Impregnation	1013	0,52	0,06	9,0	1,0	0,36	91,0	16,0				77,0	12,3
	Na	1,3	Ca	98,7										Impregnation	1013	0,52	0,06	9,0	1,0	0,14	80,0	16,0				78,0	12,5
	K	1,2	Ca	98,8										Impregnation	1013	0,52	0,06	9,0	1,0	0,36	98,0	15,0				72,0	10,8
	Pb	2,4	Ca	97,6										Impregnation	1040	0,64	0,08	8,2	1,0	0,18	96,0	10,0	57,0			43,0	4,3
	Pb	5,2	Ca	94,8										Impregnation	1040	0,64	0,08	8,2	1,0	0,18	91,0	9,0	64,0			36,0	3,2
	Pb	7,4	Ca	92,6										Impregnation	1040	0,64	0,08	8,2	1,0	0,19	81,0	8,0	67,0			33,0	2,6
	Mg	100,0												Impregnation	1057	0,64	0,08	8,2	1,0	0,19	94,0	11,0	47,0			53,0	5,8
	Pb	2,2	Mg	97,8										Impregnation	1057	0,64	0,08	8,2	1,0	0,68	100,0	13,0	34,0			66,0	8,6
	Pb	3,8	Mg	96,2										Impregnation	1057	0,64	0,08	8,2	1,0	0,69	99,0	12,0	34,0			66,0	7,9
	Ca	50,0					S	50,0						Impregnation	1057	0,64	0,08	8,2	1,0	4,90	53,0	6,0	47,0			53,0	3,2
	Ca	66,7	Si	33,3										Impregnation	1057	0,64	0,08	8,2	1,0	0,20	100,0	11,0	57,0			43,0	4,7
	K	66,7					C	33,3						Impregnation	1057	0,64	0,08	8,2	1,0	4,10	97,0	12,0	62,0			38,0	4,6
	Pb	,7	K	66,2			C	33,1						Impregnation	1057	0,64	0,08	8,2	1,0	9,90	50,0	7,0	45,0			55,0	3,9
	Si	100,0												Impregnation	1057	0,64	0,08	8,2	1,0	3,40	92,0	11,0				40,0	4,4
	Pb	1,7									Si	98,3		Impregnation	1057	0,64	0,08	8,2	1,0	8,70	72,0	4,0				64,0	2,6
	Pb	2,3									Si	97,7		Impregnation	1057	0,64	0,08	8,2	1,0	16,60	100,0	11,0				64,0	7,0
	Al	100,0												Impregnation	1057	0,64	0,08	8,2	1,0	0,30	99,0	7,0				17,0	1,2
	Mg	50,0					C	50,0						Therm.decomp.	1013	0,64	0,08	8,2	1,0	0,58	95,0	10,0				22,0	2,2
	Na	5,6	Ca	94,4										Impregnation	1013	0,66	0,08	8,3	1,0	0,20	75,0	13,0				74,0	9,6
	Mg	100,0												Therm.decomp.	1013	0,64	0,08	8,2	1,0	0,82	96,0	11,0				41,0	4,5
	Pb	21,7									Al	78,3		n.a.	1013	0,66	0,07	9,4	1,0	0,22	95,1	10,1		17,1	39,1	56,2	5,7
	Pb	12,0									Si	88,0		n.a.	1003	0,66	0,07	9,4	1,0	1,56	2,0	0,3		5,0	67,0	72,0	0,2
	Pb	100,0												n.a.	1013	0,65	0,07	9,3	1,0	6,24	10,0	0,5		8,7	54,1	62,8	0,3
	Na	18,1	Pb	10,7							Al	71,2		n.a.	1023	0,70	0,07	10,0	1,0	0,05	77,4	8,2		12,5	47,4	59,9	4,9
	Li	7,6	Pb	12,0							Al	80,4		n.a.	1023	0,70	0,07	10,0	1,0	0,21	100,0	10,0		21,3	35,6	56,9	5,7
	K	37,0	Pb	8,3							Al	54,7		n.a.	1023	0,70	0,07	10,0	1,0	0,21	90,0	9,8		16,3	41,9	58,2	5,7
	Ca	8,0	Pb	12,4							Al	79,6		n.a.	1023	0,70	0,07	10,0	1,0	0,21	99,0	9,9		16,6	40,4	57,0	5,6
	Li	100,0												n.a.	1023	0,70	0,07	10,0	1,0	0,42	21,5	2,2		4,2	40,9	45,1	1,0
	Na	100,0												n.a.	1023	0,70	0,07	10,0	1,0	0,16	12,4	1,2		6,0	44,0	50,0	0,6
21	Ca	100,0												n.a.	1023	0,70	0,07	10,0	1,0	0,39	96,8	8,2		9,1	32,3	41,4	3,4
	Mg	100,0												n.a.	1023	0,70	0,07	10,0	1,0	0,16	100,0	8,0		4,6	16,1	20,7	1,7
	Ba	100,0												n.a.	1023	0,70	0,07	10,0	1,0	0,16	2,7	0,2		1,9	41,7	43,6	0,1
	Li	19,1	Ca	80,9										n.a.	1023	0,67	0,07	9,6	1,0	0,41	100,0	9,4		27,0	44,6	71,6	6,7
	Na	5,3	Ca	94,7										n.a.	1023	0,67	0,07	9,6	1,0	0,16	100,0	10,8		18,3	47,9	66,2	7,1
	K	5,3	Ca	94,7										n.a.	1023	0,67	0,07	9,6	1,0	0,41	100,0	11,6		27,9	37,7	65,6	7,6
	Mg	1,4	Ca	98,6										n.a.	1023	0,67	0,07	9,6	1,0	0,42	100,0	9,0		14,3	31,8	46,1	4,1
	Sr	1,3	Ca	98,7										n.a.	1023	0,67	0,07	9,6	1,0	0,42	100,0	9,5		16,4	36,7	53,1	5,0
	Ba	1,4	Ca	98,6										n.a.	1023	0,67	0,07	9,6	1,0	0,08	100,0	12,7		16,1	33,8	49,9	6,3
	Pb	5,2	Ca	94,8										n.a.	1023	0,67	0,07	9,6	1,0	0,16	100,0	7,5		4,7	31,8	36,5	2,7
	Pb	2,5									Al	97,5		Impregnation	1057	0,64	0,08	8,2	1,0	0,73	99,0	9,0				14,0	1,3
	Pb	9,3									Al	90,7		Impregnation	1057	0,64	0,08	8,2	1,0	0,29	91,0	10,0				57,0	5,7
22	Li	15,2	Mg	84,8										n.a.	893	0,48	0,11	4,5	1,0	25,70		20,0				51,6	10,3
	Li	30,5	Mg	69,5										n.a.	973	0,47	0,11	4,4	1,0	8,00		22,0				71,0	15,6
	Li	22,2	Ca	77,8										n.a.	984	0,47	0,11	4,4	1,0	8,70		18,0	30,0	38,0	27,0	65,0	11,7
	Na	7,3	Ca	92,7										n.a.	982	0,47	0,11	4,4	1,0	8,70		16,0	25,0	35,0	35,0	70,0	11,2
	Li	17,2	Mg	82,8										n.a.	1043	0,38	0,13	3,0	1,0	5,50		59,0	48,0	36,0	17,0	53,0	31,3
	Sn	1,2	Li	17,6	Mg	81,20								n.a.	977	0,47	0,11	4,4	1,0	7,50		23,0	31,0	35,0	27,0	62,0	14,3
23	Li	22,2	Ca	77,8										n.a.	984	0,47	0,11	4,4	1,0	8,70		18,0	30,0	38,0	27,0	65,0	11,7
	Na	7,3	Ca	92,7										n.a.	982	0,47	0,11	4,4	1,0	8,70		16,0	25,0	35,0	35,0	70,0	11,2
	Na	8,5	Pb	8,5	Si	8,50	Zn	74,50						n.a.	1023	0,90	0,10	9,0	1,0	2,40	71,0	8,0		34,0	34,0	68,0	5,4
	Na	8,0	K	4,0	Co	20,00	Zr	50,00	S	16,0	P	2,0	Cl	Therm.decomp.	970	0,50	0,11	4,8	1,0	1,20		19,2		43,2	17,6	60,8	11,7
	Zr	100,0												n.a.	973	0,47	0,11	4,2	1,0	1,20		12,0		0,0	2,5	2,5	0,3
	Na	8,5	Pb	8,5	Si	8,50	Zn	74,50						n.a.	1023	0,90	0,10	9,0	1,0	2,40	71,0	8,0		34,0	34,0	68,0	5,4
	Cs	100,0											Cl	n.a.	1023	0,91	0,09	10,0	1,0	2,00		5,0		30,0	54,0	84,0	4,2
	Li	100,0											Cl	n.a.	1023	0,91	0,09	10,0	1,0	2,00		5,0		44,0	46,0	90,0	4,5
	Li	33,3	Ca	33,3	Pr	33,40							Cl	n.a.	1023	0,91	0,09	10,0	1,0	2,00		14,0		71,0	13,0	84,0	11,8
	Li	33,3	Ca	33,3	Ce	33,40							Cl	n.a.	1023	0,91	0,09	10,0	1,0	2,00		14,0		70,0	14,0	84,0	11,8
	Ca	100,0											Cl	n.a.	1023	0,67	0,07	10,0	1,0	2,00		14,0		71,0	11,0	82,0	11,5
	Mg	100,0											Cl	n.a.	1023	0,67	0,07	10,0	1,0	2,00		5,0		38,0	49,0	87,0	4,4
	Mn	100,0											Cl	n.a.	1023	0,67	0,07	10,0	1,0	2,00		14,0		71,0	13,0	84,0	11,8
	Pb	100,0											Cl	n.a.	1023	0,67	0,07	10,0	1,0	2,00		10,0		48,0	18,0	66,0	6,6
	Fe	100,0											Cl	n.a.	1023	0,67	0,07	10,0	1,0	2,00		14,0		55,0	20,0	75,0	10,5
	Ca	33,3							Cl	66,7				Impregnation	1023	0,66	0,34	1,9	1,0	0,72		19,9		60,4	9,3	69,7	13,9
	Mg	33,3							Cl	66,7				Impregnation	1023	0,66	0,07	9,4	1,0	1,80		5,3		38,2	49,1	87,3	4,6
	Li	50,0							Cl	50,0				Impregnation	1023	0,66	0,07	9,4	1,0	1,80		5,1		44,0	45,8	89,8	4,6
	Cs	50,0							Cl	50,0				Impregnation	1023	0,66	0,07	9,4	1,0	1,80		4,5		30,4	54,0	84,4	3,8
24	Mn	33,3							Cl	66,7				Impregnation	1023	0,66	0,07	9,4	1,0	1,80		14,4		71,5	12,5	84,0	12,1
	Pb	33,3							Cl	66,7				Impregnation	1023	0,66	0,07	9,4	1,0	1,80		10,5		47,5	18,3	65,8	6,9
	Cd	33,3							Cl	66,7				Impregnation	1023	0,66	0,07	9,4	1,0	1,80		3,7		15,8	36,0	51,8	1,9
	Fe	33,3							Cl	66,7				Impregnation	1023	0,66	0,07	9,4	1,0	1,80		13,9		54,6	20,1	74,7	10,4
	Ca	22,2	Mg	11,1					Cl	66,7				Impregnation	1023	0,66	0,07	9,4	1,0	1,80		14,2		50,9	24,3	75,2	10,7
	Ca	14,3	Li	14,3	Mn	14,30			Cl	57,1				Impregnation	1023	0,66	0,07	9,4	1,0	1,80		9,9		52,3	32,1	84,4	8,4
	Ca	14,3	Li	14,3	Pr	14,30			Cl	57,1				Impregnation	1023	0,66	0,07	9,4	1,0	1,80		14,3		71,2	13,3	84,5	12,1
	Ba	33,3							Br	66,7				Impregnation	1023	0,66	0,07	9,4	1,0	1,80		19,0		38,1	5,8	43,9	8,3
	Bi	50,0							Cl	50,0				Impregnation	1023	0,66	0,07	9,4	1,0	1,80		10,7		44,9	18,2	63,1	6,8
	Ca	33,3							Br	66,7				Impregnation	1023	0,66	0,07	9,4	1,0	1,80		13,3		34,4	9,7	44,1	5,9
	Ba	6,0							Br	12,0			Si	82,0	Impregnation	1023	0,66	0,07	9,4	1,0	1,80		8,9		49,8	21,4	71,2	6,3
	Ba	6,0							Br	12,0			Ca	82,0	Impregnation	1023	0,66	0,07	9,4	1,0	1,80		8,9		36,4	17,0	53,4	4,8
	Ba	6,0							Br	12,0			Zn	82,0	Impregnation	1023	0,66	0,07	9,4	1,0	1,80		11,8		41,0	25,6	66,6	7,9
	K	6,0							Br	6,0			Ti	88,0	Impregnation	1023	0,66	0,07	9,4	1,0	1,80		11,6		46,2	20,7	66,9	7,8
	La	25,0							Cl	75,0				Impregnation	1023	0,66	0,07	9,4	1,0	1,80		7,6		56,2	14,1	70,3	5,3
25	Cs	100,0											Cl	n.a.	1023	0,91	0,09	10,0	1,0	2,00		5,0		30,0	54,0	84,0	4,2

	Li	100,0										Cl				n.a.	1023	0,91	0,09	10,0	1,0	2,00		5,0		44,0	46,0	90,0	4,5
	Li	33,3	Ca	33,3	Pr	33,40						Cl				n.a.	1023	0,91	0,09	10,0	1,0	2,00		14,0		71,0	13,0	84,0	11,8
	Li	33,3	Ca	33,3	Ce	33,40						Cl				n.a.	1023	0,91	0,09	10,0	1,0	2,00		14,0		70,0	14,0	84,0	11,8
	Ca	100,0										Cl				n.a.	1023	0,67	0,07	10,0	1,0	2,00		14,0		71,0	11,0	82,0	11,5
	Mg	100,0										Cl				n.a.	1023	0,67	0,07	10,0	1,0	2,00		5,0		38,0	49,0	87,0	4,4
	Mn	100,0										Cl				n.a.	1023	0,67	0,07	10,0	1,0	2,00		14,0		71,0	13,0	84,0	11,8
	Pb	100,0										Cl				n.a.	1023	0,67	0,07	10,0	1,0	2,00		10,0		48,0	18,0	66,0	6,6
	Fe	100,0										Cl				n.a.	1023	0,67	0,07	10,0	1,0	2,00		14,0		55,0	20,0	75,0	10,5
	Li	21,1	Ti	26,3	Mg	52,60										n.a.	1024	0,50	0,10	5,0	1,0	7,90		8,0	25,0	34,0	39,0	73,0	5,8
	Li	25,0	Ti	25,0	Ca	50,00										n.a.	980	0,50	0,10	5,0	1,0	7,90		17,0	22,0	39,0	31,0	70,0	11,9
	Ti	22,3	Li	33,3	Sr	44,40										n.a.	979	0,50	0,10	5,0	1,0	7,80		13,0	2,0	42,0	49,0	91,0	11,8
	Li	45,5	La	54,5												n.a.	977	0,47	0,11	4,2	1,0	8,00		34,0	4,0	52,0	34,0	86,0	29,2
	Na	18,2	La	81,8												n.a.	976	0,50	0,11	4,7	1,0	7,20		43,0	20,0	31,0	43,0	74,0	31,8
26	K	11,5	La	88,5												n.a.	974	0,50	0,11	4,7	1,0	7,20		41,0	26,0	28,0	41,0	69,0	28,3
	Li	19,2	La	80,8												n.a.	1073	0,30	0,05	6,0	1,0	0,19	100,0	22,0	24,0	33,0	38,0	71,0	15,6
	Sr	1,9	La	98,1												n.a.	1023	0,30	0,05	6,0	1,0	0,18	100,0	21,0	31,0	29,0	35,0	64,0	13,4
	La	100,0														n.a.	1023	0,30	0,05	6,0	1,0	0,18	100,0	20,0	51,0	26,0	31,0	57,0	11,4
	Na	,3	Pb	49,8								Si	49,9			n.a.	1113	0,87	0,03	30,9	1,0	2,12	100,0	6,0	13,0	33,0	47,0	80,0	4,8
	Na	,5	Pb	6,2								Si	93,3			n.a.	1113	0,83	0,04	23,8	1,0	2,12	100,0	6,0	13,0	33,0	47,0	80,0	4,8
	Li	7,0	Mg	93,0												Therm.decomp.	973	0,47	0,11	4,4	1,0	7,60		23,7		37,5	24,1	61,6	14,6
	Li	3,0	Mg	97,0												Therm.decomp.	958	0,47	0,11	4,4	1,0	7,60		20,4		47,3	39,1	86,4	17,6
	Sn	3,0	Li	3,0	Mg	94,00										Therm.decomp.	977	0,47	0,11	4,4	1,0	7,60		23,0		35,0	37,0	72,0	16,6
	Mg	100,0														Therm.decomp.	978	0,47	0,11	4,4	1,0	7,60		15,7		6,8	8,9	15,7	2,5
27	Li	3,0										Si	97,0			Therm.decomp.	989	0,47	0,11	4,4	1,0	7,60		2,0		11,0	0,0	11,0	0,2
	Li	3,0										Al	97,0			Therm.decomp.	973	0,47	0,11	4,4	1,0	7,60		15,0		0,0	3,0	3,0	0,5
	Li	3,0										Ca	48,5	Si	48,5	Therm.decomp.	973	0,47	0,11	4,4	1,0	7,60		3,0		0,0	0,0	0,0	0,0
	Pb	25,0										Al	75,0			Therm.decomp.	943	0,47	0,11	4,4	1,0	7,60		16,7		8,9	8,7	17,6	2,9
	Pb	25,0	Li	,2								Al	74,8			Therm.decomp.	978	0,47	0,11	4,4	1,0	7,60		16,7		8,7	3,7	12,4	2,1
28	Zr	25,0	Li	50,0						C	25,0					Therm.decomp.	1060	0,67	0,33	2,0	1,0	6,00	99,8	40,6		30,4	11,3	41,7	16,9
	Zr	25,0	Li	50,0						C	25,0					Therm.decomp.	1078	0,67	0,33	2,0	1,0	6,00	99,7	31,4		33,4	12,5	45,9	14,4
29	Ba	50,0	Ce	50,0												Therm.decomp.	1023	0,73	0,28	2,6	1,0	0,00		11,8				38,0	4,5
30	Sm	100,0														n.a.	1023	0,87	0,14	6,1	1,0	0,00		20,0				61,0	12,2
31	Ba	8,3	Ca	91,7												Impregnation	1073	0,40	0,08	5,0	1,0	0,55	99,7	21,5		30,0	27,0	57,1	12,3
32	Mg	2,8	Ca	91,5						Cl	5,7					Impregnation	1023	0,13	0,01	9,3	1,0	0,16	45,0	8,0		40,0	47,0	87,1	7,0
33	Li	50,0	Be	50,0												Impregnation	1033	0,76	0,25	3,0	1,0	0,01	73,0	24,2				63,0	15,2
34	Pb	4,3	Mg	95,7												n.a.	1073	0,14	0,02	8,9	1,0	0,16	97,0	13,0	29,0	16,0	54,0	70,0	9,1
35	Pb	,9	Mg	99,1												Precipitation	1073	0,14	0,02	8,9	1,0	0,16	98,0	13,0				71,0	9,2
	Li	20,0										Al	80,0			Impregnation	1064	0,68	0,07	9,9	1,0	0,22	100,0	13,0				76,0	9,9
	Li	24,7										Al	75,3			Precipitation	1076	0,50	0,11	4,8	1,0	0,22	100,0	23,0				54,0	12,4
	Pb	16,1										Al	83,9			Impregnation	986	0,50	0,10	4,8	1,0	0,22	100,0	19,0				48,0	9,1
	Na	23,5	Pb	8,0								Al	68,5			Precipitation	1095	0,50	0,10	4,8	1,0	0,22	100,0	20,0				52,0	10,4
	Na	7,1										Al	92,9			Impregnation	1102	0,52	0,10	5,1	1,0	0,22		15,0				19,0	2,9
	Ca	33,3										Al	66,7			Impregnation	1112	0,68	0,07	9,9	1,0	0,22		8,0				31,0	2,5
36	Mg	100,0														n.a.	1139	0,67	0,07	10,1	1,0	0,22		8,0				30,0	2,4
	Cu	50,0	Mg	50,0												Impregnation	1113	0,70	0,06	11,7	1,0	0,22		6,0				9,0	0,5
	Si	50,0								C	50,0					n.a.	1115	0,64	0,08	8,5	1,0	0,22		7,0				30,0	2,1
	Bi	50,0	Sn	50,0												n.a.	1054	0,50	0,10	5,0	1,0	0,22		13,0				25,0	3,3
	Bi	33,3										Al	66,7			Impregnation	1022	0,50	0,10	5,0	1,0	0,22		12,0				8,0	1,0
	Mn	12,4										Al	87,6			Impregnation	1113	0,50	0,10	5,0	1,0	0,22		12,0				6,0	0,7
	Fe	25,0	Cr	25,0								Al	50,0			Impregnation	1073	0,50	0,10	5,0		0,22		11,0				7,0	0,8
	Li	24,8	Mg	75,2												n.a.	803	0,51	0,11	4,7	1,0	0,23		23,0				54,0	12,4
37	Na	16,7	Mn	66,6						Cl	16,7					Impregnation	1023	0,57	0,28	2,0	1,0	0,24	99,4	46,8		55,0	4,0	59,0	27,6
38	Yb	5,0	Ce	45,0	Sr	50,00										n.a.	1023	0,13	0,07	2,0	1,0	0,79		56,0	40,0	36,0	24,0	60,0	33,6
	Li	50,0	Ni	50,0												Pyrolysis	1023	0,10	0,05	2,0	1,0	0,60	43,6	22,2				59,0	13,1
39	Li	30,5	Mg	69,5												n.a.	973	0,10	0,05	2,0	1,0	0,87		22,6				56,7	12,8
40	Pb	4,7	Mg	95,3												n.a.	1073	0,14	0,02	8,8	1,0	0,16		13,0				71,0	9,2
	Li	37,0	Mg	63,0												n.a.	1043	0,91	0,09	10,0	1,0	1,30	71,0	11,0	22,0	31,0	41,0	72,0	7,9
41	Sr	100,0														n.a.	1073	0,20	0,01	40,8	1,0	2,00		7,0				93,0	6,5
	Ba	100,0														n.a.	1073	0,20	0,01	40,8	1,0	2,00		8,0				90,0	7,2
42	Li	14,3	Mg	85,7												n.a.	1008	0,67	0,07	10,0	1,0	3,90		10,0		31,0	42,0	73,0	7,3
	Li	14,3	Mg	85,7								Cl				n.a.	1008	0,67	0,07	10,0	1,0	3,90		10,0		43,0	31,0	74,0	7,4
43	Li	75,0	Ti	25,0								Cl				n.a.	1008	0,20	0,02	9,8	1,0	3,90		14,0		48,0	21,0	69,0	9,7
	Ti	33,3	Li	66,7												n.a.	1033	0,67	0,33	2,0	1,0	6,00	98,0	22,0	42,0	13,0	42,0	55,0	12,1
	Ce	33,3	Li	66,7												n.a.	1061	0,67	0,33	2,0	1,0	6,00	100,0	38,0	48,0	34,0	14,0	48,0	18,2
44	Zr	33,3	Li	66,7												n.a.	1067	0,67	0,33	2,0	1,0	6,00	100,0	38,0	51,0	32,0	13,0	45,0	17,1
	Li	15,5	Pr	84,5												n.a.	1057	0,67	0,33	2,0	1,0	6,00	100,0	40,0	48,0	28,0	16,0	44,0	17,6
	Li	11,5	Na	11,5	Pr	77,00										n.a.	1031	0,67	0,33	2,0	1,0	6,00	100,0	41,0	47,0	30,0	15,0	45,0	18,5
	Li	50,0	Th	50,0												n.a.	1078	0,67	0,33	2,0	1,0	6,00	100,0	31,0	47,0	33,0	13,0	46,0	14,3
	K	12,0	Zn	76,0						P	12,0					Impregnation	1084	0,75	0,25	3,0	1,0	2,77		21,0		20,0	14,0	34,0	7,1
	Ca	5,0	Zn	95,0												n.a.	1049	0,75	0,25	3,0	1,0	2,77		24,0		26,0	15,0	41,0	9,8
	Si	28,5	Al	4,7						C	66,8					n.a.	1176	0,75	0,25	3,0	1,0	2,77		26,0		19,0	2,0	21,0	5,5
										B	50,0	N	50,0			n.a.	1117	0,75	0,25	3,0	1,0	2,77		27,0		19,0	2,0	21,0	5,7
	K	12,0	Ca	76,0						P	12,0					Impregnation	927	0,75	0,25	3,0	1,0	0,30		22,0		25,0	14,0	39,0	8,6
45	K	12,0	Gd	76,0						P	12,0					Impregnation	1032	0,75	0,25	3,0	1,0	0,30		13,0		12,0	11,0	23,0	3,0
	K	12,0	Si	76,0						P	12,0					Impregnation	1103	0,75	0,25	3,0	1,0	2,77		26,0		29,0	7,0	36,0	9,4
	Si	90,0								B	10,0					Impregnation	1123	0,75	0,25	3,0	1,0	36,00		20,5		15,5	0,0	15,5	3,2
	K	12,0	Zr	76,0						P	12,0					Impregnation	1076	0,60	0,20	3,0	1,0	2,77		23,0		15,0	10,0	25,0	5,8
	K	12,0	Cr	76,0						P	12,0					Impregnation	1217	0,75	0,25	3,0	1,0	2,77		20,0		5,0	1,0	6,0	1,2
	K	12,0	Ti	76,0						P	12,0					Impregnation	1088	0,60	0,20	3,0	1,0	0,30		21,0		7,0	5,0	12,0	2,5
46	Mn	8,0	Na	10,0								P	5,0	Si	77,0	Impregnation	1048	0,50	0,11	4,8	1,0	1,00	92,0	48,0		26,0	13,0	39,0	18,7
	Na	25,0	Mn	12,0	Mg	63,00										Impregnation	1098	0,50	0,11	4,8	1,0	1,00	93,0	28,0		54,0	13,0	67,0	18,8
	Li	7,5	Na	15,0	K	7,50	Mn	20,00	C	50,0						Therm.decomp.	1173	0,90	0,10	9,0	1,0			6,2				98,0	6,1
	Na	66,7	W	33,3												n.a.	1123	0,90	0,10	9,0	1,0			2,5				96,0	2,4
47	Na	66,7	Mo	33,3												n.a.	1123	0,90	0,10	9,0	1,0			3,3				42,0	1,4
	Na	66,7								S	33,3					n.a.	1123	0,90	0,10	9,0	1,0			1,0				70,0	0,7
	Li	25,0	Na	30,0	K	20,00	Pr	4,00	C	21,0						Therm.decomp.	1173	0,90	0,10	9,0	1,0			10,2				37,0	3,8
	Mo	1,8	W	,1	V	0,10								Si	98,0	Therm.decomp.	823	0,49	0,11	4,7	1,0	8,00		17,2		5,8	13,4	19,2	3,3
	Mo	1,7	W	,1	Co	0,10	K	0,10						Si	98,0	Impregnation	823	0,08	0,01	6,7	1,0	0,50		9,0		4,3	15,1	19,4	1,7
	W	1,8	Mo	,1	Co	0,10								Si	98,0	Impregnation	823	0,18	0,03	6,0	1,0	1,00		9,1		3,0	9,3	12,3	1,1
48	Mo	1,0	W	,1	V	0,10	K	0,80						Si	98,0	Impregnation	823	0,18	0,03	6,0	1,0	1,30		11,6		5,8	13,4	19,2	2,2
	Mo	1,6	W	,1	V	0,10	K	0,20						Si	98,0	Impregnation	823	0,06	0,01	6,0	1,0	0,70		9,3		8,0	16,1	24,1	2,2
	Mo	1,8	W	,1	Co	0,10								Si	98,0	Sol-gel	823	0,08	0,01	8,0	1,0	0,50		9,6		3,5	14,4	17,9	1,7
	Mo	,4	W	,0	Co	0,02								Si	19,6	Al	80,0	Impregnation	923	0,08	0,02	4,0	1,0	0,85		13,2		20,0	14,9	34,9	4,6

	Mo	1,8	W	,1	Co	0,10							Si	98,0			Impregnation	823	0,17	0,04	4,3	1,0	2,60		15,1		8,8	14,5	23,3	3,5
	Mo	,4	W	,0	Co	0,02							Si	19,6	Al	80,0	Impregnation	823	0,09	0,01	9,0	1,0	0,70		6,8		9,5	15,0	24,5	1,7
49	Li	20,0	Mn	60,1				Cl	19,9								Impregnation	1023	0,50	0,02	25,0	1,0	0,75	90,0	33,7	41,0	49,0	12,0	61,3	20,7
	Na	10,0	Mn	80,0				Cl	10,0								n.a.	1023	0,50	0,03	20,0	1,0	0,38		13,0				75,8	9,9
50	Li	50,0	Y	50,0													Therm.decomp.	970	0,18	0,03	6,1	1,0	1,60	99,0	24,0		23,0	49,0	72,0	17,3
51	Li	19,8	Ce	,6	Mg	79,60											n.a.	973	0,22	0,11	2,0	1,0	2,43	90,0	25,0	2,0	67,0	31,0	91,0	22,8
52	Na	20,5	Si	46,1	Mn	33,40							P				n.a.	1198	0,50	0,10	5,0	1,0	0,75		22,0				66,0	14,5
	Na	3,8	Mn	3,8	Mg	92,40											n.a.	1198	0,50	0,10	5,0	1,0	0,38		22,0				70,0	15,4
53	Pb	7,7	Mg	92,3													n.a.	1073	0,69	0,10	6,7	1,0	0,11		16,0				78,0	12,5
54	La	34,9	Sr	65,1													Therm.decomp.	1023	0,30	0,05	6,0	1,0	0,18	100,0	20,9	32,0	29,0	35,0	64,0	13,4
55	Li	50,0	Ni	50,0													n.a.	1023	0,10	0,05	2,0	1,0	0,65	44,0	22,0				59,0	13,0
56	Na	5,0	La	45,0	Mn	50,00											n.a.	1093	0,51	0,10	5,0	1,0	0,87	80,0	21,0				63,4	13,3
	Na	5,0	La	45,0	Mn	50,00											n.a.	1093	0,83	0,17	5,0	1,0	2,20		21,0				64,0	13,4
57	Na	5,0	Gd	45,0	Mn	50,00											n.a.	1093	0,83	0,17	5,0	1,0	2,20		20,0				71,0	14,2
	Na	5,0	Sm	45,0	Mn	50,00											n.a.	1093	0,83	0,17	5,0	1,0	2,20		19,0				69,0	13,1
58	La	50,0	Al	50,0													Pyrolysis	983	0,51	0,10	5,0	1,0	0,06		21,1				40,0	8,4
	Li	5,6	Mg	94,4													n.a.	1123	0,30	0,05	6,0	1,0	0,09	100,0	21,0	29,0	38,0	29,0	67,0	14,1
59	Ag	1,5	La	98,5													n.a.	1073	0,30	0,05	6,0	1,0	0,18	100,0	20,0	37,0	28,0	32,0	60,0	12,0
	Ca	4,0	La	96,0													n.a.	1023	0,30	0,05	6,0	1,0	0,18	100,0	19,0	35,0	29,0	31,0	60,0	11,4
60	Zn	33,3	Fe	66,7													Sol-gel	1103	0,42	0,08	5,0	1,0	0,25		18,0				72,2	13,0
61	Li	2,1	Zn	97,9													n.a.	1023	0,08	0,04	2,0	1,0	5,20	56,0	28,0		29,0	25,0	54,0	15,1
62	Na	30,3	Ca	69,7													n.a.	948	0,40	0,03	14,6	1,0	1,20		8,0				80,0	6,4
63	Na	23,1	Pr	76,9													n.a.	1173	0,50	0,10	5,0	1,0	0,75		22,0				64,0	14,1
	Li	5,8	Mg	93,3			B	0,90									n.a.	1069	0,60	0,08	7,1	1,0	0,72		21,0				86,0	18,1
64	Li	68,8	Ti	31,2													n.a.	1023	0,32	0,08	4,0	1,0	0,16	68,0	10,0	27,0	21,0	46,0	67,0	6,7
	Ni	20,0	Ti	20,0	Li	60,00											n.a.	1023	0,32	0,08	4,0	1,0	0,16		19,0				70,0	13,3
	Ca	100,0											Cl				n.a.	1073	0,15	0,08	2,0	1,0	0,90		40,0		57,0	8,0	65,0	26,0
	Ce	2,0	Li	4,1	Mg	93,90											n.a.	973	0,22	0,11	2,0	1,0	2,65		46,0				44,0	20,2
65	Ce	2,0	Li	4,1	Ca	93,90											n.a.	973	0,22	0,11	2,0	1,0	2,65		46,0				46,0	21,2
	Ce	2,0	Li	4,1	Sr	93,90											n.a.	973	0,22	0,11	2,0	1,0	2,65		14,0				88,0	12,3
	Ce	2,0	Li	4,1	Ba	93,90											n.a.	973	0,22	0,11	2,0	1,0	2,65		18,0				71,0	12,8
66	Zn	,4	Li	18,1	Mg	81,50											n.a.	1073	0,28	0,13	2,1	1,0	0,52		16,0		40,0	33,0	73,0	11,7
	Li	17,9	Mg	82,1													n.a.	1073	0,28	0,13	2,1	1,0	0,52		21,0		34,0	30,0	64,0	13,4
	Li	20,0	Ti	80,0									Cl				n.a.	1023	0,05	0,03	2,0	1,0	0,65	40,0	18,0		77,0	6,0	83,0	14,9
67	Li	7,7	Co	92,3									Cl				n.a.	1023	0,05	0,03	2,0	1,0	0,65	91,0	48,0		32,0	3,0	35,0	16,8
	Li	20,0	Ni	80,0									Cl				n.a.	1023	0,05	0,03	2,0	1,0	0,65	57,0	26,0		56,0	16,0	72,0	18,7
	Li	20,0	Zn	80,0									Cl				n.a.	1023	0,05	0,03	2,0	1,0	0,65	49,0	22,0		43,0	26,0	69,0	15,2
	Co	,4	Li	18,1	Mg	81,50											n.a.	1073	0,28	0,13	2,1	1,0	0,52		22,0		52,0	45,0	97,0	21,3
68	Fe	,4	Li	18,1	Mg	81,50											n.a.	1073	0,28	0,13	2,1	1,0	0,52		23,0		52,0	43,0	95,0	21,9
	Mn	,4	Li	18,1	Mg	81,50											n.a.	1073	0,28	0,13	2,1	1,0	0,52		26,0		46,0	34,0	80,0	20,8
69	Li	14,3	Mg	85,7													n.a.	1053	0,67	0,07	9,6	1,0	0,22	100,0	13,0	27,0	31,0	42,0	73,0	9,5
70	Pb	10,0	Al	90,0													n.a.	1073	0,14	0,02	8,9	1,0	0,16	94,0	13,0	30,0	19,0	51,0	70,0	9,1
71	Na	5,8	Ca	94,2													Impregnation	1013	0,70	0,08	9,3	1,0	0,36	95,0	16,0				76,0	12,2
	Ba	100,0															n.a.	1013	0,70	0,08	9,3	0,1	14,45	98,0	14,0				70,0	9,8
	Ba	100,0															n.a.	1013	0,67	0,08	8,0	1,0	16,00	98,0	14,0	30,0	31,0	32,0	63,0	8,8
72	Li	25,0	Bi	75,0									Cl				n.a.	1023	0,06	0,03	2,0	1,0	90,00		22,0		60,0	17,0	77,0	16,9
	Na	25,0	Bi	75,0									Cl				n.a.	1023	0,06	0,03	2,0	1,0	90,00		23,0		65,0	18,0	83,0	19,1
	K	25,0	Bi	75,0									Cl				n.a.	1023	0,06	0,03	2,0	1,0	90,00		24,0		65,0	17,0	82,0	19,7
	Bi	100,0											Cl				n.a.	1023	0,06	0,03	2,0	1,0	90,00		23,0		58,0	13,0	71,0	16,3
73	Li	15,2	Mg	84,8													n.a.	973	0,28	0,16	1,8	1,0	4,90		39,4				37,6	14,8
74	Na	2,5	Mn	15,0				P	2,5				Si	80,0			n.a.	1198	0,50	0,10	5,0	1,0	0,75		22,0				66,0	14,5
	Li	4,0	Ce	2,0	Mg	94,00											Impregnation	973	0,22	0,11	2,0	1,0	2,40		46,3				43,8	20,3
75	Li	4,0	Ce	2,0	Ca	94,00											Impregnation	973	0,22	0,11	2,0	1,0	2,40		44,0				45,7	20,1
	Li	4,0	Ce	2,0	Sr	94,00											Impregnation	973	0,22	0,11	2,0	1,0	2,40		14,2				87,8	12,5
	Li	4,0	Ce	2,0	Ba	94,00											Impregnation	973	0,22	0,11	2,0	1,0	2,40		18,4				71,2	13,1
76	Na	7,7	Ca	92,3													Impregnation	1013	0,66	0,08	8,3	1,0			17,5				80,0	14,0
	Na	6,0	Ca	94,0													Impregnation	1013	0,35	0,14	2,5	1,0			30,4				56,0	17,0
77	Li	29,4	Zn	70,6													n.a.	980	0,50	0,06	8,3	1,0	4,40		11,0	19,0	31,0	46,0	77,0	8,5
	Na	14,3	Mn	28,6	Mg	57,10							B				n.a.	1123	0,50	0,10	5,0	1,0	1,50		29,0				69,0	20,0
	Na	6,7	La	93,3													n.a.	1073	0,30	0,05	6,0	1,0	0,19	100,0	33,0	30,0	31,0	33,0	64,0	21,1
	K	4,0	La	96,0													n.a.	1073	0,30	0,05	6,0	1,0	0,19	100,0	30,0	36,0	30,0	30,0	60,0	18,0
78	Mg	6,3	La	93,7													n.a.	1023	0,30	0,05	6,0	1,0	0,18	100,0	21,0	35,0	28,0	32,0	60,0	12,6
	Ba	1,2	La	98,8													n.a.	1073	0,30	0,05	6,0	1,0	0,18	100,0	20,0	32,0	31,0	34,0	65,0	13,0
	Bi	,8	La	99,2													n.a.	1023	0,30	0,05	6,0	1,0	0,18	100,0	18,0	35,0	27,0	35,0	62,0	11,2
79	La	66,7						C	33,3								Therm.decomp.	973	0,88	0,12	7,3	1,0	0,05	97,2	17,7		34,1	34,0	68,1	12,1
80	Li	12,0	Mn	50,0	Mg	21,00		B	17,0								Therm.decomp.	1143	0,50	0,11	4,8	1,0	19,80	69,8	15,1		33,2	9,8	43,0	6,5
	Li	12,0	Mn	25,0	Mg	21,00		B	17,0				Al	25,0			Therm.decomp.	1143	0,50	0,11	4,8	1,0	19,80	99,0	23,5		35,8	5,5	41,3	9,7
	Na	20,0	Mn	60,0				Cl	20,0								Impregnation	1073	0,67	0,33	2,0	1,0	3,00	99,0	37,5		24,0	12,1	36,1	13,5
	Al	2,3	Na	19,5	Mn	58,70		Cl	19,5								Impregnation	1073	0,67	0,33	2,0	1,0	3,00	99,0	29,3		8,5	7,5	16,0	4,7
	Sn	2,3	Na	19,5	Mn	58,70		Cl	19,5								Impregnation	1073	0,67	0,33	2,0	1,0	3,00	99,0	38,4		30,6	9,4	40,0	15,4
	Ti	2,3	Na	19,5	Mn	58,70		Cl	19,5								Impregnation	1073	0,67	0,33	2,0	1,0	3,00	99,0	41,8		31,3	10,4	41,7	17,4
81	W	2,3	Na	19,5	Mn	58,70		Cl	19,5								Impregnation	1073	0,67	0,33	2,0	1,0	3,00	99,0	40,7		31,2	12,3	43,5	17,7
	Ta	2,3	Na	19,5	Mn	58,70		Cl	19,5								Impregnation	1073	0,67	0,33	2,0	1,0	3,00	99,0	44,1		34,6	9,8	44,4	19,6
	Si	5,0	Na	19,9	Mn	55,20		Cl	19,9								Impregnation	1073	0,67	0,33	2,0	1,0	3,00	99,0	44,3		39,7	6,8	46,5	20,6
	Na	10,0	Mn	30,0				Cl	10,0				Si	25,0	C	25,0	Impregnation	1073	0,67	0,33	2,0	1,0	3,00	99,0	46,2		35,8	8,6	44,4	20,5
	Na	10,0	Mn	30,0				Cl	10,0				Si	50,0			Impregnation	1073	0,67	0,33	2,0	1,0	3,00	99,0	44,8		45,4	6,7	52,1	23,3
82	Sm	50,0	Li	50,0													Impregnation	973	0,14	0,07	2,0	1,0	0,80	50,3	31,9	72,0	5,0	24,0	28,7	9,2
	Nd	50,0	Li	50,0													Impregnation	973	0,14	0,07	2,0	1,0	0,80	56,1	30,4	62,0	14,0	24,0	38,0	11,6
83	Li	8,3	Mo	27,8	Bi	55,60		Cl	8,3								Therm.decomp.	1023	0,05	0,03	2,0	1,0	108,00	43,0	18,0	62,0	34,0	2,0	35,8	6,4
84	Li	3,0	Mg	97,0													Impregnation	973	0,76	0,25	3,0	1,0	0,01	91,0	38,3		19,0	37,0	56,0	21,4
85	Na	3,7	Mn	92,7				Cl	3,6								Impregnation	1023	0,51	0,03	20,3	1,0	0,10		5,5				87,8	4,8
86	Li	5,0	Sb	6,2									Si	88,8			Precipitation	1053	0,51	0,11	4,5	1,0	0,33		2,0	32,0	8,0	60,0	68,0	1,4
87	La	50,0	Ti	50,0													Pyrolysis	1023	0,41	0,10	4,0	1,0	0,60	99,0	20,0				50,0	10,0
88	Ti	5,5	Li	11,6									Si	82,9			n.a.	1047	0,14	0,05	3,0	1,0	3,00	100,0	15,0	25,0	31,0	44,0	75,0	11,3
89	Sn	1,6	Li	20,2	Mg	78,20											Mech. Mixing	953	0,67	0,07	9,6	1,0	0,23	90,0	14,3				84,0	12,0
90	Li	4,6	Si	40,8	Mg	54,60											n.a.	1123	0,19	0,09	2,0	1,0	10,91	90,0	43,1				39,6	17,1
	Li	2,6	Zn	1,0	Mg	96,40											Impregnation	1053	0,17	0,07	2,3	1,0	0,24	90,0	42,0				47,0	19,7
	Mg	3,0	Ca	97,0									Cl				n.a.	1023	0,13	0,01	8,9	1,0	0,16	45,0	8,0		40,0	47,0	87,0	7,0
91	Mg	1,6	Ca	98,4									Br				n.a.	1023	0,13	0,01	8,9	1,0	0,16	65,0	8,0		18,0	56,0	74,0	5,9
	Ca	100,0											Cl				n.a.	1023	0,13	0,01	8,9	1,0	0,16	35,0	5,0		34,0	49,0	83,0	4,2
	Mg	100,0											Cl				n.a.	1023	0,13	0,01	8,9	1,0	0,16	45,0	8,0		18,0	56,0	74,0	5,9
92	Ca	1,9	Mg	98,1									Cl				n.a.	1023	0,13	0,01	8,9	1,0	0,16	58,0	7,0		28,0	48,0	76,0	5,3

93	Li	14,5	Co	70,9			Cl	14,6					Therm.decomp.	973	0,10	0,05	2,0	1,0	2,40	90,0	42,0				50,0	21,0
94	La	4,8	Ca	95,2									Impregnation	1073	0,81	0,20	4,0	1,0	0,03		22,7				66,8	15,2
	Ba	100,0											n.a.	1073	0,14	0,06	2,3	1,0	0,04	90,0	34,8				42,8	14,9
95	Ba	100,0											Impregnation	1073	0,14	0,06	2,3	1,0	0,04	81,0	34,2	60,0			43,0	14,7
	La	13,6	Ba	86,4									Impregnation	1073	0,14	0,06	2,3	1,0	0,04	99,9	36,6	51,0			50,0	18,3
96	Ce	18,8	Li	8,8	Mg	72,40							Therm.decomp.	1023	0,08	0,04	2,0	1,2	0,16		33,0				45,0	14,9
97	Li	50,0	Mg	50,0									n.a.	1053	0,40	0,20	2,0	1,0	1,30		40,0		32,0	11,0	43,0	17,2
98	Ca	100,0							Cl				n.a.	1073	0,15	0,08	2,0	1,0	0,90		39,0	37,0	56,0	7,0	63,0	24,6
	Ca	100,0							Cl				n.a.	1073	0,15	0,08	2,0	1,0	0,90		26,0	25,0	66,0	9,0	75,0	19,5
99	Li	21,4	Ca	14,3	Bi	64,30			Cl				n.a.	993	0,20	0,10	2,0	1,0	2,60		18,0		49,0	18,0	67,0	12,1
	Li	20,0	Ca	20,0	Bi	60,00			Cl				n.a.	993	0,20	0,10	2,0	1,0	2,60		22,0		54,0	13,0	67,0	14,7
	Na	20,0	Ca	20,0	Bi	60,00			Cl				n.a.	993	0,20	0,10	2,0	1,0	2,60		16,0		45,0	20,0	65,0	10,4
	Li	16,7	Ca	33,3	Bi	50,00			Cl				n.a.	993	0,20	0,10	2,0	1,0	2,60		42,0		45,0	2,0	47,0	19,7
100	Na	4,3	Zr	95,7									n.a.	1023	0,40	0,13	3,1	1,0	0,12		18,2				59,0	10,7
101	Na	5,0	La	45,0	Mn	50,00							Impregnation	1118	0,41	0,20	2,0	1,0	0,40	44,5	19,8	53,0	30,0	17,0	47,4	9,4
102	Li	11,1	Ca	11,1	Bi	33,30	Cl	44,5					Impregnation	993	0,20	0,10	2,0	1,0	2,40	47,0	21,9				67,0	14,7
103	La	9,1	Mg	90,9									Impregnation	1073	0,81	0,20	4,0	1,0	0,03		24,1				63,3	15,3
104	La	9,1	Mg	90,9									Impregnation	1023	0,81	0,20	4,0	1,0	0,04	98,7	29,1				70,0	20,4
105	Sr	2,6	Sm	94,8			C	2,6					Therm.decomp.	573	0,71	0,29	2,5	1,0	1,40		31,4		25,0	14,5	39,5	12,4
	Sm	100,0											Therm.decomp.	573	0,71	0,29	2,5	1,0	1,40		29,3				24,5	7,2
106	Ba	4,3	La	8,7	Mg	87,00							Therm.decomp.	1073	0,81	0,20	4,0	1,0	0,07		26,0				65,3	17,0
107	Ti	16,6	La	16,7	Li	66,70							n.a.	1023	0,32	0,08	4,0	1,0	0,16		19,0				75,0	14,3
108	Li	5,8	Ca	94,2									Impregnation	1013	0,67	0,07	9,1	1,0	0,36	91,0	16,0	23,0	27,0	41,0	68,0	10,9
	K	2,4	Ca	97,6									Impregnation	1013	0,67	0,07	9,1	1,0	0,25	93,0	15,0	26,0	24,0	42,0	66,0	9,9
	Li	5,7	Ca	91,4			C	2,9					n.a.	1013	0,67	0,07	9,0	1,0	0,36	91,0	16,0		41,0	27,0	68,0	10,9
	K	6,9	Ca	89,7			C	3,4					n.a.	1013	0,67	0,07	9,0	1,0	0,14	91,0	14,0		42,0	20,0	62,0	8,7
	Na	6,5	Ca	90,3			C	3,2					n.a.	1013	0,67	0,07	9,0	1,0	0,14	83,0	15,0		42,0	25,0	67,0	10,1
	Na	5,9	Ca	94,1									n.a.	1013	0,67	0,07	9,0	1,0	0,15	90,0	14,0		43,0	24,0	67,0	9,4
	Na	6,7	Ca	90,0			S	3,3					n.a.	1013	0,67	0,07	9,0	1,0	0,19	92,0	16,0		45,0	26,0	71,0	11,4
	K	5,7	Ca	91,4			S	2,9					n.a.	1013	0,67	0,07	9,0	1,0	0,22	85,0	15,0		42,0	27,0	69,0	10,4
	Li	6,5	Ca	90,3			S	3,2					n.a.	1013	0,67	0,07	9,0	1,0	1,40	99,0	16,0		32,0	33,0	65,0	10,4
	Sr	100,0											n.a.	1013	0,67	0,08	8,0	1,0	25,00	88,0	12,0	28,0	36,0	28,0	64,0	7,7
109	Pb	8,9								Al	91,1		Therm.decomp.	1017	0,51	0,05	10,1	1,0	3,28	94,0	6,5	66,0	28,0	6,0	33,9	2,2
	Pb	8,7	Al	91,3									Therm.decomp.	1017	0,51	0,05	10,1	1,0	0,00	94,0	6,5	66,0	28,0	6,0	33,9	2,2
	Mn	40,0	Li	60,0									n.a.	1053	0,33	0,17	2,0	1,0	0,39		32,0				50,0	16,0
	Fe	40,0	Li	60,0									n.a.	1073	0,33	0,17	2,0	1,0	0,39		40,0				55,0	22,0
	In	40,0	Li	60,0									n.a.	1053	0,33	0,17	2,0	1,0	0,39		35,0				57,0	20,0
	Ni	40,0	Li	60,0									n.a.	1033	0,33	0,17	2,0	1,0	0,39		35,0				68,0	23,8
110	Li	50,0	Ni	50,0									n.a.	1013	0,33	0,17	2,0	1,0	0,39		40,0				52,0	20,8
	Ti	28,6	Li	71,4									n.a.	1053	0,33	0,17	2,0	1,0	0,39		30,0				62,0	18,6
	Ge	28,6	Li	71,4									n.a.	1113	0,33	0,17	2,0	1,0	0,39		32,0				50,0	16,0
	Sr	28,6	Li	71,4									n.a.	1073	0,33	0,17	2,0	1,0	0,39		37,0				55,0	20,4
	Sn	28,6	Li	71,4									n.a.	1053	0,33	0,17	2,0	1,0	0,39		29,0				63,0	18,3
111	La	10,7	Ba	89,3									n.a.	1023	0,50	0,10	5,0	1,0	2,77		23,0				65,0	15,0
112	Li	9,1	Ti	90,9					Cl				n.a.	1023	0,12	0,04	3,0	1,0	0,65	85,0	40,0		39,0	2,0	41,0	16,4
	Na	9,1	Ti	90,9					Cl				n.a.	1023	0,12	0,04	3,0	1,0	0,65	100,0	35,0		56,0	9,0	65,0	22,8
	K	9,1	Ti	90,9					Cl				n.a.	1023	0,12	0,04	3,0	1,0	0,65	80,0	32,0		44,0	10,0	54,0	17,3
	Na	9,9	Mn	1,0	Ti	89,10			Cl				n.a.	1023	0,12	0,04	3,0	1,0	0,65	100,0	43,0		52,0	9,0	61,0	26,2
113	Li	4,5	Mg	95,5									n.a.	973	0,67	0,33	2,0	1,0	0,01	76,0	34,0		40,0	16,0	56,0	19,0
	Li	5,0	Zn	5,0	Mg	90,00							n.a.	973	0,67	0,33	2,0	1,0	0,01		35,0		29,0	21,0	50,0	17,5
	Li	5,0	Ni	5,0	Mg	90,00							n.a.	973	0,67	0,33	2,0	1,0	0,01		34,0		26,0	20,0	46,0	15,6
	Li	5,0	Sm	5,0	Mg	90,00							n.a.	973	0,67	0,33	2,0	1,0	0,01		40,0		23,0	23,0	46,0	18,4
	Li	5,0	Ce	5,0	Mg	90,00							n.a.	973	0,67	0,33	2,0	1,0	0,01		42,0		24,0	24,0	48,0	20,2
114	Na	33,3	Mn	66,7					Cl				n.a.	1072	0,67	0,33	2,0	1,0	3,00	100,0	37,0		24,0	12,0	36,0	13,3
	Sn	,5	Na	33,2	Mn	66,30			Cl				n.a.	1064	0,67	0,33	2,0	1,0	3,00	100,0	38,0		31,0	9,0	40,0	15,2
	Ti	,5	Na	33,2	Mn	66,30			Cl				n.a.	1087	0,67	0,33	2,0	1,0	3,00	100,0	42,0		31,0	11,0	42,0	17,6
	W	,5	Na	33,2	Mn	66,30			Cl				n.a.	1089	0,67	0,33	2,0	1,0	3,00	100,0	41,0		32,0	12,0	44,0	18,0
	Ta	,5	Na	33,2	Mn	66,30			Cl				n.a.	1077	0,67	0,33	2,0	1,0	3,00	100,0	44,0		35,0	10,0	45,0	19,8
	Si	1,1	Na	33,0	Mn	65,90			Cl				n.a.	1041	0,67	0,33	2,0	1,0	3,00	100,0	44,0		40,0	7,0	47,0	20,7
	Si	18,2	Na	27,3	Mn	54,50			Cl				n.a.	1053	0,67	0,33	2,0	1,0	3,00	100,0	46,0		36,0	9,0	45,0	20,7
115	Li	5,5	Mg	94,5									Impregnation	975	0,87	0,03	29,0	1,0	0,72		4,0				80,0	3,2
	Mg	98,0					B	2,0					Impregnation	983	0,87	0,03	29,0	1,0	0,72		2,3				18,0	0,4
	Li	5,5	Mg	93,8			B	,7					Impregnation	973	0,87	0,03	29,0	1,0	0,72		4,4				88,0	3,9
	Li	5,5	Mg	89,8			B	4,7					Impregnation	1073	0,87	0,03	29,0	1,0	0,72		17,0				74,0	12,6
	Li	5,5	Al	1,0	Mg	93,50							Impregnation	1075	0,60	0,08	7,1	1,0	0,72		17,3				45,0	7,8
	Li	5,5	Y	,9	Mg	93,60							Impregnation	1072	0,60	0,08	7,1	1,0	0,72		20,0				68,0	13,6
	Li	5,5	La	,7	Mg	93,80							Impregnation	1072	0,60	0,08	7,1	1,0	0,72		18,0				74,0	13,3
	Li	5,5	La	1,5	Mg	93,00							Impregnation	1072	0,60	0,08	7,1	1,0	0,72		16,0				71,0	11,4
116	Ag	8,5							Cl	Al	91,5		Impregnation	973	0,10	0,05	2,0	1,0	1,50		31,5				19,6	6,2
	K	3,0	Ag	8,5			Cl	3,0	Cl	Al	85,5		Impregnation	973	0,10	0,05	2,0	1,0	1,50		30,8				33,6	10,3
	Li	3,0	Ag	8,5			Cl	3,0	Cl	Al	85,5		Impregnation	973	0,10	0,05	2,0	1,0	1,50		2,2				76,9	1,7
	Ba	3,0	Ag	8,5			Cl	6,0	Cl	Al	82,5		Impregnation	973	0,10	0,05	2,0	1,0	1,50		32,1				32,1	10,3
	Na	3,0	Ag	8,5			Cl	3,0	Cl	Al	85,5		Impregnation	973	0,10	0,05	2,0	1,0	1,50		35,0				33,5	11,7
	Cs	3,0	Ag	8,5			Cl	3,0	Cl	Al	85,5		Impregnation	973	0,10	0,05	2,0	1,0	1,50		30,2				24,3	7,3
	Ag	18,0							Cl	Al	82,0		Impregnation	973	0,10	0,05	2,0	1,0	1,50		20,4				0,0	0,0
	Ag	18,0	Ba	41,0			C	41,0	Cl				Impregnation	973	0,10	0,05	2,0	1,0	1,50		26,8				0,3	0,1
	Pr	5,0	Ag	8,5					Cl	Al	86,5		Impregnation	973	0,10	0,05	2,0	1,0	1,50		26,6				0,2	0,1
	Pr	1,0	Ag	8,5					Cl	Al	90,5		Impregnation	973	0,10	0,05	2,0	1,0	1,50		26,1				0,0	0,0
	Bi	1,0	Ag	18,0					Cl	Al	81,0		Impregnation	973	0,10	0,05	2,0	1,0	1,50		23,4				1,3	0,3
	Ba	1,0	Ag	18,0					Cl	Al	81,0		Impregnation	973	0,10	0,05	2,0	1,0	1,50		27,8				0,7	0,2
	Ba	5,0	Ag	18,0					Cl	Al	77,0		Impregnation	973	0,10	0,05	2,0	1,0	1,50		26,0				1,7	0,4
	K	3,0	Ag	18,0					Cl	Al	79,0		Impregnation	973	0,10	0,05	2,0	1,0	1,50		17,2				23,3	4,0
117	Ag	18,0							Cl	Al	82,0		Therm.decomp.	973	0,10	0,05	2,0	1,0	1,50		5,0				0,0	0,0
	Ba	3,0	Ag	18,0			Cl	6,0	Cl	Al	73,0		Therm.decomp.	973	0,10	0,05	2,0	1,0	1,50		17,2				25,4	4,4
	Ba	3,0	La	91,0			Cl	6,0	Cl				Therm.decomp.	973	0,10	0,05	2,0	1,0	1,50		26,7				15,3	4,1
	Ba	3,0	La	9,0			Cl	6,0	Cl	Al	82,0		Impregnation	973	0,10	0,05	2,0	1,0	1,50		15,8				28,0	4,4
	Ba	3,0	La	18,0			Cl	6,0	Cl	Al	73,0		Impregnation	973	0,10	0,05	2,0	1,0	1,50		27,1				30,4	8,2
	Ba	3,0	Ag	18,0			Cl	6,0	Cl	Al	73,0		Therm.decomp.	973	0,10	0,05	2,0	1,0	1,50		21,3				30,4	6,5
	Ca	1,0	Ag	18,0			Cl	2,0	Cl	Al	79,0		Impregnation	973	0,10	0,05	2,0	1,0	1,50		15,8				25,4	4,0
	Sr	3,0					Cl	6,0	Cl	Al	91,0		Impregnation	1023	0,10	0,05	2,0	1,0	1,50		30,3				56,0	17,0
	Ba	28,0					C	28,0	Cl	Al	44,0		Impregnation	1023	0,10	0,05	2,0	1,0	1,50		43,2				41,8	18,1

	Ba	3,0							Cl	6,0	Cl	Al	91,0	Impregnation	1048	0,06	0,05	1,2	1,0	2,10		47,0				41,6	19,6
	Ba	6,0							Br	12,0	Cl	Al	82,0	Impregnation	1023	0,10	0,05	2,0	1,0	1,60		38,6				40,6	15,7
	Ba	3,0									Cl	Al	97,0	Impregnation	1023	0,10	0,05	2,0	1,0	1,60		33,3				49,6	16,5
	Ba	3,0							C	3,0	Cl	Ti	94,0	Impregnation	1023	0,10	0,05	2,0	1,0	0,31		38,8				54,5	21,1
	Ba	3,0							Cl	6,0		Ti	91,0	Impregnation	1023	0,10	0,05	2,0	1,0	4,10		38,2				47,9	18,3
	Ba	3,0							C	3,0	Cl	Zr	94,0	Impregnation	1023	0,10	0,05	2,0	1,0	0,70		28,1				42,8	12,0
	Y	16,7	Ba	33,3	Sn	50,00								Therm.decomp.	1023	0,15	0,08	2,0	1,0	0,15	100,0	29,0				20,0	5,8
118																											
	Y	15,0	Ba	30,0	Sn	55,00								Therm.decomp.	1073	0,83	0,17	4,9	1,0	0,15	83,0	16,4				53,0	8,7
119	Y	17,2	Ba	36,2	Sn	46,60								Therm.decomp.	1023	0,83	0,17	4,9	1,0	0,15	49,0	5,2				38,0	2,0
	K	28,6	La	28,6	Ti	42,80								Therm.decomp.	1023	0,29	0,15	1,9	1,0	1,20		39,0				42,0	16,4
	K	28,6	Nd	28,6	Ti	42,80								Therm.decomp.	1023	0,29	0,15	1,9	1,0	0,96		26,0				24,0	6,2
	K	28,6	Sm	28,6	Ti	42,80								Therm.decomp.	1023	0,29	0,15	1,9	1,0	1,20		25,0				23,0	5,8
	K	28,6	Dy	28,6	Ti	42,80								Therm.decomp.	1023	0,29	0,15	1,9	1,0	1,00		25,0				15,0	3,8
120	K	28,6	Gd	28,6	Ti	42,80								Therm.decomp.	1023	0,29	0,15	1,9	1,0	2,00		29,0				20,0	5,8
	Rb	28,6	La	28,6	Ti	42,80								Therm.decomp.	1023	0,29	0,15	1,9	1,0	0,80		21,0				31,0	6,5
	Na	28,6	La	28,6	Ti	42,80								Therm.decomp.	1023	0,29	0,15	1,9	1,0	0,80		35,0				28,0	9,8
	K	28,6	Pr	28,6	Ti	42,80								Therm.decomp.	1023	0,29	0,15	1,9	1,0	1,20		30,0				40,0	12,0
	K	28,6	Ce	28,6	Ti	42,80								Therm.decomp.	1023	0,29	0,15	1,9	1,0	5,00		29,0				36,0	10,4
	Ba	3,0							Cl	6,0	Cl	Al	91,0	Impregnation	1048	0,06	0,05	1,2	1,0	2,10		47,0				56,0	26,3
121	Ba	6,0							Br	12,0	Cl	Al	82,0	Impregnation	1023	0,10	0,05	2,0	1,0	1,60		38,6				41,8	16,1
	Ba	3,0							C	3,0	Cl	Zr	94,0	Impregnation	1023	0,10	0,05	2,0	1,0	0,70		28,1				41,6	11,7
122	Sr	9,1	La	90,9										Precipitation	1189	0,70	0,10	7,0	1,0	0,15		14,6				9,1	1,3
	Si	100,0												n.a.	1073	0,96	0,04	24,0	1,0	3,60	97,0	4,1		25,0	22,0	47,0	1,9
123	K	1,0							Br	1,0		Si	98,0	Impregnation	1173	0,91	0,09	10,1	1,0	3,00	98,0	16,0		48,0	6,0	54,0	8,6
	Pb	20,0										Si	80,0	Impregnation	1190	0,83	0,16	5,2	1,0	0,40	88,7	18,7		30,2	20,2	50,4	9,4
	Pb	3,2	Si	96,8										n.a.	1110	0,87	0,03	30,9	1,0	2,12	99,0	8,0	14,0	31,0	51,0	82,0	6,6
124	Li	2,0	Mg	97,0					B	1,0				Therm.decomp.	1073	0,60	0,08	7,1	1,0	0,72		21,2				86,0	18,2
	Li	2,0	Al	1,0	Mg	97,00								Therm.decomp.	1073	0,60	0,08	7,1	1,0	0,72		17,3				45,0	7,8
	Li	15,4	Zn	46,2	Mg	38,40								Therm.decomp.	1073	0,27	0,06	4,7	1,0			20,1				76,3	15,3
	Li	4,3	Cs	,9	Zn	94,80								Therm.decomp.	1013	0,27	0,06	4,7	1,0			21,8				77,0	16,8
125	Li	14,8	Al	3,7	Zn	44,40	Mg	37,10						Therm.decomp.	1073	0,27	0,06	4,7	1,0			22,2				78,0	17,3
	Li	4,3	Zn	52,2	Zr	43,50								Therm.decomp.	1073	0,27	0,06	4,7	1,0			9,1				52,9	4,8
	Li	15,4	Mg	38,5	Zn	46,10								n.a.	1073	0,27	0,06	4,8	1,0	0,49		26,0		37,0	36,0	73,0	19,0
	Li	14,8	Al	3,8	Zn	44,40	Mg	37,00						n.a.	1073	0,27	0,06	4,8	1,0	0,49		28,0		43,0	32,0	75,0	21,0
	Li	6,2	Na	35,0	Ti	32,60	Si	20,00	Cl	6,2				Impregnation	973	0,05	0,02	2,4	1,0	0,60		50,0		39,5	0,0	39,5	19,8
	Rb	6,2	Na	35,0	Ti	32,60	Si	20,00	Cl	6,2				Impregnation	973	0,05	0,02	2,4	1,0	0,60		36,9		3,8	3,6	7,4	2,7
126	Li	5,8	Ti	88,4					Cl	5,8				Impregnation	973	0,05	0,02	2,4	1,0	0,60		33,6		19,9	0,0	19,9	6,7
	Li	5,8	Mn	88,4					Cl	5,8				Impregnation	973	0,05	0,02	2,4	1,0	0,60		41,0		28,0	0,0	28,0	11,5
	Rb	28,0	Ti	44,0					Cl	28,0				Impregnation	973	0,05	0,02	2,4	1,0	0,60		20,3		2,6	3,7	6,3	1,3
127	Bi	20,0	Pb	30,0	Ba	50,00								Impregnation	1048	0,30	0,04	7,5	1,0	1,60		3,8				21,0	0,8
128	Li	11,6	Mg	88,4										Impregnation	1073	0,67	0,07	9,6	1,0	0,23		16,3				84,0	13,7
129	Sr	33,3	La	66,7										Precipitation	1153	0,88	0,13	6,7	1,0	0,02	99,6	21,2				73,1	15,5
130	Y	18,2	Ca	81,8										Precipitation	1023	0,15	0,08	2,0	1,0	0,75	90,0	37,0				35,0	13,0
	Ca	100,0												Therm.decomp.	1073	0,09	0,05	2,0	1,0	0,19	100,0	38,0	79,0	12,0	9,0	21,0	8,0
131	Sr	100,0												Therm.decomp.	1073	0,09	0,05	2,0	1,0	0,19	39,0	24,0	52,0	25,0	23,0	48,0	11,5
	Sm	3,9	Mg	96,1										Therm.decomp.	1073	0,09	0,05	2,0	1,0	0,19	93,0	39,0	64,0	20,0	16,0	36,0	14,0
132	Ca	20,0	Ba	80,0										Impregnation	1073	0,67	0,07	9,6	1,0	0,23	16,0	2,0	76,0	24,0	0,0	24,0	0,5
	Li	,4	Mg	99,6										Precipitation	1023	0,03	0,02	1,9	1,0	1,23	90,0	46,0				62,8	28,9
133	Mn	,8	Mg	99,2										n.a.	1023	0,03	0,02	1,9	1,0	1,23	90,0	34,9				46,0	16,1
	Co	10,0	Mg	90,0										Impregnation	1023	0,03	0,02	1,9	1,0	1,23	90,0	32,7				35,7	11,7
134	Na	15,3	P	7,7	Gd	38,50	Mn	38,50						Pyrolysis	1101	0,41	0,21	2,0	1,0	0,29		15,0	47,0	36,0	17,0	53,0	8,0
	Zn	100,0												Therm.decomp.	973	0,44	0,11	4,0	1,0	0,15	100,0	18,0				23,0	4,1
135	Li	47,9	Zn	52,1										Therm.decomp.	973	0,44	0,11	4,0	1,0	0,15	23,0	5,0				42,0	2,1
	Li	2,6	Zn	1,0	Mg	96,40								Impregnation	1053	0,17	0,07	2,3	1,0	0,24	90,0	42,0				47,0	19,7
136	Li	2,6	Cd	1,0	Mg	96,40								Impregnation	1053	0,17	0,07	2,3	1,0	0,24		29,0				49,0	14,2
	Ba	100,0												n.a.	1073	0,14	0,06	2,3	1,0	0,04	90,0	34,8				42,8	14,9
	Ba	50,0							Cl	50,0				n.a.	1073	0,14	0,06	2,3	1,0	0,04	81,0	34,2	60,0			43,0	14,7
137	La	13,6	Ba	86,4										Impregnation	1073	0,14	0,06	2,3	1,0	0,04	99,9	36,6	51,0			50,0	18,3
	Ba	100,0												Impregnation	1073	0,17	0,06	3,0	1,0	42,29	95,9	21,7	65,0	30,0	5,0	34,7	7,5
138	Ba	100,0												n.a.	1013	0,70	0,08	9,3	1,0	14,45	98,0	14,0				70,0	9,8
	Sr	50,0							C	50,0				Therm.decomp.	1153	0,91	0,09	10,0	1,0	0,24	43,3	7,0				67,5	4,7
	Ba	50,0							C	50,0				Therm.decomp.	1153	0,91	0,09	10,0	1,0	0,24	43,1	7,6				74,9	5,7
	Th	100,0												Therm.decomp.	1153	0,91	0,09	10,0	1,0	0,24	54,7	8,6				64,3	5,5
	Sr	50,0	Th	50,0										Therm.decomp.	1153	0,91	0,09	10,0	1,0	0,24	56,5	9,3				73,3	6,8
	Ca	50,0							C	50,0				Therm.decomp.	1153	0,91	0,09	10,0	1,0	0,24	70,3	9,5				63,9	6,1
	La	100,0												Therm.decomp.	1153	0,91	0,09	10,0	1,0	0,24	69,6	10,1				65,3	6,6
	Th	9,1	Sr	45,5					C	45,4				Therm.decomp.	1153	0,91	0,09	10,0	1,0	0,24	68,4	11,3				75,6	8,5
139	Sr	50,0	Th	50,0										Therm.decomp.	1153	0,91	0,09	10,0	1,0	0,24	74,1	12,0				75,0	9,0
	Ba	50,0	Th	50,0										Therm.decomp.	1153	0,91	0,09	10,0	1,0	0,24	84,8	12,2				69,0	8,4
	Th	9,1	Ca	45,5					C	45,4				Therm.decomp.	1153	0,91	0,09	10,0	1,0	0,24	89,5	12,4				68,6	8,5
	Ca	50,0	Th	50,0										Therm.decomp.	1153	0,91	0,09	10,0	1,0	0,24	97,4	14,2				70,9	10,1
	La	4,5	Sr	4,6	Th	90,90								Therm.decomp.	1153	0,91	0,09	10,0	1,0	0,24	99,4	15,1				74,9	11,3
	La	9,1	Th	90,9										Therm.decomp.	1153	0,91	0,09	10,0	1,0	0,24	99,7	13,8				68,3	9,4
	Th	9,1	La	90,9										Therm.decomp.	1153	0,91	0,09	10,0	1,0	0,24	99,8	14,0				68,3	9,6
	Y	100,0												n.a.	1073	0,30	0,05	6,0	1,0	0,16	100,0	18,0	44,0			56,2	10,1
	La	100,0												n.a.	998	0,18	0,02	8,8	1,0	2,38	91,0	9,4	53,0			46,6	4,4
	Nd	100,0												Therm.decomp.	1023	0,30	0,05	6,0	1,0	0,18	100,0	17,1	43,0			57,0	9,7
	Eu	100,0												Therm.decomp.	973	0,30	0,05	6,0	1,0	0,19	100,0	18,2	44,0			55,9	10,2
140	Gd	100,0												Therm.decomp.	1073	0,30	0,05	6,0	1,0	0,23	100,0	19,2	39,0			61,0	11,7
	Ce	25,0	Na	75,0										Impregnation	970	0,18	0,03	6,1	1,0	1,50	100,0	15,7				59,0	9,3
	Na	,5	La	99,5										Therm.decomp.	1073	0,30	0,05	6,0	1,0	0,10	100,0	20,0	31,0			69,2	13,8
	Yb	5,0	Ce	45,0	Sr	50,00								Therm.decomp.	1023	0,14	0,07	2,0	1,0	0,72	90,0	52,6				60,1	31,6
	Na	15,0	Mg	85,0										Impregnation	1073	0,03	0,01	2,0	1,0	2,17	90,0	39,4				56,8	22,4
	Na	5,8	Ca	94,2										n.a.	1013	0,70	0,08	9,3	1,0	0,36	95,0	16,0				76,0	12,2
	Li	5,8	Ca	94,2										n.a.	1013	0,67	0,07	9,1	1,0	0,36	91,0	16,0	23,0	27,0	41,0	68,0	10,9
	K	2,4	Ca	97,6										n.a.	1013	0,67	0,07	9,1	1,0	0,25	93,0	15,0	26,0	24,0	42,0	66,0	9,9
	Ca	100,0												n.a.	1040	0,64	0,08	8,2	1,0	0,17	94,0	11,0	45,0			55,0	6,1
	Pb	7,5	Mg	92,5										n.a.	1057	0,64	0,08	8,2	1,0	0,54	98,0	13,0	31,0			69,0	9,0
141	Pb	3,7	Ca	96,3							S			n.a.	1020	0,64	0,08	8,2	1,0	7,30	99,0	12,0	40,0			60,0	7,2
	Pb	,1	Si	33,3	Ca	66,60								n.a.	1054	0,64	0,08	8,2	1,0	0,20	94,0	9,0	54,0			46,0	4,1
	Pb	1,9	K	98,1										n.a.	1013	0,64	0,08	8,2	1,0	5,90	95,0	10,0	42,0			58,0	5,8
	Na	5,6	Ca	94,4										n.a.	1013	0,35	0,14	2,4	1,0	0,30	84,0	30,0				56,0	16,8
	Li	4,5	Ca	95,5										n.a.	1013	0,52	0,06	9,0	1,0	0,36	91,0	16,0				77,0	12,3

	Na	1,3	Ca	98,7									n.a.	1013	0,52	0,06	9,0	1,0	0,14	80,0	16,0				78,0	12,5
	K	1,2	Ca	98,8									n.a.	1013	0,52	0,06	9,0	1,0	0,36	98,0	15,0				72,0	10,8
	Li	20,0	Mn	80,0						Cl			n.a.	1023	0,05	0,03	2,0	1,0	0,60	90,0	47,3				64,7	30,6
	Na	15,0	Mg	85,0									n.a.	1073	0,03	0,01	2,0	1,0	2,17	90,0	39,4				56,8	22,4
	K	2,0	Ba	98,0									n.a.	1073	0,03	0,01	2,0	1,0	2,17	90,0	48,1				42,0	20,2
142	Ca	15,0	Mg	85,0									Precipitation	1023	0,13	0,01	9,4	1,0	0,16		16,9				71,8	12,1
	Ca	1,9	Mg	98,1						Cl			Impregnation	1073				1,0	0,60		26,6				59,4	15,8
143	Pb	1,1	Mg	98,9									Impregnation	1073				1,0	0,60		25,1				64,9	16,3
	La	9,1	Mg	90,9									Impregnation	1073				1,0	0,06		29,2				60,3	17,6
144	K	3,2	Ni	32,3	Ca	64,50							Therm.decomp.	873				1,0	4,20		10,0	0,0	38,0	48,0	86,0	8,6
145	Mg	28,6	Si	23,8	Li	47,60							n.a.	1023	0,08	0,05	1,7	1,0	0,11		17,0		34,0	45,0	79,0	13,4
146	Li	10,0	Ca	90,0									n.a.	1023	0,03	0,01	1,9	1,0	2,40		42,0		34,0	19,0	53,0	22,3
	Li	5,0	Ba	5,0	Ca	90,00							n.a.	1023	0,03	0,01	1,9	1,0	2,40		48,0		29,0	20,0	49,0	23,5
147	La	24,4	Na	75,6									n.a.	1023	0,40	0,08	5,0	1,0	0,65	92,0	26,0	22,0	32,0	40,0	72,0	18,7
	Mg	5,0	Sr	5,0	Li	45,00	La	45,00					n.a.	973	0,13	0,07	2,0	1,0	0,80		28,0	43,0	26,0	32,0	58,0	16,2
148	Mg	5,0	Sr	5,0	Li	45,00	Sm	45,00					n.a.	973	0,13	0,07	2,0	1,0	0,80		23,0	42,0	30,0	29,0	59,0	13,6
	Mg	5,0	Sr	5,0	Li	45,00	Nd	45,00					n.a.	973	0,13	0,07	2,0	1,0	0,80		33,0	49,0	19,0	33,0	52,0	17,2
	Li	70,0	Ti	30,0									Impregnation	1023	0,32	0,08	4,0	1,0	0,15		10,0				73,5	7,4
149	Li	58,0	La	28,0	Ti	14,00							Impregnation	1023	0,32	0,08	4,0	1,0	0,15		18,6				75,3	14,0
	Li	61,1	Ni	19,5	Ti	19,40							Impregnation	1023	0,32	0,08	4,0	1,0	0,15		18,9				69,7	13,2
150	Li	50,0	Mn	50,0						Cl			n.a.	1023	0,50	0,03	20,0	1,0	0,11		14,0	10,0	44,0	44,0	88,0	12,3
151	K	27,8	Mn	72,2						Cl			n.a.	1023	0,51	0,10	5,0	1,0	0,15	100,0	29,0	28,0	59,0	13,0	72,0	20,9
	Ba	10,0	La	90,0									Therm.decomp.	1073	0,15	0,08	1,9	1,0	0,72		36,9				32,0	11,8
	Ba	33,0	La	67,0									Precipitation	1073	0,15	0,08	1,9	1,0	0,72		39,1				35,0	13,7
152	Ba	33,0	La	67,0									Pyrolysis	1073	0,15	0,08	1,9	1,0	0,72		38,3				42,5	16,3
	La	100,0											Therm.decomp.	1073	0,15	0,08	1,9	1,0	0,72		37,6				24,8	9,3
	Ba	8,0	Ca	92,0									Therm.decomp.	1073	0,15	0,08	1,9	1,0	0,72		38,8				36,4	14,1
153	Li	33,3	Mg	33,3	Nd	33,40							n.a.	1003	0,60	0,40	1,5	1,0	0,78		62,0		33,0	18,0	51,0	31,6
154	Mn	25,0	Ti	25,0	Li	50,00				S			n.a.	1073	0,42	0,17	2,5	1,0	3,60		37,0				82,0	30,3
155	Li	27,7	Mn	72,3						B			n.a.	1023	0,63	0,38	1,7	1,0	1,20		42,0				80,0	33,6
	Zr	100,0											n.a.	1093	0,40	0,10	4,0	1,0	0,01		18,0		23,0	20,0	43,0	7,7
	Ca	50,0	Zr	50,0									n.a.	973	0,40	0,10	4,0	1,0	0,01		20,0		30,0	32,0	62,0	12,4
	Sr	50,0	Zr	50,0									n.a.	1013	0,40	0,10	4,0	1,0	0,01		21,0		34,0	34,0	68,0	14,3
	Ba	50,0	Zr	50,0									n.a.	1093	0,40	0,10	4,0	1,0	0,01		20,0		33,0	33,0	66,0	13,2
156	Zr	45,0	Mg	5,0	Ca	50,00							n.a.	893	0,40	0,10	4,0	1,0	0,01		19,0		29,0	33,0	62,0	11,8
	Zr	45,0	Mg	5,0	Sr	50,00							n.a.	973	0,40	0,10	4,0	1,0	0,01		23,0		33,0	35,0	68,0	15,6
	Zr	45,0	Mg	5,0	Ba	50,00							n.a.	1073	0,40	0,10	4,0	1,0	0,01		22,0		33,0	32,0	65,0	14,3
	Na	25,0	La	25,0	Zr	50,00							n.a.	993	0,40	0,10	4,0	1,0	0,01		21,0		33,0	28,0	61,0	12,8
	K	25,0	La	25,0	Zr	50,00							n.a.	953	0,40	0,10	4,0	1,0	0,01		22,0		31,0	30,0	61,0	13,4
	Rb	25,0	La	25,0	Zr	50,00							n.a.	953	0,40	0,10	4,0	1,0	0,01		23,0		27,0	31,0	58,0	13,3
157	K	12,8	Mn	87,2									Impregnation	1023	0,51	0,03	20,3	1,0	0,10		2,5	4,0	11,0	85,0	96,1	2,4
158	Mo	25,0	Na	75,0									n.a.	1002	0,54	0,48	1,1	1,0	3,75	90,0	60,0				12,0	7,2
159	Mg	47,8	Li	52,2									n.a.	1023	0,52	0,12	4,4	1,0		99,6	17,2	59,0	5,0	36,0	41,0	7,1
160	La	27,0	Ca	73,0									Therm.decomp.	1013	0,93	0,07	13,3	1,0	0,02	95,0	11,8				76,0	9,0
161	Na	16,7	Ca	83,3									n.a.	1101	0,40	0,20	2,0	1,0	0,31		40,0	55,0	10,0	33,0	43,0	17,2
162	Fe	100,0								P			n.a.	848	2,70	1,35	2,0	1,0	0,13		15,0				43,0	6,5
163	Na	16,1	Si	16,1	Mn	67,80				Cl			n.a.	1048	0,29	0,04	7,8	1,0	3,30	100,0	16,0		56,0	20,0	76,0	12,2
	Mg	100,0											Impregnation	1053	0,43	0,16	2,7	1,0	0,04		9,4				25,0	2,4
	Sn	,2	Mg	99,8									Impregnation	1053	0,43	0,16	2,7	1,0	0,04		14,0				31,0	4,3
	Sn	,4	Mg	99,6									Impregnation	1053	0,43	0,16	2,7	1,0	0,04		20,0				40,0	8,0
	Sn	,8	Mg	99,2									Impregnation	1053	0,43	0,16	2,7	1,0	0,04		24,0				31,0	7,4
	Sn	2,6	Mg	97,4									Impregnation	1053	0,43	0,16	2,7	1,0	0,04		22,0				26,0	5,7
164	Sn	100,0											Impregnation	1053	0,43	0,16	2,7	1,0	0,04		16,5				4,0	0,7
	Pb	,2	Mg	99,8									Impregnation	1053	0,43	0,16	2,7	1,0	0,04		12,8				42,6	5,5
	Pb	,4	Mg	99,6									Impregnation	1053	0,43	0,16	2,7	1,0	0,04		13,1				51,0	6,7
	Pb	,8	Mg	99,2									Impregnation	1053	0,43	0,16	2,7	1,0	0,04		13,9				46,0	6,4
	Pb	2,6	Mg	97,4									Impregnation	1053	0,43	0,16	2,7	1,0	0,04		10,8				38,0	4,1
	Pb	4,4	Mg	95,6									Impregnation	1053	0,43	0,16	2,7	1,0	0,04		10,4				20,0	2,1
	Pb	7,3	Mg	92,7									Impregnation	1053	0,43	0,16	2,7	1,0	0,04		10,5				20,0	2,1
	Mg	100,0											Therm.decomp.	973	0,75	0,25	3,0	1,0	0,05	100,0	21,9		11,1	13,7	24,8	5,4
165	Li	,2	Mg	99,6			C	,2					Impregnation	973	0,75	0,25	3,0	1,0	0,05	94,2	29,8		17,3	41,5	58,8	17,5
	Li	2,0	Mg	96,0			C	2,0					Impregnation	973	0,75	0,25	3,0	1,0	0,05	63,9	22,1		24,7	38,1	62,8	13,9
	Li	5,0	Mg	90,0			C	5,0					Impregnation	973	0,75	0,25	3,0	1,0	0,05	27,8	11,8		16,2	36,8	53,0	6,3
	Ni	50,0	Ti	50,0									Impregnation	1073	0,27	0,13	2,1	1,0	0,40		4,9				59,5	2,9
	Na	1,6	Ni	49,2	Ti	49,20							Impregnation	1073	0,27	0,13	2,1	1,0	0,40		22,0				38,0	8,4
	Na	1,6	Ni	49,2	Ti	49,20							Impregnation	1123	0,27	0,13	2,1	1,0	0,40		39,0				41,3	16,1
	Na	22,0	Ni	39,0	Ti	39,00							Impregnation	1023	0,32	0,08	4,0	1,0	0,40		12,7				60,1	7,6
166	Na	22,0	Ni	39,0	Ti	39,00							Impregnation	1073	0,32	0,08	4,0	1,0	0,40		22,1				61,5	13,6
	Li	,5	Ni	49,5	Ti	50,00							Impregnation	1073	0,27	0,13	2,1	1,0	0,40		20,1				49,1	9,9
	Li	,5	Ni	49,5	Ti	50,00							Impregnation	1123	0,27	0,13	2,1	1,0	0,40		35,5				47,0	16,7
	Li	9,0	Ni	41,0	Ti	50,00							Impregnation	1023	0,32	0,08	4,0	1,0	0,40		18,9				69,7	13,2
	Li	9,0	Ni	41,0	Ti	50,00							Impregnation	1073	0,27	0,13	2,1	1,0	0,40		38,2				46,6	17,8
	Na	66,7					C	33,3					Therm.decomp.	1048	0,50	0,09	5,5	1,0	0,38	10,0	5,3				47,8	2,5
	La	100,0											Therm.decomp.	1048	0,50	0,09	5,5	1,0	0,38	99,0	25,1				46,2	11,6
	Ce	100,0											Therm.decomp.	1048	0,50	0,09	5,5	1,0	0,38	100,0	13,7				1,2	0,2
167	Yb	100,0											Therm.decomp.	1048	0,50	0,09	5,5	1,0	0,38	83,0	20,1				40,3	8,1
	Na	4,0	La	92,0			C	4,0					Impregnation	1048	0,50	0,09	5,5	1,0	0,38	73,0	21,8				56,8	12,4
	Na	4,0	Ce	92,0			C	4,0					Impregnation	1048	0,50	0,09	5,5	1,0	0,38	81,0	21,7				52,7	11,4
	Na	4,0	Yb	92,0			C	4,0					Impregnation	1048	0,50	0,09	5,5	1,0	0,38	81,0	21,9				52,3	11,5
	Zr	100,0											Therm.decomp.	1023	0,88	0,13	7,0	1,0	4,20		11,0				5,0	0,6
168	Na	30,7	Zr	69,3									Impregnation	1023	0,88	0,13	7,0	1,0	4,20		16,0				43,5	7,0
	K	22,5	Zr	77,5									Impregnation	1023	0,88	0,13	7,0	1,0	4,20		16,0				37,3	6,0
	Li	47,6	Zr	52,4									Impregnation	1023	0,88	0,13	7,0	1,0	4,20		15,0				28,2	4,2
169	Mn	11,0	Na	20,5	Si	68,50				Cl			n.a.	1023	0,67	0,33	2,0	1,0	3,30	100,0	52,0	43,0	44,0	5,0	49,0	25,5
170	Li	6,3	Mg	93,7									n.a.	1057	0,59	0,09	7,0	1,0	0,72		17,0				74,0	12,6
171	Pb	50,0									Si	50,0	n.a.	1104	0,83	0,04	23,1	1,0	2,12	99,0	9,0	12,0	34,0	42,0	76,0	6,8
172	Li	12,5	Ti	87,5						Cl			n.a.	1033	0,05	0,02	2,6	1,0	0,65		34,0		59,0	0,0	59,0	20,1
	Li	20,0	Mn	80,0						Cl			n.a.	1033	0,05	0,02	2,6	1,0	0,65		41,0		68,0	0,0	68,0	27,9
	Ca	1,3								Cl	Al	98,7	n.a.	973	0,10	0,05	2,0	1,0	3,10		52,0	48,0	48,0	3,0	51,0	26,5
173	Sr	1,3								Cl	Al	98,7	n.a.	1023	0,10	0,05	2,0	1,0	4,60		49,0	56,0	42,0	2,0	44,0	21,6
	Ba	1,3								Cl	Al	98,7	n.a.	1023	0,10	0,05	2,0	1,0	4,60		49,0	56,0	41,0	3,0	44,0	21,6
174	Na	45,8	Ag	40,3	Cu	13,90				Cl			n.a.	1023	0,32	0,08	4,0	1,0	0,50		24,0		60,0	5,0	65,0	15,6

	Na	53,2	Ag	46,8							Cl					n.a.	1023	0,32	0,08	4,0		1,0	0,50		21,0		53,0	7,0	60,0	12,6
	Mn	68,8	Ag	31,2							Cl					n.a.	1023	0,32	0,08	4,0		1,0	0,50		13,0		49,0	14,0	63,0	8,2
175	Li	33,3	Ni	33,3	Mg	33,40										n.a.	953	0,34	0,17	2,0		1,0	0,12		36,1				59,0	21,3
	Na	33,3	La	33,3	Mg	33,40										n.a.	953	0,34	0,17	2,0		1,0	0,12		34,2				51,1	17,5
176	Co	,6	Sr	2,1							Cl	Al	97,3			n.a.	923	0,13	0,06	2,2		1,0	2,40		33,0				68,3	22,5
	Na	5,0	Mn	18,0			Cl	5,0				Si	72,0			Sol-gel	1023	0,67	0,33	2,0		1,0	3,00	46,5	19,3				40,8	7,9
177	Na	5,0	Mn	18,0			Cl	5,0			Cl	Si	72,0			Sol-gel	1023	0,67	0,33	2,0		1,0	3,00	100,0	48,2				50,4	24,3
	Na	5,0	Mn	18,0	Fe	3,00	Cl	5,0				Si	69,0			Sol-gel	1023	0,67	0,33	2,0		1,0	3,00	100,0	49,0		42,4	4,1	46,5	22,8
	Si	50,0					C	50,0								n.a.	1023	0,67	0,33	2,0		1,0	3,00	16,4	5,1		2,8	17,0	19,8	1,0
	Sr	2,0					Cl	4,0				Al	94,0			Impregnation	923	0,09	0,04	2,2		1,0	2,40		7,5				61,0	4,6
	Co	1,0	Sr	4,0			Cl	8,0				Al	87,0			Impregnation	923	0,09	0,04	2,2		1,0	2,40		33,0				65,0	21,5
	Ni	1,0	Sr	4,0			Cl	8,0				Al	87,0			Impregnation	923	0,09	0,04	2,2		1,0	2,16		22,0				70,0	15,4
	Fe	1,0	Sr	4,0			Cl	8,0				Al	87,0			Impregnation	923	0,09	0,04	2,2		1,0	2,27		6,9				16,0	1,1
	Cu	1,0	Sr	4,0			Cl	8,0				Al	87,0			Impregnation	923	0,09	0,04	2,2		1,0	2,47		21,0				4,7	1,0
	Co	1,0										Al	99,0			Impregnation	923	0,10	0,05	1,9		1,0	6,10		19,0				3,0	0,6
178	Co	1,0	Ba	4,0			Cl	8,0				Al	87,0			Impregnation	923	0,09	0,04	2,2		1,0	4,80		24,0				32,0	7,7
	Co	1,0	Sr	4,0			C	8,0				Al	87,0			Impregnation	923	0,09	0,04	2,2		1,0	4,80		20,0				3,4	0,7
	Rh	1,0	Sr	8,0			Cl	16,0				Al	75,0			Impregnation	1023	0,09	0,04	2,2		1,0	4,56		36,0				51,0	18,4
	Pd	1,0	Sr	8,0			Cl	16,0				Al	75,0			Impregnation	943	0,10	0,05	1,9		1,0	4,56		18,0				30,0	5,4
	Co	1,0	Sr	4,0			C	8,0			Cl	Al	87,0			Impregnation	973	0,09	0,04	2,2		1,0	4,00		23,0				54,0	12,4
	Sr	2,0					Cl	4,0			Cl	Al	94,0			Impregnation	923	0,09	0,04	2,2		1,0	6,00		8,9				67,0	6,0
	Co	1,0	Sr	4,0			Cl	8,0			Cl	Al	87,0			Impregnation	923	0,09	0,04	2,2		1,0	4,70		26,0				55,0	14,3
179	Fe	50,0					P	50,0								Therm.decomp.	998	0,75	0,25	3,0		1,0	6,80		8,5				35,0	3,0
180	Dy	1,0	Li	19,8	Mg	79,20										Therm.decomp.	893	0,29	0,10	2,8		1,0	10,00		29,4	49,0	12,0	39,0	50,7	14,9
181	Y	8,0	Zr	92,0												Therm.decomp.	1373	0,01	0,01	1,0		1,0	182,50	90,0	54,3				21,6	11,7
182	Li	17,6	Pr	82,4												Therm.decomp.	1023	0,81	0,13	6,1		1,0	0,11	95,0	16,0				65,0	10,4
	Mn	15,0	Na	3,4								Si	81,6			Impregnation	1073	0,22	0,04	5,0		1,0	6,43		11,9	30,0			70,0	8,3
183	Pb	10,0	Na	1,7								Si	88,3			Impregnation	1073	0,22	0,04	5,0		1,0	6,43		11,0	20,0			80,0	8,8
	Pb	10,0	Na	1,7			Cl	1,7				Si	86,6			Impregnation	1023	0,22	0,04	5,0		1,0	6,43		9,7	13,0			87,0	8,4
184	Ca	30,0	Ce	70,0												Precipitation	1013	0,84	0,16	5,3		1,0	0,36	95,0	14,8	79,0			20,9	3,1
185	La	85,0	Ba	15,0												n.a.	1023	0,40	0,20	2,0		1,0	0,18		42,0				43,0	18,1
186	Sm	100,0									Cl					n.a.	1023	0,30	0,15	2,0		1,0	0,10		44,0		36,0	3,0	39,0	17,2
187	Li	75,0					P	25,0								Precipitation	1048	0,27	0,03	8,1		1,0	1,20		6,0	22,0	19,0	55,0	74,0	4,4
188	Na	18,6	Ca	1,3								Mg	26,7	Al	53,4	Impregnation	1073	0,51	0,11	4,8		1,0	0,61	78,3	20,0	40,0			58,0	11,6
189	Sm	70,6					Cl	29,4								Therm.decomp.	993	0,20	0,10	2,0		1,0	1,20	91,0	34,5				24,8	8,6
190	Y	20,0	La	80,0												Precipitation	1023	0,14	0,07	2,0		1,0	0,80	99,0	25,4	84,0	7,0	9,0	15,7	4,0
191	Li	23,7	Pb	4,1	Ca	72,20										Precipitation	973	0,13	0,07	2,0		1,0	3,60	42,0	37,0				22,7	8,4
	Sr	33,3	Y	66,7												Therm.decomp.	1051	0,92	0,09	10,0		1,0	0,02	92,0	14,7	23,0			77,4	11,4
	Sr	9,1	Y	90,9												Impregnation	1059	0,92	0,09	10,0		1,0	0,02	94,5	14,6	26,0			74,9	10,9
	Ba	33,3	Y	66,7												Therm.decomp.	1045	0,92	0,09	10,0		1,0	0,02	94,3	14,7	23,0			76,7	11,3
192	Sr	100,0														n.a.	1141	0,91	0,09	10,0		1,0	0,02	88,0	13,0	30,0	46,0	24,0	70,0	9,1
	Ba	100,0														n.a.	1129	0,91	0,09	10,0		1,0	0,02	68,0	11,0	27,0	45,0	29,0	74,0	8,1
	Y	100,0														n.a.	1080	0,91	0,09	10,0		1,0	0,02	87,0	13,0	32,0	41,0	26,0	67,0	8,7
	La	100,0														n.a.	1032	0,91	0,09	10,0		1,0	0,02	100,0	14,0	30,0	30,0	40,0	70,0	9,8
	Ca	33,3	Y	66,7												n.a.	1099	0,91	0,09	10,0		1,0	0,02	75,0	11,0	31,0	42,0	27,0	69,0	7,6
	Sr	33,3	Y	66,7												n.a.	1051	0,91	0,09	10,0		1,0	0,02	92,0	15,0	23,0	41,0	36,0	77,0	11,6
	Ba	33,3	Y	66,7												n.a.	1045	0,91	0,09	10,0		1,0	0,02	94,0	15,0	24,0	39,0	38,0	77,0	11,6
	Sr	33,3	Th	66,7												n.a.	1080	0,91	0,09	10,0		1,0	0,02	74,0	12,0	25,0	37,0	38,0	75,0	9,0
	Sr	33,3	La	66,7												n.a.	1032	0,91	0,09	10,0		1,0	0,02	100,0	15,0	22,0	34,0	44,0	78,0	11,7
193	Li	9,1	Mg	90,9												n.a.	1023	0,89	0,11	8,0		1,0	0,18		20,0				79,0	15,8
194	Pr	33,3	Na	66,7												n.a.	1073	0,40	0,10	4,0		1,0	0,13		29,0		36,0	31,0	67,0	19,4
195	Co	1,3	Li	32,9	Mg	65,80										n.a.	973	0,67	0,07	9,6		1,0	0,23		7,5				79,0	5,9
196	Ba	16,7	Li	16,7	Fe	16,60	La	50,00								n.a.	1093	0,68	0,34	2,0		1,0		89,7	38,7		41,0	17,0	57,5	22,3
197	La	100,0														Therm.decomp.	1073	0,81	0,19	4,3		1,0	0,03	62,0	12,0	36,0			64,0	7,7
198	Li	18,8	Mg	62,4			Cl	18,8								Sol-gel	913	0,10	0,05	1,9		1,0	7,20	90,0	37,0	43,0	45,0	8,0	52,9	19,6
199	Sr	100,0														Therm.decomp.	1073	0,03	0,01	2,0		1,0	2,17	95,0	32,0	3,0			31,3	10,0
	Zn	,1	Li	27,0	Mg	72,90										n.a.	1078	0,28	0,13	2,1		1,0	0,48	58,0	27,0	44,0	26,0	30,0	56,0	15,1
200	Li	27,0	Mg	73,0												n.a.	1073	0,28	0,13	2,1		1,0	0,48	49,0	27,0	36,0	34,0	30,0	64,0	17,3
	Mn	,1	Li	27,0	Mg	72,90										n.a.	1078	0,28	0,13	2,1		1,0	0,48	95,0	39,0	47,0	31,0	22,0	53,0	20,7
201	Na	40,0	Sm	40,0			P	20,0								Therm.decomp.	1101	0,10	0,05	2,0		1,0	0,30	90,0	44,4		36,0	15,0	50,6	22,5
202	Bi	16,7	Mg	83,3												n.a.	1073	0,20	0,04	5,0		1,0	1,20	90,0	20,0	37,0	25,0	37,0	62,0	12,4
203	Li	28,6	Mg	71,4												n.a.	1073	0,20	0,10	2,0		1,0	0,65		24,0				75,0	18,0
204	Al	100,0														n.a.	1163	0,85	0,16	5,2		1,0	1,17		24,0				37,5	9,0
205	Ti	37,5	Mg	12,5	Ba	50,00										n.a.	1141	0,17	0,03	5,1		1,0	0,01	90,0	21,0	40,0	21,0	37,0	58,0	12,2
206	K	28,6	La	28,6	Ti	42,80										n.a.	1073	0,30	0,15	2,0		1,0	1,20		39,0				42,0	16,4
	Ba	2,0	Ti	98,0							Cl					n.a.	1023	0,10	0,05	1,9		1,0	4,10		38,0	52,0	44,0	4,0	48,0	18,2
207	Sr	33,3	Al	66,7							Cl					n.a.	923	0,10	0,04	2,2		1,0	2,40		7,0		23,0	38,0	61,0	4,3
	Co	8,3	Al	16,7	Sr	75,00					Cl					n.a.	923	0,10	0,04	2,2		1,0	2,40		24,0		46,0	20,0	66,0	15,8
	Ni	8,3	Al	16,7	Sr	75,00					Cl					n.a.	923	0,10	0,04	2,2		1,0	2,20		19,0		45,0	25,0	70,0	13,3
	Rh	5,0	Al	10,0	Sr	85,00					Cl					n.a.	923	0,10	0,05	2,1		0,1	4,60		34,0		38,0	9,0	47,0	16,0
	Ba	2,0	Ti	98,0							Cl					n.a.	1023	0,10	0,05	2,0		1,0	1,30		31,0	36,0	53,0	10,0	63,0	19,5
	Ba	1,3									Cl	Al	98,7			n.a.	1023	0,10	0,05	2,0		1,0	1,60		28,0		54,0	12,0	66,0	18,5
	Ba	3,0	Zr	97,0							Cl					n.a.	1048	0,10	0,05	2,0		1,0	1,80		42,0	59,0	30,0	11,0	41,0	17,2
208	Ba	1,3									Cl	Al	98,7			n.a.	1033	0,10	0,05	2,0		1,0	1,70		40,0	48,0	36,0	16,0	52,0	20,8
	Ba	,3									Cl	Al	99,7			n.a.	1023	0,10	0,05	2,0		1,0	3,16		28,0	45,0	47,0	7,0	54,0	15,1
	Sr	3,5									Cl	Al	96,5			n.a.	1023	0,10	0,05	2,0		1,0	3,00		21,0	35,0	41,0	24,0	65,0	13,7
	Sr	2,6									Cl	Al	97,4			n.a.	1023	0,10	0,05	2,0		1,0	1,50		32,0	44,0	37,0	19,0	56,0	17,9
	Ba	2,3	Ga	97,7							Cl					n.a.	1023	0,10	0,05	2,0		1,0	4,00		43,0	50,0	43,0	43,0	86,0	37,0
209	Al	16,6	Li	41,7	Mg	41,70										n.a.	1007	0,82	0,04	20,9		1,0	0,35	99,0	9,0	18,0	28,0	51,0	79,0	7,1
	Ni	6,7	Al	26,7	Li	33,30	Mg	33,30								n.a.	1033	0,70	0,06	10,9		1,0	0,06	99,0	14,0	21,0	25,0	47,0	72,0	10,1
210	Si	13,0	Li	43,5	Mg	43,50										n.a.	1067	0,70	0,06	10,9		1,0	0,24	100,0	15,0	19,0	38,0	33,0	71,0	10,7
	Al	13,0	Li	43,5	Ca	43,50										n.a.	963	0,70	0,06	10,9		1,0	0,37	62,0	6,0	5,0	28,0	62,0	90,0	5,4
211	Ni	6,7	Al	26,7	Li	33,30	Mg	33,30								n.a.	1033	0,71	0,07	11,0		1,0	0,06	99,0	14,0	20,0	25,0	47,0	72,0	10,1
212	Li	24,2	Mg	75,8												n.a.	923	0,09	0,04	2,1		1,0	5,20		32,0		48,0	7,0	55,0	17,6
	Al	10,8	Li	21,6	Mg	67,60										n.a.	923	0,09	0,04	2,2		1,0	5,20		35,0		46,0	6,0	52,0	18,2
213	Na	4,3	Sr	95,7												n.a.	1023	0,95	0,05	19,0		1,0	0,07	55,0	7,0	10,0	66,0	22,0	88,0	6,2
214	Pb	7,7	Mg	92,3												n.a.	1098	0,71	0,08	9,0		1,0	0,09		16,0				75,0	12,0
	Ba	50,0	Co	40,0	Fe	10,00										Sol-gel	1073	0,67	0,33	2,0		1,0			6,2				93,1	5,8
	Sr	50,0	Co	40,0	Fe	10,00										Sol-gel	1023	0,67	0,33	2,0		1,0			4,7				93,9	4,4
215	Ca	50,0	Co	40,0	Fe	10,00										Sol-gel	1023	0,67	0,33	2,0		1,0			26,7				20,2	5,4
	Co	80,0	Fe	20,0												Sol-gel	973	0,67	0,33	2,0		1,0			5,5				0,0	0,0
	Ba	50,0	Co	30,0	Fe	20,00										Sol-gel	1023	0,67	0,33	2,0		1,0			5,7				84,9	4,8

	Sr	50,0	Co	30,0	Fe	20,00											Sol-gel	1023	0,67	0,33	2,0	1,0		12,8			47,0	6,0
	Li	40,0	Mg	40,0	Nd	20,00											Sol-gel	1193	0,47	0,12	4,0	1,0	0,11	28,1		32,4	27,4	59,8	16,8
	Li	57,0	Mg	29,0	Nd	14,00											Sol-gel	1193	0,47	0,12	4,0	1,0	0,11	27,1		29,8	29,7	59,5	16,1
	Li	14,0	Mg	57,0	Nd	29,00											Sol-gel	1193	0,47	0,12	4,0	1,0	0,11	26,9		26,4	28,9	55,3	14,9
	Li	3,0	Mg	65,0	Nd	32,00											Sol-gel	1193	0,47	0,12	4,0	1,0	0,11	25,8		25,6	27,8	53,4	13,8
216	Li	,8	Mg	66,1	Nd	33,10											Sol-gel	1193	0,47	0,12	4,0	1,0	0,11	23,6		21,5	25,8	47,3	11,2
	Li	40,0	Mg	40,0	Nd	20,00											Therm.decomp.	1193	0,47	0,12	4,0	1,0	0,11	26,9		29,2	29,0	58,2	15,7
	Li	,8	Mg	66,1	Nd	33,10											Therm.decomp.	1193	0,47	0,12	4,0	1,0	0,11	22,4		18,6	23,7	42,3	9,5
	Li	40,0	Mg	40,0	La	20,00											Sol-gel	1193	0,47	0,12	4,0	1,0	0,11	27,0		28,9	25,9	54,8	14,8
	Mg	67,0	Nd	33,0													Sol-gel	1193	0,47	0,12	4,0	1,0	0,11	23,6		19,5	25,4	44,9	10,6
	La	25,0	Ca	25,0	Mn	25,00	Co	25,00									Therm.decomp.	973	0,90	0,20	4,5	1,0	6,80	2,2				5,9	0,1
	Na	20,0	La	15,0	Ca	15,00	Mn	15,00	C	20,0					Co	15,0	Therm.decomp.	1073	0,90	0,20	4,5	1,0	2,00	7,3				90,6	6,6
	K	20,0	La	15,0	Ca	15,00	Mn	15,00	C	20,0					Co	15,0	Therm.decomp.	1073	0,90	0,20	4,5	1,0	1,80	9,4				79,7	7,5
217	Li	20,0	La	15,0	Ca	15,00	Mn	15,00	C	20,0					Co	15,0	Therm.decomp.	1023	0,90	0,20	4,5	1,0	1,80	3,5				95,8	3,4
	Rb	20,0	La	15,0	Ca	15,00	Mn	15,00	C	20,0					Co	15,0	Therm.decomp.	1023	0,90	0,20	4,5	1,0	1,80	4,2				96,2	4,0
	Cs	20,0	La	15,0	Ca	15,00	Mn	15,00	C	20,0					Co	15,0	Therm.decomp.	973	0,90	0,20	4,5	1,0	1,80	1,8				78,5	1,4
	Mn	44,0	Na	3,0					P	3,0					Si	50,0	Therm.decomp.	1123	0,90	0,20	4,5	1,0	1,80	1,7				75,0	1,3
	Na	20,0	Pr	60,0					C	20,0							Therm.decomp.	1023	0,90	0,20	4,5	1,0	1,80	19,0				79,7	15,1
	Li	35,0	Mg	35,0											Al	30,0	Sol-gel	944	0,60	0,40	1,5	1,0	22,00	99,4	41,7		16,2	11,3	27,5	11,5
	Li	15,0	Mg	15,0											Al	70,0	Sol-gel	1069	0,95	0,05	19,0	1,0	2,90	99,5	6,6		24,7	30,2	54,9	3,6
218	Li	42,5	Mg	42,5											Al	15,0	Sol-gel	1069	0,95	0,05	19,0	1,0	2,90	99,1	8,8		26,0	52,9	78,9	6,9
	K	42,5	B	42,5											Al	15,0	Sol-gel	1064	0,91	0,09	10,1	1,0	2,20	99,1	11,3		30,1	29,1	59,2	6,7
	Li	29,2	Ca	58,4											Al	12,4	Sol-gel	916	0,91	0,09	10,1	1,0	2,20	46,2	5,8		12,6	70,3	82,9	4,8
	Li	42,5	Mg	42,5											Si	15,0	Sol-gel	1097	0,91	0,09	10,1	1,0	2,20	99,0	15,0		41,9	30,4	72,3	10,8
219	Co	9,0	Li	12,0	Mg	22,00									Al	57,0	Precipitation	1073	0,91	0,09	10,1	1,0	4,30	99,5	11,2		25,1	16,0	41,1	4,6
	Ni	9,0	Li	12,0	Mg	22,00									Al	57,0	Precipitation	1073	0,91	0,09	10,1	1,0	4,30	99,4	12,7		36,2	25,0	61,2	7,8
220	Sr	50,0							C	50,0							n.a.	1223	0,95	0,05	19,0	1,0	0,02		0,6				52,0	0,3
	Na	2,0	Sr	49,0					C	49,0							Impregnation	1223	0,95	0,05	19,0	1,0	0,02		0,8				80,0	0,6
221	Na	8,3	Ca	16,7	Bi	25,00			Cl	50,0							Therm.decomp.	1023	0,50	0,25	2,0	1,0	0,10		4,9	15,0	32,0	53,0	84,5	4,1
	Ca	100,0															n.a.	1073	0,29	0,03	10,1	1,0	1*10-6	44,8	3,2	62,9	2,4	34,6	37,0	1,2
	V	3,0	Ca	97,0													Impregnation	1073	0,29	0,03	10,1	1,0	1*10-6	47,6	3,3	71,8	1,4	26,8	28,2	0,9
	V	2,0	Al	30,0	Ca	68,00											Sol-gel	1073	0,29	0,03	10,1	1,0	1*10-6	66,5	4,1	98,0		2,0	2,0	0,1
	V	2,0	Si	30,0	Ca	68,00											Sol-gel	1073	0,29	0,03	10,1	1,0	1*10-6	45,0	2,7	94,4		5,6	5,6	0,2
222	V	2,0	Ti	30,0	Ca	68,00											Sol-gel	1073	0,29	0,03	10,1	1,0	1*10-6	91,2	6,3	80,2	2,4	17,5	19,9	1,3
	V	2,0	Zr	30,0	Ca	68,00											Sol-gel	1073	0,29	0,03	10,1	1,0	1*10-6	100,0	6,4	86,9	0,6	12,6	13,2	0,8
	Mg	100,0															Therm.decomp.	1073	0,29	0,03	10,1	1,0	1*10-6	26,6	1,4	95,7		4,3	4,3	0,1
	V	2,0	Ti	30,0	Mg	68,00											Sol-gel	1073	0,29	0,03	10,1	1,0	1*10-6	61,5	3,7	99,2		0,8	0,8	0,0
	V	2,0	Zr	30,0	Mg	68,00											Sol-gel	1073	0,29	0,03	10,1	1,0	1*10-6	81,3	5,4	78,4		21,6	21,6	1,2
	Mg	100,0															n.a.	1123	0,96	0,05	18,9	1,0	0,02	71,0	5,3				70,0	3,7
	Ca	100,0															n.a.	1123	0,96	0,05	18,9	1,0	0,02	87,0	7,8				75,0	5,9
	Sr	100,0															n.a.	1123	0,96	0,05	18,9	1,0	0,02	92,0	9,5				79,0	7,5
	Ba	100,0															n.a.	1123	0,96	0,05	18,9	1,0	0,02	76,0	7,0				84,0	5,9
	La	100,0															Precipitation	1123	0,91	0,10	9,0	1,0	0,00	82,0	13,1				70,0	9,2
	Ce	100,0															Precipitation	1123	0,91	0,10	9,0	1,0	0,00	1,0	0,3				61,0	0,2
	Pr	100,0															Precipitation	1123	0,91	0,10	9,0	1,0	0,00	99,0	9,0				41,0	3,7
	Nd	100,0															Precipitation	1123	0,91	0,10	9,0	1,0	0,00	75,0	11,7				66,0	7,7
	Sm	100,0															Precipitation	1123	0,91	0,10	9,0	1,0	0,00	83,0	12,5				71,0	8,9
223	Eu	100,0															Precipitation	1123	0,91	0,10	9,0	1,0	0,00	72,0	10,9				71,0	7,7
	Gd	100,0															Precipitation	1123	0,91	0,10	9,0	1,0	0,00	86,0	13,4				64,0	8,6
	Tb	100,0															Precipitation	1123	0,91	0,10	9,0	1,0	0,00	96,0	7,9				28,0	2,2
	Dy	100,0															Precipitation	1123	0,91	0,10	9,0	1,0	0,00	51,0	9,3				74,0	6,9
	Ho	100,0															Precipitation	1123	0,91	0,10	9,0	1,0	0,00	63,0	10,6				71,0	7,5
	Er	100,0															Precipitation	1123	0,91	0,10	9,0	1,0	0,00	50,0	8,1				64,0	5,2
	Tm	100,0															Precipitation	1123	0,91	0,10	9,0	1,0	0,00	48,0	7,8				61,0	4,8
	Yb	100,0															Precipitation	1123	0,91	0,10	9,0	1,0	0,00	51,0	7,5				60,0	4,5
	Lu	100,0															Precipitation	1123	0,91	0,10	9,0	1,0	0,00	43,0	7,2				67,0	4,8
224	Pb	25,6													Al	74,4	Impregnation	993	0,03	0,00	9,3	1,0	1,14	100,0	12,9	32,3	16,4	47,2	63,6	8,2
	K	16,7	Ca	33,3	Nb	50,00											Therm.decomp.	1073	0,40	0,08	5,0	1,0	0,30	81,2	16,7	45,6	27,7	24,1	51,8	8,7
	K	12,5	Na	12,5	Ca	25,00	Nb	50,00									Therm.decomp.	1073	0,40	0,08	5,0	1,0	0,30	98,0	22,2	53,6	29,3	13,7	43,0	9,5
	K	20,0	La	40,0	Nb	40,00											Therm.decomp.	1023	0,40	0,08	5,0	1,0	0,30	42,1	6,7	64,0	12,4	23,6	36,0	2,4
225	K	16,7	Sr	33,3	Nb	50,00											Therm.decomp.	1023	0,40	0,08	5,0	1,0	0,30	23,6	7,7	38,3	25,2	34,4	59,6	4,6
	Cs	16,7	Ca	33,3	Nb	50,00											Therm.decomp.	1023	0,40	0,08	5,0	1,0	0,30	41,0	8,2	43,3	20,2	36,5	56,7	4,6
	K	16,7	Ca	33,3	Ta	50,00											Therm.decomp.	1023	0,40	0,08	5,0	1,0	0,30	92,0	14,2	60,9	10,9	28,2	39,1	5,6
	Li	16,7	Zr	66,6					Cl	16,7							Sol-gel	1023	0,32	0,08	4,0	1,0	0,48	50,0	9,6	51,0	33,0	16,0	49,0	4,7
	Na	16,7	Zr	66,6					Cl	16,7							Sol-gel	1023	0,32	0,08	4,0	1,0	0,48	58,8	13,8	23,0	59,0	18,0	77,0	10,6
226	K	16,7	Zr	66,6					Cl	16,7							Sol-gel	1023	0,32	0,08	4,0	1,0	0,48	51,0	7,0	65,8	20,0	14,2	34,2	2,4
	Rb	16,7	Zr	66,6					Cl	16,7							Sol-gel	1023	0,32	0,08	4,0	1,0	0,48	44,0	6,2	70,6	15,2	14,0	29,2	1,8
	Cs	16,7	Zr	66,6					Cl	16,7							Sol-gel	1023	0,32	0,08	4,0	1,0	0,48	50,4	6,8	67,0	20,0	13,0	33,0	2,2
	Mg	100,0															Therm.decomp.	1023	0,20	0,05	4,0	1,0	0,24	43,2	4,5	46,2	8,3	39,5	47,8	2,2
	Bi	50,0							Cl	50,0							Therm.decomp.	1023	0,20	0,05	4,0	1,0	0,24	43,8	5,0	48,0	15,0	37,0	52,0	2,6
	Bi	28,6	Mg	42,8					Cl	28,6							Therm.decomp.	1023	0,20	0,05	4,0	1,0	0,24	81,5	14,5	37,5	37,5	25,0	62,5	9,1
227	Bi	25,0	Li	12,5	Mg	31,20			Cl	25,0	C	6,3					Therm.decomp.	1023	0,20	0,05	4,0	1,0	0,24	80,5	22,8	24,0	60,0	16,0	76,0	17,3
	Li	44,4	Mg	33,4					C	22,2							Therm.decomp.	1023	0,20	0,05	4,0	1,0	0,24	50,5	12,4	29,1	17,2	53,7	70,9	8,8
	Li	3,0	Mg	94,0					Cl	3,0							Therm.decomp.	1023	0,20	0,05	4,0	1,0	0,24	48,2	11,8	59,6	10,1	30,3	40,4	4,8
	Li	8,8	Mg	85,0					Cl	3,5	C	2,7					Therm.decomp.	1023	0,20	0,05	4,0	1,0	0,24	52,4	13,6	56,8	16,1	27,2	43,3	5,9
	Ca	20,0	Nb	40,0	Bi	40,00											Impregnation	1023	0,40	0,08	5,0	1,0	0,60	83,4	14,5	54,6	14,5	30,9	45,4	6,6
	Sr	20,0	Nb	40,0	Bi	40,00											Therm.decomp.	1023	0,40	0,08	5,0	1,0	0,60	82,7	13,9	54,6	16,2	29,1	45,3	6,3
228	Ba	20,0	Nb	40,0	Bi	40,00											Therm.decomp.	1023	0,40	0,08	5,0	1,0	0,60	75,1	14,1	43,8	18,3	36,8	55,1	7,8
	Pb	20,0	Nb	40,0	Bi	40,00											Therm.decomp.	1023	0,40	0,08	5,0	1,0	0,60	57,4	9,6	45,2	18,7	36,0	54,7	5,3
	Ba	20,0	Ta	40,0	Bi	40,00											Therm.decomp.	1023	0,40	0,08	5,0	1,0	0,60	93,1	13,4	63,9	9,4	26,7	36,1	4,8
	Li	17,2	Mg	82,8													n.a.	973	0,48	0,11	4,4	1,0	8,80		23,0	31,0	40,0	24,0	64,0	14,7
	Li	22,2	Ca	77,8													n.a.	984	0,48	0,11	4,4	1,0	8,80		20,0	28,0	39,0	27,0	66,0	13,2
	Li	29,4	Zn	70,6													n.a.	993	0,52	0,15	3,5	1,0	8,80		13,0	23,0	32,0	42,0	74,0	9,6
229	Li	45,5	La	54,5													n.a.	983	0,48	0,11	4,4	1,0	8,80		21,0	33,0	39,0	22,0	61,0	12,8
	Li	25,0	Ti	25,0	Ca	50,00											n.a.	980	0,48	0,11	4,4	1,0	8,80		17,0	24,0	40,0	31,0	71,0	12,1
	Li	25,0	Ti	25,0	Sr	50,00											n.a.	983	0,48	0,11	4,4	1,0	8,80		15,0	30,0	32,0	34,0	66,0	9,9
230	Mo	33,3	Na	66,7													n.a.	999	0,52	0,48	1,1	1,0	4,10		74,0	85,0	9,0	3,0	12,0	8,9
231	Na	11,1	Fe	88,9									Cl, B				n.a.	1023	0,32	0,08	4,0	1,0	0,24	64,0	23,0	21,0	59,0	16,0	75,0	17,3
231	Na	2,1	W	1,0											Si	96,9	impregnation	1073	0,50	0,11	4,8	1,0	0,60	94,7	33,2	47,2	37,7	15,1	52,8	17,5
	Li	9,6	Mg	90,4													n.a.	941	0,51	0,10	5,0	1,0	7,20		10,0				57,0	5,7
233	Zn	9,8	Li	11,1	Mg	79,10											n.a.	948	0,51	0,10	5,0	1,0	7,20		19,0				54,0	10,3

	Li	15,0	Ca	85,0									n.a.	978	0,51	0,10	5,0	1,0	7,20		19,0				59,0	11,2
	Li	25,6	Zn	74,4									n.a.	973	0,51	0,10	5,0	1,0	7,20		9,0				68,0	6,1
234	Li	9,1	Mg	90,9									Therm.decomp.	1018	0,80	0,20	4,0	1,0	0,35		28,1				57,4	16,1
	Li	3,0									Si	97,0	Impregnation	1073	0,83	0,17	4,9	1,0	0,90		9,0		44,0	23,0	67,0	6,0
	Co	10,0									Si	90,0	Impregnation	1073	0,83	0,17	4,9	1,0	0,90		8,8		4,0	10,3	14,3	1,3
	Co	10,0					P	,2			Si	89,8	Impregnation	1073	0,83	0,17	4,9	1,0	0,90		8,4		7,9	14,7	22,6	1,9
235	Co	10,0	Na	1,0			P	,2	Cl	1,0	Si	87,8	Impregnation	1073	0,83	0,17	4,9	1,0	0,90		12,6		11,6	12,1	23,7	3,0
	Na	1,0	Li	6,0	Co	10,00	P	,2			Si	82,8	Impregnation	1073	0,83	0,17	4,9	1,0	0,90		10,6		24,9	29,0	53,9	5,7
	Na	1,0	Li	6,0	Co	10,00	P	,2	Cl	1,0	Si	81,8	Impregnation	1073	0,83	0,17	4,9	1,0	0,90		17,0		30,5	22,3	52,8	9,0
	Li	75,0					P	25,0					precipitation	973	0,27	0,03	8,3	1,0	1,20	10,0	5,7		18,8	54,9	73,7	4,2
	Li	57,1	Ca	14,3			P	28,6					precipitation	973	0,27	0,03	8,3	1,0	1,20		6,8		13,2	40,8	54,0	3,7
	Li	33,4	Ca	33,3			P	33,3					precipitation	973	0,27	0,03	8,3	1,0	1,20	25,0	3,5		4,7	22,1	26,8	0,9
236	Ca	66,7					P	33,3					precipitation	973	0,27	0,03	8,3	1,0	1,20	95,0	10,6		9,6	16,4	26,0	2,8
	Ca	60,0					P	40,0					precipitation	973	0,27	0,03	8,3	1,0	1,20	95,0	13,3		3,2	6,3	9,5	1,3
	Ca	50,0					P	50,0					precipitation	973	0,27	0,03	8,3	1,0	1,20		0,5		0,0	3,8	3,8	0,0
	Li	37,5					P	12,5			Si	50,0	precipitation	973	0,27	0,03	8,3	1,0	1,20		0,4		0,0	1,3	1,3	0,0
	Pr	100,0											n.a.	1023	0,28	0,04	7,0	1,0	2,80	98,0	6,5		9,7	22,1	31,8	2,1
	Sm	100,0											n.a.	1023	0,28	0,04	7,0	1,0	2,80	100,0	17,0		27,0	23,8	50,8	8,6
237	La	100,0											n.a.	1023	0,28	0,04	7,0	1,0	2,80	100,0	14,3		26,1	35,8	61,9	8,9
	Ce	100,0											n.a.	1023	0,28	0,04	7,0	1,0	2,80	100,0	13,5		0,0	0,0	0,0	0,0
	Zr	100,0											n.a.	1023	0,32	0,08	4,0	1,0	0,48	28,0	2,4		3,4	14,6	18,0	0,4
	Na	50,0					Cl	50,0					n.a.	1023	0,32	0,08	4,0	1,0	0,48	30,0	2,9		13,0	11,0	24,0	0,7
	Li	20,0	Zr	60,0			Cl	20,0					Impregnation	1023	0,32	0,08	4,0	1,0	0,48	39,2	4,8		18,0	14,0	32,0	1,5
	Na	20,0	Zr	60,0			Cl	20,0					Impregnation	1023	0,32	0,08	4,0	1,0	0,48	45,0	8,7		41,0	19,0	60,0	5,2
	K	20,0	Zr	60,0			Cl	20,0					Impregnation	1023	0,32	0,08	4,0	1,0	0,48	41,0	4,8		15,0	13,0	28,0	1,3
	Rb	20,0	Zr	60,0			Cl	20,0					Impregnation	1023	0,32	0,08	4,0	1,0	0,48	38,0	4,2		14,0	13,0	27,0	1,1
	Cs	20,0	Zr	60,0			Cl	20,0					Impregnation	1023	0,32	0,08	4,0	1,0	0,48	40,0	5,0		16,0	14,0	30,0	1,5
	Li	20,0	Zr	60,0			Cl	20,0					Sol-gel	1023	0,32	0,08	4,0	1,0	0,48	50,0	9,6		33,0	16,0	49,0	4,7
	Na	20,0	Zr	60,0			Cl	20,0					Sol-gel	1023	0,32	0,08	4,0	1,0	0,48	58,8	13,8		59,0	18,0	77,0	10,6
	K	20,0	Zr	60,0			Cl	20,0					Sol-gel	1023	0,32	0,08	4,0	1,0	0,48	51,0	7,0		20,0	14,2	34,2	2,4
	Rb	20,0	Zr	60,0			Cl	20,0					Sol-gel	1023	0,32	0,08	4,0	1,0	0,48	44,0	6,2		15,2	14,0	29,2	1,8
238	Cs	20,0	Zr	60,0			Cl	20,0					Sol-gel	1023	0,32	0,08	4,0	1,0	0,48	50,4	6,8		20,0	13,0	33,0	2,2
	Li	20,0	Zr	60,0			Cl	20,0					Therm.decomp.	1023	0,32	0,08	4,0	1,0	0,48	34,0	3,4		16,0	14,0	30,0	1,0
	Na	20,0	Zr	60,0			Cl	20,0					Therm.decomp.	1023	0,32	0,08	4,0	1,0	0,48	49,0	7,8		35,0	15,0	50,0	3,9
	K	20,0	Zr	60,0			Cl	20,0					Therm.decomp.	1023	0,32	0,08	4,0	1,0	0,48	40,8	4,0		17,0	14,0	31,0	1,2
	Rb	20,0	Zr	60,0			Cl	20,0					Therm.decomp.	1023	0,32	0,08	4,0	1,0	0,48	38,0	3,8		15,0	13,0	28,0	1,1
	Cs	20,0	Zr	60,0			Cl	20,0					Therm.decomp.	1023	0,32	0,08	4,0	1,0	0,48	42,0	4,8		22,0	14,0	36,0	1,7
	Li	20,0	Zr	60,0			Cl	20,0					precipitation	1023	0,32	0,08	4,0	1,0	0,48	44,0	6,4		22,0	16,0	38,0	2,4
	Na	20,0	Zr	60,0			Cl	20,0					precipitation	1023	0,32	0,08	4,0	1,0	0,48	48,8	8,8		41,0	14,0	55,0	4,8
	K	20,0	Zr	60,0			Cl	20,0					precipitation	1023	0,32	0,08	4,0	1,0	0,48	42,4	6,9		18,0	15,0	33,0	2,3
	Rb	20,0	Zr	60,0			Cl	20,0					precipitation	1023	0,32	0,08	4,0	1,0	0,48	42,0	5,0		16,0	16,0	32,0	1,6
	Cs	20,0	Zr	60,0			Cl	20,0					precipitation	1023	0,32	0,08	4,0	1,0	0,48	45,4	6,2		19,0	16,0	35,0	2,2
	Ba	50,0	Pb	50,0									Therm.decomp.	1073	0,32	0,08	4,0	1,0	0,60		22,0				65,0	14,3
239	Ba	50,0	Bi	50,0									Therm.decomp.	1073	0,32	0,08	4,0	1,0	0,60		18,0				75,0	13,5
	Ba	50,0	Sn	50,0									Therm.decomp.	1073	0,32	0,08	4,0	1,0	0,60		15,0				30,0	4,5
	La	40,0	Sr	10,0	Mn	50,00							Therm.decomp.	1068	0,30	0,05	6,0	1,0	0,24		11,9				18,4	2,2
	La	40,0	Fe	10,0	Nb	50,00							Therm.decomp.	1068	0,30	0,05	6,0	1,0	0,24		11,4				18,9	2,2
	La	50,0	Y	50,0									Sol-gel	1068	0,30	0,05	6,0	1,0	0,24		16,8				45,7	7,7
	La	50,0	Y	50,0									Therm.decomp.	1068	0,30	0,05	6,0	1,0	0,24		14,4				27,1	3,9
240	La	40,0	Sr	10,0	Y	50,00							Therm.decomp.	1068	0,30	0,05	6,0	1,0	0,24		15,4				43,7	6,7
	La	90,0	Sr	10,0									Sol-gel	1068	0,30	0,05	6,0	1,0	0,24		18,3				59,6	10,9
	La	100,0											n.a.	1068	0,30	0,05	6,0	1,0	0,24		17,5				52,6	9,2
	Y	100,0											Therm.decomp.	1068	0,30	0,05	6,0	1,0	0,24		17,2				36,0	6,2
	Li	1,0	Mg	98,0			Cl	1,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	59,0	5,5		27,0	12,0	39,0	2,1
	Li	5,0	Mg	90,0			Cl	5,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	60,0	8,0		30,0	14,0	44,0	3,5
	Li	10,0	Mg	80,0			Cl	10,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	68,0	10,4		31,0	16,0	47,0	4,9
	Li	20,0	Mg	60,0			Cl	20,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	66,0	11,0		33,0	16,0	49,0	5,4
	Na	1,0	Mg	98,0			Cl	1,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	61,0	6,7		28,0	14,0	42,0	2,8
	Na	5,0	Mg	90,0			Cl	5,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	64,0	9,8		30,0	15,0	45,0	4,4
	Na	10,0	Mg	80,0			Cl	10,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	65,0	12,0		34,0	15,0	49,0	5,9
	Na	20,0	Mg	60,0			Cl	20,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	67,0	13,4		34,0	16,0	50,0	6,7
	Cs	1,0	Mg	98,0			Cl	1,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	65,0	6,0		19,0	17,0	36,0	2,2
	Cs	5,0	Mg	90,0			Cl	5,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	68,0	8,5		22,0	18,0	40,0	3,4
	Cs	10,0	Mg	80,0			Cl	10,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	70,0	10,2		22,0	18,0	40,0	4,1
	Cs	20,0	Mg	60,0			Cl	20,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	71,0	11,2		23,0	19,0	42,0	4,7
241	Li	1,0	Na	1,0	Mg	96,00	Cl	2,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	70,0	12,8		46,0	22,0	68,0	8,7
	Li	5,0	Na	5,0	Mg	80,00	Cl	10,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	82,0	22,4		51,0	27,0	78,0	17,5
	Li	10,0	Na	10,0	Mg	60,00	Cl	20,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	85,0	21,5		52,0	28,0	80,0	17,2
	Li	20,0	Na	20,0	Mg	20,00	Cl	40,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	86,0	19,0		39,0	22,0	61,0	11,6
	Li	1,0	Cs	1,0	Mg	96,00	Cl	2,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	72,0	13,2		49,0	20,0	69,0	9,1
	Li	5,0	Cs	5,0	Mg	80,00	Cl	10,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	85,0	22,8		53,0	28,0	81,0	18,5
	Li	10,0	Cs	10,0	Mg	60,00	Cl	20,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	86,0	22,0		52,0	27,0	79,0	17,4
	Li	20,0	Cs	20,0	Mg	20,00	Cl	40,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	88,0	19,2		42,0	21,0	63,0	12,1
	Na	1,0	Cs	1,0	Mg	96,00	Cl	2,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	71,0	14,5		44,0	23,0	67,0	9,7
	Na	5,0	Cs	5,0	Mg	80,00	Cl	10,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	85,0	23,6		57,0	26,0	83,0	19,6
	Na	10,0	Cs	10,0	Mg	60,00	Cl	20,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	88,0	24,8		55,0	25,0	80,0	19,8
	Na	20,0	Cs	20,0	Mg	20,00	Cl	40,0					Impregnation	1023	0,80	0,20	4,0	1,0	0,24	90,0	20,0		43,0	21,0	64,0	12,8
242	Li	50,0	Y	50,0									Therm.decomp.	1000	0,18	0,03	6,0	1,0	1,60	90,0	27,0		26,0	38,0	64,0	17,3
	Gd	50,0	Ti	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		30,0				6,2	1,9
	Gd	50,0	Zr	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		28,0				15,6	4,4
	Gd	50,0	Sn	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		35,0				42,8	15,0
	Ho	50,0	Ti	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		30,0				0,0	0,0
	Ho	50,0	Sn	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		30,0				26,2	7,9
	Sm	50,0	Ti	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		28,0				10,0	2,8
243	Sm	50,0	Zr	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		32,0				22,1	7,1
	Sm	50,0	Sn	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		40,0				48,8	19,5
	Y	50,0	Ti	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		30,0				3,4	1,0
	Y	50,0	Sn	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		35,0				45,3	15,9
	Eu	50,0	Ti	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		27,0				8,7	2,3
	Eu	50,0	Zr	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		29,0				23,7	6,9
	Eu	50,0	Sn	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		33,0				41,3	13,6
	Dy	50,0	Zr	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		29,0				16,0	4,6

	Nd	50,0	Zr	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		32,0				10,8	3,5
	Nd	50,0	Sn	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		35,0				43,6	15,3
	La	50,0	Zr	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		33,0				33,6	11,1
	La	50,0	Sn	50,0									Sol-gel	973	0,13	0,07	2,0	1,0	0,80		35,0				42,8	15,0
	Li	15,0	Na	15,0						Si	70,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		0,5				50,0	0,3
	Li	15,0	K	15,0						Si	70,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		1,0				81,0	0,8
	Li	15,0	Rb	15,0						Si	70,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		1,5				30,0	0,5
	Li	15,0	Cs	15,0						Si	70,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		9,0				24,0	2,2
	Na	15,0	K	15,0						Si	70,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		1,0				46,0	0,5
	Na	15,0	Rb	15,0						Si	70,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		0,5				65,0	0,3
	Na	15,0	Cs	15,0						Si	70,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		2,0				25,0	0,5
244	K	15,0	Rb	15,0						Si	70,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		0,5				15,0	0,1
	K	15,0	Cs	15,0						Si	70,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		1,0				18,0	0,2
	Rb	15,0	Cs	15,0						Si	70,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		1,0				16,0	0,2
	Mg	8,0	Ca	8,0						Si	84,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		7,0				17,0	1,2
	Mg	8,0	Sr	8,0						Si	84,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		11,0				19,0	2,1
	Mg	8,0	Ba	8,0						Si	84,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		7,5				12,0	0,9
	Ca	8,0	Sr	8,0						Si	84,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		8,5				17,0	1,4
	Ca	8,0	Ba	8,0						Si	84,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		7,0				19,0	1,3
	Sr	8,0	Ba	8,0						Si	84,0		Impregnation	1048	0,28	0,04	7,3	1,0	3,00		6,5				20,0	1,3
	Ca	60,2					P	39,8					Therm.decomp.	973	0,29	0,05	6,0	1,0	1,20	93,0	9,0		3,6	5,1	8,7	0,8
	Pb	9,1	Ca	54,7			P	36,2					Therm.decomp.	973	0,29	0,07	4,3	1,0	1,20	63,0	17,1		31,3	37,8	69,1	11,8
245	Ca	60,0					P	40,0					Therm.decomp.	973	0,29	0,04	6,7	1,0	1,20	41,0	4,4		1,3	6,0	7,3	0,3
	Pb	4,3	Mg	95,7									Therm.decomp.	973	0,29	0,04	6,9	1,0	0,20	72,0	6,7		4,9	26,2	31,1	2,1
	Pb	9,0	Ca	77,9			P	13,1					Therm.decomp.	973	0,29	0,04	7,1	1,0	0,20	42,0	4,5		5,7	34,7	40,4	1,8
	Mg	100,0											sol-gel	1023	0,81	0,20	4,0	1,0	0,24	52,0	5,8	71,0	8,0	21,0	29,0	1,7
	Li	5,0	Mg	90,0			Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	68,0	10,4	53,0	31,0	16,0	47,0	4,9
	Na	5,0	Mg	90,0			Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	65,0	12,0	51,0	34,0	15,0	49,0	5,9
	K	5,0	Mg	90,0			Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	64,0	7,0	62,0	20,0	18,0	38,0	2,7
	Rb	5,0	Mg	90,0			Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	65,0	6,0	65,0	21,0	14,0	35,0	2,1
	Cs	5,0	Mg	90,0			Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	70,0	10,2	59,0	22,0	18,0	40,0	4,1
	Li	2,5	Na	2,5	Mg	90,00	Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	82,0	22,4	22,0	51,0	27,0	78,0	17,5
246	Li	2,5	K	2,5	Mg	90,00	Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	81,0	16,0	32,0	43,0	25,0	68,0	10,9
	Li	2,5	Rb	2,5	Mg	90,00	Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	82,0	14,2	40,0	39,0	21,0	60,0	8,5
	Li	2,5	Cs	2,5	Mg	90,00	Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	85,0	22,8	19,0	53,0	28,0	81,0	18,5
	Na	2,5	K	2,5	Mg	90,00	Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	80,0	17,0	35,0	43,0	22,0	65,0	11,1
	Na	2,5	Rb	2,5	Mg	90,00	Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	84,0	14,2	43,0	37,0	20,0	57,0	8,1
	Na	2,5	Cs	2,5	Mg	90,00	Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	85,0	23,8	17,0	57,0	26,0	83,0	19,8
	K	2,5	Rb	2,5	Mg	90,00	Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	80,0	14,5	44,0	37,0	19,0	56,0	8,1
	K	2,5	Cs	2,5	Mg	90,00	Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	85,0	14,6	41,0	40,0	19,0	59,0	8,6
	Rb	2,5	Cs	2,5	Mg	90,00	Cl	5,0					sol-gel	1023	0,81	0,20	4,0	1,0	0,24	84,0	14,0	43,0	39,0	18,0	57,0	8,0
	Mo	25,0	Na	75,0									n.a.	1003	0,25	0,28	0,9	1,0	2,40	90,0	22,0				15,0	3,3
247	Mo	16,7	Na	58,3			Cl	25,0					n.a.	1003	0,25	0,28	0,9	1,0	2,40	90,0	19,0				23,0	4,4
	Mo	16,7	Na	25,0	Li	33,30	Cl	25,0					n.a.	1003	0,25	0,28	0,9	1,0	2,40	90,0	17,0				18,0	3,1
	Ba	50,0	Ti	50,0									Therm.decomp.	973	0,40	0,10	4,0	1,0	0,24		7,8	41,1	13,5	45,4	58,9	4,6
248	Ba	16,7	Ti	50,0			F	33,3					Therm.decomp.	973	0,40	0,10	4,0	1,0	0,24		28,1	39,4	36,7	24,0	60,7	17,1
	Zr	100,0											Therm.decomp.	973	0,38	0,13	3,0	1,0	0,24		26,0	84,0			16,1	4,2
	Ce	100,0											Therm.decomp.	773	0,38	0,13	3,0	1,0	0,24		21,1	98,1			1,9	0,4
	Th	100,0											Therm.decomp.	1123	0,38	0,13	3,0	1,0	0,24		24,0	68,0			32,0	7,7
	La	100,0											Therm.decomp.	923	0,38	0,13	3,0	1,0	0,24		6,8				12,1	0,8
249	Zr	33,3	La	16,7			F	50,0					Therm.decomp.	923	0,38	0,13	3,0	1,0	0,24		27,1	47,8			52,2	14,1
	Ce	33,3	La	16,7			F	50,0					Therm.decomp.	823	0,38	0,13	3,0	1,0	0,24		28,8	49,6			50,4	14,5
	Ce	20,0	La	20,0			F	60,0					Therm.decomp.	873	0,38	0,13	3,0	1,0	0,24		28,9	51,4			48,2	13,9
	Th	33,3	La	16,7			F	50,0					Therm.decomp.	823	0,38	0,13	3,0	1,0	0,24		29,6	55,6			44,5	13,2
	Th	20,0	La	20,0			F	60,0					Therm.decomp.	773	0,38	0,13	3,0	1,0	0,24		30,8	54,0			45,6	14,0
	Si	100,0											Sol-gel	1073	0,55	0,18	3,0	1,0	0,10		0,6				90,1	0,5
250	Mn	2,1								Si	97,9		Sol-gel	1073	0,55	0,18	3,0	1,0	0,10		16,4				34,3	5,6
	W	1,3	Na	21,3						Si	77,4		Sol-gel	1073	0,55	0,18	3,0	1,0	0,10		12,3				74,3	9,1
	Mn	1,7	W	1,3	Na	20,00				Si	77,0		Sol-gel	1073	0,55	0,18	3,0	1,0	0,10		36,8				64,9	23,9
251	Ca	100,0											n.a.	1073	0,90	0,10	9,0	1,0	0,60	98,0	11,9				55,1	6,6
	Ca	50,0					C	50,0					n.a.	1073	0,90	0,10	9,0	1,0	0,60	98,9	10,7				60,8	6,5
252	Zn	50,0					S	50,0					n.a.	1073	0,60	0,00	600,0	1,0	0,24		1,4		0,0	100,0	100,0	1,4
253	Y	25,0	Ba	50,0						Al	25,0		Sol-gel	1123	0,30	0,06	5,0	1,0	0,02	99,0	21,7				63,0	13,7
254	Y	25,4	Ba	38,6	Zr	36,00							Therm.decomp.	1073	0,91	0,09	10,1	1,0	0,05	85,7	14,1		30,2	43,0	73,2	10,3
255	Li	10,0	Mg	20,0						Al	70,0		Therm.decomp.	1048	0,90	0,10	9,0	1,0	0,85		21,0		80,0	15,0	95,0	20,0
	Li	10,0	Mo	5,0	Mg	15,00				Al	70,0		Therm.decomp.	1048	0,90	0,10	9,0	1,0	0,40		40,0		60,0	35,0	95,0	38,0
256	Li	19,0	Ti	81,0									Therm.decomp.	1173	0,50	0,16	3,1	1,0	0,25	90,0	12,0				70,0	8,4
	Al	100,0											Impregnation	1023	0,40	0,04	10,9	1,0	311785,00		1,5	69,5	6,1	24,6	30,7	0,5
257	Pb	9,5								Al	90,5		Impregnation	1023	0,40	0,04	10,9	1,0	311785,00		4,5	50,3	9,2	39,3	48,5	2,2
	Pb	5,1	Na	12,2						Al	82,7		Impregnation	1023	0,40	0,04	10,9	1,0	311785,00		6,2	41,7	10,2	41,2	51,4	3,2
	Si	16,7	Sr	83,3									Precipitation	1123	0,95	0,05	19,0	1,0	0,05	89,0	10,2				79,0	8,1
	Ba	100,0											Precipitation	1123	0,95	0,05	19,0	1,0	0,05	80,0	9,9				78,0	7,7
	Al	44,4	Ba	55,6									Precipitation	1123	0,95	0,05	19,0	1,0	0,05	95,0	10,5	3,0	27,0		84,0	8,8
	Sr	37,0	Mg	63,0									Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	10,3	4,0	31,0		83,0	8,5
	Ba	24,0	Mg	76,0									Precipitation	1123	0,95	0,05	19,0	1,0	0,05	99,0	10,3	3,0	31,0		83,0	8,5
	Li	1,4	Sr	20,0	Mg	78,60							Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	10,0				88,0	8,8
	Na	1,6	Sr	20,0	Mg	78,40							Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	9,4				89,0	8,4
	Al	2,2	Sr	20,0	Mg	77,80							Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	10,2				83,0	8,5
	Fe	1,1	Sr	20,0	Mg	78,90							Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	7,8				68,0	5,3
258	La	2,1	Sr	20,0	Mg	77,90							Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	10,6				85,0	9,0
	Zr	,2	Sr	20,0	Mg	79,00	Cl	,8					Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	10,3				87,0	9,0
	Zr	1,0	Sr	20,0	Mg	79,00							Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	10,2				83,0	8,5
	Sr	20,0	Mg	78,0			P	2,0					Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	4,6				72,0	3,3
	Nb	1,0	Sr	20,0	Mg	79,00							Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	10,4				88,0	9,2
	Mo	1,1	Sr	20,0	Mg	78,90							Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	8,0				69,0	5,5
	Li	,8	Ba	20,0	Mg	79,20							Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	10,0				86,0	8,6
	Na	1,6	Ba	20,0	Mg	78,40							Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	10,0				86,0	8,6
	La	2,0	Ba	20,0	Mg	78,00							Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	10,0				83,0	8,3
	Sm	2,0	Ba	20,0	Mg	78,00							Precipitation	1123	0,95	0,05	19,0	1,0	0,05	100,0	10,2				82,0	8,4
	Zr	2,0	Ba	20,0	Mg	78,00							Precipitation	1123	0,95	0,05	19,0	1,0	0,05	96,0	9,1				84,0	7,6
259	Ba	50,0	Pr	50,0									Therm.decomp.	1023	0,10	0,05	2,0	1,0	0,50	68,7	20,5	65,6	13,8	20,5	34,3	7,0
	Na	4,5	Ba	45,5	Pr	45,50	Cl	4,5					Therm.decomp.	1023	0,10	0,05	2,0	1,0	0,50	55,1	26,1	59,4	30,6	22,5	53,1	13,9

	Ca	50,0	Pr	50,0									Therm.decomp.	1023	0,10	0,05	2,0	1,0	0,50	99,5	25,3	92,7	3,9	3,4	7,3	1,8
	Na	4,5	Ca	45,5	Pr	45,50			Cl	4,5			Therm.decomp.	1023	0,10	0,05	2,0	1,0	0,50	94,5	33,3	57,7	34,5	7,7	42,2	14,1
	La	50,0	Y	50,0									Therm.decomp.	1023	0,10	0,05	2,0	1,0	0,50	99,3	36,5	73,3	21,1	5,6	26,7	9,7
	Na	4,5	La	45,5	Y	45,50			Cl	4,5			Therm.decomp.	1023	0,10	0,05	2,0	1,0	0,50	91,9	40,8	49,4	35,9	14,7	50,6	20,6
	Na	50,0	Nb	50,0									Therm.decomp.	1023	0,10	0,05	2,0	1,0	0,50	49,0	16,1	59,4	18,1	20,6	38,7	6,2
	Nb	45,5	Na	40,9					Cl	13,6			Therm.decomp.	1023	0,10	0,05	2,0	1,0	0,50	89,8	45,5	54,3	43,0	2,6	45,6	20,7
	K	50,0	Nb	50,0									Therm.decomp.	1023	0,10	0,05	2,0	1,0	0,50	22,3	8,5	58,8	13,8	27,4	41,2	3,5
	Na	4,5	K	45,5	Nb	45,50			Cl	4,5			Therm.decomp.	1023	0,10	0,05	2,0	1,0	0,50	67,2	36,8	53,4	42,9	3,6	46,5	17,1
	Pb	50,0	Ti	50,0									Therm.decomp.	1023	0,10	0,05	2,0	1,0	0,50	2,2	0,6	100,0	0,0	0,0	0,0	0,0
	Na	4,5	Pb	45,5	Ti	45,50			Cl	4,5			Therm.decomp.	1023	0,10	0,05	2,0	1,0	0,50	45,8	26,5	34,2	48,5	17,3	65,8	17,4
	Na	4,5	Li	45,5	Nb	45,50			Cl	4,5			Therm.decomp.	1023	0,10	0,05	2,0	1,0	0,50	25,1	16,9	24,0	55,5	20,5	76,0	12,8
	Na	4,5	Li	45,5	Ta	45,50			Cl	4,5			Therm.decomp.	1023	0,10	0,05	2,0	1,0	0,50	60,5	33,4	37,8	58,4	3,8	62,2	20,8
	Na	4,5	Pb	45,5	Ti	45,50			Cl	4,5			Therm.decomp.	1023	0,10	0,05	2,0	1,0	13,20		50,7				55,7	28,2
260	Na	7,0	Al	42,0	Li	51,00							Therm.decomp.	1123	0,18	0,06	2,9	1,0	0,55	78,9	20,4	45,6	37,5	16,8	54,3	11,1
261	La	100,0											precipitation	1073	0,33	0,07	5,0	1,0	0,03	90,0	26,0				58,0	15,1
262	Sr	50,0	Fe	50,0									Therm.decomp.	1000	0,84	0,03	25,5	1,0	0,61	95,0	4,0	50,0	15,0	35,0	50,0	2,0
	Ca	20,0	Ti	20,0	Co	30,00	Sr	30,00					Therm.decomp.	1020	0,84	0,03	25,5	1,0	0,61	94,0	12,0	95,0	1,0	4,0	5,0	0,6
263	W	25,0	Ba	75,0									Therm.decomp.		0,30	0,15	2,0	1,0	0,06	9,1	4,1	27,9			72,1	3,0
	Ba	50,0	Ce	50,0									Therm.decomp.		0,30	0,15	2,0	1,0	0,06	94,9	31,5	66,4			33,6	10,6
	Ce	10,0	W	22,5	Ba	67,50							Therm.decomp.		0,30	0,15	2,0	1,0	0,06	90,9	38,4	51,1			48,9	18,8
	Ce	10,0	W	20,0	Ba	70,00							Therm.decomp.		0,30	0,15	2,0	1,0	0,06	91,7	36,8	54,6			45,4	16,7
264	La	25,0							F	75,0			Therm.decomp.	1023	0,17	0,06	2,6	1,0	0,60		25,0				50,0	12,5
	Ce	20,0	Ba	26,7					F	53,3			Therm.decomp.	1073	0,73	0,27	2,7	1,0	0,24		34,0	45,7	34,0	20,3	54,3	18,5
265	Ru	6,3	Sb	18,7	Bi	25,00	Ba	50,00					Therm.decomp.	1023	0,67	0,33	2,0	1,0	0,08		32,2	60,1	26,8	5,5	32,3	10,4
	Sb	12,5	Bi	37,5	Ba	50,00							Therm.decomp.	1023	0,67	0,33	2,0	1,0	0,08		32,4	68,3	23,7	4,4	28,1	9,1
	Ru	12,5	Bi	37,5	Ba	50,00							Therm.decomp.	1023	0,67	0,33	2,0	1,0	0,08		27,6	68,5	21,9	6,3	28,2	7,8
	Sb	25,0	La	12,5	Bi	12,50	Ba	50,00					Therm.decomp.	1023	0,67	0,33	2,0	1,0	0,08		35,9	52,4	25,1	17,5	42,6	15,3
	Ni	16,7	Sb	16,7	Bi	16,60	Ba	50,00					Therm.decomp.	1023	0,67	0,33	2,0	1,0	0,08		33,4	61,6	24,7	5,8	30,5	10,2
	Ni	16,7	Sb	16,7	Ta	16,60	Ba	50,00					Therm.decomp.	1023	0,67	0,33	2,0	1,0	0,08		31,6	64,9	23,1	4,1	27,2	8,6
	Ni	16,7	Sb	16,7	Nb	16,60	Ba	50,00					Therm.decomp.	1023	0,67	0,33	2,0	1,0	0,08		33,4	64,5	22,9	4,3	27,2	9,1
	Sb	12,5	Ta	25,0	Li	12,50	Ba	50,00					Therm.decomp.	1123	0,67	0,33	2,0	1,0	0,08		36,4	66,0	22,6	3,2	25,8	9,4
	Sb	25,0	Ta	12,5	Na	12,50	Ba	50,00					Therm.decomp.	1123	0,67	0,33	2,0	1,0	0,08		38,3	75,9	17,4	2,9	20,3	7,8
	Sb	12,5	Ta	25,0	Na	12,50	Ba	50,00					Therm.decomp.	1123	0,67	0,33	2,0	1,0	0,08		35,0	66,5	22,3	3,6	25,9	9,1
266	Sb	12,5	Nb	25,0	Na	12,50	Ba	50,00					Therm.decomp.	1123	0,67	0,33	2,0	1,0	0,08		35,6	69,1	21,3	2,8	24,1	8,6
	Sb	25,0	Ta	12,5	Li	12,50	Ba	50,00					Therm.decomp.	1123	0,67	0,33	2,0	1,0	0,08		36,3	66,7	22,5	2,9	25,4	9,2
	Sb	25,0	Nb	12,5	Li	12,50	Ba	50,00					Therm.decomp.	1123	0,67	0,33	2,0	1,0	0,08		38,5	79,3	14,8	3,8	18,6	7,2
	Sb	12,5	Nb	25,0	Li	12,50	Ba	50,00					Therm.decomp.	1123	0,67	0,33	2,0	1,0	0,08		36,3	66,9	23,5	2,8	26,3	9,5
	Ni	1,1	K	9,0	Ca	89,90							Therm.decomp.	903	0,30	0,12	2,5	1,0	9000,00		37,0				54,2	20,1
	Ni	2,1	K	8,9	Ca	89,00							Therm.decomp.	923	0,30	0,12	2,5	1,0	9000,00		35,1				53,3	18,7
	Ni	1,2	K	2,3	Ca	96,50							Therm.decomp.	903	0,30	0,12	2,5	1,0	9000,00		34,0				55,5	18,9
267	Co	1,1	K	9,0	Ca	89,90							Therm.decomp.	1023	0,30	0,12	2,5	1,0	9000,00		34,1				53,4	18,2
	Ba	1,1	Ni	1,0	K	8,90	Ca	89,00					Therm.decomp.	983	0,30	0,12	2,5	1,0	9000,00		35,8				54,9	19,7
	Ni	1,1	K	9,0	Ba	89,90							Therm.decomp.	1053	0,30	0,12	2,5	1,0	9000,00		29,6				34,3	10,2
	Sn	,8	Li	17,2	Mg	82,00							Therm.decomp.	923	0,30	0,12	2,5	1,0	9000,00		21,7				37,0	8,0
268	Li	18,8	Mg	62,4					Cl	18,8			Sol-gel	923	0,13	0,05	2,6	1,0	7,20	85,0	36,3	43,3	49,7	6,9	56,6	20,5
	Mn	50,0	Mo	50,0									impregnation	973	0,40	0,20	2,0	1,0	7,20	10,0	3,3	79,0			2,4	0,1
269	Li	1,0	Mn	49,5	Mo	49,50							impregnation	973	0,40	0,20	2,0	1,0	7,20	16,0	6,4	63,0			24,0	1,5
	Na	1,0	Mn	49,5	Mo	49,50							impregnation	973	0,40	0,20	2,0	1,0	7,20	28,0	9,8	63,0			19,0	1,9
	K	1,0	Mn	49,5	Mo	49,50							impregnation	973	0,40	0,20	2,0	1,0	7,20	12,0	5,4	44,0			43,0	2,3
270	Sr	50,0	Ti	50,0									Therm.decomp.	1003	0,29	0,14	2,0	1,0	0,06		10,1				29,0	2,9
	Sr	66,7	Ti	33,3									Therm.decomp.	1003	0,29	0,14	2,0	1,0	0,06		12,6				33,3	4,2
	Sr	50,0	Sn	50,0									Therm.decomp.	1003	0,29	0,14	2,0	1,0	0,06		6,2				24,2	1,5
	Sr	66,7	Sn	33,3									Therm.decomp.	1003	0,29	0,14	2,0	1,0	0,06		8,0				27,4	2,2
	Sr	50,0	Zr	50,0									Therm.decomp.	1003	0,29	0,14	2,0	1,0	0,06		12,3				26,1	3,2
	Sr	66,7	Zr	33,3									Therm.decomp.	1003	0,29	0,14	2,0	1,0	0,06		10,4				30,7	3,2
271	Sr	3,9	La	96,1									n.a.	973	0,83	0,17	4,8	1,0	0,05		25,0				55,0	13,8
	Sr	3,9	La	92,2					S	3,9			Impregnation	973	0,83	0,17	4,8	1,0	0,05		21,0				45,0	9,5
	Ba	25,0	Ce	25,0					F	50,0			Therm.decomp.	1073	0,20	0,25	0,8	1,0	0,24		32,8		31,9	20,0	51,9	17,0
	Ba	28,6	Ce	14,3					F	57,1			Therm.decomp.	1073	0,20	0,25	0,8	1,0	0,24		33,7		32,3	21,0	53,3	18,0
	Ba	30,0	Ce	10,0					F	60,0			Therm.decomp.	1073	0,20	0,25	0,8	1,0	0,24		32,9		33,7	21,0	54,7	18,0
	Ba	30,8	Ce	7,6					F	61,6			Therm.decomp.	1073	0,20	0,25	0,8	1,0	0,24		34,0		33,6	20,0	53,6	18,2
	Ba	31,3	Ce	6,2					F	62,5			Therm.decomp.	1073	0,20	0,25	0,8	1,0	0,24		32,8		31,0	21,0	52,0	17,1
272	La	100,0											Therm.decomp.	873	0,20	0,25	0,8	1,0	0,24		29,1		24,6	20,2	44,8	13,0
	Sr	25,0							F	75,0			Therm.decomp.	1023	0,20	0,25	0,8	1,0	0,24		2,1		0,0	53,8	53,8	1,1
	Sr	100,0											Therm.decomp.	1023	0,20	0,25	0,8	1,0	0,24		0,9		0,0	51,2	51,2	0,5
	Sr	20,0	La	80,0									Therm.decomp.	873	0,20	0,25	0,8	1,0	0,24		28,4		27,2	22,6	49,8	14,1
	Sr	50,0	La	50,0									Therm.decomp.	973	0,20	0,25	0,8	1,0	0,24		30,2		29,2	21,7	50,9	15,4
	Sr	20,0	La	20,0					F	60,0			Therm.decomp.	1023	0,20	0,25	0,8	1,0	0,24		31,8		37,8	16,2	54,0	17,2
	Sr	33,0	La	16,7					F	50,3			Therm.decomp.	973	0,20	0,25	0,8	1,0	0,24		33,1		36,4	20,5	56,9	18,8
	Sr	50,0	La	12,5					F	37,5			Therm.decomp.	1023	0,20	0,25	0,8	1,0	0,24		33,8		40,0	13,9	53,9	18,2
273	Fe	3,0									Si	97,0	Impregnation	1123	0,05	0,03	1,7	1,0			10,0				60,0	6,0
274	Na	50,0	La	50,0									Therm.decomp.	1023	0,90	0,10	9,0	1,0	0,60		8,0		6,0	14,0	20,0	1,6
	V	13,0	Na	43,5	La	43,50							Therm.decomp.	1023	0,90	0,10	9,0	1,0	0,60		16,0		7,0	13,0	20,0	3,2
	Nb	13,0	Na	43,5	La	43,50							Therm.decomp.	1023	0,90	0,10	9,0	1,0	0,60		16,0		8,0	12,5	20,5	3,3
	Ta	13,0	Na	43,5	La	43,50							Therm.decomp.	1023	0,90	0,10	9,0	1,0	0,60		18,0		8,0	12,5	20,5	3,7
	Nb	23,1	Na	76,9									Therm.decomp.	1023	0,90	0,10	9,0	1,0	0,60		4,0		3,6	11,0	14,6	0,6
	Nb	13,0	Na	43,5	Sc	43,50							Therm.decomp.	1023	0,90	0,10	9,0	1,0	0,60		14,0		6,5	13,0	19,5	2,7
	Nb	13,0	Na	43,5	Y	43,50							Therm.decomp.	1023	0,90	0,10	9,0	1,0	0,60		16,7		7,8	13,0	20,8	3,5
	Nb	13,0	Na	43,5	La	43,50							Therm.decomp.	1023	0,90	0,10	9,0	1,0	0,60		15,8		8,0	13,5	21,5	3,4
	Nb	13,0	Na	43,5	Ce	43,50							Therm.decomp.	1023	0,90	0,10	9,0	1,0	0,60		14,5		6,5	13,2	19,7	2,9
	Nb	13,0	Na	43,5	Sm	43,50							Therm.decomp.	1023	0,90	0,10	9,0	1,0	0,60		14,5		7,0	13,2	20,2	2,9
275	Ba	7,2	La	78,2					F	14,6			Therm.decomp.	1053	0,80	0,20	4,0	1,0	0,24		28,7	32,7	44,6	22,6	67,2	19,3
276	Mn	50,0	Mg	50,0									Impregnation	1023	0,75	0,25	3,0	1,0	0,25		24,5				19,7	4,8
	Li	33,3	Mn	33,3	Mg	33,40							Impregnation	1023	0,75	0,25	3,0	1,0	0,25		25,9				25,0	6,5
	Na	33,3	Mn	33,3	Mg	33,40							Impregnation	1023	0,75	0,25	3,0	1,0	0,25		24,8				21,0	5,2
	K	33,3	Mn	33,3	Mg	33,40							Impregnation	1023	0,75	0,25	3,0	1,0	0,25		24,7				20,4	5,0
	Mn	20,0	Mg	20,0	Na	60,00							Impregnation	1023	0,75	0,25	3,0	1,0	0,25		25,1				24,4	6,1
	Na	33,3	Mn	33,3	Mg	33,40							Impregnation	1023	0,75	0,25	3,0	1,0	0,25		23,7				19,0	4,5
277	Ca	100,0											Therm.decomp.	1013	0,67	0,07	9,6	1,0	0,11	94,0	11,0		33,0	18,0	51,0	5,6
	Na	11,9	Ca	88,1									Therm.decomp.	1013	0,67	0,07	9,6	1,0	0,96	93,0	15,0		36,0	30,0	66,0	9,9
	Li	11,0	Ca	89,0									Therm.decomp.	1013	0,67	0,07	9,6	1,0	1,37	96,0	16,0		29,0	34,0	63,0	10,1
278	Na	8,1	Pb	18,5							Al	36,7	Si	36,7	Therm.decomp.	1023	0,70	0,07	10,0	1,0	1,03	25,3	2,1	8,0	33,1	41,1	0,9
	Pb	20,0									Al	40,0	Si	40,0	Therm.decomp.	1023	0,70	0,07	10,0	1,0	1,03	58,4	3,9	5,0	14,5	19,5	0,8
279	Pb	33,3	Al	66,7									Sol-gel	993	0,36	0,05	7,3	1,0	0,65		9,7				81,0	7,9
	Pb	33,3	Al	66,7									precipitation	1123	0,48	0,07	7,1	1,0	0,75		12,2				50,3	6,1

	La	100,0										Cl			Therm.decomp.	923	0,75	0,25	3,0	1,0	0,24		29,3	58,3	24,6	19,2	43,8	12,8
	La	25,0							F	75,0					Therm.decomp.	1023	0,75	0,25	3,0	1,0	0,24		2,1	46,2	0,0	53,8	53,8	1,1
280	Sr	100,0													Therm.decomp.	1023	0,75	0,25	3,0	1,0	0,24		0,9	48,8	0,0	51,2	51,2	0,5
	Sr	25,0							F	75,0					Therm.decomp.	1023	0,75	0,25	3,0	1,0	0,24		0,7	46,0	0,0	54,0	54,0	0,4
	Sr	33,3	La	66,7											Therm.decomp.	973	0,75	0,25	3,0	1,0	0,24		30,2	49,1	29,2	21,7	50,9	15,4
	Sr	12,9	La	61,5					F	25,6					Therm.decomp.	973	0,75	0,25	3,0	1,0	0,24		34,7	42,5	35,8	21,7	57,5	20,0
281	Pb	6,3	Ca	93,7											Therm.decomp.	973	0,29	0,04	7,3	1,0	1,20	80,0	15,0				78,0	11,7
	Fe	100,0													Impregnation	1023	0,32	0,08	4,0	1,0	0,24	100,0	13,5	100,0	0,0	0,0	0,0	0,0
282	Na	16,6	Fe	66,7					Cl	16,7					Impregnation	1023	0,32	0,08	4,0	1,0	0,24	100,0	18,2	70,5	15,7		29,1	5,3
	Fe	55,6	Na	13,9					B	16,6	Cl	13,9			Impregnation	1023	0,32	0,08	4,0	1,0	0,24		22,7	23,7	54,6		75,8	17,2
283	Ag	100,0													Impregnation	1080	0,63	0,16	4,0	1,0	0,50		13,0				32,0	4,2
	Na	5,0	Ag	90,0					P	5,0					Impregnation	1100	0,63	0,16	4,0	1,0	0,50		7,0				91,0	6,4
284	Au	,3	La	1,8	Ca	97,90									Impregnation	1073	0,69	0,31	2,2	1,0	0,29		32,3				35,8	11,6
	Sr	16,7	La	33,3	Ca	50,00									Impregnation	1073	0,90	0,10	9,0	1,0	0,06		18,5				78,4	14,5
285	La	33,3	Ca	66,7											Impregnation	1073	0,90	0,10	9,0	1,0	0,06		14,8				67,4	10,0
	Sr	4,7	La	33,3	Ca	62,00									Impregnation	1073	0,90	0,10	9,0	1,0	0,06		16,8				77,3	13,0
286	Na	7,5	Ca	92,5											sol-gel	1063	0,90	0,10	9,0	1,0	0,60	95,0	18,0				80,0	14,4
	Ti	100,0													Impregnation	1073	0,75	0,25	3,0	1,0	2,10		6,3		7,5		13,8	0,9
	Mn	9,9	Ti	90,1											Impregnation	1073	0,75	0,25	3,0	1,0	2,10		17,7		11,8		23,0	4,1
287	La	,7	Mn	9,3	Ti	90,00									Impregnation	1073	0,75	0,25	3,0	1,0	2,10		16,0		0,8		2,8	0,4
	Li	1,0	Mn	9,0	Ti	90,00									Impregnation	1073	0,75	0,25	3,0	1,0	2,10		22,1		55,2		71,5	15,8
	Li	1,0	La	,7	Mn	8,30	Ti	90,00							Impregnation	1073	0,75	0,25	3,0	1,0	2,10		27,5		61,2		76,1	20,9
288	V	1,8	Na	18,4	Mo	1,10	Si	78,70				Cl			Therm.decomp.	1023	0,21	0,03	6,4	1,0	0,29		17,0	20,0			70,0	11,9
289	Sr	3,5											Si	96,5	Impregnation	1048	0,28	0,04	7,1	1,0	3,00		9,0		10,0	7,0	17,0	1,5
	Li	6,6	Sr	7,4									Si	86,0	Impregnation	1048	0,28	0,04	7,1	1,0	3,00		4,0		43,0	15,0	58,0	2,3
290	Ce	,3	Li	15,6	Mg	84,10									Impregnation	1003	0,67	0,33	2,0	1,0	1,32		38,8	61,5	35,1	3,4	38,5	14,9
	Ce	,3	Li	23,0	Ca	12,90	Mg	63,80							Impregnation	1003	0,67	0,33	2,0	1,0	1,32		28,0	23,2	57,5	19,3	76,8	21,5
	Bi	100,0													Therm.decomp.	1088	0,34	0,13	2,6	1,0	0,50		14,4	64,3	19,4	11,7	31,1	4,5
291	Sm	4,0	Bi	96,0											Therm.decomp.	1088	0,34	0,13	2,6	1,0	0,50		18,9	64,0	22,7	9,5	32,2	6,1
	Er	4,0	Bi	96,0											Therm.decomp.	1088	0,34	0,13	2,6	1,0	0,50		19,4	62,8	23,7	7,9	31,6	6,1
	Lu	4,0	Bi	96,0											Therm.decomp.	1088	0,34	0,13	2,6	1,0	0,50		20,2	63,9	24,9	7,4	32,3	6,5
	W	3,0											Si	97,0	Impregnation	1073	0,43	0,14	3,1	1,0	0,15		22,5				4,2	0,9
292	Na	9,1	W	4,5									Si	86,4	Impregnation	1073	0,43	0,14	3,1	1,0	0,15		23,4				70,2	16,4
	Li	23,0	W	3,8									Si	73,2	Impregnation	1073	0,43	0,14	3,1	1,0	0,15		17,4				50,9	8,9
	Na	15,8	W	7,9									Si	76,3	Therm.decomp.	1053	0,42	0,09	4,8	1,0	1,00	19,5	4,1	25,7	16,7	57,6	74,3	3,0
	Na	9,0	W	4,5									La	86,5	Therm.decomp.	1053	0,42	0,09	4,8	1,0	1,00	97,0	25,8	46,7	28,7	24,6	53,3	13,8
	Na	15,8	W	7,9									Ce	76,3	Therm.decomp.	1053	0,42	0,09	4,8	1,0	1,00	94,8	22,4	26,5	35,8	37,7	73,5	16,5
	Na	3,3	W	1,6									Pr	95,1	Therm.decomp.	1053	0,42	0,09	4,8	1,0	1,00	94,5	27,6	37,7	29,5	32,8	62,3	17,2
293	Na	9,0	W	4,5									Nd	86,5	Therm.decomp.	1053	0,42	0,09	4,8	1,0	1,00	88,6	25,2	35,7	33,7	30,6	64,3	16,2
	Na	9,0	W	4,5									Sm	86,5	Therm.decomp.	1053	0,42	0,09	4,8	1,0	1,00	92,5	26,3	36,7	33,1	30,2	63,3	16,6
	Na	4,8	W	2,4									Tb	92,8	Therm.decomp.	1053	0,42	0,09	4,8	1,0	1,00	95,4	26,6	43,9	25,1	31,0	56,1	14,9
	Na	9,0	W	4,5									Dy	86,5	Therm.decomp.	1053	0,42	0,09	4,8	1,0	1,00	88,1	22,7	41,6	28,4	30,0	58,4	13,3
	Na	9,0	W	4,5									Yb	86,5	Therm.decomp.	1053	0,42	0,09	4,8	1,0	1,00	76,5	20,5	43,5	25,5	31,0	56,5	11,6
294	Mn	1,8	Na	9,1	W	4,80	Mg	84,30							Impregnation	1073	0,88	0,12	7,3	1,0	0,52		20,0				80,0	16,0
	Zn	100,0													precipitation	1023	0,08	0,04	2,0	1,0	0,60		11,0	74,0			26,0	2,9
	Zn	48,5											Al	51,5	precipitation	1023	0,08	0,04	2,0	1,0	0,60		11,0	23,2	18,0	33,0	51,0	5,6
	Zn	15,8											Si	84,2	precipitation	1023	0,08	0,04	2,0	1,0	0,60		6,7	83,0			16,0	1,1
295	Na	13,0	Zn	36,5					Cl	12,9			Al	37,6	precipitation	1023	0,08	0,04	2,0	1,0	0,60		27,0	45,0	49,0	6,4	55,4	15,0
	Na	11,6	Zn	12,1					Cl	11,5			Si	64,8	precipitation	1023	0,08	0,04	2,0	1,0	0,60		7,2	43,0			57,0	4,1
	Li	16,1	Zn	32,9					Cl	16,1			Al	34,9	precipitation	1023	0,08	0,04	2,0	1,0	0,60		29,0	20,9	78,0	1,8	79,8	23,1
	K	9,7	Zn	24,0					Cl	9,6			Al	56,7	precipitation	1023	0,08	0,04	2,0	1,0	0,60		16,0	32,2	51,0	17,0	68,0	10,9
296	Ba	50,0	Ti	50,0											sol-gel	1023	0,13	0,07	2,0	1,0	12,00	100,0	40,0				35,0	14,0
	Pb	5,6	Ca	94,4											Therm.decomp.	1023	0,07	0,03	2,0	1,0	1,80		29,0				13,0	3,8
297	La	3,0	Pb	5,9	Ca	91,10									Therm.decomp.	1023	0,07	0,03	2,0	1,0	1,80		32,0				26,0	8,3
	K	6,8	Pb	5,5	Ca	87,70									Therm.decomp.	1023	0,07	0,03	2,0	1,0	1,80		32,0				28,0	9,0
	Li	24,6	Pb	4,0	Ca	71,40									Therm.decomp.	1023	0,07	0,03	2,0	1,0	1,80		34,0				36,0	12,2
	Y	100,0													Precipitation	1023	0,70	0,17	4,1	1,0	0,59	94,6	15,7	69,9	18,1	12,0	30,1	4,7
298	Sr	4,8	Y	95,2											precipitation	1023	0,70	0,17	4,1	1,0	0,59	100,0	18,7	65,6	24,3	10,1	34,4	6,4
	Na	4,8	Y	95,2											precipitation	1023	0,70	0,09	7,8	1,0	0,59	87,0	7,5	55,4	0,0	44,6	44,6	3,3
	Na	33,3	Y	66,7											precipitation	1023	0,70	0,10	7,0	1,0	0,59	83,3	6,8	52,7	0,0	47,3	47,3	3,2
	Zr	100,0													Therm.decomp.	1023	0,17	0,08	2,0	1,0	1,20		24,6	96,9	1,0	2,1	3,1	0,8
299	Na	37,5	Zr	62,5											Therm.decomp.	1023	0,17	0,08	2,0	1,0	1,20		26,0	36,1	36,4	24,0	60,4	15,7
	Na	27,3	Zr	45,4					Cl	27,3					Therm.decomp.	1023	0,17	0,08	2,0	1,0	1,20		33,5	59,2	22,4	17,2	39,6	13,3
300	Nb	100,0													n.a.	1023	0,70	0,07	10,0	1,0	0,59		13,0				30,0	3,9
	La	50,0							F	50,0					Therm.decomp.	1053	0,80	0,20	4,0	1,0	0,24		25,0		27,2	19,4	46,6	11,7
301	Ba	3,3	La	45,0					F	51,7					Therm.decomp.	1053	0,80	0,20	4,0	1,0	0,24		28,7		44,7	22,6	67,3	19,3
	Ba	100,0													Impregnation	1093	0,81	0,19	4,3	1,0	0,30		3,0	44,6	0,0	55,4	55,4	1,7
302	V	9,1	Ba	90,9											Impregnation	1093	0,81	0,19	4,3	1,0	0,30		25,0	49,0	37,2	23,8	61,0	15,3
	Ba	5,0	Ca	95,0											Impregnation	1123	0,80	0,20	4,0	1,0	0,72		26,2				52,7	13,8
303	Ba	10,0	Ca	90,0											Impregnation	1123	0,80	0,20	4,0	1,0	0,72		27,6				48,4	13,4
	Ba	5,3	La	94,7											Impregnation	1093	0,85	0,15	5,7	1,0	0,72		24,2				56,7	13,7
	Cu	33,3	La	66,7											Therm.decomp.	1023	0,18	0,07	2,5	1,0	2,40	34,0	9,5	64,0	20,0	16,0	36,0	3,4
304	Ba	6,7	Cu	33,3	La	60,00									Therm.decomp.	1023	0,18	0,09	1,9	1,0	2,40	37,2	13,6	62,5	24,3	13,2	37,5	5,1
	Y	16,7	Ba	33,3	Cu	50,00									Therm.decomp.	1023	0,18	0,09	2,0	1,0	2,40	12,4	6,2	37,2	40,5	22,5	63,0	3,9
305	Sr	33,3	La	33,3	Zr	33,40									n.a.	1153	0,42	0,17	2,4	1,0	0,30		36,5				49,0	17,9
	La	40,0	Na	40,0	Ba	20,00									Therm.decomp.	1003	0,78	0,22	3,5	1,0	1,62		36,2				49,2	17,8
306	La	40,0	Na	40,0	Mg	20,00									Therm.decomp.	1003	0,78	0,22	3,5	1,0	1,62		37,3				51,3	19,1
	La	40,0	Na	40,0	Zn	20,00									Therm.decomp.	1003	0,78	0,22	3,5	1,0	1,62		24,7				45,5	11,2
	La	40,0	Ba	20,0	Na	40,00									Impregnation	1003	0,78	0,22	3,5	1,0	1,62		34,5	56,7	34,8	13,2	48,0	16,6
	La	40,0	Na	40,0	Mg	20,00									Impregnation	1003	0,78	0,22	3,5	1,0	1,62		37,3	45,2	30,8	20,5	51,3	19,1
307	La	40,0	Na	40,0	Zn	20,00									Impregnation	1003	0,78	0,22	3,5	1,0	1,62		24,7	53,8	27,9	17,6	45,5	11,2
	Li	16,7	La	45,8	Ba	37,50									Impregnation	1023	0,38	0,13	2,9	1,0	0,54		22,9	31,6	32,9	32,7	65,6	15,0
	Na	8,8	La	50,0	Ba	41,20									Impregnation	1023	0,38	0,13	2,9	1,0	0,54		31,3	34,4	38,9	22,3	61,2	19,2
	Cs	2,1	La	55,0	Ba	42,90									Impregnation	1023	0,38	0,13	2,9	1,0	0,54		24,0	38,9	28,2	30,8	59,0	14,2
	La	100,0													Therm.decomp.	1023	0,17	0,06	2,6	1,0	0,60	92,9	24,1	72,0	15,0	13,1	28,1	6,8
	Ba	100,0													Therm.decomp.	1023	0,17	0,06	2,6	1,0	0,60	13,5	5,1	71,6	6,4	22,0	28,4	1,4
	Ba	1,2	La	98,8											Therm.decomp.	1023	0,17	0,06	2,6	1,0	0,60	96,0	27,1	69,4	16,4	14,9	31,3	8,5
308	Ba	33,3							F	66,7					Therm.decomp.	1023	0,17	0,06	2,6	1,0	0,60	6,0	2,2	45,8	0,0	54,2	54,2	1,2
	Ba	33,3							Br	66,7					Therm.decomp.	1023	0,17	0,06	2,6	1,0	0,60	16,0	9,3	39,4	33,8	26,8	60,6	5,6
	Ba	3,3	La	90,0					F	6,7					Therm.decomp.	1023	0,17	0,06	2,6	1,0	0,60	99,0	27,0	56,8	24,3	19,4	43,7	11,8
	Ba	3,3	La	90,0					Br	6,7					Therm.decomp.	1023	0,17	0,06	2,6	1,0	0,60	100,0	44,7	59,5	27,5	13,0	40,5	18,1

	La	92,5						Br	7,5							Therm.decomp.	1023	0,17	0,06	2,6	1,0	0,60	93,0	35,0	78,3	14,5	7,1	21,6	7,6
309	Li	20,0	Fe	80,0												Impregnation	1000	0,67	0,33	2,0	1,0	2,00		55,0				5,0	2,8
	Li	9,0	Ni	1,1	Mg	89,90										Therm.decomp.	978	0,30	0,12	2,5	1,0	0,01		25,0				36,5	9,1
310	Na	9,0	Ni	1,1	Mg	89,90										Therm.decomp.	978	0,30	0,12	2,5	1,0	0,01		19,3				25,4	4,9
	K	9,0	Ni	1,1	Mg	89,90										Therm.decomp.	978	0,30	0,12	2,5	1,0	0,01		25,9				25,7	6,7
	K	9,0	Ni	1,1	Ca	89,90										Precipitation	978	0,30	0,12	2,5	1,0	0,01		34,1				53,6	18,3
	V	,7										Si	99,3			Sol-gel	898	2,21	0,31	7,2	4,5	0,05		10,7		6,0	15,1	21,1	2,3
311	V	6,9										Si	93,1			Sol-gel	923	2,21	0,31	7,2	4,5	0,05		1,2		0,0	16,1	16,1	0,2
	V	18,1										Si	81,9			Sol-gel	923	2,21	0,31	7,2	4,5	0,05		3,4		0,0	0,0	0,0	0,0
	Zn	48,5										Al	51,5			precipitation	1023	0,08	0,04	2,0	1,0	0,60	36,7	10,6	48,8	18,1	33,1	51,2	5,4
	Na	4,1	Zn	44,8				I	4,0			Al	47,1			precipitation	1023	0,08	0,04	2,0	1,0	0,60	33,0	8,5	49,7	21,1	29,2	50,3	4,3
312	Na	5,7	Zn	43,5				Br	5,7			Al	45,1			precipitation	1023	0,08	0,04	2,0	1,0	0,60	87,0	43,1	53,6	44,7	1,7	46,4	20,0
	Na	11,9	Zn	37,0				F	11,9			Al	39,2			precipitation	1023	0,08	0,04	2,0	1,0	0,60	43,0	19,9	36,1	54,1	9,8	63,9	12,7
	Na	9,2	Zn	39,8				Cl	9,2			Al	41,8			precipitation	1023	0,08	0,04	2,0	1,0	0,60	1,3	1,9	30,8	10,6	58,6	69,2	1,3
	Mg	100,0														Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,07		8,6				37,6	3,2
	La	,5	Mg	99,5												Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,07		17,0				68,3	11,6
	Ce	,5	Mg	99,5												Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,07		19,8				65,3	12,9
	Nd	,5	Mg	99,5												Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,07		14,1				53,1	7,5
	Eu	,5	Mg	99,5												Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,07		15,3				58,9	9,0
313	Yb	,5	Mg	99,5												Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,07		11,5				42,8	4,9
	La	9,9	Mg	90,1												Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,07		17,7				69,8	12,4
	Ce	9,9	Mg	90,1												Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,07		19,8				65,7	13,0
	Nd	9,9	Mg	90,1												Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,07		16,4				61,5	10,1
	Eu	9,9	Mg	90,1												Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,07		19,6				68,2	13,4
	Yb	9,9	Mg	90,1												Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,07		12,9				44,2	5,7
	Ca	50,0	Ti	50,0												Therm.decomp.	1073	0,08	0,04	2,0	1,0	1,80		37,0				36,0	13,3
314	Li	5,0	Ca	50,0	Ti	45,00										Therm.decomp.	1073	0,08	0,04	2,0	1,0	1,80		40,0				50,0	20,0
	Mg	5,0	Ca	50,0	Ti	45,00										Therm.decomp.	1073	0,08	0,04	2,0	1,0	1,80		36,0				39,0	14,0
	Mg	2,6	Nd	97,4												precipitation	1023	0,60	0,06	10,0	1,0	0,93	91,0	11,0				64,0	7,0
315	Ca	2,6	Nd	97,4												precipitation	1023	0,60	0,06	10,0	1,0	0,93	91,0	11,0				68,0	7,5
	Sr	2,6	Nd	97,4												precipitation	1023	0,60	0,06	10,0	1,0	0,93	93,0	13,0				70,0	9,1
	Ba	2,6	Nd	97,4												precipitation	1023	0,60	0,06	10,0	1,0	0,93	90,0	12,0				68,0	8,2
	Y	100,0														Therm.decomp.	1073	0,75	0,15	5,0	1,0	0,18	99,2	27,0	68,1	20,0	11,9	31,9	8,6
316	Ca	22,3	Y	33,0				F	44,7							Therm.decomp.	1073	0,75	0,15	5,0	1,0	0,18	99,5	31,5	58,0	28,8	13,2	42,0	13,2
	Sr	22,3	Y	33,0				F	44,7							Therm.decomp.	1073	0,75	0,15	5,0	1,0	0,18	99,1	34,0	42,9	36,7	20,4	57,1	19,4
	Ba	22,3	Y	33,0				F	44,7							Therm.decomp.	1073	0,75	0,15	5,0	1,0	0,18	99,3	30,5	50,2	32,5	17,3	49,8	15,2
317	Na	2,7	Zr	10,8						Cl	Si	86,5				Impregnation	1073	0,17	0,08	2,0	1,0	1,20		40,0				60,0	24,0
	Bi	100,0														precipitation	1143	0,56	0,19	2,9	1,0	0,36		7,5				60,0	4,5
318	Bi	30,0	Y	70,0												precipitation	1123	0,56	0,19	2,9	1,0	0,13		39,1				46,0	18,0
	Y	100,0														Therm.decomp.	1023	0,56	0,19	2,9	1,0	0,24		31,4				43,0	13,5
	Li	23,4	Mg	76,6												Impregnation	1073	0,56	0,19	2,9	1,0	2,30		37,1				52,0	19,3
319	La	50,0						Cl	50,0							Therm.decomp.	1073	0,18	0,07	2,5	1,0	0,60		37,0	71,0			29,0	10,7
	Ba	5,0	La	45,0				Cl	45,0	C	5,0					Therm.decomp.	1073	0,18	0,07	2,5	1,0	0,60		39,0	41,0			58,0	22,6
	Ce	100,0														Therm.decomp.	1073	0,75	0,15	5,0	1,0	0,18	99,6	22,4				2,8	0,6
	Ce	7,7	Ba	30,8				F	61,5							Therm.decomp.	1073	0,75	0,15	5,0	1,0	0,18	99,5	32,3	45,4			54,6	17,6
320	Pr	100,0														Therm.decomp.	1073	0,75	0,15	5,0	1,0	0,18	99,5	23,1	78,4			21,6	5,0
	Pr	14,2	Ba	28,6				F	57,2							Therm.decomp.	1073	0,75	0,15	5,0	1,0	0,18	99,4	33,5	42,5			57,5	19,3
	Tb	100,0														Therm.decomp.	1073	0,75	0,15	5,0	1,0	0,18	99,5	24,2	77,1			22,9	5,5
	Tb	14,2	Ba	28,6				F	57,2							Therm.decomp.	1073	0,75	0,15	5,0	1,0	0,18	99,4	33,1	43,9			56,1	18,6
	La	100,0														Impregnation	1073	0,50	0,10	5,0	1,0	0,04		16,4	51,4	10,4	38,2	48,6	8,0
321	La	46,2	Zn	53,8												Impregnation	1073	0,50	0,10	5,0	1,0	0,04		24,3	45,5	22,1	32,4	54,5	13,2
	Sr	9,1	La	18,2	Zr	72,70										Impregnation	1073	0,50	0,10	5,0	1,0	0,04		23,1	35,4	26,7	37,9	64,6	14,9
	K	16,7	Sr	8,3	La	16,70	Zr	58,30								Impregnation	1073	0,50	0,10	5,0	1,0	0,04		26,6	31,8	27,9	40,3	68,2	18,1
	Ni	100,0														Therm.decomp.	973	0,50	0,08	6,0	1,0	1,00		20,3	100,0	0,0	0,0	0,0	0,0
	Zr	100,0														Therm.decomp.	1048	0,50	0,08	6,0	1,0	1,00		8,9	64,5	4,5	31,0	35,5	3,2
	Mn	100,0														Therm.decomp.	1023	0,50	0,08	6,0	1,0	1,00		15,1	91,3	0,0	8,7	8,7	1,3
322	Nd	100,0														Therm.decomp.	1023	0,50	0,08	6,0	1,0	1,00		16,1	43,1	38,2	18,7	56,9	9,2
	Ni	2,6	Nd	97,4												Therm.decomp.	923	0,50	0,08	6,0	1,0	1,00		16,4	30,6	37,8	31,6	69,4	11,4
	Mn	4,2	Nd	95,8												Therm.decomp.	993	0,50	0,08	6,0	1,0	1,00		17,3	31,0	35,0	34,0	69,0	11,9
	Zr	2,6	Nd	97,4												Therm.decomp.	1023	0,50	0,08	6,0	1,0	1,00		17,5	33,8	28,9	37,3	66,2	11,6
	Ba	5,0										Si	95,0			n.a.	1048	0,29	0,03	8,8	1,0	3,00		4,8	87,0	6,2	6,8	13,0	0,6
323	Cs	5,0										Si	95,0			n.a.	1048	0,29	0,03	8,8	1,0	3,00		3,9	88,0	10,0	2,0	12,0	0,5
	Co	5,0										Si	95,0			n.a.	1048	0,29	0,03	8,8	1,0	3,00		5,9	88,0	3,5	8,5	12,0	0,7
	Zr	100,0														Impregnation	1073	0,15	0,05	3,0	1,0	0,60		16,0	82,1	11,3	6,6	17,9	2,9
	Zr	94,0						S	6,0							Impregnation	1073	0,15	0,05	3,0	1,0	0,60		16,8	82,0	11,7	6,3	18,0	3,0
324	Li	5,0	Zr	95,0												Impregnation	1073	0,15	0,05	3,0	1,0	0,60		17,2	49,9	27,2	22,9	50,1	8,6
	Li	5,0	Zr	89,0				S	6,0							Impregnation	1073	0,15	0,05	3,0	1,0	0,60		32,1	21,0	58,3	20,7	79,0	25,4
	Li	5,0	Zr	89,0				S	6,0							Impregnation	1073	0,10	0,05	2,0	1,0	0,60		43,3	21,0	58,3	20,7	79,0	34,2
325	Y	25,0	Bi	75,0												precipitation	1173	0,30	0,10	3,0	1,0	0,24		29,3				58,0	17,0
	Li	5,0	Mg	95,0												precipitation	1073	0,30	0,10	3,0	1,0	2,20		37,5				51,4	19,3
326	Sr	9,1	La	90,9												Impregnation	1073	0,80	0,20	4,0	1,0	0,04		26,7				60,7	16,2
	Sr	1,0	La	5,6								Si	9,4	Al	84,0	Impregnation	1073	0,80	0,20	4,0	1,0	0,04		29,1				63,3	18,4
	Pr	100,0														Therm.decomp.	1123	0,55	0,16	3,4	1,0	0,20	98,2	19,9		7,8	13,1	20,9	4,2
327	Sr	11,1	Pr	66,7				F	22,2							Therm.decomp.	1123	0,55	0,16	3,4	1,0	0,20	98,1	29,2		31,4	26,6	58,0	16,9
	Sr	20,0	Pr	40,0				F	40,0							Therm.decomp.	1123	0,55	0,16	3,4	1,0	0,20	98,3	29,4		30,7	28,0	58,7	17,3
	Sr	27,3	Pr	18,1				F	54,6							Therm.decomp.	1123	0,55	0,16	3,4	1,0	0,20	86,8	26,8		35,4	26,1	61,5	16,5
	Sr	50,0	Ce	47,5	Yb	2,50										Therm.decomp.	883	0,44	0,11	4,0	1,0	0,33		19,9		24,6	24,5	49,1	9,8
328	Ba	50,0	Ce	46,5	La	3,50										Therm.decomp.	923	0,44	0,11	4,0	1,0	0,33		26,1		32,1	28,8	60,9	15,9
	Li	24,0	Sr	38,0	Ce	36,10	Yb	1,90								Therm.decomp.	893	0,44	0,11	4,0	1,0	0,33		18,0		28,4	44,6	73,0	13,1
	Li	24,0	Ba	38,0	Ce	35,30	La	2,70								Therm.decomp.	883	0,44	0,11	4,0	1,0	0,33		18,3		31,6	41,0	72,6	13,3
	Ca	4,7	La	1,8	Mg	93,50										Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,02		20,4				71,1	14,5
	Ca	8,3	La	8,3	Mg	83,40										Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,02		18,7				78,6	14,7
	Ca	1,9	La	1,9	Mg	96,20										Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,02		17,1				88,9	15,2
	Ca	1,8	La	8,9	Mg	89,30										Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,02		22,3				71,3	15,9
329	Ba	4,7	La	,9	Mg	94,40										Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,02		20,4				73,0	14,9
	Ba	4,3	La	8,7	Mg	87,00										Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,02		19,4				72,2	14,0
	Ba	1,8	La	8,9	Mg	89,30										Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,02		19,2				71,9	13,8
	Ba	1,9	La	1,9	Mg	96,20										Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,02		21,0				74,8	15,7
	Ba	8,3	La	8,3	Mg	83,40										Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,02		20,6				74,3	15,3
	Mg	90,1	La	9,9												Therm.decomp.	1073	0,89	0,11	8,1	1,0	0,02		16,6				72,3	12,0
330	Li	9,1	Mg	90,9												Impregnation	1023	0,80	0,20	4,0	1,0	0,35		27,6				64,0	17,7
	Na	9,1	Mg	90,9												Impregnation	1023	0,80	0,20	4,0	1,0	0,35		26,6				58,7	15,6

	K	9,1	Mg	90,9												Impregnation	1023	0,80	0,20	4,0	1,0	0,35		22,4				34,9	7,8
	Rb	9,1	Mg	90,9												Impregnation	1023	0,80	0,20	4,0	1,0	0,35		20,7				29,9	6,2
	Cs	9,1	Mg	90,9												Impregnation	1023	0,80	0,20	4,0	1,0	0,35		5,1				42,5	2,2
331	Bi	82,4	W	17,6												Therm.decomp.	1098	0,38	0,13	3,0	1,0	0,75		20,0				60,0	12,0
332	Mg	100,0														n.a.	1173	0,80	0,20	4,0	1,0	0,20		16,1		39,8	11,3	51,1	8,2
	Na	20,0	Mg	80,0												Impregnation	1173	0,80	0,20	4,0	1,0	0,20		21,5		42,8	17,5	60,3	13,0
333	Mg	30,0	Ba	70,0												Therm.decomp.	1053	0,80	0,20	4,0	1,0	0,20		24,0				43,0	10,3
334	Ba	100,0														Impregnation	973	0,17	0,07	2,5	1,1	0,60		3,0		0,9	40,3	41,2	1,2
	Gd	100,0														Impregnation	973	0,17	0,07	2,5	1,1	0,60		25,6		16,6	12,3	28,9	7,4
	Ba	17,6	Gd	82,4												Impregnation	1073	0,17	0,07	2,5	1,1	0,60		32,0				56,0	17,9
	Gd	100,0														Impregnation	1023	0,17	0,07	2,5	1,0	0,60		28,1	57,2			42,8	12,0
335	Ba	10,0	Gd	70,0			F	20,0								Impregnation	1023	0,17	0,07	2,5	1,0	0,60		32,4	46,6			53,4	17,3
	Ba	10,0	Gd	70,0			Cl	20,0								Impregnation	1023	0,17	0,07	2,5	1,0	0,60		36,6	42,4			57,6	21,1
	Ba	10,0	Gd	70,0			Br	20,0								Impregnation	1023	0,17	0,07	2,5	1,0	0,60		31,2	45,0			55,0	17,2
	Ca	100,0														Therm.decomp.	1103	0,07	0,03	2,0	1,0	0,10		40,6	63,3	20,1	15,8	35,9	14,6
336	La	9,0	Ca	91,0												Therm.decomp.	1103	0,07	0,03	2,0	1,0	0,10		48,4	66,4	17,9	13,7	31,6	15,3
	Sr	16,0	La	10,0	Ca	74,00										Therm.decomp.	1103	0,07	0,03	2,0	1,0	0,10		47,0	59,6	22,5	16,0	38,5	18,1
337	Mg	33,3	Fe	66,7						F						Therm.decomp.	1123	0,85	0,15	5,7	1,0			23,8	33,0			67,0	15,9
338	Li	65,9	Zr	17,1			S	17,0								Impregnation	1000	0,15	0,05	3,0	1,0	0,67		20,0				70,0	14,0
339	Sr	12,0	La	8,2							Al	69,4	Si	10,4		Impregnation	1123	0,80	0,20	4,0	1,0	0,04		29,1				57,5	16,7
	Sr	33,3					F	66,7								Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	1,4	0,8		0,0	54,0	54,0	0,4
340	Nd	100,0														Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	99,7	27,2		20,1	19,2	39,3	10,7
	Sr	50,0	Nd	50,0												Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	99,1	29,4		27,8	22,3	50,1	14,7
	Sr	16,7	Nd	50,0			F	33,3								Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	98,9	34,3		33,1	34,0	67,1	23,0
	La	100,0														Therm.decomp.	1073	0,80	0,20	4,0	1,0	0,04		25,7				54,9	14,1
	Sr	9,1	La	90,9												Therm.decomp.	1073	0,80	0,20	4,0	1,0	0,04		29,0				59,3	17,2
	Sm	100,0														Therm.decomp.	1073	0,80	0,20	4,0	1,0	0,04		24,3				51,0	12,4
	Sr	9,1	Sm	90,9												Therm.decomp.	1073	0,80	0,20	4,0	1,0	0,04		25,5				56,5	14,4
	Eu	100,0														Therm.decomp.	1073	0,80	0,20	4,0	1,0	0,04		22,8				47,8	10,9
	Sr	9,1	Eu	90,9												Therm.decomp.	1073	0,80	0,20	4,0	1,0	0,04		26,0				53,8	14,0
341	Yb	100,0														Therm.decomp.	1073	0,80	0,20	4,0	1,0	0,04		10,0				48,2	4,8
	Sr	9,1	Yb	90,9												Therm.decomp.	1073	0,80	0,20	4,0	1,0	0,04		25,0				52,8	13,2
	Sr	9,1	Ce	90,9												Therm.decomp.	1073	0,80	0,20	4,0	1,0	0,04		17,0				57,6	9,8
	Sr	9,1	Pr	90,9												Therm.decomp.	1073	0,80	0,20	4,0	1,0	0,04		24,0				41,7	10,0
	Sr	9,1	Nd	90,9												Therm.decomp.	1073	0,80	0,20	4,0	1,0	0,04		26,0				53,1	13,8
	Sr	9,1	Gd	90,9												Therm.decomp.	1073	0,80	0,20	4,0	1,0	0,04		25,0				55,2	13,8
	Sr	9,1	Dy	90,9												Therm.decomp.	1073	0,80	0,20	4,0	1,0	0,04		15,0				33,3	5,0
	Sr	9,1	Er	90,9												Therm.decomp.	1073	0,80	0,20	4,0	1,0	0,04		25,0				56,0	14,0
	Y	100,0														Therm.decomp.	1023	0,17	0,07	2,5	1,0	0,60	92,8	30,3	73,8	18,0	8,2	26,2	7,9
342	Ba	3,3	Y	90,0			F	6,7								Therm.decomp.	1023	0,17	0,07	2,5	1,0	0,60	94,0	32,5	50,8	25,0	24,2	49,2	16,0
	Ba	10,0	Y	70,0			F	20,0								Therm.decomp.	1023	0,17	0,07	2,5	1,0	0,60	92,4	38,2	53,4	29,9	16,7	46,6	17,8
	Ba	16,7	Y	50,0			F	33,3								Therm.decomp.	1023	0,17	0,07	2,5	1,0	0,60	92,2	36,7	46,8	30,8	22,4	53,2	19,5
	Ba	23,3	Y	30,0			F	46,7								Therm.decomp.	1023	0,17	0,07	2,5	1,0	0,60	92,1	36,3	42,6	34,0	23,4	57,4	20,8
	Ba	31,7	Y	5,0			F	63,3								Therm.decomp.	1023	0,17	0,07	2,5	1,0	0,60	80,1	36,1	37,9	41,3	20,8	62,1	22,4
	Nd	100,0														Impregnation	1023	0,17	0,07	2,5	1,0	0,60		28,1	66,7			33,3	9,4
	Ba	30,0	Nd	70,0												Impregnation	1023	0,17	0,07	2,5	1,0	0,60		35,9	54,6			45,4	16,3
343	Ba	10,0	Nd	70,0			F	20,0								Impregnation	1023	0,17	0,07	2,5	1,0	0,60		33,8	47,6			52,4	17,7
	Ba	10,0	Nd	70,0			Cl	20,0								Impregnation	1023	0,17	0,07	2,5	1,0	0,60		42,4	49,3			50,7	21,5
	Ba	10,0	Nd	70,0			Br	20,0								Impregnation	1023	0,17	0,07	2,5	1,0	0,60		35,9	53,1			46,9	16,8
	Mn	2,1	Na	2,1	W	1,00					Si	94,8				Impregnation	1123	0,16	0,04	4,6	1,0	1,33		33,0				80,0	26,4
	Na	2,1	W	1,0							Si	96,9				Impregnation	1123	0,16	0,04	4,6	1,0	1,33		44,0				52,0	22,9
344	Mn	2,2	W	1,1							Si	96,7				Impregnation	1123	0,16	0,04	4,6	1,0	1,33		20,0				40,0	8,0
	Mn	2,0									Si	98,0				Impregnation	1123	0,16	0,04	4,6	1,0	1,33		23,0				23,0	5,3
	W	1,1									Si	98,9				Impregnation	1123	0,16	0,04	4,6	1,0	1,33		12,0				20,0	2,4
345	Nd	100,0														precipitation	1023	0,60	0,06	10,0	1,0	0,03	97,0	10,9				50,6	5,5
	Sr	,5	Nd	99,5												precipitation	1023	0,60	0,06	10,0	1,0	0,03	97,4	12,5				63,8	8,0
346	Mn	2,2	Na	2,1	W	1,00					Si	94,7				Impregnation	1023	0,22	0,03	7,4	1,0	0,02		2,7				78,0	2,1
	Mn	1,5	Na	1,4	W	0,70	Mg	96,40								Impregnation	1023	0,22	0,03	7,4	1,0	0,02		3,0				88,0	2,6
	Na	,1	Ca	99,9												Impregnation	1073	0,80	0,20	4,0	1,0			29,0				61,9	18,0
	Na	1,8	Ca	98,2												Impregnation	1073	0,80	0,20	4,0	1,0			28,2				61,9	17,5
	Na	16,7	Ca	83,3												Impregnation	1073	0,80	0,20	4,0	1,0			28,5				62,8	17,9
	Ce	,1	Ca	99,9												Impregnation	1073	0,80	0,20	4,0	1,0			27,2				43,9	11,9
347	Ce	,1	Na	1,8	Ca	98,10										Impregnation	1073	0,80	0,20	4,0	1,0			28,8				63,4	18,3
	Ce	,3	Na	1,8	Ca	97,90										Impregnation	1073	0,80	0,20	4,0	1,0			28,3				62,6	17,7
	Ce	,7	Na	1,8	Ca	97,50										Impregnation	1073	0,80	0,20	4,0	1,0			28,5				60,0	17,1
	Ce	1,3	Na	1,8	Ca	96,90										Impregnation	1073	0,80	0,20	4,0	1,0			28,3				60,7	17,2
	Ce	50,0	Ca	50,0												Impregnation	1073	0,80	0,20	4,0	1,0			21,6				30,8	6,7
	K	4,2					P	2,1			Si	93,7				Precipitation	1073	0,80	0,20	4,0	1,0			25,9				51,0	13,2
	Mn	,2	K	4,2			P	2,1			Si	93,5				Precipitation	1073	0,80	0,20	4,0	1,0			22,1				37,9	8,4
	Mn	,2	K	3,0			P	1,5			Si	95,3				Precipitation	1073	0,80	0,20	4,0	1,0			22,2				37,8	8,4
348	Mn	,5	K	4,2			P	2,1			Si	93,2				Precipitation	1073	0,80	0,20	4,0	1,0			25,5				50,0	12,8
	Mn	,8	K	5,8			P	2,9			Si	90,5				Precipitation	1073	0,80	0,20	4,0	1,0			16,9				25,5	4,3
	Mn	,9									Si	99,1				Precipitation	1073	0,80	0,20	4,0	1,0			14,6				17,6	2,6
	Mn	2,6	K	1,5							Al	95,9				Precipitation	1073	0,80	0,20	4,0	1,0			18,3				21,6	4,0
	La	100,0														Therm.decomp.	973	0,75	0,15	5,0	1,0	0,18	100,0	29,4	62,8	21,5	15,7	37,2	10,9
	Sr	6,7	La	80,0			F	13,3								Therm.decomp.	973	0,75	0,15	5,0	1,0	0,18	98,1	34,2	42,7	36,1	21,2	57,3	19,6
	Nd	100,0														Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	99,1	27,2	60,7	20,1	19,2	39,3	10,7
	Sr	6,7	Nd	80,0			F	13,3								Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	98,9	34,3	42,9	33,1	24,0	57,1	19,6
	Sm	100,0														Therm.decomp.	1073	0,75	0,15	5,0	1,0	0,18	99,2	26,3	61,2	21,6	17,2	38,8	10,2
	Sr	6,7	Sm	80,0			F	13,3								Therm.decomp.	1073	0,75	0,15	5,0	1,0	0,18	99,5	34,0	44,2	33,1	22,7	55,8	19,0
	Eu	100,0														Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	98,4	26,3	66,9	21,8	11,3	33,1	8,7
	Sr	6,7	Eu	80,0			F	13,3								Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	99,0	33,1	47,1	31,9	21,0	52,9	17,5
349	Gd	100,0														Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	99,7	29,5	66,5	20,1	13,4	33,5	9,9
	Sr	6,7	Gd	80,0			F	13,3								Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	99,5	34,4	45,4	32,0	22,6	54,6	18,8
	Dy	100,0														Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	99,5	31,3	57,4	25,0	17,6	42,6	13,3
	Sr	6,7	Dy	80,0			F	13,3								Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	96,3	32,6	48,5	32,0	19,5	51,5	16,8
	Ho	100,0														Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	99,3	28,8	67,0	19,9	13,1	33,0	9,5
	Sr	6,7	Ho	80,0			F	13,3								Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	97,3	30,8	54,2	26,7	19,1	45,8	14,1
	Er	100,0														Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	99,1	27,6	65,6	20,0	14,4	34,4	9,5
	Sr	6,7	Er	80,0			F	13,3								Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	96,6	29,3	57,1	23,8	19,1	42,9	12,6
	Tm	100,0														Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	99,4	26,4	72,0	16,4	11,6	28,0	7,4
	Sr	6,7	Tm	80,0			F	13,3								Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	99,5	28,6	59,7	21,2	19,1	40,3	11,5

	Yb	100,0													Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	99,4	28,8	68,8	19,3	11,9	31,2	9,0
	Sr	6,7	Yb	80,0			F	13,3							Therm.decomp.	1023	0,75	0,15	5,0	1,0	0,18	99,4	28,7	64,3	19,9	15,8	35,7	10,2
	La	50,0					F	50,0							Therm.decomp.	1053	0,80	0,20	4,0	1,0	0,24		25,0	53,4	27,2	19,4	46,6	11,7
	Ba	3,3	La	45,0			F	51,7							Therm.decomp.	1053	0,80	0,20	4,0	1,0	0,24		28,7	32,7	44,7	22,6	67,3	19,3
	La	100,0													Impregnation	1073	0,80	0,20	4,0	1,0	0,04		25,7				51,0	13,1
	La	17,3							Si	11,5	Al	71,2			Impregnation	1073	0,80	0,20	4,0	1,0	0,04		26,5				53,2	14,1
	Sr	11,0	La	17,3					Al	10,0	Si	61,7			Impregnation	1073	0,80	0,20	4,0	1,0	0,04		30,9				64,4	19,9
	Nd	100,0													Impregnation	1073	0,80	0,20	4,0	1,0	0,04		23,5				22,1	5,2
	Nd	17,3							Al	11,5	Si	71,2			Impregnation	1073	0,80	0,20	4,0	1,0	0,04		26,0				48,5	12,6
	Sr	11,0	Nd	17,3					Al	10,0	Si	61,7			Impregnation	1073	0,80	0,20	4,0	1,0	0,04		29,2				55,8	16,3
	Sr	11,0							Al	12,4	Si	76,6			Impregnation	1073	0,80	0,20	4,0	1,0	0,04		6,1				63,9	3,9
	Mg	8,1	La	19,3					Al	10,1	Si	62,5			Impregnation	1123	0,94	0,06	15,9	1,0	0,04		9,8				69,4	6,8
350	Ca	8,1	La	19,3					Al	10,1	Si	62,5			Impregnation	1123	0,94	0,06	15,9	1,0	0,04		11,3				77,7	8,8
	Sr	8,1	La	19,3					Al	10,1	Si	62,5			Impregnation	1123	0,94	0,06	15,9	1,0	0,04		12,5				80,7	10,1
	Ba	8,1	La	19,3					Al	10,1	Si	62,5			impregnation	1123	0,94	0,06	15,9	1,0	0,04		11,1				72,9	8,1
	Sr	9,0	La	16,0					Al	10,4	Si	64,6			impregnation	1123	0,94	0,06	15,9	1,0	0,04		12,5				80,7	10,1
	Sr	9,0	Ce	16,0					Al	10,4	Si	64,6			impregnation	1123	0,94	0,06	15,9	1,0	0,04		0,1				0,0	0,0
	Sr	9,0	Nd	16,0					Al	10,4	Si	64,6			impregnation	1123	0,94	0,06	15,9	1,0	0,04		11,1				81,7	9,1
	Sr	9,0	Sm	16,0					Al	10,4	Si	64,6			impregnation	1123	0,94	0,06	15,9	1,0	0,04		6,5				83,8	5,4
	Sr	9,0	Gd	16,0					Al	10,4	Si	64,6			impregnation	1123	0,94	0,06	15,9	1,0	0,04		7,4				82,5	6,1
	Sr	9,0	Er	16,0					Al	10,4	Si	64,6			impregnation	1123	0,94	0,06	15,9	1,0	0,04		7,0				81,3	5,7
	Sr	9,0	Yb	16,0					Al	10,4	Si	64,6			impregnation	1123	0,94	0,06	15,9	1,0	0,04		8,9				75,5	6,7
351	Sr	23,1	Zr	30,8			P	46,1							Therm.decomp.	1023	0,17	0,08	2,0	1,0	0,60		16,5				15,3	2,5
	Ca	59,4	Pb	3,1			P	37,5							Therm.decomp.	1073	0,22	0,15	1,5	1,0	0,80		37,7		33,9	15,4	49,3	18,6
	Ca	62,5					P	37,5							Therm.decomp.	1073	0,22	0,15	1,5	1,0	0,80		35,9		28,7	10,3	39,0	14,0
	Ca	60,9	Pb	1,6			P	37,5							Therm.decomp.	1073	0,22	0,15	1,5	1,0	0,80		39,0		37,8	14,7	52,5	20,5
352	Ca	56,3	Pb	6,3			P	37,4							Therm.decomp.	1073	0,22	0,15	1,5	1,0	0,80		40,8		38,9	16,9	55,8	22,8
	Ca	53,1	Pb	9,4			P	37,5							Therm.decomp.	1073	0,22	0,15	1,5	1,0	0,80		38,6		37,6	15,5	53,1	20,5
	Ca	50,0	Pb	12,5			P	37,5							Therm.decomp.	1073	0,22	0,15	1,5	1,0	0,80		38,4		37,0	15,6	52,6	20,2
	Ca	43,8	Pb	18,8			P	37,4							Therm.decomp.	1073	0,22	0,15	1,5	1,0	0,80		34,5		38,8	14,0	52,8	18,2
	Mg	100,0													n.a.	1173	0,50	0,21	2,4	1,0	1,50		20,6				48,9	10,1
	Li	,7	Mg	99,3											Impregnation	1173	0,50	0,21	2,4	1,0	1,50	93,0	23,3		44,0	16,0	60,0	14,0
	Li	10,0	Mg	90,0											Impregnation	1173	0,50	0,21	2,4	1,0	1,50		22,5		47,9	7,2	55,1	12,4
	Na	3,0	Mg	97,0											Impregnation	1173	0,50	0,21	2,4	1,0	1,50	93,0	21,5		36,8	21,5	58,3	12,5
	K	4,0	Mg	96,0											Impregnation	1173	0,50	0,21	2,4	1,0	1,50		19,3		32,2	14,5	46,7	9,0
353	Si	100,0													n.a.	1173	0,50	0,21	2,4	1,0	1,50		14,0		12,1	9,6	21,7	3,0
	Na	2,0							Si	98,0					Impregnation	1173	0,50	0,21	2,4	1,0	1,50	54,0	13,4		30,1	11,0	41,1	5,5
	Li	,6							Si	99,4					Impregnation	1173	0,50	0,21	2,4	1,0	1,50		14,2		30,2	9,0	39,2	5,6
	Si	50,0					C	50,0							n.a.	1173	0,50	0,21	2,4	1,0	1,50		2,6		19,2	38,5	57,7	1,5
	Al	100,0													n.a.	1173	0,50	0,21	2,4	1,0	1,50		2,6		21,4	38,2	59,6	1,5
	Li	3,0							Al	97,0					Impregnation	1173	0,50	0,21	2,4	1,0	1,50	60,0	14,9		31,2	10,2	41,4	6,2
	Li	,5							Ti	99,5					Impregnation	1173	0,50	0,21	2,4	1,0	1,50		20,5		37,1	10,1	47,2	9,7
354	Li	25,0	Sb	25,0	Te	50,00									Therm.decomp.	973	0,17	0,03	5,1	1,0	1,20		17,0		58,0	8,0	66,0	11,2
	Si	100,0													impregnation	1123	0,09	0,02	4,5	1,0	1,80		17,0			15,0	23,0	3,9
	Li	1,8							Si	98,2					impregnation	1123	0,09	0,02	4,5	1,0	1,80		6,0			0,0	0,0	0,0
	Na	1,8							Si	98,2					impregnation	1123	0,09	0,02	4,5	1,0	1,80		2,0			0,0	0,0	0,0
	K	1,8							Si	98,2					impregnation	1123	0,09	0,02	4,5	1,0	1,80		2,0			0,0	0,0	0,0
	Rb	1,8							Si	98,2					impregnation	1123	0,09	0,02	4,5	1,0	1,80		2,0			0,0	8,0	0,2
	Cs	1,8							Si	98,2					impregnation	1123	0,09	0,02	4,5	1,0	1,80		5,0			0,0	10,0	0,5
	Mg	1,8							Si	98,2					impregnation	1123	0,09	0,02	4,5	1,0	1,80		15,0			0,0	20,0	3,0
355	Ca	1,8							Si	98,2					impregnation	1123	0,09	0,02	4,5	1,0	1,80		15,0			0,0	21,0	3,2
	Na	1,2	W	,6					Si	98,2					impregnation	1123	0,09	0,02	4,5	1,0	1,80		44,0			42,0	52,0	22,9
	K	1,2	W	,6					Si	98,2					impregnation	1123	0,09	0,02	4,5	1,0	1,80		30,0			52,0	67,0	20,1
	Rb	1,2	W	,6					Si	98,2					impregnation	1123	0,09	0,02	4,5	1,0	1,80		32,0			59,0	78,0	25,0
	Cs	1,2	W	,6					Si	98,2					impregnation	1123	0,09	0,02	4,5	1,0	1,80		33,0			39,0	55,0	18,2
	Li	1,2	W	,6					Si	98,2					impregnation	1123	0,09	0,02	4,5	1,0	1,80		36,0			26,0	27,0	9,7
	Ca	,9	W	,9					Si	98,2					impregnation	1123	0,09	0,02	4,5	1,0	1,80		16,0			20,0	25,0	4,0
	Mg	,9	W	,9					Si	98,2					impregnation	1123	0,09	0,02	4,5	1,0	1,80		20,0			15,0	20,0	4,0
	Ca	100,0													impregnation	973	0,50	0,10	5,0	1,0	0,21	33,3	4,7				16,0	0,8
356	Na	21,9	Ca	78,1											impregnation	973	0,50	0,10	5,0	1,0	0,21	14,4	4,2				73,5	3,1
	Ce	28,1	Na	15,7	Ca	56,20									impregnation	973	0,50	0,10	5,0	1,0	0,21	23,2	5,0				56,4	2,8
	Ni	10,0							La	90,0					impregnation	923	0,83	0,17	5,0	1,0	0,45		42,0				0,0	0,0
357	Ni	5,3							Sm	94,7					impregnation	823	0,83	0,17	5,0	1,0	0,45		6,0				58,0	3,5
	Ni	10,0							Ce	90,0					impregnation	823	0,83	0,17	5,0	1,0	0,45		25,0				62,0	15,5
358	La	9,1	Mg	90,9											Therm.decomp.	1023	0,80	0,20	4,0	1,0	0,07		30,0				56,7	17,0
359	Li	12,9	Mg	87,1											impregnation	1173	0,09	0,02	4,1	1,0	0,45		25,0				97,0	24,3
360	Li	9,1	Mg	90,9											precipitation	1023	0,75	0,25	3,0	1,0	0,35		36,1				60,1	21,7
	Ca	62,6					Cl	9,3	P	28,1					precipitation	1023	0,17	0,08	2,0	1,0	0,60		7,3	78,9	0,0	21,1	21,1	1,5
	Ca	40,6					Cl	56,0	P	3,4					precipitation	1023	0,17	0,08	2,0	1,0	0,60		39,3	43,7	51,0	5,3	56,3	22,1
361	Pb	1,0	Ca	40,0			Cl	56,0	P	3,0					precipitation	1023	0,17	0,08	2,0	1,0	0,60		39,0	40,8	53,7	5,5	59,2	23,1
	Ni	,8	Ca	40,0			Cl	56,0	P	3,2					precipitation	1023	0,17	0,08	2,0	1,0	0,60		38,8	43,5	51,7	4,8	56,5	21,9
	Zn	,7	Ca	35,6			Cl	45,9	P	17,8					precipitation	1023	0,17	0,08	2,0	1,0	0,60		36,6	41,7	49,3	9,0	58,3	21,3
	W	2,0							Si	98,0					impregnation	923	0,90	0,10	9,0	1,0	0,60		1,2		0,4	6,8	7,2	0,1
	K	3,8	W	1,2					Si	95,0					impregnation	923	0,90	0,10	9,0	1,0	0,60		1,5		8,0	26,2	34,2	0,5
362	K	3,8	W	1,2					Ti	95,0					impregnation	923	0,90	0,10	9,0	1,0	0,60		2,6		0,5	5,8	6,3	0,2
	K	3,8	W	1,2					Al	95,0					impregnation	923	0,90	0,10	9,0	1,0	0,60		3,3		0,0	1,4	1,4	0,0
	K	3,8	W	1,2					Mg	95,0					impregnation	923	0,90	0,10	9,0	1,0	0,60		2,6		0,4	3,3	3,7	0,1
363	Sm	10,0	Y	15,0	Bi	75,00									Therm.decomp.	1223	0,33	0,17	2,0	1,0	0,40		43,1				62,0	26,7
364	Sr	,8							La	99,2					impregnation	923	0,78	0,22	3,6	1,0	0,06		23,0				52,0	12,0
	Sr	,8	Ni	2,6					La	96,6					impregnation	923	0,78	0,22	3,6	1,0	0,06		38,0				2,0	0,8
	Si	100,0													impregnation	1050	0,88	0,12	7,5	1,0	0,22		0,0		0,0		0,0	0,0
	Mn	4,0							Si	96,0					impregnation	1050	0,88	0,12	7,5	1,0	0,22		0,0		0,0		0,0	0,0
	Na	9,1	W	4,5					Si	86,4					impregnation	1050	0,88	0,12	7,5	1,0	0,22		11,0		17,0		63,0	6,9
	V	3,6	Na	9,1	W	4,50			Si	82,8					impregnation	1050	0,88	0,12	7,5	1,0	0,22		10,0		4,0		12,0	1,2
365	Cr	3,6	Na	9,1	W	4,50			Si	82,8					impregnation	1050	0,88	0,12	7,5	1,0	0,22		10,0		9,0		24,0	2,4
	Mn	3,6	Na	9,1	W	4,50			Si	82,8					impregnation	1050	0,88	0,12	7,5	1,0	0,22		20,0		46,0		80,0	16,0
	Fe	3,6	Na	9,1	W	4,50			Si	82,8					impregnation	1050	0,88	0,12	7,5	1,0	0,22		15,0		30,0		60,0	9,0
	Co	3,6	Na	9,1	W	4,50			Si	82,8					impregnation	1050	0,88	0,12	7,5	1,0	0,22		16,0		40,0		68,0	10,9
	Zn	3,6	Na	9,1	W	4,50			Si	82,8					impregnation	1050	0,88	0,12	7,5	1,0	0,22		9,0		17,0		63,0	5,7
	Li	16,7	Mg	83,3											impregnation	1053	0,41	0,20	2,0	1,0	0,24		25,1		28,0	24,0	52,0	13,1
366	Li	16,7	Y	83,3											impregnation	1053	0,41	0,20	2,0	1,0	0,24		39,9		27,0	19,0	46,0	18,4
	Li	16,7	La	83,3											impregnation	1053	0,41	0,20	2,0	1,0	0,24		19,8		32,0	28,0	60,0	11,9

	Li	16,7	Sm	83,3											impregnation	1053	0,41	0,20	2,0		1,0	0,24		22,3		28,0	29,0	57,0	12,7
	Li	16,7	Ho	83,3											impregnation	1053	0,41	0,20	2,0		1,0	0,24		34,7		23,0	16,0	39,0	13,5
	La	50,0	Al	50,0											Sol-gel	1013	0,33	0,07	5,0		1,0			15,0				4,5	0,7
	Li	5,0	La	50,0	Al	45,00									Sol-gel	1013	0,33	0,07	5,0		1,0			17,0				4,8	0,8
	Mg	5,0	La	50,0	Al	45,00									Sol-gel	1013	0,33	0,07	5,0		1,0			18,3				6,4	1,2
367	Na	5,0	La	45,0	Al	50,00									Sol-gel	1013	0,33	0,07	5,0		1,0			14,5				4,2	0,6
	K	5,0	La	45,0	Al	50,00									Sol-gel	1013	0,33	0,07	5,0		1,0			16,2				5,8	0,9
	Ca	5,0	La	45,0	Al	50,00									Sol-gel	1013	0,33	0,07	5,0		1,0			14,6				3,5	0,5
	Ba	5,0	La	45,0	Al	50,00									Sol-gel	1013	0,33	0,07	5,0		1,0			16,5				3,0	0,5
	Sr	65,5					P	34,5							Therm.decomp.	1023	0,17	0,08	2,0		1,0	0,60		19,7				4,1	0,8
	Sr	65,5					P	34,5		Cl					Therm.decomp.	1023	0,17	0,08	2,0		1,0	0,60		8,4				9,7	0,8
	Pb	,8	Sr	69,4			P	29,8							Therm.decomp.	1023	0,17	0,08	2,0		1,0	0,60		38,6				40,7	15,7
368	Pb	,8	Sr	69,4			P	29,8		Cl					Therm.decomp.	1023	0,17	0,08	2,0		1,0	0,60		26,5				60,2	16,0
	Zn	,7	Sr	63,7			P	35,6							Therm.decomp.	1023	0,17	0,08	2,0		1,0	0,60		26,4		7,8	14,4	22,2	5,9
	Co	,8	Sr	67,5			P	31,7							Therm.decomp.	1023	0,17	0,08	2,0		1,0	0,60		28,4		0,7	1,1	1,8	0,5
	Ni	,7	Sr	63,8			P	35,5							Therm.decomp.	1023	0,17	0,08	2,0		1,0	0,60		99,9		0,0	0,0	0,0	0,0
	Na	2,1	W	1,0							Si	96,9			impregnation	1073	0,75	0,25	3,0		1,0	0,10		8,8	45,5	21,8	32,7	54,5	4,8
369	Na	2,1	Mn	2,2							Si	95,7			impregnation	1073	0,75	0,25	3,0		1,0	0,10		2,4	42,5	9,6	47,9	57,5	1,4
	W	1,0	Mn	2,2							Si	96,8			impregnation	1073	0,75	0,25	3,0		1,0	0,10		3,1	72,7	0,0	17,3	17,3	0,5
	Na	2,1	W	1,0	Mn	1,10					Si	95,8			impregnation	1073	0,75	0,25	3,0		1,0	0,10		30,2	36,7	39,6	23,8	63,4	19,1
370	Ni	27,3	Sb	18,2	Te	54,50									precipitation	923	0,25	0,05	5,0		1,0	0,90		13,9	21,0	39,0	40,0	79,0	11,0
371	Na	9,1	W	4,5							Si	86,4			impregnation	1048	0,88	0,12	7,3		1,0	0,22		7,0				40,0	2,8
	Mn	1,0	Na	9,1	W	4,50					Si	85,4			impregnation	1048	0,88	0,12	7,3		1,0	0,22		24,0				77,0	18,5
372	Bi	75,0	Y	15,0	Sm	10,00									sol-gel	1173	0,18	0,05	4,0		1,0	0,12		25,0				32,0	8,0
373	Na	8,9	W	4,5	Mn	3,50					Si	83,1			impregnation	1023	0,89	0,11	8,1		1,0	0,04		15,1				71,8	10,8
	Ce	100,0													precipitation	1078	0,55	0,10	5,8		1,0	0,47	93,0	10,0	83,7	9,0	7,2	16,2	1,6
	Tb	100,0													precipitation	1073	0,75	0,05	14,4		1,0	0,32	100,0	11,0	29,4	28,6	36,6	65,2	7,2
	La	100,0													precipitation	1093	0,74	0,05	13,7		1,0	0,38	100,0	13,0	20,1	45,4	29,1	74,5	9,7
	Y	100,0													precipitation	1143	0,59	0,09	6,7		1,0	0,31	100,0	16,0	34,7	47,5	13,2	60,7	9,7
	Tm	100,0													precipitation	1073	0,60	0,08	7,2		1,0	0,27	59,0	9,0	34,6	34,5	23,7	58,2	5,2
	Sm	100,0													precipitation	1083	0,54	0,10	5,6		1,0	0,25	100,0	19,0	35,1	36,3	25,2	61,5	11,7
	Yb	100,0													precipitation	1078	0,60	0,08	7,1		1,0	0,27	80,0	14,1	26,7	39,8	28,6	68,4	9,6
	Eu	100,0													precipitation	1068	0,60	0,08	7,1		1,0	0,28	100,0	20,0	30,0	42,0	25,3	67,3	13,5
374	La	63,0	Nd	37,0											precipitation	1128	0,56	0,09	6,6		1,0	0,26	100,0	19,6	38,3	42,8	13,9	56,7	11,1
	La	55,9	Pr	11,0	Nd	33,10									precipitation	1108	0,63	0,08	8,0		1,0	0,27	100,0	15,0	32,3	35,7	27,9	63,6	9,5
	La	18,7	Pr	7,2	Nd	9,60	Ce	64,50							precipitation	1113	0,61	0,08	7,3		1,0	0,34	100,0	11,0	58,8	26,7	12,0	38,7	4,3
	La	53,1	Pr	9,4	Nd	26,60	Ce	10,90							precipitation	1108	0,61	0,08	7,4		1,0	0,30	100,0	19,0	29,8	38,9	25,2	64,1	12,2
	Gd	41,7	Eu	12,9	Tb	1,00	Nd	0,90			Sm	43,5			precipitation	1068	0,61	0,08	7,5		1,0	0,29	100,0	17,0	34,1	35,6	27,5	63,1	10,7
	Sm	12,1	Gd	11,6	Eu	3,70	Tb	2,10			Y	70,5			precipitation	1023	0,61	0,08	7,5		1,0	0,22	100,0	17,0	30,4	42,4	22,8	65,2	11,1
	Li	18,2	La	15,5	Pr	6,10	Nd	8,10			Ce	52,1			precipitation	1123	0,61	0,08	7,3		1,0	0,34		17,2				76,5	13,2
	K	68,3	La	5,8	Pr	2,30	Nd	3,00			Ce	20,6			precipitation	1040	0,61	0,08	7,3		1,0	0,34		15,6				67,2	10,5
	Li	8,9	W	4,5	Mn	3,50					Si	83,1			impregnation	1073	0,76	0,24	3,2		1,0	0,14		20,5	35,9	35,4	28,7	64,1	13,1
	Na	8,9	W	4,5	Mn	3,50					Si	83,1			Impregnation	1073	0,76	0,24	3,2		1,0	0,14		29,5	33,6	42,6	23,8	66,4	19,6
	K	8,9	W	4,5	Mn	3,50					Si	83,1			Impregnation	1073	0,76	0,24	3,2		1,0	0,14		29,6	37,6	39,6	22,8	62,4	18,5
	Ba	8,9	W	4,5	Mn	3,50					Si	83,1			Impregnation	1073	0,76	0,24	3,2		1,0	0,14		21,3	67,5	18,7	13,8	32,5	6,9
375	Ca	8,9	W	4,5	Mn	3,50					Si	83,1			Impregnation	1073	0,76	0,24	3,2		1,0	0,14		19,0	74,7	12,1	13,2	25,3	4,8
	Fe	8,9	W	4,5	Mn	3,50					Si	83,1			Impregnation	1073	0,76	0,24	3,2		1,0	0,14		18,3	85,4	7,5	7,1	14,6	2,7
	Co	8,9	W	4,5	Mn	3,50					Si	83,1			Impregnation	1073	0,76	0,24	3,2		1,0	0,14		18,3	77,0	11,9	11,1	23,0	4,2
	Ni	8,9	W	4,5	Mn	3,50					Si	83,1			Impregnation	1073	0,76	0,24	3,2		1,0	0,14		18,4	76,2	12,1	11,7	23,8	4,4
	Al	8,9	W	4,5	Mn	3,50					Si	83,1			Impregnation	1073	0,76	0,24	3,2		1,0	0,14		17,9	83,4	8,6	8,0	16,6	3,0
	Ba	50,0	Ti	50,0											Sol-gel	1048	0,67	0,33	2,0		1,0	0,30	99,0	20,5				66,8	13,7
	Ba	32,2	Ca	33,9	Ti	33,90									Sol-gel	1048	0,67	0,33	2,0		1,0	0,30	99,0	34,1				55,7	19,0
	Ba	32,2	Sr	33,9	Ti	33,90									Sol-gel	1048	0,67	0,33	2,0		1,0	0,30	99,0	34,2				53,8	18,4
	Ba	42,9	Ca	2,4	Ti	47,50	Mg	2,40	Cl	4,8					Sol-gel	1048	0,67	0,33	2,0		1,0	0,30	99,0	55,4				30,9	17,1
376	Ba	43,9	Ca	2,4	Ti	48,90	Li	2,40	Cl	2,4					Sol-gel	1048	0,67	0,33	2,0		1,0	0,30	99,0	29,2				54,8	16,0
	Ba	43,6	Ti	51,2	Na	2,60			Cl	2,6					Sol-gel	1048	0,67	0,33	2,0		1,0	0,30	99,0	27,3				77,3	21,1
	Ba	30,3	Ti	60,7	Sn	3,00			Cl	6,0					Sol-gel	1048	0,67	0,33	2,0		1,0	0,30	99,0	66,6				52,1	34,7
	Ca	31,3	Ti	62,5	Na	3,10			Cl	3,1					Sol-gel	1048	0,67	0,33	2,0		1,0	0,30	99,0	37,7				41,9	15,8
	Ba	45,2	Ca	2,4	Ti	47,60			Cl	4,8					Sol-gel	1048	0,67	0,33	2,0		1,0	0,30	99,0	29,7				56,2	16,7
	Li	,6	Mg	99,4											Therm.decomp.	1023	0,50	0,10	5,0		1,0	0,36	95,9	24,7		28,8	18,9	47,7	11,8
377	Li	6,1	Mg	93,9											Therm.decomp.	1023	0,50	0,10	5,0		1,0	0,36	96,2	28,9		43,3	25,7	69,0	19,9
	Li	15,3	Mg	84,7											Therm.decomp.	1023	0,50	0,10	5,0		1,0	0,36	82,5	27,6		28,6	25,7	54,3	15,0
	Li	30,6	Mg	69,4											Therm.decomp.	1023	0,50	0,10	5,0		1,0	0,36	42,3	16,0		43,8	20,4	64,2	10,3
378	Nb	1,9	Mn	2,0	Na	1,80	W	2,80			Si	91,5			Impregnation	1123	0,32	0,08	4,0		1,0	0,30		32,5				80,2	26,1
379	Pt	3,0									Al	97,0			Impregnation	1273	0,71	0,29	2,4		1,0	0,01		8,1		24,0	14,8	38,8	3,1
380	Sr	2,0	La	98,0											Impregnation	973	0,78	0,22	3,6		1,0	0,06		23,2				51,7	12,0
	Ni	2,0	Sr	2,0	La	96,04									Impregnation	973	0,78	0,22	3,6		1,0	0,06		19,0				12,4	2,4
	Mn	16,9									Si	83,1			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		20,6	72,0	15,0		28,0	5,8
	Na	8,9	W	4,5	Mn	3,50					Si	83,1			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		35,5	46,0	41,0		54,0	19,2
	Na	8,9	Mo	4,5	Mn	3,50					Si	83,1			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		30,7	54,3	31,0		45,7	14,0
	Na	8,9	Mn	3,5			S	4,5			Si	83,1			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		35,7	43,6	41,1		56,4	20,1
	Na	10,0	Mn	3,5			P	4,5			Si	82,0			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		31,0	49,5	38,6		50,5	15,7
	Na	8,9	Mn	3,5			P	4,5			Si	83,1			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		33,5	47,5	36,9		52,5	17,6
	Na	8,9	Mn	3,5			C	4,5			Si	83,1			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		8,9	50,4	19,0		49,6	4,4
381	Na	8,9	Mn	3,5							Si	87,6			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		9,4	55,1	21,7		44,9	4,2
	Na	11,3	W	5,6							Si	83,1			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		15,2	37,6	33,0		62,4	9,5
	Na	11,3	Mo	5,6							Si	83,1			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		14,0	40,7	21,5		59,3	8,3
	Na	11,3					S	5,6			Si	83,1			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		4,0	55,6	6,3		44,4	1,8
	Na	12,7					P	4,2			Si	83,1			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		5,0	60,5	6,5		39,5	2,0
	Na	11,3					P	5,6			Si	83,1			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		5,1	65,7	13,3		34,3	1,7
	Na	11,3					C	5,6			Si	83,1			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		3,2	100,0	0,0		0,0	0,0
	Na	11,3									Si	88,7			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		3,1	100,0	0,0		0,0	0,0
	Mn	16,9							S		Si	83,1			Impregnation	1073	0,42	0,17	2,5		1,0	0,11		20,9	70,3	17,1		29,7	6,2
	Ca	100,0													Therm.decomp.	1073	0,89	0,11	8,0		1,0	0,07		13,3				49,3	6,6
	La	4,8	Ca	95,2											Therm.decomp.	1073	0,89	0,11	8,0		1,0	0,07		19,8				67,2	13,3
382	Ce	4,8	Ca	95,2											Therm.decomp.	1073	0,89	0,11	8,0		1,0	0,07		17,7				65,0	11,5
	Sm	4,8	Ca	95,2											Therm.decomp.	1073	0,89	0,11	8,0		1,0	0,07		18,7				62,5	11,7
	Nd	4,8	Ca	95,2											Therm.decomp.	1073	0,89	0,11	8,0		1,0	0,07		19,5				70,8	13,8
	Yb	4,8	Ca	95,2											Therm.decomp.	1073	0,89	0,11	8,0		1,0	0,07		20,1				66,4	13,3
	Na	8,9	W	4,5	Mn	3,50					Si	83,1			Impregnation	1093	0,80	0,20	4,0		1,0	0,12	96,3	30,3		42,0		68,4	20,7
383	Na	8,9	W	4,5	Mn	3,50					Si	83,1			Sol-gel	1093	0,80	0,20	4,0		1,0	0,12	65,6	22,4		36,3		69,4	15,5
	Na	8,9	W	4,5	Mn	3,50					Si	83,1			Impregnation	973	0,67	0,33	2,0		1,0	0,22	100,0	41,0				42,8	17,5

384	La	1,1	Na	2,1	W	1,00	Mn	2,20					Si	93,6	Impregnation	973	0,67	0,33	2,0	1,0	0,22	100,0	45,8			55,9	25,6	
	W	,6	Li	,9									Si	98,5	Impregnation	973	0,88	0,12	7,5	1,0	0,30		10,0			52,0	5,2	
385	Mn	4,3	Li	,8									Si	94,9	Impregnation	973	0,88	0,12	7,5	1,0	0,30		15,0			40,0	6,0	
	Mn	4,5	W	,6									Si	94,9	Impregnation	973	0,88	0,12	7,5	1,0	0,30		15,0			40,0	6,0	
	Li	6,5	Mn	4,3	W	5,90							Si	83,3	Impregnation	973	0,88	0,12	7,5	1,0	0,30		19,0			79,0	15,0	
	Na	13,8	W	,7	Mn	1,50	Zr	2,20	S	3,6	P	,7	Si	77,5	Sol-gel	1023	0,75	0,25	3,0	1,0	0,75		43,8			53,6	23,5	
386	Na	13,8	W	,7	Mn	1,50	Zr	2,20	S	3,6			Si	78,2	Sol-gel	1023	0,75	0,25	3,0	1,0	0,75		38,0			47,4	18,0	
	Na	13,8	W	,7	Mn	1,50	Zr	2,20	P	,7			Si	81,1	Sol-gel	1023	0,75	0,25	3,0	1,0	0,75		34,0			47,1	16,0	
	Na	13,8	W	,7	Mn	1,50	Zr	2,20					Si	81,8	Sol-gel	1023	0,75	0,25	3,0	1,0	0,75		15,0			66,7	10,0	
	La	10,0	Sr	20,0	Ca	70,00									n.a.	1073	0,10	0,03	3,0	1,0	0,06	97,0	33,0			57,0	18,8	
	La	10,0	Ca	90,0											n.a.	1073	0,10	0,03	3,0	1,0	0,06	97,0	32,0			52,0	16,6	
	La	10,0	Mg	90,0											n.a.	1073	0,10	0,03	3,0	1,0	0,06	98,0	28,0			46,0	12,9	
	Li	10,0	Mg	90,0											n.a.	1073	0,10	0,03	3,0	1,0	0,06	22,0	3,0			69,0	2,1	
	Sn	10,0	Li	20,0	Mg	70,00									n.a.	1073	0,10	0,03	3,0	1,0	0,06	84,0	29,0			61,0	17,7	
	La	6,0	Ti	94,0											n.a.	1073	0,10	0,03	3,0	1,0	0,06	43,0	6,0			6,0	0,4	
	Mg	51,4	W	48,6											n.a.	1073	0,10	0,03	3,0	1,0	0,06	20,0	0,0			1,0	0,0	
	Co	5,6	Mg	94,4											n.a.	1073	0,10	0,03	3,0	1,0	0,06	97,0	17,0			0,0	0,0	
	La	3,1	Mg	96,9											n.a.	1073	0,10	0,03	3,0	1,0	0,06	97,0	22,0			34,0	7,5	
	Sr	21,0	La	79,0											n.a.	1073	0,10	0,03	3,0	1,0	0,06	50,0	20,0			75,0	15,0	
	V	14,0	Mg	86,0											n.a.	1073	0,10	0,03	3,0	1,0	0,06	98,0	21,0			0,0	0,0	
	Pd	2,0	Mg	98,0											n.a.	1073	0,10	0,03	3,0	1,0	0,06	98,0	93,0			1,0	0,9	
387	Pt	2,0	Mg	98,0											n.a.	1073	0,10	0,03	3,0	1,0	0,06	99,0	63,0			1,0	0,6	
	Pt	6,7	V	6,7	Li	6,60	Mg	80,00							n.a.	1073	0,10	0,03	3,0	1,0	0,06	62,0	17,0			46,0	7,8	
	La	20,0	Mg	80,0											n.a.	1073	0,10	0,03	3,0	1,0	0,06	96,0	28,0			51,0	14,3	
	Li	20,0	Mg	80,0											n.a.	1073	0,10	0,03	3,0	1,0	0,06	44,0	7,0			64,0	4,5	
	Cu	2,3	Zn	5,4									Si	92,3	n.a.	1073	0,10	0,03	3,0	1,0	0,06	78,0	12,0			5,0	0,6	
	Li	30,0	Mg	70,0											n.a.	1073	0,10	0,03	3,0	1,0	0,06	41,0	10,0			62,0	6,2	
	La	11,1	Mg	88,9											n.a.	1073	0,10	0,03	3,0	1,0	0,06	95,0	28,0			50,0	14,0	
	Ce	22,2	Zn	77,8											n.a.	1073	0,10	0,03	3,0	1,0	0,06	97,0	17,0			3,0	0,5	
	Ni	2,6	Nd	97,4											n.a.	1073	0,10	0,03	3,0	1,0	0,06	97,0	73,0			2,0	1,5	
	Fe	53,8	P	46,2											n.a.	1073	0,10	0,03	3,0	1,0	0,06	95,0	18,0			2,0	0,4	
	Fe	50,0	P	50,0											n.a.	1073	0,10	0,03	3,0	1,0	0,06	34,0	1,0			32,0	0,3	
	Sn	100,0													n.a.	1073	0,10	0,03	3,0	1,0	0,06	97,0	16,0			0,0	0,0	
	La	10,0	Sr	20,0	Ca	70,00									n.a.	1073	0,07	0,03	2,0	1,0	0,06	97,0	42,0			47,0	19,7	
388	Li	5,0	Ti	45,0	Sr	50,00									Pyrolysis	1123	0,50	0,38	1,3	1,0	0,79		43,2			25,7	11,1	
	Li	5,0	Ti	45,0	Sr	50,00									Sol-gel	1123	0,50	0,38	1,3	1,0	0,79		33,0			3,5	1,2	
	Na	7,0	Ca	93,0											Impregnation	1123	0,90	0,09	9,9	1,0	0,40	100,0	13,0			75,0	9,8	
389	Na	6,9	Ca	90,1					Cl	3,0					Impregnation	1123	0,90	0,09	9,9	1,0	0,40	75,0	9,0			90,0	8,1	
	Na	6,6	Ca	77,7					Cl	15,7					Impregnation	1123	0,90	0,09	9,9	1,0	0,40	65,0	8,5			83,0	7,1	
	Ba	37,9	Sr	25,8	Ti	36,30									Impregnation	1073	0,40	0,20	2,0	1,0	0,60		47,0			29,5	13,9	
390	Li	6,8	Ba	36,4	Sr	27,80	Ti	29,00							Impregnation	1073	0,40	0,20	2,0	1,0	0,60		37,0			59,5	22,0	
	Mg	8,9	Ba	37,1	Sr	24,90	Ti	29,10							Impregnation	1073	0,40	0,20	2,0	1,0	0,60		46,5			43,0	20,0	
	Na	5,6	Ba	38,0	Sr	25,70	Ti	30,70							Impregnation	1073	0,40	0,20	2,0	1,0	0,60		47,0			51,0	24,0	
391	Na	8,9	W	4,5	Mn	3,50							Si	83,1	Therm.decomp.	973	0,40	0,10	4,0	1,0	1,33	100,0	40,0		48,0	63,0	25,2	
	Ba	50,0							C	50,0					Impregnation	1133	0,29	0,07	4,0	1,0	0,86		24,7			35,0	8,6	
392	Mg	100,0													Impregnation	1133	0,29	0,07	4,0	1,0	0,86		24,2			29,4	7,1	
	Li	3,0	Mg	97,0											Impregnation	1053	0,29	0,07	4,0	1,0	0,86		30,0			65,0	19,5	
	Ca	100,0													Therm.decomp.	1023	0,80	0,20	4,0	1,0	0,70		21,2			31,0	6,6	
	Li	9,1	Ca	90,9											Therm.decomp.	1023	0,80	0,20	4,0	1,0	0,70		12,8			68,0	8,7	
	Na	9,1	Ca	90,9											Therm.decomp.	1023	0,80	0,20	4,0	1,0	0,70		24,7			61,6	15,2	
	K	9,1	Ca	90,9											Therm.decomp.	1023	0,80	0,20	4,0	1,0	0,70		25,2			53,3	13,4	
	Rb	9,1	Ca	90,9											Therm.decomp.	1023	0,80	0,20	4,0	1,0	0,70		26,7			50,9	13,6	
393	Cs	9,1	Ca	90,9											Therm.decomp.	1023	0,80	0,20	4,0	1,0	0,70		22,8			49,1	11,2	
	Li	28,6	Ca	71,4											Therm.decomp.	1023	0,80	0,20	4,0	1,0	0,70		22,0			62,2	13,7	
	Na	28,6	Ca	71,4											Therm.decomp.	1023	0,80	0,20	4,0	1,0	0,70		17,9			62,6	11,2	
	K	28,6	Ca	71,4											Therm.decomp.	1023	0,80	0,20	4,0	1,0	0,70		24,4			52,6	12,8	
	Rb	28,6	Ca	71,4											Therm.decomp.	1023	0,80	0,20	4,0	1,0	0,70		26,6			43,7	11,6	
	Cs	28,6	Ca	71,4											Therm.decomp.	1023	0,80	0,20	4,0	1,0	0,70		11,0			69,9	7,7	
	Zn	33,3	Fe	58,3	Nd	8,40									Sol-gel	1043	0,42	0,08	5,0	1,0	0,25		16,0			50,0	8,0	
394	Zn	33,3	Fe	50,0	Nd	16,70									Sol-gel	1043	0,42	0,08	5,0	1,0	0,25		12,0			25,0	3,0	
	Zn	33,3	Fe	33,3	Nd	33,40									Sol-gel	1093	0,42	0,08	5,0	1,0	0,25		14,0			50,0	7,0	
	Zn	33,3	Nd	66,7											Sol-gel	1073	0,42	0,08	5,0	1,0	0,25		27,0			66,7	18,0	
	Fe	4,8	La	95,2											Sol-gel	1023	0,24	0,02	10,2	1,0	0,01	87,0	8,0			44,0	3,5	
395	Na	,1	Fe	4,8	La	95,10									Sol-gel	1023	0,24	0,02	10,2	1,0	0,01	20,0	2,0			65,0	1,3	
	Na	,0	Fe	4,8	La	95,17			P	,0					Sol-gel	1023	0,24	0,02	10,2	1,0	0,01	25,0	3,0			56,0	1,7	
	Na	,1	Fe	4,8	La	95,09			P	,0					Sol-gel	1023	0,24	0,02	10,2	1,0	0,01	5,0	1,0			83,0	0,8	
	Zr	100,0													Therm.decomp.	873	0,67	0,33	2,0	1,0	0,20		23,6			26,8	6,3	
396	Ba	4,6	Zr	90,8					C	4,6					Therm.decomp.	873	0,67	0,33	2,0	1,0	0,20		39,2			30,1	11,8	
	Ba	50,0							C	50,0					Therm.decomp.	873	0,67	0,33	2,0	1,0	0,20		4,9			51,1	2,5	
	Ca	100,0													Therm.decomp.	1073	0,08	0,00	103,8	1,0		100,0					2,8	
	Ba	100,0													Therm.decomp.	1073	0,08	0,00	103,8	1,0		100,0					2,5	
	Sm	100,0													Therm.decomp.	1073	0,08	0,00	103,8	1,0							0,7	
	Mn	100,0													Therm.decomp.	1073	0,08	0,00	103,8	1,0							0,2	
	Sr	50,0							C	50,0					Therm.decomp.	1073	0,08	0,00	103,8	1,0		100,0					2,6	
	Ba	50,0							C	50,0					Therm.decomp.	1073	0,08	0,00	103,8	1,0		100,0					3,3	
	Li	20,0	Ca	80,0											Therm.decomp.	1073	0,08	0,00	103,8	1,0		100,0					1,9	
397	K	20,0	Ca	80,0											Therm.decomp.	1073	0,08	0,00	103,8	1,0		100,0					3,0	
	Cs	20,0	Ca	80,0											Therm.decomp.	1073	0,08	0,00	103,8	1,0		100,0					2,5	
	Mg	20,0	Ca	80,0											Therm.decomp.	1073	0,08	0,00	103,8	1,0		100,0						2,45
	Ca	20,0	Ca	80,0											Therm.decomp.	1073	0,08	0,00	103,8	1,0		100,0					2,7	
	Sr	20,0	Ca	80,0											Therm.decomp.	1073	0,08	0,00	103,8	1,0		100,0					2,3	
	Ba	20,0	Ca	80,0											Therm.decomp.	1073	0,08	0,00	103,8	1,0		100,0					0,9	
	Pb	20,0	Ca	80,0											Therm.decomp.	1073	0,08	0,00	103,8	1,0		100,0					1,5	
	Bi	20,0	Ca	80,0											Therm.decomp.	1073	0,08	0,00	103,8	1,0		100,0					1,0	
398	Li	73,7	La	26,3											Therm.decomp.	1023	0,18	0,01	16,3	1,0	0,07	65,0	1,8			100,0	1,8	
	Sm	100,0													n.a.	1053	0,68	0,07	10,0	1,0	0,22	100,0	12,2			54,0	6,6	
	Dy	100,0													n.a.	1066	0,68	0,07	10,0	1,0	0,22	100,0	12,9			53,0	6,8	
399	Gd	100,0													n.a.	1043	0,68	0,07	10,0	1,0	0,22	100,0	12,1			48,0	5,8	
	La	100,0													n.a.	1013	0,68	0,07	10,0	1,0	0,22	100,0	18,8			40,0	7,5	
	Tb	100,0													n.a.	1093	0,68	0,07	10,0	1,0	0,22	100,0	7,8			28,0	2,2	
	Li	10,0	Mg	90,0											Impregnation	1063	0,68	0,07	10,0	1,0	0,22		12,9			75,0	9,7	

	Ca	30,0	Sm	70,0								Impregnation	948	0,68	0,07	10,0	1,0	0,22		12,7			71,0	9,0
	Na	55,0	Sm	45,0								Impregnation	1053	0,68	0,07	10,0	1,0	0,22	9,8				65,0	6,4
400	Li	37,5	Mg	62,5								Impregnation	907	0,08	0,05	1,7	1,0	1,00	0,3				56,7	0,2
401	Li	20,0	Ni	60,0			Cl	20,0				Impregnation	1023	0,10	0,05	2,0	1,0	0,60						8,0
	Ca	100,0										Therm.decomp.	1043	0,37	0,07	5,0	1,0	0,04	28,5				13,5	3,8
	Na	12,0	Ca	88,0								Impregnation	1043	0,37	0,07	5,0	1,0	0,04	22,0				13,7	3,0
402	Pb	1,9	Ca	98,1								Impregnation	1043	0,37	0,07	5,0	1,0	0,04	28,0				11,0	3,1
	Bi	1,8	Ca	98,2								Impregnation	1043	0,37	0,07	5,0	1,0	0,04	24,0				10,6	2,5
	La	10,0	Ba	90,0								Precipitation	1073	0,91	0,09	10,0	1,0	9,00	10,0				73,5	7,4
	La	40,0	Ba	60,0								Precipitation	1073	0,91	0,09	10,0	1,0	9,00	12,0				77,0	9,2
403	La	80,0	Ba	20,0								Precipitation	1073	0,91	0,09	10,0	1,0	9,00	10,0				71,5	7,2
	La	90,0	Ba	10,0								Precipitation	1073	0,91	0,09	10,0	1,0	9,00	12,0				71,0	8,5
	Sb	9,3							Si	90,7		Precipitation	1053	0,50	0,11	4,5	1,0	0,33	3,8				48,0	1,8
	K	,5	Sb	9,3					Si	90,2		Precipitation	1053	0,50	0,11	4,5	1,0	0,33	4,3				57,0	2,5
	K	3,1	Sb	9,3					Si	87,6		Precipitation	1053	0,50	0,11	4,5	1,0	0,33	4,8				45,0	2,2
404	Sb	100,0										Precipitation	1053	0,50	0,11	4,5	1,0	0,33	3,7				55,0	2,0
	K	5,0	Sb	95,0								Precipitation	1053	0,50	0,11	4,5	1,0	0,33	4,9				52,0	2,5
	K	33,0	Sb	67,0								Precipitation	1053	0,50	0,11	4,5	1,0	0,33	8,8				16,0	1,4
	La	100,0										Precipitation	1023	0,08	0,04	2,0	1,0	2,00	30,0				40,0	12,0
	K	,1	La	99,9			S	,1				Precipitation	1023	0,08	0,04	2,0	1,0	2,00	27,0				46,0	12,4
405	K	,2	La	99,7			S	,1				Precipitation	1023	0,08	0,04	2,0	1,0	2,00	33,0				46,1	15,2
	K	,4	La	99,4			S	,2				Precipitation	1023	0,08	0,04	2,0	1,0	2,00	28,0				55,7	15,6
	K	66,7					S	33,3				Precipitation	1023	0,08	0,04	2,0	1,0	2,00	5,0				60,0	3,0
	Li	6,3	Mg	90,6			C	3,1				Impregnation	923	0,07	0,03	2,0	1,0	0,16	16,0				24,0	3,8
	Li	18,0	Zn	73,0			C	9,0				Impregnation	923	0,07	0,03	2,0	1,0	0,16	1,0				30,0	0,3
	Mn	31,7	Li	3,6	Mg	62,90	C	1,8				Impregnation	923	0,07	0,03	2,0	1,0	0,16	25,0				0,0	0,0
	Fe	35,2	Li	3,4	Mg	59,70	C	1,7				Impregnation	923	0,07	0,03	2,0	1,0	0,16	24,0				0,0	0,0
	Co	19,7	Li	3,2	Mg	56,00	C	21,1				Impregnation	923	0,07	0,03	2,0	1,0	0,16	18,0				1,0	0,2
	Sn	20,3	Li	4,2	Mg	52,70	C	22,8				Impregnation	923	0,07	0,03	2,0	1,0	0,16	23,0				3,0	0,7
	W	1,8	Li	5,6	Mg	89,80	C	2,8				Impregnation	923	0,07	0,03	2,0	1,0	0,16	7,0				2,0	0,1
	Ce	18,6	Li	1,7	Mg	78,80	C	,9				Impregnation	923	0,07	0,03	2,0	1,0	0,16	7,0				37,0	2,6
	Ce	24,4	Li	22,7	Zn	41,60	C	11,3				Impregnation	923	0,07	0,03	2,0	1,0	0,16	6,0				18,0	1,1
	Li	6,3	Mg	90,6			C	3,1				Impregnation	973	0,07	0,03	2,0	1,0	0,16	24,0				28,0	6,7
	Li	18,0	Zn	73,0			C	9,0				Impregnation	973	0,07	0,03	2,0	1,0	0,16	3,0				37,0	1,1
	Mn	31,7	Li	3,6	Mg	62,90	C	1,8				Impregnation	973	0,07	0,03	2,0	1,0	0,16	27,0				0,0	0,0
	Fe	35,2	Li	3,4	Mg	59,70	C	1,7				Impregnation	973	0,07	0,03	2,0	1,0	0,16	25,0				1,0	0,3
406	Co	19,7	Li	3,2	Mg	56,00	C	21,1				Impregnation	973	0,07	0,03	2,0	1,0	0,16	23,0				1,0	0,2
	Sn	20,3	Li	4,2	Mg	52,70	C	22,8				Impregnation	973	0,07	0,03	2,0	1,0	0,16	26,0				3,0	0,8
	W	1,8	Li	5,6	Mg	89,80	C	2,8				Impregnation	973	0,07	0,03	2,0	1,0	0,16	15,0				2,0	0,3
	Ce	18,6	Li	1,7	Mg	78,80	C	,9				Impregnation	973	0,07	0,03	2,0	1,0	0,16	20,0				45,0	9,0
	Ce	24,4	Li	22,7	Zn	41,60	C	11,3				Impregnation	973	0,07	0,03	2,0	1,0	0,16	20,0				10,0	2,0
	Li	6,3	Mg	90,6			C	3,1				Impregnation	1023	0,07	0,03	2,0	1,0	0,16	25,0				40,0	10,0
	Li	18,0	Zn	73,0			C	9,0				Impregnation	1023	0,07	0,03	2,0	1,0	0,16	17,0				36,0	6,1
	Mn	31,7	Li	3,6	Mg	62,90	C	1,8				Impregnation	1023	0,07	0,03	2,0	1,0	0,16	27,0				0,0	0,0
	Fe	35,2	Li	3,4	Mg	59,70	C	1,7				Impregnation	1023	0,07	0,03	2,0	1,0	0,16	27,0				1,0	0,3
	Co	19,7	Li	3,2	Mg	56,00	C	21,1				Impregnation	1023	0,07	0,03	2,0	1,0	0,16	23,0				2,0	0,5
	Sn	20,3	Li	4,2	Mg	52,70	C	22,8				Impregnation	1023	0,07	0,03	2,0	1,0	0,16	29,0				3,0	0,9
	W	1,8	Li	5,6	Mg	89,80	C	2,8				Impregnation	1023	0,07	0,03	2,0	1,0	0,16	20,0				1,0	0,2
	Ce	18,6	Li	1,7	Mg	78,80	C	,9				Impregnation	1023	0,07	0,03	2,0	1,0	0,16	35,0				43,0	15,1
	Ce	24,4	Li	22,7	Zn	41,60	C	11,3				Impregnation	1023	0,07	0,03	2,0	1,0	0,16	24,0				33,0	7,9
	Mg	100,0										n.a.	1073	0,86	0,14	6,1	1,0	0,30	95,0	10,0			37,5	3,8
	Si	100,0										n.a.	1073	0,86	0,14	6,1	1,0	0,60	94,0	10,5			3,0	0,3
	Ca	100,0										n.a.	1073	0,86	0,14	6,1	1,0	0,80	92,0	13,9			9,0	1,3
	Na	50,0	Al	50,0								n.a.	1073	0,86	0,14	6,1	1,0	0,40	85,0	13,4			60,0	8,0
	Li	10,0	Al	90,0								n.a.	1073	0,86	0,14	6,1	1,0	0,50	91,0	8,0			21,0	1,7
407	Sm	100,0										Therm.decomp.	1073	0,86	0,14	6,1	1,0	0,60	95,0	14,2			58,5	8,3
	Sm	5,8	Si	94,2								Therm.decomp.	1073	0,86	0,14	6,1	1,0	0,50	92,0	13,8			11,5	1,6
	Sm	7,8	Mg	92,2								Therm.decomp.	1073	0,86	0,14	6,1	1,0	0,30	90,0	16,5			57,0	9,4
	Sm	10,6	Ca	89,4								Therm.decomp.	1073	0,86	0,14	6,1	1,0	0,40	96,0	13,8			50,0	6,9
	Sm	6,0	Na	47,0	Al	47,00						Therm.decomp.	1073	0,86	0,14	6,1	1,0	0,90	95,0	15,5			63,0	9,8
	Sm	4,5	Li	45,6	Al	49,90						Therm.decomp.	1073	0,86	0,14	6,1	1,0	1,00	95,0	15,0			59,5	8,9
	Li	15,9	Mg	84,1								Impregnation	973	0,91	0,09	10,0	1,0		100,0	5,0			76,0	3,8
	Li	62,3	Zr	37,7								Impregnation	973	0,91	0,09	10,0	1,0		50,0	2,0			70,0	1,4
	Zr	20,0	Mg	80,0								Impregnation	973	0,91	0,09	10,0	1,0		100,0	5,0			6,0	0,3
	Li	15,9	Mg	84,1								Impregnation	1023	0,91	0,09	10,0	1,0		100,0	12,0			80,0	9,6
	Li	62,3	Zr	37,7								Impregnation	1023	0,91	0,09	10,0	1,0		50,0	3,0			80,0	2,4
408	Zr	20,0	Mg	80,0								Impregnation	1023	0,91	0,09	10,0	1,0		100,0	8,0			25,0	2,0
	Li	15,9	Mg	84,1								Impregnation	1073	0,91	0,09	10,0	1,0		100,0	16,0			85,0	13,6
	Li	62,3	Zr	37,7								Impregnation	1073	0,91	0,09	10,0	1,0		50,0	4,0			84,0	3,4
	Zr	20,0	Mg	80,0								Impregnation	1073	0,91	0,09	10,0	1,0		100,0	10,0			55,0	5,5
	Li	26,8	Zr	,4	Mg	72,80						Impregnation	1013	0,82	0,18	4,6	1,0		100,0	20,0			55,0	11,0
	K	9,0	Ni	1,1	Ca	89,90						Therm.decomp.	978	0,30	0,12	2,5	1,0	4,80	100,0	28,6			46,2	13,2
	K	9,0	Ni	1,1	Mg	89,90						Therm.decomp.	978	0,30	0,12	2,5	1,0	4,80	100,0	25,7			26,1	6,7
409	Na	9,0	Ni	1,1	Mg	89,90						Therm.decomp.	978	0,30	0,12	2,5	1,0	4,80	100,0	19,3			25,4	4,9
	Li	9,0	Ni	1,1	Mg	89,90						Therm.decomp.	978	0,30	0,12	2,5	1,0	4,80	100,0	25,0			36,6	9,2
	Sr	1,8	La	98,2								Impregnation	973	0,46	0,05	10,2	1,0	0,01	70,0	10,0			72,0	7,2
410	Sr	1,8	La	98,2								Impregnation	998	0,46	0,05	10,2	1,0	0,01	70,0	15,0			75,0	11,3
	Sr	1,8	La	98,2								Impregnation	1023	0,46	0,05	10,2	1,0	0,01	70,0	16,0			78,0	12,5
411	Li	,4	Ca	99,6								Impregnation	1023	0,30	0,15	2,0	1,0	0,06	9,0	5,0			55,0	2,8
	Mn	100,0										n.a.	1023	0,40	0,08	5,0	1,0	0,06		11,5	4,9	7,3	12,2	1,4
	Na	10,0	Mn	90,0								Impregnation	1023	0,40	0,08	5,0	1,0	0,06		11,5	6,4	14,4	20,8	2,4
	Nb	100,0										n.a.	1023	0,40	0,08	5,0	1,0	0,06		3,5	42,0	42,0	84,0	2,9
	Ca	5,0	Nb	95,0								Impregnation	1023	0,40	0,08	5,0	1,0	0,06		2,8	39,2	44,0	83,2	2,3
	Ce	100,0										n.a.	1023	0,40	0,08	5,0	1,0	0,06		10,5	2,5	4,8	7,3	0,8
	La	100,0										n.a.	1023	0,40	0,08	5,0	1,0	0,06		17,3	31,0	10,0	41,0	7,1
412	Na	1,0	La	99,0								Impregnation	1023	0,40	0,08	5,0	1,0	0,06		17,4	21,0	36,5	57,5	10,0
	Zn	100,0										n.a.	1023	0,40	0,08	5,0	1,0	0,06		18,6	32,1	27,4	59,5	11,1
	Na	1,0	La	99,0								Impregnation	923	0,40	0,08	5,0	1,0	0,06	62,0	10,1	8,9	23,5	32,4	3,3
	Na	3,0	La	97,0								Impregnation	923	0,40	0,08	5,0	1,0	0,06	34,4	8,1	10,1	34,4	44,5	3,6
	Na	5,0	La	95,0								Impregnation	923	0,40	0,08	5,0	1,0	0,06	30,2	9,5	13,3	44,6	57,9	5,5
	Na	10,0	La	90,0								Impregnation	923	0,40	0,08	5,0	1,0	0,06	21,4	4,8	9,4	43,8	53,2	2,6
	Na	20,0	La	80,0								Impregnation	923	0,40	0,08	5,0	1,0	0,06	9,3	3,0	7,3	46,6	53,9	1,6

413	Bi	66,7	Ge	33,3									Therm.decomp.	1053	0,30	0,15	2,0	1,0	1,80		5,0	25,0	35,0	60,0	3,0
	Bi	57,1	Ge	42,9									Therm.decomp.	1053	0,30	0,15	2,0	1,0	1,80		5,0	15,0	28,0	43,0	2,2
414	Sm	,2							Si	99,8			Pyrolysis	1123	0,85	0,15	5,7	1,0	3,20	80,0	19,0			48,0	9,1
	Sm	,8							Si	99,2			Pyrolysis	1123	0,85	0,15	5,7	1,0	3,20	95,0	27,0			49,0	13,2
	Sm	1,6							Si	98,4			Pyrolysis	1123	0,85	0,15	5,7	1,0	3,20	95,0	35,0			22,0	7,7
	Sm	,8			B	49,6	N	49,6					Pyrolysis	1123	0,85	0,15	5,7	1,0	3,20	99,0	23,0			50,0	11,5
	Sm	,8					N	49,6	Zr	49,6			Pyrolysis	1123	0,85	0,15	5,7	1,0	2,40	99,0	17,0			48,0	8,2
	Sm	,8					N	49,6	Si	49,6			Pyrolysis	1123	0,85	0,15	5,7	1,0	4,00	99,0	21,0			49,0	10,3
415	Li	5,1	Ti	94,9									Therm.decomp.	1073	0,03	0,03	1,0	1,0	4,00		45,0			58,0	26,1
	Li	5,1	Zn	94,9									Therm.decomp.	1073	0,03	0,03	1,0	1,0	8,00		25,0			32,0	8,0
416	Sm	100,0											Precipitation	973	0,13	0,07	2,0	1,0	0,80	45,7	25,5	14,7	10,4	25,1	6,4
	Nd	100,0											Precipitation	973	0,13	0,07	2,0	1,0	0,80	65,7	28,6	14,5	16,5	31,0	8,9
	La	100,0											Precipitation	973	0,13	0,07	2,0	1,0	0,80	46,9	26,9	12,3	11,2	23,5	6,3
	Sm	50,0	Li	50,0									Precipitation	973	0,13	0,07	2,0	1,0	0,80	50,3	31,9	4,6	24,1	28,7	9,2
	Nd	50,0	Li	50,0									Precipitation	973	0,13	0,07	2,0	1,0	0,80	56,1	30,4	14,0	24,0	38,0	11,6
	La	50,0	Li	50,0									Precipitation	973	0,13	0,07	2,0	1,0	0,80	39,0	17,7	13,1	29,8	42,9	7,6
	Sm	50,0	Na	50,0									Precipitation	973	0,13	0,07	2,0	1,0	0,80	59,8	30,4	6,4	25,1	31,5	9,6
	Nd	50,0	Na	50,0									Precipitation	973	0,13	0,07	2,0	1,0	0,80	74,8	36,8	8,4	25,5	33,9	12,5
	La	50,0	Na	50,0									Precipitation	973	0,13	0,07	2,0	1,0	0,80	52,7	30,3	11,3	21,1	32,4	9,8
	Sm	50,0			Cl	50,0							Therm.decomp.	948	0,13	0,07	2,0	1,0	0,80	61,4	24,8	21,8	18,7	40,5	10,0
	Nd	50,0			Cl	50,0							Therm.decomp.	948	0,13	0,07	2,0	1,0	0,80	59,5	27,5	12,1	6,8	18,9	5,2
	La	50,0			Cl	50,0							Therm.decomp.	948	0,13	0,07	2,0	1,0	0,80	49,7	29,5	9,8	9,5	19,3	5,7
	Sm	50,0			Br	50,0							Therm.decomp.	948	0,13	0,07	2,0	1,0	0,80	90,0	33,8	36,8	1,7	38,5	13,0
	Nd	50,0			Br	50,0							Therm.decomp.	948	0,13	0,07	2,0	1,0	0,80	99,9	32,3	14,8	10,3	25,1	8,1
	La	50,0			Br	50,0							Therm.decomp.	948	0,13	0,07	2,0	1,0	0,80	49,0	24,6	37,5	5,2	42,7	10,5
417	Li	68,9	Ti	31,1									Impregnation	1023	0,32	0,08	4,0	1,0	0,15		10,0			73,5	7,4
	Li	56,6	la	21,7	Ti	21,70							Impregnation	1023	0,32	0,08	4,0	1,0	0,15		18,6			75,3	14,0
	Li	58,0	Ti	42,0									Impregnation	1023	0,32	0,08	4,0	1,0	0,15		18,9			69,7	13,2
418	Sm	100,0											n.a.	973	0,18	0,01	20,2	1,0	2,40	66,9	5,4	33,3	52,6	85,9	4,6
	Sm	100,0											n.a.	1023	0,18	0,04	5,2	1,0	2,40	77,4	15,1	37,2	23,4	60,6	9,2
419	Al	10,0	La	90,0									Pyrolysis	983	0,50	0,11	4,8	1,0	0,45		25,0			47,0	11,8
420	Sb	100,0											Therm.decomp.	1053	0,50	0,11	4,5	1,0	0,33		3,7			55,0	2,0
	K	2,5	Sb	97,5									Therm.decomp.	1053	0,50	0,11	4,5	1,0	0,33		3,5			40,0	1,4
	K	5,0	Sb	95,0									Therm.decomp.	1053	0,50	0,11	4,5	1,0	0,33		4,9			52,0	2,5
	K	33,0	Sb	67,0									Therm.decomp.	1053	0,50	0,11	4,5	1,0	0,33		8,8			16,0	1,4
	K	50,0	Sb	50,0									Therm.decomp.	1053	0,50	0,11	4,5	1,0	0,33		8,3			7,0	0,6
	K	66,0	Sb	34,0									Therm.decomp.	1053	0,50	0,11	4,5	1,0	0,33		7,5			30,0	2,3
	Sb	50,6							Si	49,4			Precipitation	1053	0,50	0,11	4,5	1,0	0,33		3,8			48,0	1,8
	K	5,0	Sb	50,6					Si	44,4			Precipitation	1053	0,50	0,11	4,5	1,0	0,33		4,3			57,0	2,5
421	Pr	100,0											n.a.	1098	0,5	0,11	4,8	1,0	1,50		99,0			0,0	0,0
	Tb	100,0											n.a.	1098	0,5	0,11	4,8	1,0	1,50		74,6			0,4	0,3
	Ce	100,0											n.a.	1098	0,5	0,11	4,8	1,0	1,50		39,0			0,0	0,0
	Na	23,8	Pr	76,2									Impregnation	1048	0,5	0,11	4,8	1,0	1,50		27,5			70,3	19,3
	Na	23,8	Tb	76,2									Impregnation	1048	0,5	0,11	4,8	1,0	1,50		20,1			59,0	11,9
	Na	23,8	Ce	76,2									Impregnation	1048	0,5	0,11	4,8	1,0	1,50		1,8			47,7	0,9
	K	23,8	Pr	76,2									Impregnation	1048	0,5	0,11	4,8	1,0	1,50		28,6			50,9	14,6
	Li	23,8	Pr	76,2									Impregnation	1048	0,5	0,11	4,8	1,0	1,50		8,2			89,4	7,3
	Ag	23,8	Pr	76,2									Impregnation	1048	0,5	0,11	4,8	1,0	1,50		41,0			1,0	0,4
	Mg	23,8	Pr	76,2									Impregnation	1048	0,5	0,11	4,8	1,0	1,50		40,0			3,0	1,2
	Ca	23,8	Pr	76,2									Impregnation	1048	0,5	0,11	4,8	1,0	1,50		20,0			13,0	2,6
	Bi	23,8	Pr	76,2									Impregnation	1048	0,5	0,11	4,8	1,0	1,50		32,0			16,0	5,1
	Sr	23,8	Pr	76,2									Impregnation	1048	0,5	0,11	4,8	1,0	1,50		13,0			24,0	3,1
	In	23,8	Pr	76,2									Impregnation	1048	0,5	0,11	4,8	1,0	1,50		1,5			28,0	0,4

Tabelle 3: *References*

Nr of publication	Authors	References
1	G.E. Keller, M.M. Bhasin	J. Catal., 73 (1982) 9.
2	M. Baerns, W. Hinsen	Germ. Pat. Appl. 3237079A1 (1982), DE 3237079 A1 (1984), U.S. Patent 4,608,449 (1986)
3	T. Ito andJ.H. Lunsford	Nature (London), 314 (1985) 721.
4	M. Baerns, S.P. Carreiro, W. Bytyn	CA Patent 1270861A1, DE 850927, 1985

5	Breder, J.; E. William, J.; John A. , Johnson; Marvin F. L.	US 4544786 (1985)
6	J.L. Jezl, G.O. Michaels, M.J. Spangler	US 4754091 A (1985)
7	R. F. Hicks	ES 8707705 A1 (1985)
8	W. Bytyn, M. Baerns	Appl. Catal. (1986), 28(1-2), 199.
9	T. Moriyama, N. Takasaki, E. Iwamatsu and K Aika	Chem. Lett., (1986) 1165.
10	K. Otsuka, Q. Liu, M. Natano, A. Morikawa	Chem. Let., (1986) 4, 467.
11	I. Matsuura, Y. Utsumi, M. Nakai, T. Doi	Chem. Lett. (1986), 11, 1981.
12	K. Asami, S. Hashimoto, T. Shikada, K. Fujimoto, H. Tominaga	Chem. Lett. (1986), 7, 1233.
13	J .B. Kimble and J .H. Kolts	Energy Prog., 6 (1986) 226.
14	K. Otsuka, Q. Liu, A. Morikawa	Inorganica Chimica Acta, 118 (1986) 1, 23.
15	H. Imai, T. Tagawa	J. Chem. Soc., Chem. Communications, (1986) 1, 52.
16	K. Otsuka, Q. Liu, A. Morikawa	J. Chem. Soc., Chem. Communications, (1986) 8, 586.
17	K Aika, T. Moriyama, N. Takasaki and E. Iwamatsu	J. Chem. Soc., Chem. Commun.,(1986) 1210.
18	M. Sinev, V.Vorob'eva, V. Korchak	Kinet. Katal. 27, 1007 (1986)
19	I. T. A. Emesht, Y. Amenomiya	J. Phys. Chem. (1986), 90, 4785.
20	J.A.S.P. Carreiro, M. Baerns	PhD. Thesis “Catalyst development for oxidative coupling of methane”, Bochum, 1986

21 W. Bytyn, M. Baerns PhD. Thesis "Catalyst development for oxidative coupling of methane", 1986 Bochum

22 J.H. Kolts and J.H. Lunsford Austr. Patent AU 8654352 (1986), European Patent 0196(1986) 541.

23 J.H. Kolts and J.B. Kimble Austr. Patent AU 8 654 351 (1986), Eur. Patent EP 206 042 (1986), US 4620057 (1986)

24 K Wohlfahrt, M. Bergfeld and H. Zengel Austr. Patent AU 8 654 467 (1986), DE 3503664 C2 (1986)

25 R.F. Hicks World Patent WO 8 607351 (1986).

26 J.L. Jezl, G.O. Michaels and M.J. Spangler World Patent WO 8 605176 (1986).

27 J.H. Kolts EP 0196541 B1 (1986)

60	H.S. Zhang, J.X. Wang, D.J. Driscoll and J .H. Lunsford	J. Catal., 112 (1988) 366.
61	C.H. Lin,J.X. WangandJ.H. Lunsford	J. Catal., 111 (1988) 302.
62	A.M. Gaffney, C.A. Jones, J.J. Leonard and J.A. Sofranko	Prepr.- Am. Chem. Soc., Div. Pet. Chem., 33 (1988) 445.
63	E.J. Erekson and A.L. Lee	Prepr. - Am. Chem. Soc., Div. Pet. Chem., 33 (1988) 443.
64	G.S. Lane and E.E. Wolf	Prepr. - Am. Chem. Soc., Div. Fuel Chem., 33 (1988) 373.
65	A.N. Shigapov, M.A. Novozhilova, S.N. Vereshchagin, A.G. Anshits and V.D. Sokolovskii	React. Kinet. Catal. Lett., 37 (1988) 397.
66	K Zhen, Y. Bi and X. Yang	React. Kinet. Catal, Lett., 37 (1988) 133.
67	F.P. Larkins and M.R. Nordin	Stud. Surf. Sci. Catal., 36 (1988) 409.
68	J.A. Roos, S.J. Korf, A.G. Bakker, N.A. de Bruijn, J.G. van Ommen andJ.R.H. Ross	Stud.Surf. Sci. Catal., 36 (1988) 427.
69	K Asami, S. Hashimoto, K Fujimoto and H. Tominaga	Stud. Surf. Sci. Catal., 36 (1988)
70	J.A.S.P. Carreiro, G. Follmer, L. Lehmann and M. Baems	Proc. 9th Int. Congr. Catal., Calgary, 1988, Vol. 2, The Chemical Institute of Canada, Ottawa, 1988, p. 891.
71	W. Ueda and J.M. Thomas	Proe. 9th Int. Congr. Catal., Cargary, 1988, Vol. 2, The Chemical Institute of Canada, Ottawa, 1988, p. 960.
72	Khan	Proc. NATO-Meeting on Heter. Catal. for CO Conversion, Belgien, (1988), 83.
73	Yates, D. J. C. & Zlotin, N. E.	J . Catal., 113(1988) 317.
74	A. M. Gaffney, C.A. Jones, J.J. Leonard, J. A. Sofranko, H.P. Withers	Stud. Surf. Sci. Catal. 38 (1988) 523.
75	Z. Kaiji, B. Yingli, Y. Xiangguang	React. Kinet. Catal. Lett., 37 (1988) 133.
76	J.H. Kolts and J.B. Kimble	US Patent 4 775 654 (1988).
77	R.G. Gastinger, A.C. Jones and J.A. Sofranko	US Patent 4777 313 (1988).
78	R.F. Hicks	US Patent US 4 780 449 (1988).
79	C. Cameron, H. Mimoun, S. Bonnaudet, A. Robine	CA Patent 1327612 (1988)
80	D. W. Leyshon, R.A. Bader	EP 0285337 B1 (1988)
81	S.R. Wade	US 4939310 A (1988)
82	A. Kaddouri, R. Kieffer, A. Kiennemann	Appl. Catal. (1989), 51(1), L1.
83	Y. Ohtsuka, M. Kuwabara, A. Tomita	Applied Catalysis (1989), 47(2), 307.
84	I. Matsuura, Y. Utsumi, T. Doi	Applied Catalysis (1989), 47(2), 299.
85	R. Burch, G.D. Squire, S.C. Tsang	Applied Catalysis (1989), 46(1), 69-87.
86	S.K. Agarwal, R.A. Migone, G. Marcelin	Applied Catalysis (1989), 53(1), 71-80.
87	G.S. Lane, Z. Kalenik, E.E. Wolf	Applied Catalysis (1989), 53(2-3), 183-95.
88	S. Ahmed, J.B. Moffat	Applied Catalysis (1989), 54(3), 241-55.
89	S.J. Korf, J.A. Roos, L.J. Veltman, J.G. Van Ommen and J.R.H. Ross	Applied Catalysis (1989), 56(1), 119-35.
90	S. J. Conway, J. Szanyi, J. H. Lunsford	Applied Catalysis (1989), 56(2), 149-61.
91	T.R. Baldwin, R. Burch, E.M. Crabb, G.D. Squire, S.C. Tsang	Applied Catalysis (1989), 56(2), 219-29.
92	K. Fujimoto, S. Hashimoto, K. Aaami, K. Omata and H. Tominaga	Appl. Catal., 50 (1989) 223.
93	T. Komatsu, T. Amaya, K. Otsuka	Catalysis Letters 3 (1989) 317-322
94	V. R. Choudhary, S. T. Chaudhari, A. M. Rajput, V. H. Rane	Catalysis Letters (1989), 3(1), 85-7.
95	J. Williams, R. H. Jones, J. M. Thomas, J. Kent	Catalysis Letters (1989), 3(3), 247-55.
96	S. Bartsch, J. Falkowski, H. Hofmann	Catal. Today, 4 (1989) 421.

97	C. Chevalier, P. Ramirez de Is Piseina, M. Ceruso, A. Choplin and J.M. B8BBet	Catal. Today, 4 (1989) 433.
98	A.G. Anshits, N.P. Kirik, V.G. Roguleva,A.N. Shigapov and G.E.Selyutin	Catal. Today, 4 (1989) 399.
99	W. Ueda, T.lsozaki, Y. Morikawa andJ.M. Thomas	Chem. Lett., (1989) 2103.
100	H. Matsuhashi, K. Sakurai, K. Arata	Chem Lett., 585 (1989).
101	A. Shamsi, K. Zahirt	Energy & Fuels (1989), 3(6), 727-30.
102	J. M. Thomas, W. Ueda, J. Williams, K. D. M. Harris	Faraday Disc. Chem. Soc. (1989), 87, 33-45.
103	V. R. Choudhary, S. T. Chaudhari, A. M. Rajput, V. H. Rane	J. Chem. Soc., Chem. Comm. (1989), (9), 555.
104	V. R. Choudhary, S. T. Chaudhari, A. M. Rajput, V. H. Rane	J. Chem. Soc., Chem. Commun. (1989), (20), 1526.
105	Kai Wang, Shengfu Ji, Xuejun Shi, Jingjing Tang	Catalysis Communications 10 (2009) 807–810
106	V. R. Choudhary, S. T. Chaudhari, A. M. Rajput, V. H. Rane	J. Chem. Soc., Chem. Comm. (1989), (10), 605.
107	G.S. Lane, E. Miro andE.E. Wolf	J. Catal., 119 (1989) 16l.
108	J. A.S.P. Carreiro, M. Baerns	J. Catal. 117 (1989) 396.
109	J. S. Lee, S. T. Oyama	Kor. J. Chem. Eng. (1989), 6(1), 54.
110	I. Matsuura, Y. Utsumi, T. Doi and K Ohyachi	Prepr. Pacifichem '89: Symposium on Methane Activation, Conversion and Utilization, 17-20 Dec. 1989, Honolulu, p. 70.
111	Z. Yu, S. Shen, S. Li and H. Wang	Prepr. - Pacifichem '89: Symposium on Methane Activation, Conversion and Utilization, 17-20 Dec. 1989, Honolulu, p. 126.
112	F.-C. Wang, Z.L. Zhang, C.T. Au and K.R. Tsai	Prepr. Pacifichem '89: Symposium on Methane Activation, Conversion and Utilization, 17-20 Dec. 1989, Honolulu, p, 2.
113	I. Matsuura and Y. Yoshida	Eur. Pat. Appl, EP 320301 (1989), to Ube Industries, Ltd., Japan.
114	S.R Wade	Eur. Pat. Appl. EP 316075 (1989).
115	E. Erekson, A. Lee	CA Patent 1330981 (1989)
116	B. Warren	WO 9104239 A1 (1989)

117	B. Warren	WO 9104241 A1 (1989)
118	M.P. Kaminsky, M.S. Kleefish, J.W. Zajac	US 4971940 A (1989)
119	M.P. Kaminsky, M.S. Kleefish, G.A. Huff, D.M. Washecheck, A.E. Alvarado-Svaisgood, M.K. Barr	US 5024984 A (1989)
120	K.D. Kampbell	US 5026945 A (1989)
121	R.B. Chafin and B.K. Warren	US 5073656 A (1989)
122	Brazdil, Jr.; James F., Hattenberger; John S., Hildebrand; Richard E., Bartek; Joseph P.	US 4822944 (1989)
123	Jezl; James L., Michaels; Glenn O., Spangler; Michael J., Winzenburg; Mark L.	US 4814539 (1989)
124	Erekson; Erek J. , Lee; Anthony L.	US 4826796 (1989)
125	Bartek; Joseph P. , Brazdil, Jr.; James F. , Hupp; John M. , Grasselli; Robert K.	US 4886931 (1989)
126	Chu; Pochen, Landis; Michael E.	US 4914252 US 4886931 (1989)
127	S. Ahmed, J.B. Moffat	Applied Catalysis (1990), 58(1), 83-103.
128	S.J. Korf, J.A. Roos, N.A. De Bruijn, J.G. Van Ommen, J.R.H. Ross	Applied Catalysis (1990), 58(1), 131-46.
129	H. Mimoun, A. Robine, S. Bonnaudet, C. J. Cameron	Applied Catalysis (1990), 58(2), 269-80.
130	Y. Osada, S. Koike, T. Fukushima, S. Ogasawara	Applied Catalysis (1990), 59(1), 59-74.
131	T. Suzuki, K. Wada, Y. Watanabe	Applied Catalysis (1990), 59(2), 213-25.
132	S.J. Korf, J.A. Roos, J.W.H.C. Derksen, J.A. Vreeman, J.G. Van Ommen, J.R.H. Ross	Applied Catalysis (1990), 59(2), 291-309.
133	T. K. Chan, K. J. Smith	Applied Catalysis (1990), 60(1), 13-31.
134	R. V. Siriwardane, A. Shamsi	Applied Catalysis (1990), 60(1), 119-36.
135	S. Arndt, E. Yilmaz Aksu, M. Driess, Reinhard Schomacker	Catal Lett (2009) 13, 258–265
136	V.R. Choudhary, A.M. Rajput, D.B. Akolekar, V.A. Seleznev	Appl. Catal., 62 (1990) 171-187=Appl. Catal., 69 (1991) 187.
137	Z. Zhang, C.T. Au, K.R. Tsai	Applied Catalysis, 62 (1990) 29.
138	C. Moneuse, M. Cassir, C. Piolet, J. Devynck	Applied Catalysis, 63 (1990) 67-76
139	J. Dubois, B. Rebours, C. J. Cameron	Appl. Catal., 67 (1990) 73.
140	J. Dubois, C. J. Cameron	Applied Catalysis, 67 (1990) 49.

141	Y. Amenomiya, V. I. Birss; M. Goledzinowski, J. Galuszka; A. R. Sanger	CATAL. REV. SCI. ENG., 32(3), 163-227 (1990)
142	K. Omata, A. Aoki, K. Fujimoto	Catalysis Letters 4 (1990) 241-244
143	V. R. Choudhary, V. H. Rane, S. T. Chaudhari	Catalysis Letters 6 (1990) 95-98
144	P. Pereira, S.H. Lee, G.A. Somorjai, H. Heinemann	Catalysis Letters 6 (1990) 255-262
145	G.A. Martin, P. Turlier, V. Ducarme, C. Mirodatos and M. Pinabiau	Catal. Today, 6 (1990), 373.
146	T. Nishiyama, T. Watanabe and K Aika	Catal. Today, 6 (1990) 39l.
147	T. Barrault, M. Grosset, M. Hadj. Aissa, M. Dion and M. Toumoux	Catal. Today, 6 (1990) 535.
148	A. Kiennemann, R. Kieffer, A. Kaddouri, P. Poix and J.L. Rehspringer	Catal. Today, 6 (1990) 409.
149	E.E. Miro, Z. Kalenik, J. Santamaria, E.E. Wolf	Catal. Today, (1990) 511.
150	R. Burch, G.D. Squire and S.C. Taang	Catal. Today, 6 (1990) 503.
151	D.I. Bradshaw, P.T. Coolen, R.W. Judd and C. Komodromos	Catal. Today, 6 (1990) 427.
152	N. Yamagata, Y. Abe, K. Igarashi, T. Ishikawa, M. Sahara, S. Okazaki	Chem Lett., (1990) 1893-1896.
153	Qiquan Yu, Yun Jin and Xiaohui Yao, Wuli Huaxue Xuebao	Chinese J. Catal. (1990) 645, Chem. Abs. 114, (6) : 45443k.
154	H. Shen et al.	Chinese J. Catal., 11 (1990) 60. Chem. Abs, 112(22) : 199159t.
155	J. Wang and Q. Lin	C1 Chemistry and Chemical Industry, 4 (1990) 10 (referred to in Appl. Catal.,74 (1991) N2).
156	N. Matsuda, K Ohyachi and I. Matsuura	Chem. Express, 5 (1990) 533.
157	R. Burch, S. Chalker, G. D. Squire, S. C. Tsang	J. CHEM. SOC. FARADAY TRANS., 1990, 86(9), 1607-1614
158	J. Kiwi, K. R. Thampi, M. Gratzel	J. CHEM. SOC., CHEM. COMMUN., 1990
159	J. W. M. H. Geerts, H. M. N. van Kasteren, K. van der Wiele	J. Chem. Soc., Chem. Comm. (1990), (11), 802-3
160	S. Becker, M. Baerns	J. Catal. 128 (1990) 512
161	R.V. Siriwardane	J. Catal., 123 (1990) 496.
162	Annapragada, A. V. & Gulari, E.	J. C atal , 123 (1990) 130.
163	S. Ahmed and J.B. Moffat	J. Catal., 125 (1990) 54.
164	S.G. Agarwal, R.A. Migone, G. Marcelin	J . Catal., 123 (1990) 228.
165	G. Hutchings, M. Scurrell, J. Woodhouse	Catalysis Letters 5 (1990) 301
166	E. Miro, J. Santamaria, E. E. Wolf	J. C atal , 124 (1990) 451.

167	Y. Tong, M. Posynek, J. Lunsford	J . Catal., 126(1990) 291.
168	T.A. Valasanyan, R. K. Aliev	Kinetika I Kataliz 31 (1990) 240.
169	P.A. Diddams, R.I. Little and S.R. Wade	Austr. Patent AU-A-42806/89 (1990).
170	E.J. Erekson, A.L. Lee, S.P. Barone and I.J. Solomon	US Patent 4945078 (1990).
171	J.L. Jezl, G.O. Michaels, M.J. Spangler and M.L. Winzenburg	US Patent 4 968 655 (1990).
172	P. Chu and M.E. Landis	US Patent 4 914 252 (1990).
173	B.K. Warren, K.D. Campbell, J.L. Matherne, G.L. Culp, N.E. Kinkade, and P.H. Tate	US Dep. Energy, DOE/PC/79817-8 (1990).
174	J.H. Murib	World Patent WO 90/00532 (1990).
175		J P 02,225 (1990)425.
176	Campbell, K. D.	European Patent 0,418 (1990) 975Al.
177	P.A. Diddams, I.e. Little, S.R. Wade	EP 0365181 B1 (1990)
178	K.D. Campbell	WO 9104237 A1 (1990)
179	Annapragada; Ananth V., Gulari; Erdogan	US 4952547 (1990)
180	S.J. Conway, D.J. Wang, J.H. Lunsford	Applied Catalysis A General, 79 (1991) Ll-L5
181	S. Seimanides, P. Tsiakaras, X.E. Verykios, C.G. Vayenas	Applied Catalysis, 68 (1991) 41-53
182	M. G. Poirier, R. Breault, S. Kaliaguine, A. Adnot	Applied Catalysis, 71 (1991) 103-122
183	A. Machocki, A Denis, T Borowiecki, J. Barcicki	Applied Catalysis, 72 (1991) 283-294
184	Z. Zhang, M. Baerns	Applied Catalysis, 75 (1991) 299-310
185	H. Yamashita, Y. Machidaand A. Tomita	Appl. Catal., 79 (1991) 203.
186	R. Burch, R. S. Chalker, P. Loader and D.A. Rice	Appl. Catal., 79 (1991) 265.
187	T. Ohno, J. B. Moffat	Catalysis Letters 9 (1991) 23-34
188	A. Machocki	Catalysis Letters 9 (1991) 97-102
189	W. Ueda, F. Sakyu, T. Isozaki, Y. Morikawa, J. M. Thomas	Catalysis Letters 10 (1991) 83-90
190	J.L. Rehspringer, P. Poix	Catalysis Letters 10 (1991) 111-120
191	K. J. Smith, T. M. Painter, J. Galuszka	Catalysis Letters 11 (1991) 301-308
192	J. Dubois, C. J. Cameron	Chemistry Letters (1991), (7), 1089-92.
193	V.R. Choudhary, S.T. Chaudhari and M.Y. Pandit, J. Chem. Soc.	Chem. Commun., (1991) 1158.
194	N. Matsuda, T. Azukino, K Ohyachi and I. Matsuura	Chem. Express, 6 (1991) 77.
195	D.J. McNamara, S.J. Korf, K Seshan, J.G. van Ommen and J.R.H. Ross	Can. J. Chem. Eng., 69 (1991) 883.
196	Q. Yan, J. Shen, Y. Wang, X. Fu	Hyperfine Interactions 69 (1991) 855-858
197	R. P. Taylor, G. L. Schrader	Ind. Eng. Chem. Res., Vol. 30, No. 5, 1991
198	P. G. Hinson, A. Clearfield, J. H. Lunsford	J. CHEM. SOC., CHEM. COMMUN., 1991
199	K. Aika, K. Aono	J. CHEM. SOC. FARADAY TRANS., 1991, 87(8), 1273-1277
200	F.P. Larkins and M.R. Nordin	J. Catal., 130 (1991) 147.
201	R. V. Siriwardane	Langmuir 1991, 7, 497-502
202	M. Hatano andJ.H. Lunsford	React. Kinet. Catal. Lett., 45 (1991) 1.
203	KM. Parida and S.B. Rao	React. Kinet. Catal. Lett., 44 (1991) 103.

204	J. Kiwi, K. R. Thampi, M. Gratzel	Solid State lonics 48 (I99 1) 123-l 25
205	W.J.M. Vermeiren, I.D.M.L. Lenotte, J.A. Martens and P.A. Jacobs	Stud. Surf. Sci. Catal.,61 (1991) 33.
206	KD. Campbell	Eur. Patent EP 418 973 (1991).
207	R.B. Chafin and B.K. Warren	Eur. Patent EP 418 971 (1991).
208	K.D. Campbell	Eur. PatentEP 418975 (1991).
209	B.K. Warren and R.B. Chafin	Eur. Patent EP 418 972 (1991).
210	R.B. Chafin and B.K. Warren	Eur. Patent EP 418 971 (1991).
211	G.O. MichaelsandM.J. Spangler	US Patent 4992 409 (1991).
212	J.H. Lunsford and P.G. Hinson	US Patent 5 041 405 (1991).
213	C.A. Lukey, A.M. Maitra and R.J. Tyler	US Patent 5 066 629 (1991).
214	V. Gupta, C.L. Bodolus, C. Paparizos and W.G. Shaw	US Patent 5 012 028 (1991).
215	T. Hayakawa, K. Takehira, H. Orita, M. Shimizu, Y. Watanabe	EP 0450810 B1 (1991)
216	G. Fornasari, S. Palmery, G. Piro, G. Belussi	EP 0492695 B1 (1991)
217	Campbell; Kenneth D.	US 4988660 (1991)
218	Michaels; Glenn O., Spangler; Michael J.	US 4992409 (1991)
219	Michaels; Glenn O., Spangler; Michael J.	US 5028577 (1991)
220	Lukey; Christopher A. , Maitra; Ashit M., Tyler; Ralph J.	US 5066629 (1991)
221	R. Burch, S. Chalker, P. Loader	Applied Catalysis A General, 82 (1992) 77-90
222	A. Gervasini, G. Fornasari, G. Bellussi	Applied Catalysis A General, 83 (1992) 235
223	A.M. Maitra, I. Campbell and R.J. Tyler	Applied Catalysis A General, 85 (1992) 27

224	S. Park, J. Chang	Applied Catalysis A General, 85 (1992) 117.
225	J. Barrault, C. Grosset	Applied Catalysis A General, 88 (1992) 197.
226	A. Z. Khan, E. Ruckenstein	Applied Catalysis A: General, 90 (1992) 199
227	A. Z. Khan, E. Ruckenstein	Catalysis Letters 13 (1992) 95-102
228	oE1 Barrault *, C6cile Grosset	Catalysis Letters 16 (1992) 203-210
229	J.H. Kolts, J.B. Kimble and R.A. Porter, in A.F. Albright, B.L. Crynes and S. Nowak	Novel Production Methods for Ethylene, Light Hydrocarbons and Aromatics, Marcel Dekker, New York, 1992, p. l.
230	J. Kiwi, K.R Thampi, M. Gratzel, P. Albers and K. Seibold	J. Phys. Chem., 96 (1992)
231	X.-R. Xia, G.-X. Xiong and X.-X. Guo	in A.F. Albright, B.L. Crynes and S. Nowak (Editors), Novel Production Methods for Ethylene, Light Hydrocarbons and Aromatics, Marcel Dekker, 1992, p. 107.
231	Q.J. Yan, Y. Wang, Y.S. Jin, Y. Chen	Catalysis Letters 13 (1992) 221
233	Kimble, J. B. & Kolts, J. H.	US Patent 5, 118 (1992) 899.
234	Choudhary; Vasant R. , Pandit; Meenakshi Y., Chaudhari; Sopan T.	US 5118654 (1992)
235	Kimble; James B., Kolts; John H.	US 5160502 (1992)
236	T. Ohno, J. B. Moffat	Appl. Catal., 93 (1993) 141.
237	S. Sugiyama, Y. Matsumura, J. Moffat	J . Catal., 139(1993) 338.
238	A. Z. Khan, E. Ruckenstein	J . Catal., 119 (1993) 304.
239	D. Dissanayaka, K. Kharas, J. Lunsford, M. Posynek	J. Catal. 139 (1993) 652.
240	C.B. Alcock, J.Carberry, R. Doshi, N. Gunasekaran	J . Catal., 143(1993) 533.

241	E. Ruckenstein, A. Khan	J . Catal., 141 (1993) 628.
242	X. Zhang, D. Jefferson, R. Lambert	J . Catal., 141 (1993) 583.
243	C. Petit, A. Kaddouri, S. Libs, A. Kiennemann, J. Rehspringer, P. Poix	J . Catal., 140 (1993) 328.
244	R. Voyatzis and J. B. Moffat	J . Catal., 142 (1993) 45.
245	Y. Matsumura, J. B. Moffat	Catalysis Letters 17 (1993) 197-204
246	E. Ruckenstein, A. Khan	Catalysis Letters 18 (1993) 27-35
247	J. Kiwi, K. R. Thampi, N. Mouaddib, M. Graetzel, Peter Albers	Catalysis Letters 18 (1993) 15-26
248	S. Zhou, X. Zhou, H. Wan and K.R. Tsai	Catalysis Letters 20 (1993) 179-183

249	X. Zhou, W. Zhang, H. W a n and K. Tsai	Catalysis Letters 21 (1993) 113-122
250	Z. Jiang, C. Yu, X. Fang, S. Li, and H. Wang	J. Phys. Chem. 1993,97, 12870-12875
251	M. Yamamura, H. Okado	EP 0565101 B1 (1993)
252	Han; Scott, Michaels; James N., Palermo; Robert E. , Stern; David L. , Walsh; Dennis E.	US 5191138 (1993)
253	Washecheck; Don M., Barr; Mark K. , Huff, Jr.; George A. , Kaminsky; Mark P., Kleefisch; Mark S., Shum; Victor K.	US 5196634 (1993)
254	Kaminsky; Mark P. , Kleefisch; Mark S. , Huff, Jr.; George A. , Washecheck; Don M. , Barr; Mark K.	US 5198596 (1993)
255	Miremadi; Bijan K., Morrison; Stanley R. , Colbow; Konrad	US 5245124 (1993)
256	D. Papageorgiou, A.M. Efstathiou, X.E. Verykios	Applied CatalysisA: General 111 (1994) 41-62
257	R. Mariscal, J. Soria, M.A. Pefia, J.L.G. Fierro	Applied Catalysis A: General 111(1994) 79-97
258	A.M. Maitra	Applied Catalysis A: General 114 (1994) 65-81
259	M. Yamamura, N. Tsuzukia, H. Okado, T. Wakatsuki, K. Otsuka	Applied Catalysis A: General 115 (1994) 269-283
260	V. Tashjian, M. Cassir, J. Devynck, W. Rummel	Applied Catalysis A: General, 108 (1994) 157-169
261	G. D. Squire, H. Luc, D. C. Puxley	Applied Catalysis A: General, 108 (1994) 261-278
262	A. G. Andersen	Catalysis Letters 23 (1994) 59-68
263	W. Ding, Y. Chen, X. Fu	Catalysis Letters 23 (1994) 69-78
264	C. T. Au,Y.Q. Zhang, C. F. Ng, H.L. Wan	Catalysis Letters 23 (1994) 377-386.
265	X.P. Zhou, Z.S. Chao, W.Z. Weng, W.D. Zhang, S.J. Wang, H.L. Wan and K.R. Tsai	Catalysis Letters 29 (1994) 177-188
266	P. D. Battle, S. W. Carr, F. A. Copplestone, R. S. Mellen	J. MATER. CHEM., 1994, 4(3), 421-427

267	K.M. Dooley, S. Chen, J.R.H. Ross	J. Catal. 145 (1994) 402.
268	J. Lunsford, P. Hinson, M. Rosynek, C. Shi, M. Xu, X. Yang	J. Catal. 147 (1994) 301.
269	S. Driscoll, D. Gardner, U. Ozkan	J. Catal. 147 (1994) 379.
270	M. Yang, Q.J. Yan, C. Fu	Div.of petroleum Chemistry, Inc. 207th Nat. Meeting, Am. Chem. Soc., San Diego, CA, 1994, p. 258.
271	J. Sarkany, Q. Sun, R. G. Herman, K.Klier	Div.of petroleum Chemistry, Inc. 207th Nat. Meeting, Am. Chem. Soc., San Diego, CA, 1994, p. 226.
272	X.P. Zhou, S.Q. Zhou, W.D. Zhang, Z.S. Chao, W.Z. Zhang, R.Q. Long, D.L. Tang, H.Y. Wang, S.J. Wang, J. Cai, H. Wan, K. Tsai	Div.of petroleum Chemistry, Inc. 207th Nat. Meeting, Am. Chem. Soc., San Diego, CA, 1994, p. 222.
273	van der Vaart; Donald R.	US 5321185 (1994)
274	M. Yamamura, H. Okado, N. Tsuzuki, T. Wakatsuki, K. Otsuka	Applied Catalysis A: General 122 (1995) 135 149
275	Z. Sheng Chao, Xiao Ping Zhou, Hui Lin Wan, Khi Rui Tsai	Applied Catalysis A: General 130 (1995) 127-133
276	R. Mariscal, M.A. Pefia, J.L.G. Fierro	Applied Catalysis A: General 131 (1995) 243-261
277	G.C. Maiti, M. Baerns	Applied Catalysis A: General 127 (1995) 219-232
278	W. Bytyn, M. Baerns	Applied Catalysis A: General 127 (1995) 219-232
279	J.S. Chang, S.E. Park	Bull. Korean Chem. Soc. (1995) 16, 1148.
280	Rui-qiang Long, Shui-qin Zhou, Ya-ping Huang, W. W e n g , Hui-lin Wan *, Khi-rui Tsai	Applied Catalysis A: General 133 (1995) 269-280
281	Y. Matsumura, S. Sugiyama, H. Hayashi, John B. Moffat	Catalysis Letters 30 (1995) 235-240
282	Qing, Xin-Rui Xia, Guo-xing Xiong Miao, Xie-xia G u o	Catalysis Letters 31 (1995) 183-195
283	X. Bao, M. Muhler, R. Schl6gl and G. Ertl	Catalysis Letters 32 (1995) 185-194
284	I. Eskendirov, N.J. Coville and V.D. Sokolovskii	Catalysis Letters 35 (1995) 33-37
285	Yide Xu, Lin Yu, Chen Cai, Jiasheng Huang and Xiexian Guo	Catalysis Letters 35 (1995) 215-231
286	M. Y a m a m u r a, H. Okado, K. Chaki, T. Wakatsuki, K. Inaba, S. Suzuki b, T. Yoshinari	Catalysis Today 24 (1995) 299-300
287	M.-C. Gong, J.-L. Zhou, Z.-H. Xu, Y.-Q. Chen, Y. C h e n	Catalysis Today 24 (1995) 259-261
288	Z.R. I s m a g i l o v, A. P a r m a l i a n a, F. Frusteri, D. Miceli A.A. K i r c h a n o v a	Catalysis Today 24 (1995) 281-284
289	R. Voyatzis and J. B. Moffat	Energy & Fuels 1995,9, 240-247

290	Kaushal K. Tiwari, Tarak N. Roy, Somnath Banerjee, Subrato Ganguly &Deba P. Bhattacharyya	J . Chem. Tech. Biotechnol. 1995,63,190-194
291	M. A. Centeno, M. J. Capitan, P. Bosch, P. Malet, J. J. Benitez, Carrizosaaand J. A. Odriozola	J. MATER. CHEM., 1995,5(l), 175-181
292	Jingang Wu and Shuben Li	J. Phys. Chem. 1995, 99, 4566-4568
293	Z. Yu, X. Yang, J. Lunsford, M. Rosynek	J. Catal., 154 (1995) 163.
294	D. Wang, M. Rosynek, J. Lunsford	J. Catal., 155 (1995) 390.
295	Sang C. Kim, Larry E. Erickson, Eui Y. Yu	Journal of Hazardous Materials 41 (1995) 327-340
296	M. T E Y M O U F 1 l , E. B A G H E R Z A D E H, C. PETIT, J. L. REHSPRINGER, S. LIBS, A. K I E N N E M A N N	J O U R N A L OF MATERIALS S C I E N C E 30 (1995) 3005-3009
297	B. ZHOU' and R. A . McFARLANE, K. J. SMITH	THE CANADIAN JOURNAL OF CHEMICAL ENGINEERING, VOLUME 73, FEBRUARY, 1995
298	Yesim Erarslanoglu, Isik Onal, Timur Dogu, Selim Senkan	Applied Catalysis A: General 145 (1996) 75-84
299	Ki June Yoon, Sang Won Seo	Applied Catalysis B: Environmental 7 (1996) 237-250
300	Yesim Erarslanoglu, Isik Onal, Timur Dogu, Selim Senkan	Catalysis Letters 38 (1996)215-218
301	Huilin Wan, Zisheng Chao, Weizheng Weng, Xiaoping Zhou, Junxiu Cai, Khirui Tsai	Catalysis Today 30 (1996) 67-76
302	Zhongyuan Dang, Jingfang Gu, Jingzhi Lin and Dexing Yang	Chem. Commun., 1996, 1901
303	X U Z H U S H E N G , Z H A N G TAO, Z A N G L I A N F A , W A N G TAO, W U J I N R O N G , C H E N, L A I Y U A N and LIN L I W U	Chemical Enaineerin. Science, VoL 51, No. 4, pp. 515-519, 1996
304	Y. ERARSLANOGLU, I. ONAL, T. DOGU, JOHN B. BUTI	Chemical Engineering Communications (1995), 135 71-9.
305	L. Mleczko and U. Pannek, V. M. Niemi, and J. Hiltunen	Ind. Eng. Chem. Res., Vol. 35, No. 1, 1996
306	N. Wong, K. Tin, Q. Zhu, M. Zhang, X. Qiu	J. Chem. Technol. Biotechnol. 1996, 67, 164.
307	Ning-bew Wong, Kam-chung Tin, Qi-ming Zhu, Mei-zhen Zhang & Xian-qing Qiu	J . Chem. Tech. BiotechnoL 1996,67, 164-168
	Ning-bew Wong, Kam-chung Tin, Keung Lau, Xian-qing Qiu & Qi-ming Zhu	J . Chem. Tech. BiotechnoL 1996,65, 351-354
308	C. T. Au, H. He, S. Y. Lai, and C. F. Ng	JOURNAL OF CATALYSIS 159, 280–287 (1996)
309	D. Lazarov, V. Rives,*, R. Klissurska, I. Mitov ‘, D. Klissurki	Materials Letters 27 (1996) 129-333
310	M. Baerns, R. Blom, G.B. Marin, C. Mirodatos, J.G. Van Ommen, J. Ross, I.A. Vasalos, X. Verykios	Conversion of natural gas to synthesized gas and C2 hydrocarbons, Final report, Contract No JOU2-CT92-0073 (1996)
311	K. Klier, R. G. Herman, C. Wang	U.S. Department of Energy, Report “Selective Methane Oxidation over Promoted Oxide Catalysts, 1996.
312	Sang Chai Kim, Su Jin Kim b, Eui Yeon Yu	Applied Catalysis A: General 150 (1997) 63-76
313	V.R. Choudhary, V.H. Rane, S.T. Chaudhari	Applied Catalysis A: General 158 (1997) 121-136

314	C.Y. Yu a, W . Z . Li a, G . A . Martin b, C. M i r o d a t o s	Applied Catalysis A: General 158 (1997) 201-214
315	D. Filkova a, D. W o l f b, G. G a y k o b, M. Baerns c, L. P e t r o v	Applied Catalysis A: General 159 (1997) 33-44
316	R.Q. Long, H.L. Wan	Applied Catalysis A: General 159 (1997) 45-58
317	Ki June Yoon, Hsiao Ling Tung	Applied Catalysis A: General 159 (1997) 59-74
318	Y. Zeng, Y.S. Lin	Applied Catalysis A: General 159 (1997) 101-117
319	C.T. Au, H. He, S.Y. Lai, C.F. Ng	Applied Catalysis A: General 159 (1997) 133-145
320	Ruiqiang Long, Jizhong Luo, Mingshu Chen, Huilin Wan	Applied Catalysis A: General 159 (1997) 171-185
321	Xu Yide, Yu Lin, Guo Xiexian	Applied Catalysis A: General 164 (1997) 47-57
322	Sung Han Lee, Da W o o n Jung, Jung Bae Kim, Yong-Rok Kim	Applied Catalysis A: General 164 (1997) 159-169
323	Shigeru Sugiyamab, Hiromu Hayashi, J.B. Moffat	Catalysis Today 37 (1997) 15-23
324	Kazuhisa Murata, Takashi Hayakawa and Ken-ichi Fujita	Chem. Commun., 1997
325	Y. Zeng and Y. S. Lin	Ind. Eng. Chem. Res. 1997, 36, 277-283
326	Vasant R. Choudhary, Balu S. Uphade, and Shafeek A. R. Mulla	Ind. Eng. Chem. Res. 1997, 36, 3594-3601
327	Ruiqiang Long and Huilin Wan	JOURNAL OF CATALYSIS 172, 471–474 (1997)
328	C.Chen, P. Hong, S. Dai, C. Zhang	React. Kinet. Catal. Lett., 61 (1997) 181.
329	V. Choudhary, V. Rane	J. Chem. Technol. Biotechnol. 1997, 69, 63.
330	V. Choudhary, V. Rane, M. Pandit	J. Chem. Tech. Biotechnol. (1997) 68, 177.
331	C.Chen, P. Hong, S. Dai, C. Zhang, X. Yang	React. Kinet. Catal. Lett., 61 (1997) 175.
332	W. Ignaczak, W.K. Jozwiak, D.T. Gebauer, T. Paryjczak	Polish J. Chem. 71 (1997) 962.
333	Yu Liua, Xuxia Liua, Jinzhen Xuea, RuiLing Houa, Bing Zhanga, Changchun Yub, Shikong Shen	Applied Catalysis A: General 168 (1998) 139.
334	C.T. Au, K.D. Chen, C.F. Ng	Applied Catalysis A: General 170 (1998) 81.
335	C.T. Au, K.D. Chen, C.F. Ng	Applied Catalysis A: General 171 (1998) 283.
336	Lin Yua, Wenzhao Lib, V. Ducarmec, C. Mirodatosc, G.A. Martin	Applied Catalysis A: General 175 (1998) 173.

337	E.V. Fomenkoa, E.V. Kondratenkob, O.M. Sharonovab, V.P. Plekhanova, S.V. Koshcheev	Catalysis Today 42 (1998) 273
338	Kazuhisa Murata, Takashi Hayakawa, Satoshi Hamakawa, Kunio Suzuki	Catalysis Today 45 (1998) 41.
339	V. R. Choudhary, S. A. R. Mulla, and B. S. Uphade	Ind. Eng. Chem. Res. 1998, 37, 2142.
340	Ruiqiang Long, and Huilin Wan	J. Chem. Soc., Faraday T rans., 1998, 94(8), 1129
341	Vasant R. Choudhary, Shafeek A. R. Mulla & Vilas H. Rane	J. Chem. T echnol. Biotechnol. 1998, 71, 167
342	C. T. Au, X. P. Zhou, Y. W. Liu, W. J. Ji, and C. F. Ng	JOURNAL OF CATALYSIS 174, 153–163 (1998)
343	Peter C. T. Au, Y. W. Liu, and C. F. Ng	JOURNAL OF CATALYSIS 176, 365–375 (1998)
344	Alejandra Palermo, Juan Pedro Holgado Vazquez, Adam F. Lee, Mintcho S. Tikhov, Richard M. Lambert	JOURNAL OF CATALYSIS 177, 259–266 (1998)
345	G. Gayko, D. Wolf, E. V. Kondratenko, and M. Baerns	JOURNAL OF CATALYSIS 178, 441–449 (1998)
346	Sergei Pak, Ping Qiu, and Jack H. Lunsford	JOURNAL OF CATALYSIS 179, 222–230 (1998)
347	Vic; Sebastian , Pena; Miguel A. , Terreros; Pilar , Gomez; Juan P. , Garcia-Fierro; Jose L. , Jimenez; Juan M.	US 5763722 (1998)
348	Vic; Sebastian , Pena; Miguel A. , Terreros; Pilar , Gomez; Juan P. , Garcia-Fierro; Jose L. , Jimenez; Juan M.	US 5817904 (1998)
349	Hui Lin Wan, Xiao Ping Zhou, Wei Zheng Weng, Rui Qiang Long, Zi Sheng Chao, Wei De Zhang, Ming Shu Chen, Ji Zhong Luo, Shui Qin Zhou	Catalysis Today 51 (1999) 161.
350	V. R. Choudhary, S.A.R. Mulla, B.S. Uphade	Fuel 78 (1999) 427.

351	Yoon Kyung Bae, Jin H y u k Jun and Ki June Yoon	KoreanJ. Chem.Eng., 16(5), 595. (1999)
352	Park; Tae-Jin, Suh; Dong Jin , Lee; Kwan-Young	US 5877387 (1999)
353	Withers, Jr.; Howard P.	US 5959170 (1999)
354	Jang Il Kong, Jin Seung Jung, Joong Gill Choi, Sung Han Lee	Applied Catalysis A: General 204 (2000) 241–250
355	Alejandra Palermo, Juan Pedro Holgado Vazquez and Richard M. Lambert	Catalysis Letters 68 (2000) 191–196
356	J.G.A. Pacheco Filho, Jean G. Eon, and Martin Schmal	Catalysis Letters 68 (2000) 197–202
357	A. Djaidja, A. Barama, M.M. Bettahar	Catalysis Today 61 (2000) 303–307
358	V.R. Choudhary, V.H. Rane, S.T. Chaudhari	Fuel 79 (2000) 1487±1491
359	H. Aritani, H. Yamada, T. Nishio, T.Shiono, S. Imamura, Kudo, Hasegawa, Yoshida	J. Phys. Chem. B 2000, 104, 10133-10143
360	Choudhary, SAR Mulla, MY Pandit, ST Chaudhari and VH Rane	Journal of Chemical Technology and Biotechnology (2000)
361	Jung Hoon Hong, Ki June Yoon	Applied Catalysis A: General 205 (2001) 253–262
362	A. Erdohelyi , R. Németh, A. Hancz, A. Oszkó	Applied Catalysis A: General 211 (2001) 109–121
363	Y. Zeng, F.T. Akin, Y.S. Lin	Applied Catalysis A: General 213 (2001) 33–45
364	S. L. González-Cortés, José Orozco , Bernardo Fontal	Applied Catalysis A: General 213 (2001) 259–271
365	A. Malekzadeh, A. Khodadadi, M. Abedini, M. Amini, A. Bahramian, A.K. Dalai	Catalysis Communications 2 (2001) 241.
366	Sakae Takenaka, Tomohiro Kaburagi, Ichiro Yamanaka, Kiyoshi Otsuka	Catalysis Today 71 (2001) 31–36
367	R. Spinicci, P. Marini, S. De Rossi, M. Faticanti, P. Porta	Journal of Molecular Catalysis A: Chemical 176 (2001) 253–265
368	Seung-Hwan Lee and Ki June Yoon	Korean .L Chem. Eng., 18(2), 228-232 (2001)

369	S. Ji , T. Xiao, S. Li, C. Xu, R. Hou, K. Coleman, M. L.H. Green	Applied Catalysis A: General 225 (2002) 271–284
370	Sung Han Lee, Jin-Seung Jung, Jae-Uk Joo, No-Seung Myung, Jong Ho Jun, Joong-Gil Choi	Applied Catalysis A: General 237 (2002) 91–101
371	A. Malekzadeh, M. Abedini , A.A. Khodadadi, M. Amini, H.K. Mishra and A.K. Dalai	Catalysis Letters Vol. 84, Nos. 1±2, November 2002
372	Codruta E. Platon and William J. Thomson	Ind. Eng. Chem. Res. 2002, 41, 6637-6641
373	Lingjun Chou, Yingchun Cai, Bing Zhang, Jianzhong Niu, Shengfu Ji, Shuben Li	Reaction Kinetics and Catalysis Letters (2002), 76(2), 311-315.
374	A.G. Dedov, A.S. Loktev, I.I. Moiseev, A. Aboukais, J.-F. Lamonier, I.N. Filimonov	Applied Catalysis A: General 245 (2003) 209–220
375	S. Ji, T. Xiao, S. Li, L. Chou, B. Zhang, C. Xu,R. Hou, A. P.E. York, and M. L.H. Green	Journal of Catalysis 220 (2003) 47–56
376	Bagherzadeh, Ebrahim; Hassan, Abbas; Hassan, Aziz	US 20040220053 (2004)
377	Yunfei Kuo Jiang-Xi	PhD Thesis TU Berlin "Effekte der spezifischen Oberfläche von Li/MgO-Katalysatoren bei der oxidativen Kopplung von Methan", 2005
378	S. Zarrinpashne, R. Ahmadi, S.M Zekordi	US 2006155157 A1 (2005)
379	J.G. Sunley	US 2007073083 A1 (2005)
380	S. M.A. R.-Baechler, Wilfredo Pernı ́ a, I. Aray, . Figueroa, Sergio L. Gonzalez-Cortes	Catalysis Letters (2006), 112(3-4), 231-237.
381	Sicong Hou, Yuan Cao, Wei Xiong, Haichao Liu, and Yuan Kou	Ind. Eng. Chem. Res. 2006, 45, 7077-7083
382	Vilas H Rane, Sopan T Chaudhari and Vasant R Choudhary	J Chem Technol Biotechnol 81, 208–215 (2006)
383	Jiaxin Wang, Lingjun Chou, Bing Zhang, Huanling Song, Jun Zhao, Jian Yang, Shuben Li	Journal of Molecular Catalysis A: Chemical 245 (2006) 272–277
384	Jingjing Wu, Haili Zhang, Song Qin, Changwei Hu	Applied Catalysis A: General 323 (2007) 126–134
385	A. Malekzadeh , A. Khodadadi , A. K. Dalai, M. Abedini	Journal of Natural Gas Chemistry 16(2007)121–129
386	Fengqiu Chen, Wen Zheng, Ning Zhu, Dang-guo Cheng, Xiaoli Zhan	Catal Lett (2008) 125, 348–351

387	L. Olivier, S. Haag, H. Pennemann, C. Hofmann, C. Mirodatos, A. C.Veen´	Catalysis Today 137 (2008) 80–89
388	Zhaobao Pang, Xiaoyao Tan, Ronggang Ding, Zi Gu, Shaomin Liu	Ceramics International 34 (2008) 1805–1810
389	Andrzej Machocki , Renata Jezior	Chemical Engineering Journal 137 (2008) 643–652
390	Z. Fakhroueian, F. Farzaneh, N. Afrookhteh	Fuel 87 (2008) 2512–2516
391	Haitao Liu, Xiaolai Wang , Dexin Yang , Runxiong Gao , Zhonglai Wang , Jian Yang	Journal of Natural Gas Chemistry 17(2008)59–63
392	Zhiming Gao , Jiansheng Zhang, Ruiyan Wang	Journal of Natural Gas Chemistry 17(2008)238–241
393	V. H. Rane, S. T. Chaudhari, V. R. Choudhary	Journal of Natural Gas Chemistry 17(2008)313–320
394	Florica Papa, Luminita Patron, Oana Carp, Carmen Paraschiv, Balint Ioan *	Journal of Molecular Catalysis A: Chemical 299 (2009) 93–97
395	Yasushi Sekine, Keisuke Tanaka, Masahiko Matsukata, and Eiichi Kikuchi	Energy & Fuels 2009, 23, 613–616
396	Kai Wang, Shengfu Ji, Xuejun Shi, JingJing Tang	Catal Lett (2009) 129, 156–162
397	K. Aika, T. Nishiyama	Catal. Today (1989) 4, 271
398	A. Kooh, H. Mimoun, C. J. Cameron	Catal. Today (1989) 4, 333
399	S. J. Korf, J. A. Roos, D. M. Difhoorn, R.H. J. Veehof, J. G. van Ommen, J.R. H. Ross	Catal. Today (1989) 4, 279

400	C. Mirodatos, G.A. Martin, J.C. Bertolini, J. Saint-Just	Catal. Today (1989) 4, 301
401	K. Otsuka, M. Hatano, T. Komatsu	Catal. Today (1989) 4, 409
402	R. Spinicci	Catal. Today (1989) 4, 311
403	U. Olsbye, G. Desgrandchamps, K. Jens, S. Kolboe	Catal. Today (1992) 13, 603.
404	M. Y. Lo, S.K. Agarwal, L.G. Galya, G. Marcelin	Catal. Today (1988) 3, 137.
405	H. Borges, S. Lacombe, C. Mirodatos	Catal. Today (1994) 21, 289.
406	S. Bartsch, H. Hofmann	Catal. Today (1990) 6, 527.
407	H.B.A. Hamid, R.B. Moyes	Catal. Today (1991) 10, 267
408	G.C. Hoogendam, K. Sechan, J.G. Van Ommen, J.R.H. Ross	Catal. Today (1994) 81, 333
409	A. Toebes, K.M. Dooley, J.R.H. Ross	Catal. Today (1994) 21, 401
410	J. M. Deboy, R.F. Hicks	J. Catal. 113 (1988) 517
411	V.G. Roguleva, M.A. Nikiphorova, N.G. Maksimov, A.G. Anshits	Catal. Today (1992) 13, 219
412	J. Barrault, C. Grosset, M. Hadj.Aissa	Catal. Today (1990) 6, 535

413 E.N. Voskresenskaya, L.I. Kurteeva, V.P. Zhereb, A.G. Anshits Catal. Today (1992) 13, 599

414 E.Y. Gankina, G.S. Salitra, Y.G. Borodko Catal. Today (1992) 13, 595

415 D. Papageorgiou, D. Vamvouka, D. Boudouvas, X.E. Verykios Catal. Today (1992) 13, 391

416 A. Kiennemann, R. Kieffer, A. Kaddouri, P. Poix, J.L. Rehspringer Catal. Today (1990) 6, 409

417 E.E. Miro, Z. Kalenik, J. Santamaria, E. E. Wolf Catal. Today (1990) 6, 511

418 K. Otsukka, K. Jinno, A. Morikawa J. Catal. 100 (1986) 353

419 H. Imai, T. Tagawa, N. Kamide J. Catal. 106 (1987) 394

420 M.Y. Lo, S.K. Agarwal, G. Marcelin J. Catal. 112 (1988) 168

421 A.M. Gaffney, C.A. Jones, J.J. Leonard, J.A. Sofranko J. Catal. 114 (1988) 422