

Coating Specifications Guide

Anti-corrosion systems for wire mesh & fencing products

DOCUMENT NO. KM-DS-003	REVISION Rev. 4 — 2024-01	PAGES 1 of 1
---------------------------	------------------------------	-----------------

1. Coating Systems Overview

System	Process	Min. Thickness	Service Environment
Zinc pre-galvanized (Z)	Sendzimir wire coating	20–60 g/m²	Indoor / dry outdoor
Hot-dip galvanized (HDG)	Post-form immersion, ≥ 440 °C	80 µm (610 g/m²)	Rural, urban
Zn-5%Al (Galfan)	Continuous immersion	85 µm	Coastal, industrial
HDG + PVC bond + PVC	Extrusion over zinc	Z 70 µm + PVC 0.5 mm	Marine, decorative
HDG + polyester powder	Electrostatic spray, cured 180 °C	Z 70 µm + 100 µm RAL	Architectural fencing

2. Selection by Environment

Corrosivity Category (ISO 9223)	Environment Example	Recommended System
C2 — Low	Rural inland	Z or HDG
C3 — Medium	Urban, light industrial	HDG ≥ 80 µm
C4 — High	Coastal < 3 km, industrial	Galfan or HDG + PVC
C5 — Very high	Marine splash, chemical	HDG + dual coat; 316 stainless

3. Verification Tests

- Coating mass: ASTM A90 / ISO 1460 (stripping gravimetric)
- Adhesion: ISO 2819 (bend / cut tests); PVC: ISO 4624 pull-off
- Salt spray: ASTM B117 neutral, 5% NaCl, 35 °C
- PVC weathering: QUV-A 1,000 h, ΔE ≤ 3, no cracking

4. Color Options (powder / PVC)

Standard RAL: 6005 green · 7016 anthracite · 9010 white · 9005 black · 7035 light grey. Custom colors from 500 m², lead-free formulations only (RoHS compliant).

All coating batches ship with thickness inspection records. Third-party witness inspection (SGS / BV / TÜV) accepted.

