

Wire Mesh Technical Datasheet

Product specification summary — woven & welded wire mesh systems

DOCUMENT NO. KM-DS-001	REVISION Rev. 3 — 2024-01	STANDARD ISO 9001:2015
---------------------------	------------------------------	---------------------------

1. Product Families

Series	Type	Wire Diameter	Aperture	Width
KESTREL WOVEN 711–714	Woven (plain / twill)	0.5 – 6.0 mm	6.4 – 100 mm	0.914 – 2.0 m
KESTREL WELDED 721–726	Welded mesh panel & roll	2.0 – 8.0 mm	25 – 200 mm	up to 2.4 m

2. Materials

Grade	Standard	Tensile Strength	Typical Use
Q195 / S235 low carbon	GB/T 700 · EN 10025	400–550 MPa	General mesh, panels
Stainless 304 / 304L	ASTM A240 · EN 10088	≥ 515 MPa	Screening, food, marine
Stainless 316 / 316L	ASTM A240 · EN 10088	≥ 485 MPa	Chemical, coastal

3. Coating Systems

Coating	Thickness	Salt Spray (ASTM B117)	Standard
Pre-galvanized (sendzimir)	20–60 g/m²	300–500 h	EN 10244-2
Hot-dip galvanized (after weave/weld)	≥ 80 µm	1,000–1,500 h	ASTM A123 · EN ISO 1461
Zn–Al alloy (Galfan type)	≥ 85 µm	2,000–2,500 h	EN 10244-2
PVC / powder overcoat	0.4–1.0 mm	up to 3,000 h (system)	EN 10244-2 · ASTM D780

4. Dimensional Tolerances

- Aperture tolerance: ±3% nominal (woven), ±2 mm (welded)
- Wire diameter tolerance: ±0.05 mm ≤ 3 mm; ±0.08 mm > 3 mm
- Panel length / width: ±3 mm; diagonal squareness: ≤ 2 mm difference

5. Weld Shear Strength

Welded intersections: minimum shear strength ≥ 50% of nominal wire tensile load, verified per ASTM A1064 sampling plan on every production batch.

Values are typical production values. Project-specific certified data (mill certificates, batch test reports) available on request at no charge.

