

# Applications of MoS<sub>2</sub> as a Two-Dimensional Material Beyond Graphene

Kraig Andrews\*

Wayne State University Department of Physics and Astronomy

(Dated: April 16, 2015)

An article usually includes an abstract, a concise summary of the work covered at length in the main body of the article.

## CONTENTS

I. Introduction	1
II. Graphene as a New Two-Dimensional Material	1
A. The Discovery of Graphene	1
B. Properties of Graphene	1
III. Transition Metal Dichalcogenides	2
A. Properties of MoS <sub>2</sub>	2
IV. Mechanical Exfoliation and Characterization of MoS <sub>2</sub> Nanosheets	3
V. Applications of MoS <sub>2</sub>	4
VI. State of the Art	4
VII. Problems and Outlook	4
References	4

## I. INTRODUCTION

### II. GRAPHENE AS A NEW TWO-DIMENSIONAL MATERIAL

#### A. The Discovery of Graphene

By the end of the last century microelectronics had revolutionized the world, the majority which are silicon-based devices. Today, millions of these silicon-based devices are used in many common electronic devices and have become unavoidable throughout everyday life. Though the first field-effect device was patented in 1925, it was not until 1960 that the first metal-oxide semiconductor field effect transistor was demonstrated [24, 31, 42]. A decade after the first device, devices were being made with several thousand components on a single chip. From there the progress increased at a rapid rate, a process now known as Moore's law, predicting that for each new generation of memory chip and microprocessor unit, the device size would be reduced by 33%, the chip size would be increased by 50%, and the number of components on a chip would

quadruple every three years [35, 42]. This proven to be true, and up until recently had shown no signs of stopping. Many times the material limitations were overcome by advances in technology that were seemingly insurmountable and effectively had placed a cap on Moore's law, which ultimately led to new techniques and even more pristine silicon-based materials. However, the limit to oxide thickness has finally placed a maximum on the growth of the silicon-based semiconductor device industry [42]. This impending limit caused many to look for solutions that involved the use of SiO<sub>2</sub> devices and also alternatives to silicon. The result of the latter has given way to a breadth of literature and research that was unforeseen a decade before. The search for alternatives to silicon resulted in research into many new, nontraditional materials. Several notable examples are organic conductors and carbon nanotubes [3, 10]. Arguably one of the most interesting nontraditional materials to come out of such research was graphene.

In 1985, with the discovery of fullerenes the amount of known carbon allotropes increased [26, 33]. Fullerenes suggested the existence of a one-dimensional form of carbon, known as carbon nanotubes, which were first demonstrated in 1991 [23]. Despite several theoretical studies involving the use of a single layer of graphite, it was not until 2004 that the first monolayer graphene sheet was isolated [36, 37]. In the most basic sense, graphene is simply a single layer of carbon atoms densely packed into a honeycomb lattice. It is used to describe properties several carbon-based materials (graphite, fullerenes, nanotubes, etc..., see Fig.1) [11, 36, 43]. This was significant because scientists had tried for many years to synthesize monolayers of graphite, though only succeeding in obtaining materials around 10 layers thick [33].

#### B. Properties of Graphene

To date, graphene's properties have been the focus of much research both theoretical and experimental. Graphene has many unique properties that have paved the way for new subfields in condensed matter physics (i.e. 'relativistic' condensed matter physics). These properties are primarily a result of its low dimensionality and its band structure that allow electrons to mimic relativistic particles [20]. This newly discovered phe-

---

\* kraig.andrews@wayne.edu




FIG. 1. Graphene can be envisioned in several dimensions. 0-dimensional buckyballs, 1-dimensional nanotubes, or 3-dimensional graphite [39].




FIG. 2. 3D representation of the electronic band structure of graphene. The right side shows an enlarged view near the Fermi level in one  $k$  point [33].

nomenon has allowed for the study of relativistic effects in condensed matter experiments. This includes the appearance of the atypical quantum Hall effect and the confirmation of other relativistic phenomena [38, 50, 56]. However, it is worth noting that this peculiar band structure can be modified by stacking three or more layers of graphene [33].

For applications to electronics a material's band gap is of interest. In graphene, however, the conduction and valence bands touch at a single point as shown in fig. 2 [33, 47]. As a result graphene has no band gap (small band gaps of a few hundred MeV can be introduced in bilayer graphene) [54]. The absence of a band gap is also interesting in the context of the material's optical properties and the implications of these. The absence of a band gap allows for the absorption of light over a large range of the electromagnetic spectrum, ranging from infrared ( $< 1.65\text{eV}$ ) to ultraviolet ( $> 3.2\text{eV}$ ) giving potential for electronic-photonic device applications [13, 48, 52].

Graphene's mechanical properties have been of much interest over the last decade. Graphene has a Young's modulus of  $\sim 1000\text{GPa}$  with a breaking strength that is 13% of that [1, 4]. It can also sustain elastic deformations of 20% and due to its two-dimensional nature it has a high pliability [33]. Mechanically, graphene is

an exciting material due to the fact that it lies in the extreme ranges of some metrics considering its size and dimensionality.

The mobility in graphene is another property that initially made the material so appealing (and still quite appealing to some degree). Graphene's mobility is about 1000 times that of silicon's [1, 9]. The outstanding crystal quality in large scale (a few microns) is the major contributing factor here. Without many defects or imperfections the electrons can travel long distances, as much as several micrometers, without being scattered even on rough substrates [12, 33]. The average electron mobility obtained in graphene varies depending on temperature, but the most commonly measured value is  $\mu = 100,000\text{cm}^2\text{V}^{-1}\text{s}^{-1}$  with values up to  $\mu = 500,000\text{cm}^2\text{V}^{-1}\text{s}^{-1}$  obtainable at low temperatures [18].

### III. TRANSITION METAL DICALCOGENIDES

Graphene is being studied for its unique properties, however, many other two-dimensional materials are known. Some of the two-dimensional materials being studied in addition to graphene are known as transition metal dichalcogenides (TMDs) [34, 51]. TMDs consist of hexagonal layers of metal atoms (M) in between two layers of chalcogen atoms (X) such that the stoichiometry of the material is  $\text{MX}_2$  [54]. The material is dependent on the combination of transition metal, typically one of: Mo, W, Nb, Re, Ni, or V, and chalcogen, typically one of: S, Se, or Te [51]. These materials are commonly stacked together which involves van der Waals interactions between adjacent sheets and covalent bonding within each individual sheet (see fig. 3) [54]. There are wide variety of properties exhibited by these structures, which include insulator or metal. In addition, they can also display some interesting properties like the topological insulator effect, superconductivity, and thermoelectricity [17, 27, 53, 55]. Ongoing research also includes graphene-like nano materials like silicene and germanene, which are the silicon and germanium-based versions of graphene and are found to show properties that are similar to graphene [6, 46]. These two-dimensional materials are becoming increasingly attractive for a wide-range of applications due to their distinct properties.

#### A. Properties of $\text{MoS}_2$

As discussed in sec. IIB, pristine graphene has no band gap. Though it is possible introduce a band gap in bilayer graphene and graphene nanoribbons, the appeal of many TMDs is that they have direct band gaps which make them ideal candidates for electronic material applications [54]. One such example of a semiconducting




FIG. 3. (a) The atomic structure of layered MoS<sub>2</sub>. Different sheets are composed of three atomic layers S-Mo-S, where Mo and S are covalently bonded [40, 54]. (b) Top view of the honeycomb lattice [54].

TMD is MoS<sub>2</sub> (molybdenum disulphide). TMDs, and more specifically MoS<sub>2</sub> and the properties it exhibits have been studied to some extent for several decades with electrical measurements dating back to the 1960s [14, 16]. However, as of late there has been renewed interest in several TMDs and their potential applications.

Like graphene, and many other 2D materials, MoS<sub>2</sub> has a Young's modulus that is comparable to steel ( $\sim 205$  GPa) [44]. The Young's modulus of single-layer MoS<sub>2</sub> is  $\sim 270$  GPa. The Young's modulus of bulk MoS<sub>2</sub> is  $\sim 240$  GPa. The fact that monolayer MoS<sub>2</sub> has a higher Young's modulus than its bulk material counterpart is thought to be mostly due to defects in the material, interlayer sliding, or the absence of stacking faults in monolayer samples [28]. In a further study it was found that the Young's modulus of multilayer MoS<sub>2</sub> ranging in thickness from 5 to 25 layers was  $330 \pm 70$  GPa [8]. In addition, both single and bilayer MoS<sub>2</sub> have a breaking strength of about 6% and 11% of their Young's modulus, respectively [4]. This is an indication that MoS<sub>2</sub> is quite flexible compared to other commonly used engineering materials (stainless steel  $\sim 0.4\%$ , kevlar  $\sim 2.6\%$ ) [19].

As stated before, what MoS<sub>2</sub> and some other TMDs appealing for applications, specifically for use in integrated circuits and logic applications (see sec.V for more on applications). Monolayer MoS<sub>2</sub> has an indirect band gap of 1.8 eV and few layer (bulk) MoS<sub>2</sub> has a direct band gap of 1.3 eV [15, 21, 25, 32, 54]. This change in transition from an indirect band gap semiconductor to a direct band gap semiconductor is shown in fig.4. The unusual electronic structure of mono and few-layer MoS<sub>2</sub> which ultimately results in some unique optical properties are due to the composition of the material's conduction and valence bands. The valence band maximum at the  $\Gamma$  point shifts downward to the  $K$  point of the Brillouin zone as the number of layers decreases [32, 45]. The change in the band structure as a function of the amount of layers is due to quantum confinement and the change in hybridization between  $p_z$  orbitals on S atoms and  $d$  orbitals on Mo atoms [30, 32, 45]. Using quantum mechanical modeling systems to investigate the many-body electronic structure of MoS<sub>2</sub> (density




FIG. 4. Calculated band structures of bulk (a) and monolayer (b) MoS<sub>2</sub> and the arrows indicate the lowest energy transition [45].

functional theory) it has been shown that the conduction band states at the  $K$  point are primarily the result of  $d$ -orbital electrons localized on the Mo atoms in between layers and are relatively unaffected by interlayer coupling [22, 49]. Conversely, states near the  $\Gamma$ -point are strongly affected by interlayer coupling due to the effects of antibonding  $p_z$ -orbitals on the S atoms and the  $d$  orbitals on the Mo atoms [45]. The result of this is that the states near the  $K$ -point are, for the most part, unchanged while the states near the  $\Gamma$ -point are shifted causing the change from an indirect to a direct band gap as the amount of layers of the material is decreased.

Carrier mobility in two-dimensional TMDs are affected by scattering. The amount by which the scattering affects the mobility is dependent on a number of factors, namely: material thickness, carrier density, effective mass, temperature, and electronic and phonon band structure [49]. The main sources of scattering in 2D TMDs are: acoustic and optical phonon scattering and Coulomb scattering [2, 41].

#### IV. MECHANICAL EXFOLIATION AND CHARACTERIZATION OF MOS<sub>2</sub> NANOSHEETS

There exist several methods that can be used to prepare atomically thin nanosheets of MoS<sub>2</sub> (and other TMDs). Among these several methods are mechanical exfoliation, chemical exfoliation, chemical vapor deposition, and sonication [54]. The method of mechanical exfoliation used to synthesize monolayer and few-layer MoS<sub>2</sub> is very similar to the method used by Geim et al. to synthesize their samples of graphene from 3D graphite [37].

To date, mechanical exfoliation remains the best method to synthesize MoS<sub>2</sub> crystals of the highest quality. The process involves taking bulk MoS<sub>2</sub> crystals and peeling thin layers from the bulk material using some adhesive material. Commonly, the adhesive material




FIG. 5. Color image of a  $\text{MoS}_2$  deposited on a 90 nm  $\text{SiO}_2/\text{Si}$  substrate. The digits indicate the layer numbers of  $\text{MoS}_2$  nanosheets [29]

is Scotch tape, though there have been variations on this such as a silicone stamp, instead [7]. This leaves a number of flakes attached to the surface of the adhesive. The flakes that are attached to the adhesive are then placed onto a substrate using instruments like plastic tweezers to further separate the flakes from the adhesive material. The process results in mono and few-layer flakes of  $\text{MoS}_2$  being deposited on the substrate [29]. In addition to mono and few-layer flakes of  $\text{MoS}_2$  being deposited on the substrate, the most common substrate

being  $\text{SiO}_2/\text{Si}$ , a quantity of thicker flakes of  $\text{MoS}_2$  are deposited as well [5]. This is demonstrated in fig.5, showing the varying thicknesses of  $\text{MoS}_2$  flakes on a substrate. As a result a method is needed to further differentiate between the flakes of varying thicknesses on that have been deposited on the substrate before any type of fundamental research can be done on the material.

Determining the size synthesized two-dimensional materials is inherently challenging due to the small sample sizes. Several methods have been developed throughout the years to indentify and characterize these materials. The method used is dependent on the desired properties of the material that are of interest. For locating and subsequently determining the thickness of  $\text{MoS}_2$  optical microscopy is one technique that does well to identify single and multi-layer flakes [5]. In addition, to identify the thickness of these flakes, a common technique involves the use of atomic force microscopy (AFM).

## V. APPLICATIONS OF $\text{MoS}_2$

## VI. STATE OF THE ART

## VII. PROBLEMS AND OUTLOOK

- 
- [1] Deji Akinwande, Nicholas Petron, and James Hone. Two-dimensional flexible nanoelectronics. *Nature Communications*, 5, 2014.
  - [2] Tsuneya Ando, Alan B. Fowler, and Frank Stern. Electronic properties of two-dimensional systems. *Rev. Mod. Phys.*, 54:437–672, Apr 1982.
  - [3] Ray H. Baughman, Anvar A. Zakhidov, and Walt A. de Heer. Carbon nanotubes—the route toward applications. *Science*, 297(5582):787–792, 2002.
  - [4] Simone Bertolazzi, Jacopo Brivio, and Andras Kis. Stretching and breaking of ultrathin mos2. *ACS Nano*, 5(12):9703–9709, 2011. PMID: 22087740.
  - [5] Sheneve Z. Butler, Shawna M. Hollen, Linyou Cao, Yi Cui, Jay A. Gupta, Humberto R. Gutierrez, Tony F. Heinz, Seung Sae Hong, Jiaying Huang, Ariel F. Ismach, Ezekiel Johnston-Halperin, Masaru Kuno, Vladimir V. Plashnitsa, Richard D. Robinson, Rodney S. Ruoff, Sayeef Salahuddin, Jie Shan, Li Shi, Michael G. Spencer, Mauricio Terrones, Wolfgang Windl, and Joshua E. Goldberger. Progress, challenges, and opportunities in two-dimensional materials beyond graphene. *ACS Nano*, 7(4):2898–2926, 2013. PMID: 23464873.
  - [6] S. Cahangirov, M. Topsakal, E. Aktürk, H. Şahin, and S. Ciraci. Two- and one-dimensional honeycomb structures of silicon and germanium. *Phys. Rev. Lett.*, 102:236804, Jun 2009.
  - [7] A Castellanos-Gomez, N Agrat, and G Rubio-Bollinger. Optical identification of atomically thin dichalcogenide crystals. *Applied Physics Letters*, 96(21):–, 2010.
  - [8] A. Castellanos-Gomez, M. Poot, G. Steele, H.S.J. van der Zant, N. Agraït, and G. Rubio-Bollinger. Elastic properties of freely suspended mos2 nanosheets. *Adv. Mater.*, 24:772–775, 2012.
  - [9] A. Dargys and J. Kundrotas. *Handbook on physical properties of Ge, Si, GaAs, InP*. Science and Encyclopedia Publishers, Vilnius, Lithuania, 1994.
  - [10] C.D. Dimitrakopoulos and D.J. Masearo. Organic thin-film transistors: A review of recent advances. *IBM Journal of Research and Development*, 45(1):11–27, Jan 2001.
  - [11] M. S. Dresselhaus and G. Dresselhaus. Intercalation compounds of graphite. *Advances in Physics*, 51(1):1–186, 2002.
  - [12] X. Du, I. Skachko, A. Barker, and E.Y. Andrei. Approaching ballistic transport in suspended graphene. *Nature Nanotech.*, 3:491–495, 2008.
  - [13] T.J. Echtermeyer, L. Britnell, P.K. Jasnós, A. Lombardo, R.V. Gorbachev, A.N. Grigorenko, A.K. Geim, A.C. Ferrari, and K.S. Novoselov. Strong plasmonic enhancement of photovoltage in graphene. *Nat. Commun.*, 2:458, 2011.
  - [14] R. Fivaz and E. Mooser. Mobility of charge carriers in semiconducting layer structures. *Phys. Rev.*, 163:743–755, Nov 1967.

- [15] E. Fortin and W.M. Sears. Photovoltaic effect and optical absorption in mos2. *Journal of Physics and Chemistry of Solids*, 43:881–884, 1982.
- [16] R. F. Frindt and A. D. Yoffe. Physical properties of layer structures: Optical properties and photoconductivity of thin crystals of molybdenum disulphide. *Proceedings of the Royal Society of London A: Mathematical, Physical and Engineering Sciences*, 273(1352):69–83, 1963.
- [17] F. R. Gamble and B. G. Silbernagel. Anisotropy of the proton spinlattice relaxation time in the superconducting intercalation complex tas2(nh3): Structural and bonding implications. *The Journal of Chemical Physics*, 63(6):2544–2552, 1975.
- [18] A.K. Geim and I.V. Grigorieva. van der waals heterostructures. *Nature*, 499:419–425, 2013.
- [19] James M. Gere and 1878–1972 Timoshenko, Stephen P. *Mechanics of materials*. Boston PWS Pub Co, 4th ed edition, 1997. Includes indexes.
- [20] A. K. Giem and K. S. Novoselov. The rise of graphene. *Nature Materials*, 6:183–191, 2007.
- [21] E. Gourmelon, O. Lignier, H. Hadouda, G. Couturier, J.C. Bernede, J. Teddb, J. Pouzeta, and J. Salardenneb. Ms2 (m = mo, w) photosensitive thin films for solar cells. *Solar Energy Materials and Solar Cells*, 46:115–121, 1997.
- [22] P. Hohenberg and W. Kohn. Inhomogeneous Electron Gas. *Physical Review*, 136:864–871, nov 1964.
- [23] Sumio Iijima. Helical microtubules of graphitic carbon. *Nature*, 354:56–58, 1991.
- [24] D. Kahng and M. Atalla. Us patents 3206670 and 3102230, 1960.
- [25] K. Kam and B.A. Parkinson. Detailed photocurrent spectroscopy of the semiconducting group-vi transition-metal dichalcogenides. *J. Phys. Chem.*, 86:463–467, 1982.
- [26] H. W. Kroto, J. R. Heath, S. C. O’Brien, R. F. Curl, and R. E. Smalley. C60: Buckminsterfullerene. *Nature*, 318:162–163, 1985.
- [27] Murong Lang, Liang He, Faxian Xiu, Xinxin Yu, Jianshi Tang, Yong Wang, Xufeng Kou, Wanjun Jiang, Alexei V. Fedorov, and Kang L. Wang. Revelation of topological surface states in bi2se3 thin films by in situ al passivation. *ACS Nano*, 6(1):295–302, 2012. PMID: 22147687.
- [28] Dominik Lembke, Simone Bertolazzi, and Andras Kis. Single-layer mos2 electronics. *Accounts of Chemical Research*, 48(1):100–110, 2015. PMID: 25555202.
- [29] Hai Li, Jumiati Wu, Zongyou Yin, and Hua Zhang. Preparation and applications of mechanically exfoliated single-layer and multilayer mos2 and wse2 nanosheets. *Accounts of Chemical Research*, 47(4):1067–1075, 2014. PMID: 24697842.
- [30] T. Li and G. Galli. Electronic properteis of mos2 nanoparticles. *J. Phys. Chem. C*, 111:3042–3047, 2007.
- [31] J.E. Lilienfeld. Us patent 174175, 1925.
- [32] Kin Fai Mak, Changgu Lee, James Hone, Jie Shan, and Tony F. Heinz. Atomically thin mos2: A new direct-gap semiconductor. *Phys. Rev. Lett.*, 105:136805, Sep 2010.
- [33] Ruben Mas-Balleste, Cristina Gomez-Navarro, Julio Gomez-Herrero, and Felix Zamora. 2d materials: to graphene and beyond. *Nanoscale*, 3:20–30, 2011.
- [34] L. F. Mattheiss. Band structures of transition-metal-dichalcogenide layer compounds. *Phys. Rev. B*, 8:3719–3740, Oct 1973.
- [35] G. Moore. Cramming more components onto integrated circuits. *Electronics*, 38(8), 1965.
- [36] K. S. Novoselov, A. K. Geim, S. V. Morozov, D. Jiang, Y. Zhang, S. V. Dubonos, I. V. Grigorieva, and A. A. Firsov. Electric field effect in atomically thin carbon films. *Science*, 306(5696):666–669, 2004.
- [37] K. S. Novoselov, D. Jiang, F. Schedin, T. J. Booth, V. V. Khotkevich, S. V. Morozov, and A. K. Geim. Two-dimensional atomic crystals. *Proceedings of the National Academy of Sciences of the United States of America*, 102(30):10451–10453, 2005.
- [38] K.S. Novoselov, A. K. Geim, S.V. Morozov, D. Jiang, M.I. Katsnelson, I.V. Grigorieva, S.V. Dubonos, and A.A. Firsov. Two-dimensional gas of massless dirac fermions in graphene. *Nature*, 438:197–200, 2005.
- [39] K.S. Novoselov and A.K. Geim. The rise of graphene. *Nature Materials*, 6:183–191, 2007.
- [40] B. Radisavljevic, A. Radenovic, J. Brivio, V. Giacometti, and A. Kis. Single-layer mos2 transistors. *Nat. Nano.*, 6:147–150, 2011.
- [41] B K Ridley. The electron-phonon interaction in quasi-two-dimensional semiconductor quantum-well structures. *Journal of Physics C: Solid State Physics*, 15(28):5899, 1982.
- [42] Max Schulz. The end of the road for silicon? *Nature*, 399:729–730, 1999.
- [43] O. A. Shenderova, V. V. Zhirnov, and D. W. Brenner. Carbon nanostructures. *Critical Reviews in Solid State and Materials Sciences*, 27(3-4):227–356, 2002.
- [44] M. Spittel and T. Spittel. 4.2 young’s modulus of steel. In H. Warlimont, editor, *Metal Forming Data of Ferrous Alloys - deformation behaviour*, volume 2C1 of *Landolt-Brnstein - Group VIII Advanced Materials and Technologies*, pages 85–88. Springer Berlin Heidelberg, 2009.
- [45] Andrea Splendiani, Liang Sun, Yuanbo Zhang, Tianshu Li, Jonghwan Kim, Chi-Yung Chim, Giulia Galli, and Feng Wang. Emerging photoluminescence in monolayer mos2. *Nano Letters*, 10(4):1271–1275, 2010. PMID: 20229981.
- [46] Kyozauro Takeda and Kenji Shiraishi. Theoretical possibility of stage corrugation in si and ge analogs of graphite. *Phys. Rev. B*, 50:14916–14922, Nov 1994.
- [47] P. R. Wallace. The band theory of graphite. *Phys. Rev.*, 71:622–634, May 1947.
- [48] Feng Wang, Yuanbo Zhang, Chuanshan Tian, Caglar Girit, Alex Zettl, Michael Crommie, and Y. Ron Shen. Gate-variable optical transitions in graphene. *Science*, 320(5873):206–209, 2008.
- [49] Qing Hua Wang, Kourosh Kalantar-Zadeh, Andras Kis, Jonathan N. Coleman, and Michael S. Strano. Electronics and optoelectronics of two-dimensional transition metal dichalcogenides. *Nature Nanotechnology*, 7:699–712, 2012.
- [50] J. R. Williams, L. DiCarlo, and C. M. Marcus. Quantum hall effect in a gate-controlled p-n junction of graphene. *Science*, 317(5838):638–641, 2007.
- [51] J.A. Wilson and A.D. Yoffe. The transition metal dichalcogenides discussion and interpretation of the observed optical, electrical and structural properties. *Advances in Physics*, 18(73):193–335, 1969.
- [52] F.N. Xia, T. Mueller, Y.M. Lin, A. Valdes-Garcia, and P. Avouris. Ultrafast graphene photodetector. *Nat. Nanotechnol.*, 4:839–843, 2009.
- [53] Wenjie Xie, Xinfeng Tang, Yonggao Yan, Qingjie Zhang, and Terry M. Tritt. Unique nanostructures and enhanced thermoelectric performance of melt-spun bisbte alloys.

- Applied Physics Letters*, 94(10):-, 2009.
- [54] Mingsheng Xu, Tao Liang, Minmin Shi, and Hongzheng Chen. Graphene-like two-dimensional materials. *Chemical Reviews*, 113(5):3766–3798, 2013. PMID: 23286380.
  - [55] Hong Bin Zhang, Hai Lin Yu, Ding Hua Bao, Shu Wei Li, Cheng Xin Wang, and Guo Wei Yang. Magnetoresistance switch effect of a sn-doped bi<sub>2</sub>te<sub>3</sub> topological insulator. *Advanced Materials*, 24(1):132–136, 2012.
  - [56] L. Zhang, Y. Zhang, J. Camacho, M. Khodas, and I. Zaliznyak. The experimental observation of quantum hall effect of l=3 chiral quasiparticles in trilayer graphene. *Nat. Phys.*, 7:953–957, 2011.