AWS A/SFA 5.15, Est.

# ROYAL CAST (Est.)

#### **Applications**

It is used for welding Gears, Cracked motor or generators housing. It is used for repair works of cast iron, carbon steels, mild steels parts.


#### **Characteristics on Usage**

A medium heavy coated low hydrogen type electrode for all types of cast iron where machinability is not essential for welding basis on cast iron. It gives high strength where a strong and rigid joints is required in between two cast iron parts. Suitable for joining of cast iron to carbon and low alloy steels.

## **Notes On Usage**

- 1) Preheat temprature vary in accordance with shape and size of base metal
- 2) Preheat at 200-350 °C gradual Cooling recommended after welding.

## **Welding Positions**



#### **Packing and Welding Current**

| SIZE ( mm ) | KG PER<br>PACKET | KG PER<br>CARTON | Current<br>(Amps) | In Amps   |
|-------------|------------------|------------------|-------------------|-----------|
| 2.50 x 350  | 5                | 20               | AC / DC (+)       | 60 - 80   |
| 3.15 x 350  | 5                | 20               |                   | 100 – 140 |
| 4.00 x 450  | 5                | 20               |                   | 140 – 180 |
| 5.00 x 450  | 5                | 20               |                   | 180 – 230 |
| 5.00 X 450  | ວ                | 20               |                   | 100 – 230 |

# **Packing**

Vaccum packing