

Thickness Survey - D-1201

Unit: Unit 12 - Kerosene Merox

Survey date: 18-Feb-2027

Method: ultrasonic, Olympus 38DL Plus, 5 MHz twin crystal

Location	Measured (mm)
Shell Course 1	10.40
Shell Course 2	10.85
Head - top	11.40

Governing (thinnest) location is Shell Course 1 at 10.40 mm.

Minimum required thickness (t-min) is 8.00 mm.

Only one survey exists for this vessel. No corrosion rate can be derived from a single survey.

Inspector: V. Menon, API 510 #52318