Technical data sheet

MULTIline FLEX

Flexible hose liner for the trenchless rehabilitation of drains and house connections.

Product features	
Product name	Lateral Repairs MULTIline FLEX 3.0mm
Product code	FLEX
Length	50 m; 100 m / 164 feet; 328 feet
Diameter	30, 40, 50, 60, 65, 70, 75, 80, 100, 125, 150, 200, 225, 250.
Wall thickness	3,00* mm / 0,12* inch
Liner undersized	5 %, 9 %, 18 %
Heat resistance	Max. 50 °C / 122 °F
Negotiating bends	90°

Material features	
Material	PES-Plush (knitted) and brushed with one sided PU-Coating.
Textile	Polyester
Textile weight	450* g/m²
Coating	One side PU
Coating weight	250* g/m²
Colour / coating	White / Transparent
Water penetration	≤ 500 Mbar / ≤ 7,25 psi
Storage	Protected from light, dry

Features			Length		Resin	Pressure		Roller
Dimension	Flat (mm)	Bend	L + *	L + **	kg / m	Inversion (bar)	3D (bar)	Roller gap
DN 30-50	~42	90°	5 cm	5 %	~0.32	0,55-0,70	0,75-0,95	7mm
DN 50-70	~71	90°	5 cm	5 %	~0.51	0,50-0,65	0,60-0,95	7mm
DN 70-100	~100	90°	5 cm	5 %	~0.73	0,50-0,60	0,55-0,90	7mm
DN 100-150	~143	90°	5 cm	5 %	~1.01	0,45-0,55	0,50-0,85	7mm
DN 125-175	~178	90°	5 cm	5 %	~1.24	0,40-0,50	0,45-0,70	7mm
DN 150-200	~214	90°	5 cm	5 %	~1.58	0,35-0,45	0,40-0,65	7mm
DN 200-250	~285	90°	5 cm	5 %	~2.08	0,30-0,40	0,35-0,55	7mm
DN 225-275	~320	90°	5 cm	5 %	~2.31	0,30-0,35	0,35-0,45	7mm
DN 250-300	~357	90°	5 cm	5 %	~2.58	0,25-0,30	0,35-0,40	7mm

Additional length *per bend >45° **Approx 5 % loss in length for every 25 % change in dimension

Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.

iPhone · App Store   Android · Google Play

Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06

www.lateralrepairs.com info@lateralrepairs.com +370 698 76 581 Paberžių g. 5, Tauragė, Lithuania, LT-72328