

Document Version: V2026.1

Date of first issue: 2021.01.21

Date viewed: 2026.05.01

MULTIline PRO 4.0 mm

Product name	Lateral Repairs MULTIline PRO 4.0 mm
Product code	PRO

Material composition	
	Multi (knitted) fleece with one sided TPU.

Supply data	
Pipe diameter	70, 80, 100, 125, 150, 200, 225, 250, 300. Other dimensions available on request
Liner undersized	13 %
Liner lengths	50 m; 100 m / 164 feet; 328 feet Other lengths available on request

General data	
Type of fibers	Polyester
Coating	One side TPU
Basic color	White
Color coating	Transparent
Type of basic material	Multi-layer knitted fleece with TPU coating
Used seam (stitched) and seam sealing	Seam construction with PES-Yarn Seam sealed with TPU-Tape

Physical properties			
Weight	DIN EN 12127	g/m ²	550*
Weight of coating		g/m ²	150*
Thickness		mm inch	4,00* 0,16*
Water penetration resistance (20 °C / 68 °F)	ISO 811	mbar psi	≤ 550 ≤ 7,97

Document Version: V2026.1

Date of first issue: 2021.01.21

Date viewed: 2026.05.01

MULTiline PRO 4.0 mm

Handling parameter	
Heat resistance	Max. 70 °C / 158 °F
Negotiating bends up to	Max. 90°
Pinch roller gap (impregnation)	2 x Wall thickness + 2 mm
Additional lengths	5 %

The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher inversion and/or curing pressures and accept no liability.

* = Modal value (typical value)

Additional Information – please see “methods of application”.

* WE RECOMMEND STEAM CURING WITH A CALIBRATION HOSE.

Document Version: V2026.1
 Date of first issue: 2021.01.01
 Date viewed: 2026.05.01

MULTIline PRO 4.5 mm

Product name	Lateral Repairs MULTIline PRO 4.5 mm
Product code	PRO

Material composition	
	Multi knitted Fleece with One - Sided TPU Coating.

Supply data	
Pipe diameter	70, 80, 100, 125, 150, 200, 225, 250, 300. Other dimensions available on request
Liner undersized	13 %
Liner lengths	50 m; 100 m / 164 feet; 328 feet Other lengths available on request

General data	
Type of fibers	Polyester
Coating	One side TPU
Basic color	White
Color coating	Transparent
Type of basic material	Multi knitted Fleece with TPU Coating.
Used seam (stitched) and seam sealing	Seam construction with PES-Yarn Seam sealed with TPU-Tape

Physical properties			
Weight	DIN EN 12127	g/m ²	650*
Weight of coating		g/m ²	150*
Thickness		mm inch	4,50* 0,18*
Water penetration resistance (20 °C / 68 °F)	ISO 811	mbar psi	≤ 600 ≤ 8,70

Document Version: V2026.1
Date of first issue: 2021.01.01
Date viewed: 2026.05.01

MULTIline PRO 4.5 mm

Handling parameter	
Heat resistance	Max. 70 °C / 158 °F
Negotiating bends up to	Max. 90°
Pinch roller gap (impregnation)	2 x Wall thickness + 2 mm
Additional length	5%

The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher inversion and/or curing pressures and accept no liability.

* = Modal value (typical value)

Additional Information – please see “methods of application”.

* WE RECOMMEND STEAM CURING WITH A CALIBRATION HOSE.

Document Version: V2026.1
 Date of first issue: 2021.01.21
 Date viewed: 2026.05.01

MULTIline FLEX

Product name	Lateral Repairs MULTIline FLEX 3.0mm
Product code	FLEX

Material composition	
	PES-Plush (knitted) and brushed with one sided PU-Coating.

Supply data	
Pipe diameter	30, 40, 50, 60, 65, 70, 75, 80, 100, 125, 150, 200, 225, 250. Other dimensions available on request
Liner undersized	5 %, 9 %, 18 %
Liner lengths	50 m; 100 m / 164 feet; 328 feet Other lengths available on request

General data	
Type of fibers	Polyester
Coating	One side PU
Basic color	White
Color coating	Transparent
Type of basic material	PES-Plush (knitted)
Used seam (stitched) and seam sealing	Stitched seam with PES-Yarn Seam sealed with a PU-Tape

Physical properties			
Weight	DIN EN 12127	g/m ²	450*
Weight of coating		g/m ²	250*
Thickness	(Simulating 0.5 bar / 7.25 psi)	mm inch	3,00* 0,12*
Water penetration resistance (20 °C / 68 °F)	ISO 811	Mbar psi	≤ 500 ≤ 7,25

Document Version: V2026.1
Date of first issue: 2021.01.21
Date viewed: 2026.05.01

MULTIline FLEX

Handling parameter	
Heat resistance	Max. 50 °C / 122 °F
Negotiating bends up to	90°
Pinch roller gap (impregnation)	2 x Wall thickness + 2 mm
Additional lengths	5 %

The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher inversion and/or curing pressures and accept no liability.

* = Modal value (typical value)

Additional Information – please see “methods of application”.

* STEAM CURING IS ONLY POSSIBLE WITH A CALIBRATION HOSE.

Document Version: V2026.1
 Date of first issue: 2021.01.21
 Date viewed: 2026.05.01

MULTIline CORE

Product name	Lateral Repairs MULTIline CORE
Product code	CORE

Material composition	
	Multi-knitted fleece with one sided Polypropylene (PP) coating.

Supply data	
Pipe diameter	70, 80, 100, 125, 150, 200, 225, 250. Other dimensions available on request
Liner undersized	13 %
Liner lengths	50 m; 100 m / 164 feet; 328 feet Other lengths available on request

General data	
Type of fibers	Polyester
Coating	One side PP
Basic color	White
Color coating	Transparent
Type of basic material	Multi-layer knitted fleece with PP coating
Used seam (stitched) and seam sealing	Seam construction with PES-Yarn Seam sealed with PP seam tape

Physical properties			
Weight	DIN EN 12127	g/m ²	550*
Weight of coating		g/m ²	150*
Thickness		mm inch	4,00* 0,16*
Water penetration resistance (20 °C / 68 °F)	ISO 811	mbar psi	≤ 550 ≤ 7,97

Document Version: V2026.1
Date of first issue: 2021.01.21
Date viewed: 2026.05.01

MULTIline CORE

Handling parameter	
Heat resistance	Max. 85 °C / 167 °F
Negotiating bends up to	Max. 90°
Pinch roller gap (impregnation)	2 x Wall thickness + 2 mm
Additional lengths	5 %

The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher inversion and/or curing pressures and accept no liability.

* = Modal value (typical value)

Additional Information – please see “methods of application”.

Document Version: V2026.1
 Date of first issue: 2021.01.21
 Date viewed: 2026.05.01

MULTiline FORCE

Product name	Lateral Repairs MULTiline FORCE 3.0mm
Product code	FORCE

Material composition	
	Polyester needle-punched fleece liner with filament reinforcement and a polypropylene (PP) coating.

Supply data	
Pipe diameter	100 mm – 300 mm / 4 inch – 12 inch Other dimensions available on request
Liner undersized	10 %
Liner lengths	50 m; 100 m / 164 feet; 328 feet Other lengths available on request

General data	
Type of fibers	Polyester
Coating	PP
Basic color	White
Color coating	Milky white
Type of basic material	Needle-punched fleece with filament
Used seam (stitched) and seam sealing	Stitched seam with PES-thread Seam sealed with PP seam tape
	Welded or glued seam Seam coating with PP seam tape

Physical properties			
Weight		g/m ²	650
Weight of coating	[Tracking force 20cN/cm ² bearing area 25 cm ²]	g/m ²	300
Thickness		mm inch	3,00 0,12
Water penetration resistance	ISO 811	mbar	≥ 500

Document Version: V2026.1
Date of first issue: 2021.01.21
Date viewed: 2026.05.01

MULTIline FORCE

Handling parameter	
Heat resistance	Max. 100 °C / 212 °F
Negotiating bends up to	Max. 45°
Pinch roller gap (impregnation)	2 x Wall thickness + 2 mm
Additional lengths	2 %

The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher inversion and/or curing pressures and accept no liability.

Document Version: V2026.1
 Date of first issue: 2021.01.21
 Date viewed: 2026.05.01

MULTiline FORCE RF

Product name	Lateral Repairs MULTiline FORCE 4.5mm
Product code	FORCE

Material composition	
	Polyester needle-punched fleece liner with filament reinforcement and a polypropylene (PP) coating.

Supply data	
Pipe diameter	100 mm – 600 mm / 4 inch – 24 inch Other dimensions available on request
Liner undersized	10 %
Liner lengths	50 m; 100 m / 164 feet; 328 feet Other lengths available on request

General data	
Type of fibers	Polyester
Coating	PP
Basic color	White
Color coating	Milky white
Type of basic material	Needle-punched fleece with filament
Used seam (stitched) and seam sealing	Stitched seam with PES-thread Seam sealed with PP seam tape

Physical properties			
Weight		g/m ²	900
Weight of coating	[Tracking force 20cN/cm ² bearing area 25 cm ²]	g/m ²	300
Thickness		mm	4,50
		inch	0,18
Water penetration resistance	ISO 811	mbar	≥ 500

Document Version: V2026.1
Date of first issue: 2021.01.21
Date viewed: 2026.05.01

MULTIline FORCE RF

Handling parameter	
Heat resistance	Max. 100 °C / 212 °F
Negotiating bends up to	Max. 45°
Pinch roller gap (impregnation)	2 x Wall thickness + 2 mm
Additional length	2 %

The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher inversion and/or curing pressures and accept no liability.

Document Version: V2026.1
 Date of first issue: 2021.01.21
 Date viewed: 2026.05.01

MULTiline FORCE UV

Product name	Lateral Repairs MULTiline FORCE UV
Product code	FORCEUV

Material composition	
	Polyester needle-punched fleece liner with filament reinforcement and a thermoplastic polyurethane (TPU) coating.

Supply data	
Pipe diameter	100 mm – 600 mm / 4 inch – 24 inch Other dimensions available on request
Liner undersized	10 %
Liner lengths	50 m; 100 m / 164 feet; 328 feet Other lengths available on request

General data	
Type of fibers	Polyester
Coating	TPU
Basic color	White
Color coating	Transparent
Type of basic material	Needle-punched fleece with filament
Used seam (stitched) and seam sealing	Stitched seam with PES-thread Seam sealed with TPU seam tape

Physical properties			
Weight		g/m ²	500
Weight of coating	[Tracking force 20cN/cm ² bearing area 25 cm ²]	g/m ²	150
Thickness	± 3 %	mm inch	3,30 0,13
Water penetration resistance	ISO 811	mbar	≥ 500

Document Version: V2026.1
Date of first issue: 2021.01.21
Date viewed: 2026.05.01

MULTIline FORCE UV

Handling parameter	
Heat resistance	Max. 80 °C / 176 °F
Negotiating bends up to	Max. 45°
Pinch roller gap (impregnation)	2 x Wall thickness + 2 mm
Additional lengths	2 %

The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher inversion and/or curing pressures and accept no liability.