

## MULTIline PRO 4.5 mm



Hose liner for the trenchless inner lining of defective, leaking and statically impaired pipes.

| Product features  |                                            | Material features   |                                            |
|-------------------|--------------------------------------------|---------------------|--------------------------------------------|
| Product name      | Lateral Repairs MULTIline PRO 4.5 mm       | ≈ Material          | Multi (knitted) fleece with one sided TPU. |
| Product code      | PRO                                        | # Textile           | Polyester                                  |
| Length            | 50 m; 100 m / 164 feet; 328 feet           | ☞ Textile weight    | 550* g/m <sup>2</sup>                      |
| ⌀ Diameter        | 70, 80, 100, 125, 150, 200, 225, 250, 300. | 🌀 Coating           | One side TPU                               |
| Wall thickness    | 4,00* mm / 0,16* inch                      | ☞ Coating weight    | 150* g/m <sup>2</sup>                      |
| Liner undersized  | 13 %                                       | 🌈 Colour / coating  | White / Transparent                        |
| Heat resistance   | Max. 70 °C / 158 °F                        | 💧 Water penetration | ≤ 550 mbar / ≤ 7,97 psi                    |
| Negotiating bends | Max. 90°                                   | 📦 Storage           | Protected from light, dry                  |

| Features   |           |        | Length |         | Resin    | Pressure        |           | Roller     |
|------------|-----------|--------|--------|---------|----------|-----------------|-----------|------------|
| Dimension  | Flat (mm) | ↷ Bend | L +  * | L +  ** | 🌊 kg / m | Inversion (bar) | 3D (bar)  | Roller gap |
| DN 70-100  | ~95       | 90°    | 5 cm   | 5 %     | ~0.82    | 0.50-0.60       | 0.60-0.75 | 9mm        |
| DN 100-150 | ~136      | 90°    | 5 cm   | 5 %     | ~1.15    | 0.40-0.55       | 0.45-0.60 | 9mm        |
| DN 150-200 | ~205      | 90°    | 5 cm   | 5 %     | ~1.70    | 0.35-0.45       | 0.40-0.50 | 9mm        |
| DN 200-250 | ~273      | 90°    | 5 cm   | 5 %     | ~2.45    | 0.30-0.35       | 0.30-0.40 | 9mm        |
| DN 250-300 | ~341      | 90°    | 5 cm   | 5 %     | ~2.99    | 0.25-0.35       | 0.30-0.40 | 9mm        |

Additional length \*per bend >45° \*\*Approx 5 % loss in length for every 25 % change in dimension

### Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

### Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06



## MULTIline PRO 5.5 mm



Hose liner for the trenchless inner lining of defective, leaking and statically impaired pipes.

| Product features  |                                            | Material features   |                                                    |
|-------------------|--------------------------------------------|---------------------|----------------------------------------------------|
| Product name      | Lateral Repairs MULTIline PRO 5.5 mm       | ≈ Material          | Multi knitted Fleece with One - Sided TPU Coating. |
| Product code      | PRO                                        | # Textile           | Polyester                                          |
| Length            | 50 m; 100 m / 164 feet; 328 feet           | ☞ Textile weight    | 800* g/m <sup>2</sup>                              |
| ⌀ Diameter        | 70, 80, 100, 125, 150, 200, 225, 250, 300. | ☞ Coating           | One side TPU                                       |
| Wall thickness    | 5,50 mm / 0,22 inch                        | ☞ Coating weight    | 150* g/m <sup>2</sup>                              |
| Liner undersized  | 13 %                                       | ⊙ Colour / coating  | White / Transparent                                |
| Heat resistance   | Max. 70 °C / 158 °F                        | ⊙ Water penetration | ≤ 600 mbar / ≤ 8,70 psi                            |
| Negotiating bends | Max. 90°                                   | ⊙ Storage           | Protected from light, dry                          |

| Features   |           |        | Length |         | Resin    | Pressure        |           | Roller     |
|------------|-----------|--------|--------|---------|----------|-----------------|-----------|------------|
| Dimension  | Flat (mm) | ↷ Bend | L +  * | L +  ** | ⊙ kg / m | Inversion (bar) | 3D (bar)  | Roller gap |
| DN 70-100  | ~95       | 90°    | 5 cm   | 5 %     | ~0.95    | 0.55-0.65       | 0.60-0.75 | 12mm       |
| DN 100-150 | ~136      | 90°    | 5 cm   | 5 %     | ~1.32    | 0.40-0.60       | 0.40-0.65 | 12mm       |
| DN 150-200 | ~205      | 90°    | 5 cm   | 5 %     | ~1.88    | 0.40-0.50       | 0.40-0.55 | 12mm       |
| DN 200-250 | ~273      | 90°    | 5 cm   | 5 %     | ~2.65    | 0.30-0.40       | 0.30-0.45 | 12mm       |
| DN 250-300 | ~341      | 90°    | 5 cm   | 5 %     | ~3.25    | 0.25-0.35       | 0.35-0.45 | 12mm       |

Additional length \*per bend >45° \*\*Approx 5 % loss in length for every 25 % change in dimension

### Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

### Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06



# Technical data sheet

## MULTIline FLEX



Flexible hose liner for the trenchless rehabilitation of drains and house connections.

| Product features  |                                                               | Material features   |                                                            |
|-------------------|---------------------------------------------------------------|---------------------|------------------------------------------------------------|
| Product name      | Lateral Repairs MULTIline FLEX 3.0mm                          | ≈ Material          | PES-Plush (knitted) and brushed with one sided PU-Coating. |
| Product code      | FLEX                                                          | # Textile           | Polyester                                                  |
| Length            | 50 m; 100 m / 164 feet; 328 feet                              | ☐ Textile weight    | 450* g/m <sup>2</sup>                                      |
| ⌀ Diameter        | 30, 40, 50, 60, 65, 70, 75, 80, 100, 125, 150, 200, 225, 250. | 🔄 Coating           | One side PU                                                |
| Wall thickness    | 3,00* mm / 0,12* inch                                         | ☐ Coating weight    | 250* g/m <sup>2</sup>                                      |
| Liner undersized  | 5 %, 9 %, 18 %                                                | 🌈 Colour / coating  | White / Transparent                                        |
| Heat resistance   | Max. 50 °C / 122 °F                                           | 💧 Water penetration | ≤ 500 Mbar / ≤ 7,25 psi                                    |
| Negotiating bends | 90°                                                           | 📦 Storage           | Protected from light, dry                                  |

| Features   |           |        | Length |         | Resin    | Pressure        |           | Roller     |
|------------|-----------|--------|--------|---------|----------|-----------------|-----------|------------|
| Dimension  | Flat (mm) | ↷ Bend | L +  * | L +  ** | ⬆ kg / m | Inversion (bar) | 3D (bar)  | Roller gap |
| DN 30-50   | ~42       | 90°    | 5 cm   | 5 %     | ~0.32    | 0.55-0.70       | 0.75-0.95 | 7mm        |
| DN 50-70   | ~71       | 90°    | 5 cm   | 5 %     | ~0.51    | 0.50-0.65       | 0.60-0.95 | 7mm        |
| DN 70-100  | ~100      | 90°    | 5 cm   | 5 %     | ~0.73    | 0.50-0.60       | 0.55-0.90 | 7mm        |
| DN 100-150 | ~143      | 90°    | 5 cm   | 5 %     | ~1.01    | 0.45-0.55       | 0.50-0.85 | 7mm        |
| DN 125-175 | ~178      | 90°    | 5 cm   | 5 %     | ~1.24    | 0.40-0.50       | 0.45-0.70 | 7mm        |
| DN 150-200 | ~214      | 90°    | 5 cm   | 5 %     | ~1.58    | 0.35-0.45       | 0.40-0.65 | 7mm        |
| DN 200-250 | ~285      | 90°    | 5 cm   | 5 %     | ~2.08    | 0.30-0.40       | 0.35-0.55 | 7mm        |
| DN 225-275 | ~320      | 90°    | 5 cm   | 5 %     | ~2.31    | 0.30-0.35       | 0.35-0.45 | 7mm        |
| DN 250-300 | ~357      | 90°    | 5 cm   | 5 %     | ~2.58    | 0.25-0.30       | 0.35-0.40 | 7mm        |

Additional length \*per bend >45° \*\*Approx 5 % loss in length for every 25 % change in dimension

### Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

### Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06



# Technical data sheet

## MULTIline CORE



Multi-knitted hose liner for the trenchless inner lining of pipes.

| Product features  |                                       |
|-------------------|---------------------------------------|
| Product name      | Lateral Repairs MULTILine CORE        |
| Product code      | CORE                                  |
| Length            | 50 m; 100 m / 164 feet; 328 feet      |
| Diameter          | 70, 80, 100, 125, 150, 200, 225, 250. |
| Wall thickness    | 4,00* mm / 0,16* inch                 |
| Liner undersized  | 13 %                                  |
| Heat resistance   | Max. 85 °C / 167 °F                   |
| Negotiating bends | Max. 90°                              |

| Material features |                                                                 |
|-------------------|-----------------------------------------------------------------|
| Material          | Multi-knitted fleece with one sided Polypropylene (PP) coating. |
| Textile           | Polyester                                                       |
| Textile weight    | 550* g/m <sup>2</sup>                                           |
| Coating           | One side PP                                                     |
| Coating weight    | 300* g/m <sup>2</sup>                                           |
| Colour / coating  | White / Transparent                                             |
| Water penetration | ≤ 550 mbar / ≤ 7,97 psi                                         |
| Storage           | Protected from light, dry                                       |

| Features   |           |      | Length |         | Resin    | Pressure        |           | Roller     |
|------------|-----------|------|--------|---------|----------|-----------------|-----------|------------|
| Dimension  | Flat (mm) | Bend | L +  * | L +  ** | Ø kg / m | Inversion (bar) | 3D (bar)  | Roller gap |
| DN 70-100  | ~95       | 90°  | 5 cm   | 4 %     | ~0.94    | 0,50-0,60       | 0,60-0,75 | 8mm        |
| DN 100-150 | ~136      | 90°  | 5 cm   | 4 %     | ~1.25    | 0,40-0,55       | 0,45-0,60 | 8mm        |
| DN 150-200 | ~205      | 90°  | 5 cm   | 4 %     | ~1.90    | 0,35-0,45       | 0,40-0,50 | 8mm        |
| DN 200-250 | ~273      | 90°  | 5 cm   | 4 %     | ~2.60    | 0,30-0,35       | 0,30-0,40 | 8mm        |
| DN 250-300 | ~341      | 90°  | 5 cm   | 4 %     | ~3.10    | 0,25-0,35       | 0,30-0,40 | 8mm        |
| DN 300-350 | ~408      | 90°  | 5 cm   | 4 %     | ~3.80    | 0,20-0,30       | 0,25-0,35 | 8mm        |

Additional length \*per bend >90° \*\*Approx 4 % loss in length for every 25 % change in dimension

### Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

### Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06



## MULTiline FORCE



High-strength, reinforced hose liner for the structural rehabilitation of pipes.

| Product features  |                                       | Material features   |                                                                                                     |
|-------------------|---------------------------------------|---------------------|-----------------------------------------------------------------------------------------------------|
| Product name      | Lateral Repairs MULTiline FORCE 3.0mm | ≈ Material          | Polyester needle-punched fleece liner with filament reinforcement and a polypropylene (PP) coating. |
| Product code      | FORCE                                 | # Textile           | Polyester                                                                                           |
| Length            | 50 m; 100 m / 164 feet; 328 feet      | ☐ Textile weight    | 650 g/m <sup>2</sup>                                                                                |
| ⌀ Diameter        | 100 mm – 300 mm / 4 inch – 12 inch    | 🌀 Coating           | PP                                                                                                  |
| Wall thickness    | 3,00 mm / 0,12 inch                   | ☐ Coating weight    | 300 g/m <sup>2</sup>                                                                                |
| Liner undersized  | 10 %                                  | 🌈 Colour / coating  | White / Milky white                                                                                 |
| Heat resistance   | Max. 100 °C / 212 °F                  | 💧 Water penetration | ≥ 500 mbar                                                                                          |
| Negotiating bends | Max. 45°                              | 📦 Storage           | Protected from light, dry                                                                           |

| Features  |           |        | Length |        | Resin    | Pressure        |          | Roller     |
|-----------|-----------|--------|--------|--------|----------|-----------------|----------|------------|
| Dimension | Flat (mm) | ↷ Bend | L +  ° | L +  ° | Ø kg / m | Inversion (bar) | 3D (bar) | Roller gap |
| DN 100    | ~140      | 2 x 45 | ~3 cm  | –      | ~115     | 0,35-0,40       | –        | 8mm        |
| DN 125    | ~175      | 2 x 45 | ~3 cm  | –      | ~144     | 0,30-0,45       | –        | 8mm        |
| DN 150    | ~212      | 2 x 45 | ~3 cm  | –      | ~172     | 0,30-0,50       | –        | 8mm        |
| DN 200    | ~282      | 2 x 45 | ~3 cm  | –      | ~230     | 0,25-0,40       | –        | 8mm        |
| DN 225    | ~318      | 2 x 45 | ~3 cm  | –      | ~260     | 0,20-0,40       | –        | 8mm        |
| DN 250    | ~353      | 2 x 45 | ~3 cm  | –      | ~290     | 0,20-0,40       | –        | 8mm        |
| DN 300    | ~424      | 2 x 45 | ~3 cm  | –      | ~321     | 0,20-0,40       | –        | 8mm        |

Additional length \*per bend >45°

### Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

### Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06



## MULTiline FORCE RF



High-strength, reinforced hose liner for the structural rehabilitation of pipes.

| Product features  |                                       | Material features   |                                                                                                     |
|-------------------|---------------------------------------|---------------------|-----------------------------------------------------------------------------------------------------|
| Product name      | Lateral Repairs MULTiline FORCE 4.5mm | ≈ Material          | Polyester needle-punched fleece liner with filament reinforcement and a polypropylene (PP) coating. |
| Product code      | FORCE                                 | # Textile           | Polyester                                                                                           |
| Length            | 50 m; 100 m / 164 feet; 328 feet      | ☐ Textile weight    | 900 g/m <sup>2</sup>                                                                                |
| ⌀ Diameter        | 100 mm – 600 mm / 4 inch – 24 inch    | 🌀 Coating           | PP                                                                                                  |
| Wall thickness    | 4,50 mm / 0,18 inch                   | ☐ Coating weight    | 300 g/m <sup>2</sup>                                                                                |
| Liner undersized  | 10 %                                  | 🌈 Colour / coating  | White / Milky white                                                                                 |
| Heat resistance   | Max. 100 °C / 212 °F                  | 💧 Water penetration | ≥ 500 mbar                                                                                          |
| Negotiating bends | Max. 45°                              | 🗑 Storage           | Protected from light, dry                                                                           |

| Features  |           |        | Length |        | Resin    | Pressure        |          | Roller     |
|-----------|-----------|--------|--------|--------|----------|-----------------|----------|------------|
| Dimension | Flat (mm) | ↷ Bend | L +  ° | L +  ° | Ø kg / m | Inversion (bar) | 3D (bar) | Roller gap |
| DN 100    | ~140      | 2 x 45 | ~3 cm  | –      | ~1.60    | 0,35-0,40       | –        | 11mm       |
| DN 125    | ~175      | 2 x 45 | ~3 cm  | –      | ~2.00    | 0,30-0,45       | –        | 11mm       |
| DN 150    | ~212      | 2 x 45 | ~3 cm  | –      | ~2.41    | 0,30-0,50       | –        | 11mm       |
| DN 200    | ~282      | 2 x 45 | ~3 cm  | –      | ~3.21    | 0,25-0,40       | –        | 11mm       |
| DN 225    | ~318      | 2 x 45 | ~3 cm  | –      | ~3.61    | 0,20-0,40       | –        | 11mm       |
| DN 250    | ~353      | 2 x 45 | ~3 cm  | –      | ~4.01    | 0,20-0,40       | –        | 11mm       |
| DN 300    | ~424      | 2 x 45 | ~3 cm  | –      | ~4.81    | 0,20-0,40       | –        | 11mm       |

Additional length \*per bend >45°

### Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

### Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06



## MULTiline FORCE UV



High-strength, reinforced hose liner for the structural rehabilitation of pipes.

| Product features  |                                    | Material features   |                                                                                                                   |
|-------------------|------------------------------------|---------------------|-------------------------------------------------------------------------------------------------------------------|
| Product name      | Lateral Repairs MULTiline FORCE UV | ≈ Material          | Polyester needle-punched fleece liner with filament reinforcement and a thermoplastic polyurethane (TPU) coating. |
| Product code      | FORCEUV                            | # Textile           | Polyester                                                                                                         |
| Length            | 50 m; 100 m / 164 feet; 328 feet   | ☐ Textile weight    | 500 g/m <sup>2</sup>                                                                                              |
| ⌀ Diameter        | 100 mm – 600 mm / 4 inch – 24 inch | ◇ Coating           | TPU                                                                                                               |
| Wall thickness    | 3,30 mm / 0,13 inch                | ☐ Coating weight    | 150 g/m <sup>2</sup>                                                                                              |
| Liner undersized  | 10 %                               | ⊖ Colour / coating  | White / Transparent                                                                                               |
| Heat resistance   | Max. 80 °C / 176 °F                | ⊖ Water penetration | ≥ 500 mbar                                                                                                        |
| Negotiating bends | Max. 45°                           | ⊖ Storage           | Protected from light, dry                                                                                         |

| Features  |           |        | Length |         | Resin    | Pressure        |          | Roller     |
|-----------|-----------|--------|--------|---------|----------|-----------------|----------|------------|
| Dimension | Flat (mm) | ↻ Bend | L +  * | L +  ** | ⌀ kg / m | Inversion (bar) | 3D (bar) | Roller gap |
| DN 100    | ~140      | 2 x 45 | ~3 cm  | –       | ~ 1.15   | 0,35-0,40       | –        | 7mm        |
| DN 125    | ~175      | 2 x 45 | ~3 cm  | –       | ~1.44    | 0,30-0,45       | –        | 7mm        |
| DN 150    | ~212      | 2 x 45 | ~3 cm  | –       | ~1.72    | 0,30-0,50       | –        | 7mm        |
| DN 200    | ~282      | 2 x 45 | ~3 cm  | –       | ~2.30    | 0,25-0,40       | –        | 7mm        |
| DN 225    | ~318      | 2 x 45 | ~3 cm  | –       | ~2.60    | 0,20-0,40       | –        | 7mm        |
| DN 250    | ~353      | 2 x 45 | ~3 cm  | –       | ~2.90    | 0,20-0,40       | –        | 7mm        |
| DN 300    | ~424      | 2 x 45 | ~3 cm  | –       | ~3.21    | 0,20-0,40       | –        | 7mm        |

Additional length \*per bend >45° \*\*Approx 4 % loss in length for every 25 % change in dimension

### Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

### Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06

