

Calibration Hose **Stitched & Welded**



PVC-coated polyester fabric with an ultra-flexible, heat-welded, overlapped and stitched seam — suitable for use with most resin types (UV Vinyl Ester, Silicate, Epoxy).

Material & construction

≈ Material	Stitched & Welded HD — Orange
◇ Base fabric	PVC-coated polyester
# Seam	Heat-welded, overlapped and stitched seam (heavy duty).
🔗 Compatible resins	UV Vinyl Ester · Silicate · Epoxy
📏 Standard roll lengths	50 m, 100 m
☀️ Maximum working temperature	80 °C

Maximum recommended pressure

Pipe diameter (mm)	100	125	150	200	225	250	300
Maximum recommended pressure (Bar)	1.70	1.60	1.40	1.20	1.00	0.80	0.60

Recommended storage

☀️ Avoid extremes of temperature	- Freezing may cause the coating structure to degrade locally, especially areas where the coating is in tension or compression – at bends and edges, and immediately adjacent to seam welds. - Recommended storage temperature 5 °C – 35 °C. - Shelf life at this temperature: in excess of 1 year.
💧 Recommended humidity	- Very high relative humidity (especially at high temperature such as tropical countries) could affect the pigmentation of the hose. - Recommended storage humidity 25 % – 65 % rh. - Shelf life at 65 %, 35 °C: 1 year.
🚰 Avoid prolonged wet storage	- As with high humidity, the coating is more susceptible to degradation at higher temperatures, and even further susceptible if the pH of liquid in contact is significantly above or below 7. - Wet storage is not recommended.
🌞 Avoid sunlight / UV	Prolonged exposure to ultraviolet light can affect the pigmentation of the hose.

Recommended handling

Mechanical damage to be avoided. Ensure that the hose is not placed directly onto grit or gravel floor – sweep and cover the floor first. Handle the hose with care. Ensure personnel are instructed not to walk on the hose.

Further recommendations

- All hose supplied is recommended as single use only. Multiple use of the material is at customer risk.
- When in use, the hose is to be supported outside the pipe.
- Due to sizing requirements at manufacture, the customer must specify the intended use as calibration hose or pre-liner.

Notice

- The information in this data sheet corresponds to our knowledge and experience at present and is given without warranty; check the product's suitability for the intended application before use.
- All values are guideline figures determined under laboratory conditions and can differ on industrial job sites.

