

## Calibration Hose **Welded · Violet**



PVC-coated polyester fabric with an ultra-flexible, heat-welded, overlapped and taped seam — suitable for use with most resin types (UV Vinyl Ester, Silicate, Epoxy).

| Material & construction        |                                                      |
|--------------------------------|------------------------------------------------------|
| ≈ Material                     | Welded LD — Violet                                   |
| ◇ Base fabric                  | PVC-coated polyester                                 |
| # Seam                         | Heat-welded, overlapped and taped seam (light duty). |
| 🔗 Compatible resins            | UV Vinyl Ester · Silicate · Epoxy                    |
| 📏 Standard roll lengths        | 50 m, 100 m                                          |
| ☀️ Maximum working temperature | 50 °C                                                |

| Maximum recommended pressure       |      |      |      |      |      |      |      |      |      |
|------------------------------------|------|------|------|------|------|------|------|------|------|
| Pipe diameter (mm)                 | 50   | 70   | 100  | 125  | 150  | 200  | 225  | 250  | 300  |
| Maximum recommended pressure (Bar) | 0.80 | 0.68 | 0.55 | 0.51 | 0.47 | 0.45 | 0.44 | 0.42 | 0.40 |

| Recommended storage              |                                                                                                                                                                                                                                                                                                                                                                   |
|----------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| ☀️ Avoid extremes of temperature | <ul style="list-style-type: none"> <li>Freezing may cause the coating structure to degrade locally, especially areas where the coating is in tension or compression – at bends and edges, and immediately adjacent to seam welds.</li> <li>Recommended storage temperature 5 °C – 35 °C.</li> <li>Shelf life at this temperature: in excess of 1 year.</li> </ul> |
| 💧 Recommended humidity           | <ul style="list-style-type: none"> <li>Very high relative humidity (especially at high temperature such as tropical countries) could affect the pigmentation of the hose.</li> <li>Recommended storage humidity 25 % – 65 % rh.</li> <li>Shelf life at 65 %, 35 °C: 1 year.</li> </ul>                                                                            |
| 🚿 Avoid prolonged wet storage    | <ul style="list-style-type: none"> <li>As with high humidity, the coating is more susceptible to degradation at higher temperatures, and even further susceptible if the pH of liquid in contact is significantly above or below 7.</li> <li>Wet storage is not recommended.</li> </ul>                                                                           |
| 🌞 Avoid sunlight / UV            | <ul style="list-style-type: none"> <li>Prolonged exposure to ultraviolet light can affect the pigmentation of the hose.</li> </ul>                                                                                                                                                                                                                                |

### Recommended handling

**Mechanical damage to be avoided.** Ensure that the hose is not placed directly onto grit or gravel floor – sweep and cover the floor first. Handle the hose with care. Ensure personnel are instructed not to walk on the hose.

### Further recommendations

- All hose supplied is recommended as single use only. Multiple use of the material is at customer risk.
- When in use, the hose is to be supported outside the pipe.
- Due to sizing requirements at manufacture, the customer must specify the intended use as calibration hose or pre-liner.

### Notice

- The information in this data sheet corresponds to our knowledge and experience at present and is given without warranty; check the product's suitability for the intended application before use.
- All values are guideline figures determined under laboratory conditions and can differ on industrial job sites.

