

Lateral Repairs End Cap Glue

Technical data sheet

Product: A solvent borne, toluene free, nearly n-hexane free special contact adhesive for industrial and professional use.
Phase: Slightly yellowish liquid synthetic rubber solution.
Suitability: Flooring, shoe and leather industry, ship, boat and car chassis building. Very well suitable for joining of rubber, leather, gasket, floor and wall coverings, sheets, mouldings, metals, woodpiles and different linings and insulations.

Technical data

Application Temperature: + 10°C - + 40°C

Curing time: 5-15 minutes, depending on conditions.
Temperature resistance: - 40°C - +75°C. Heat resistance of dry adhesive seam approx. +75°C without hardener. Solution with LR1600 hardener 3-10%, heat resistance of dry seam approx. 80-90°C

Density: 0,83 g/ml
Dosage: approx.. 4m² /l
Open Time: 10-40 minutes

Using temperature: Lowest + 5°C
Storage stability: 12 months after date of production, stored in dry place. +5°C - + 25°C. Sprayability will suffer from longer storing.

Colour: Yellowish
Tools: Brush, roller or spray gun.
Packaging: Steel cans of 1, 3, 10, 20, 200 and 1000L

Operating directions: Conditions:

Surfaces have to be clean and dry, free from grease and dust. Surfaces can be coarse grinded. Apply adhesive with a brush or a roller thin and smooth layer to both surfaces. The adhesive can be diluted with acetone 5 to 20 % by using spraying gun system. Let the glue dry 15 to 40 minutes, depending on conditions. Put the surfaces tightly together, check carefully there is no air bubbles between the surfaces. Over dried surfaces can be reactivated with heat. If heated, press surfaces together when those are still warm. The Lateral Repairs End Cap Glue will hold immediately, but the full strength will develop in about two days. The adhesive is freeze resistance after dried.

Cleaning Cleaning of tools Environment

acetone
acetone
Adhesive waste has to be delivered to hazardous waste station . Empty cans can be recycled or delivered to waste station.

Warnings Safety Fire resistant Transport

Contains hydroactive solvents 15-50%, ethyl acetate 15-50%.
Harmful. Product health and safety data sheet must be read before use.
Highly flammable
ADR transportation class UN 1133 Adhesives containing a flammable liquid
3,1. Store in well closed cans in a cool and well ventilated storage. The directions for storing and transportation of flammable liquids will apply.



LATERAL REPAIRS
CIPP TECHNOLOGY SUPPLIES