

Document Version: V2026.1
Date of first issue: 2021.01.21
Date viewed: 2026.06.18

MULTiline FLEX

Product name	Lateral Repairs MULTiline FLEX 3.0mm
Product code	FLEX

Material composition
PES-Plush (knitted) and brushed with one sided PU-Coating.

Supply data	
Pipe diameter	30, 40, 50, 60, 65, 70, 75, 80, 100, 125, 150, 200, 225, 250. Other dimensions available on request
Liner undersized	5 %, 9 %, 18 %
Liner lengths	50 m; 100 m / 164 feet; 328 feet Other lengths available on request

General data	
Type of fibers	Polyester
Coating	One side PU
Basic color	White
Color coating	Transparent
Type of basic material	PES-Plush (knitted)
Used seam (stitched) and seam sealing	Stitched seam with PES-Yarn Seam sealed with a PU-Tape

Physical properties			
Weight	DIN EN 12127	g/m²	450*
Weight of coating		g/m²	250*
Thickness	(Simulating 0.5 bar / 7.25 psi)	mm inch	3,00* 0,12*
Water penetration resistance (20 °C / 68 °F)	ISO 811	Mbar psi	≤ 500 ≤ 7,25

Handling parameter	
Heat resistance	Max. 50 °C / 122 °F
Negotiating bends up to	90°
Pinch roller gap (impregnation)	2 x Wall thickness + 2 mm
Additional lengths	5 %

The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher inversion and/or curing pressures and accept no liability.

* = Modal value (typical value)

Additional Information – please see “methods of application”.

* STEAM CURING IS ONLY POSSIBLE WITH A CALIBRATION HOSE.