

Technical data sheet

End Cap Glue



A solvent-borne, toluene-free, nearly n-hexane-free special contact adhesive for industrial and professional use.

Suitability

Flooring, shoe and leather industry, ship, boat and car-chassis building. Very well suited for joining rubber, leather, gasket, floor and wall coverings, sheets, mouldings, metals, woodpiles and different linings and insulations.

Technical data		Handling & safety	
☀ Application temperature	+10 °C – +40 °C	≈ Phase	Slightly yellowish liquid synthetic rubber solution
⏰ Using temperature	min. +5 °C	🛠 Tools	Brush, roller or spray gun
☀ Temperature resistance	-40 °C – +75 °C *	📦 Packaging	Steel cans · 1, 3, 10, 20, 200, 1000 L
⏱ Curing time	5 – 15 min (depending on conditions)	🧼 Cleaning	Acetone (product and tools)
🕒 Open time	10 – 40 min	⚠ Environment	Hazardous-waste disposal; cans recyclable
📦 Density	0,83 g/ml	☀ Fire	Highly flammable
📏 Dosage	approx. 4 m ² / l	🚚 Transport	ADR UN 1133, class 3.1
🧴 Colour	Yellowish	⚠ Safety	Harmful — read the SDS before use
⏰ Storage stability	12 months · +5 – +25 °C, dry		

Operating directions

Surfaces must be clean, dry and free from grease and dust; they can be coarse-ground. Apply the adhesive in a thin, smooth layer to both surfaces with a brush or roller — for spray-gun systems it can be diluted with acetone 5–20 %. Let the glue dry 15–40 minutes depending on conditions, then press the surfaces tightly together, checking there are no air bubbles. Over-dried surfaces can be reactivated with heat; if heated, press together while still warm. The bond holds immediately, with full strength developing in about two days. The dried adhesive is freeze-resistant.

* Heat resistance of the dry seam approx. +75 °C without hardener; with LR1600 hardener (3–10 %), approx. 80–90 °C.

Notice

- Contains hydroactive solvents 15–50 %, ethyl acetate 15–50 %. Highly flammable — store in well-closed cans in a cool, well-ventilated place; the directions for storing and transporting flammable liquids apply.
- Harmful. The product health & safety data sheet (SDS) must be read before use.
- The information in this data sheet corresponds to our knowledge and experience at present and is non-binding; check the product's suitability for your application before use.

Issue: V2026.1 · 2026.06

