

## MULTIline FORCE



High-strength, reinforced hose liner for the structural rehabilitation of pipes.

| Product features  |                                       | Material features   |                                                                                                     |
|-------------------|---------------------------------------|---------------------|-----------------------------------------------------------------------------------------------------|
| Product name      | Lateral Repairs MULTIline FORCE 3.0mm | ≈ Material          | Polyester needle-punched fleece liner with filament reinforcement and a polypropylene (PP) coating. |
| Product code      | FORCE                                 | # Textile           | Polyester                                                                                           |
| Length            | 50 m; 100 m / 164 feet; 328 feet      | ☐ Textile weight    | 650 g/m <sup>2</sup>                                                                                |
| ⌀ Diameter        | 100 mm – 300 mm / 4 inch – 12 inch    | 🌀 Coating           | PP                                                                                                  |
| Wall thickness    | 3,00 mm / 0,12 inch                   | ☐ Coating weight    | 300 g/m <sup>2</sup>                                                                                |
| Liner undersized  | 10 %                                  | 🌈 Colour / coating  | White / Milky white                                                                                 |
| Heat resistance   | Max. 100 °C / 212 °F                  | 💧 Water penetration | ≥ 500 mbar                                                                                          |
| Negotiating bends | Max. 45°                              | 📦 Storage           | Protected from light, dry                                                                           |

| Features  |           |        | Length |        | Resin    | Pressure        |          | Roller     |
|-----------|-----------|--------|--------|--------|----------|-----------------|----------|------------|
| Dimension | Flat (mm) | ↷ Bend | L +  ° | L +  ° | Ø kg / m | Inversion (bar) | 3D (bar) | Roller gap |
| DN 100    | ~140      | 2 x 45 | ~3 cm  | –      | ~115     | 0,35-0,40       | –        | 8mm        |
| DN 125    | ~175      | 2 x 45 | ~3 cm  | –      | ~144     | 0,30-0,45       | –        | 8mm        |
| DN 150    | ~212      | 2 x 45 | ~3 cm  | –      | ~172     | 0,30-0,50       | –        | 8mm        |
| DN 200    | ~282      | 2 x 45 | ~3 cm  | –      | ~230     | 0,25-0,40       | –        | 8mm        |
| DN 225    | ~318      | 2 x 45 | ~3 cm  | –      | ~260     | 0,20-0,40       | –        | 8mm        |
| DN 250    | ~353      | 2 x 45 | ~3 cm  | –      | ~290     | 0,20-0,40       | –        | 8mm        |
| DN 300    | ~424      | 2 x 45 | ~3 cm  | –      | ~321     | 0,20-0,40       | –        | 8mm        |

Additional length \*per bend >45°

### Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

### Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06

