

Technical data sheet

MULTIline CORE



Multi-knitted hose liner for the trenchless inner lining of pipes.

Product features		Material features	
Product name	Lateral Repairs MULTIline CORE	≈ Material	Multi-knitted fleece with one sided Polypropylene (PP) coating.
Length	50 m; 100 m / 164 feet; 328 feet	# Textile	Polyester
Ø Diameter	70, 80, 100, 125, 150, 200, 225, 250.	☐ Textile weight	550* g/m ²
Wall thickness	4,00* mm / 0,16* inch	📦 Coating	One side PP
↔ Liner undersized	13 %	☐ Coating weight	150* g/m ²
☀ Heat resistance	Max. 85 °C / 167 °F	🌈 Colour / coating	White / Transparent
↪ Negotiating bends	Max. 90°	📦 Storage	Protected from light, dry

Features			Length		Resin	Pressure	
Dimension	Flat (cm)	↪ Bend	↪ L + bend (cm)	↪ L + length	📦 kg / m	Inversion (bar)	Curing (bar)
DN 70	on request	Max. 90°	on request	on request	on request	on request	on request
DN 80	on request	Max. 90°	on request	on request	on request	on request	on request
DN 100	on request	Max. 90°	on request	on request	on request	on request	on request
DN 125	on request	Max. 90°	on request	on request	on request	on request	on request
DN 150	on request	Max. 90°	on request	on request	on request	on request	on request
DN 200	on request	Max. 90°	on request	on request	on request	on request	on request
DN 225	on request	Max. 90°	on request	on request	on request	on request	on request
DN 250	on request	Max. 90°	on request	on request	on request	on request	on request

Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

For further information visit www.lateralrepairs.com · info@lateralrepairs.com

Issue: V2026.1 · 2026.06