

Technical data sheet

MULTIline FLEX



Flexible hose liner for the trenchless rehabilitation of drains and house connections.

Product features		Material features	
Product name	Lateral Repairs MULTIline FLEX 3.0mm	≈ Material	PES-Plush (knitted) and brushed with one sided PU-Coating.
≡ Length	50 m; 100 m / 164 feet; 328 feet	# Textile	Polyester
⊖ Diameter	30, 40, 50, 60, 65, 70, 75, 80, 100, 125, 150, 200, 225, 250.	⊞ Textile weight	450* g/m ²
⌖ Wall thickness	3,00* mm / 0,12* inch	⊞ Coating	One side PU
↔ Liner undersized	5 %, 9 %, 18 %	⊞ Coating weight	250* g/m ²
☀ Heat resistance	Max. 50 °C / 122 °F	⊞ Colour / coating	White / Transparent
↪ Negotiating bends	90°	⊞ Storage	Protected from light, dry

Features			Length		Resin	Pressure	
Dimension	Flat (cm)	↪ Bend	↪ L + bend (cm)	≡ L + length	⊞ kg / m	Inversion (bar)	Curing (bar)
DN 50 → DN 50	on request	90°	on request	-6 cm/m	on request	0.7	on request
DN 50 → DN 70	on request	90°	on request	13 cm/m	on request	0.9	on request
DN 70 → DN 70	on request	90°	on request	4 cm/m	on request	0.5	on request
DN 70 → DN 100	on request	90°	on request	15 cm/m	on request	1.2	on request
DN 100 → DN 100	on request	90°	on request	2 cm/m	on request	0.3	on request
DN 100 → DN 125	on request	90°	on request	10 cm/m	on request	0.5	on request
DN 100 → DN 150	on request	90°	on request	20 cm/m	on request	1.0	on request
DN 125 → DN 125	on request	90°	on request	-5 cm/m	on request	0.4	on request
DN 125 → DN 150	on request	90°	on request	9 cm/m	on request	0.55	on request
DN 150 → DN 150	on request	90°	on request	0 cm/m	on request	0.1	on request
DN 150 → DN 200	on request	90°	on request	15 cm/m	on request	0.55	on request
DN 200 → DN 200	on request	90°	on request	-1 cm/m	on request	0.2	on request
DN 200 → DN 225	on request	90°	on request	8 cm/m	on request	0.35	on request
DN 200 → DN 250	on request	90°	on request	11 cm/m	on request	0.4	on request
DN 225 → DN 225	on request	90°	on request	0 cm/m	on request	0.2	on request
DN 225 → DN 250	on request	90°	on request	2 cm/m	on request	0.3	on request

Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.