

# Technical data sheet

## MULTiline FORCE RF



High-strength, reinforced hose liner for the structural rehabilitation of pipes.

| Product features    |                                       | Material features  |                                                                                                     |
|---------------------|---------------------------------------|--------------------|-----------------------------------------------------------------------------------------------------|
| Product name        | Lateral Repairs MULTiline FORCE 4.5mm | ≈ Material         | Polyester needle-punched fleece liner with filament reinforcement and a polypropylene (PP) coating. |
| 📏 Length            | 50 m; 100 m / 164 feet; 328 feet      | # Textile          | Polyester                                                                                           |
| ⌀ Diameter          | 100 mm – 600 mm / 4 inch – 24 inch    | 📦 Textile weight   | 900 g/m <sup>2</sup>                                                                                |
| 📏 Wall thickness    | 4,50 mm / 0,18 inch                   | 👉 Coating          | PP                                                                                                  |
| ↔ Liner undersized  | 10 %                                  | 📦 Coating weight   | 300 g/m <sup>2</sup>                                                                                |
| ☀ Heat resistance   | Max. 100 °C / 212 °F                  | 🎨 Colour / coating | White / Milky white                                                                                 |
| ↪ Negotiating bends | Max. 45°                              | 📦 Storage          | Protected from light, dry                                                                           |

| Features                           |            |          | Length          |              | Resin      | Pressure        |              |
|------------------------------------|------------|----------|-----------------|--------------|------------|-----------------|--------------|
| Dimension                          | Flat (cm)  | ↪ Bend   | ↪ L + bend (cm) | ⇄ L + length | ⬆ kg / m   | Inversion (bar) | Curing (bar) |
| 100 mm – 600 mm / 4 inch – 24 inch | on request | Max. 45° | on request      | on request   | on request | on request      | on request   |

### Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

### Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

For further information visit [www.lateralrepairs.com](http://www.lateralrepairs.com) · [info@lateralrepairs.com](mailto:info@lateralrepairs.com)

Issue: V2026.1 · 2026.06