

MULTIline PRO 4.5 mm



Hose liner for the trenchless inner lining of defective, leaking and statically impaired pipes.

Product features		Material features	
Product name	Lateral Repairs MULTIline PRO 4.5 mm	≈ Material	Multi (knitted) fleece with one sided TPU.
Product code	PRO	# Textile	Polyester
Length	50 m; 100 m / 164 feet; 328 feet	☞ Textile weight	550* g/m ²
⌀ Diameter	70, 80, 100, 125, 150, 200, 225, 250, 300.	☞ Coating	One side TPU
Wall thickness	4,50* mm / 0,18* inch	☞ Coating weight	150* g/m ²
Liner undersized	13 %	⊙ Colour / coating	White / Transparent
Heat resistance	Max. 70 °C / 158 °F	⊙ Water penetration	≤ 550 mbar / ≤ 7,97 psi
Negotiating bends	Max. 90°	⊙ Storage	Protected from light, dry

Features			Length		Resin	Pressure		Roller
Dimension	Flat (mm)	↷ Bend	L + *	L + **	⊙ kg / m	Inversion (bar)	3D (bar)	Roller gap
DN 70-100	~95	90°	5 cm	5 %	~0.82	0.50-0.60	0.60-0.75	9mm
DN 100-150	~136	90°	5 cm	5 %	~1.15	0.40-0.55	0.45-0.60	9mm
DN 150-200	~205	90°	5 cm	5 %	~1.70	0.35-0.45	0.40-0.50	9mm
DN 200-250	~273	90°	5 cm	5 %	~2.45	0.30-0.35	0.30-0.40	9mm
DN 250-300	~341	90°	5 cm	5 %	~2.99	0.25-0.35	0.30-0.40	9mm

Additional length *per bend >45° **Approx 5 % loss in length for every 25 % change in dimension

Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06



MULTIline PRO 5.5 mm



Hose liner for the trenchless inner lining of defective, leaking and statically impaired pipes.

Product features		Material features	
Product name	Lateral Repairs MULTIline PRO 5.5 mm	≈ Material	Multi knitted Fleece with One - Sided TPU Coating.
Product code	PRO	# Textile	Polyester
Length	50 m; 100 m / 164 feet; 328 feet	☞ Textile weight	800* g/m ²
⌀ Diameter	70, 80, 100, 125, 150, 200, 225, 250, 300.	☞ Coating	One side TPU
Wall thickness	5,50 mm / 0,22 inch	☞ Coating weight	150* g/m ²
Liner undersized	13 %	⊖ Colour / coating	White / Transparent
Heat resistance	Max. 70 °C / 158 °F	⊖ Water penetration	≤ 600 mbar / ≤ 8,70 psi
Negotiating bends	Max. 90°	📦 Storage	Protected from light, dry

Features			Length		Resin	Pressure		Roller
Dimension	Flat (mm)	↷ Bend	L + *	L + **	⊖ kg / m	Inversion (bar)	3D (bar)	Roller gap
DN 70-100	~95	90°	5 cm	5 %	~0.95	0.55-0.65	0.60-0.75	12mm
DN 100-150	~136	90°	5 cm	5 %	~1.32	0.40-0.60	0.40-0.65	12mm
DN 150-200	~205	90°	5 cm	5 %	~1.88	0.40-0.50	0.40-0.55	12mm
DN 200-250	~273	90°	5 cm	5 %	~2.65	0.30-0.40	0.30-0.45	12mm
DN 250-300	~341	90°	5 cm	5 %	~3.25	0.25-0.35	0.35-0.45	12mm

Additional length *per bend >45° **Approx 5 % loss in length for every 25 % change in dimension

Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06



Technical data sheet

MULTIline FLEX



Flexible hose liner for the trenchless rehabilitation of drains and house connections.

Product features		Material features	
Product name	Lateral Repairs MULTIline FLEX 3.0mm	≈ Material	PES-Plush (knitted) and brushed with one sided PU-Coating.
Product code	FLEX	# Textile	Polyester
Length	50 m; 100 m / 164 feet; 328 feet	☞ Textile weight	450* g/m ²
⌀ Diameter	30, 40, 50, 60, 65, 70, 75, 80, 100, 125, 150, 200, 225, 250.	🌀 Coating	One side PU
Wall thickness	3,50* mm / 0,14* inch	☞ Coating weight	250* g/m ²
Liner undersized	5 %, 9 %, 18 %	🌈 Colour / coating	White / Transparent
Heat resistance	Max. 50 °C / 122 °F	💧 Water penetration	≤ 500 Mbar / ≤ 7,25 psi
Negotiating bends	90°	📦 Storage	Protected from light, dry

Features			Length		Resin	Pressure		Roller
Dimension	Flat (mm)	↷ Bend	L + *	L + **	⬆ kg / m	Inversion (bar)	3D (bar)	Roller gap
DN 30-50	~42	90°	5 cm	5 %	~0.32	0.55-0.70	0.75-0.95	7mm
DN 50-70	~71	90°	5 cm	5 %	~0.51	0.50-0.65	0.60-0.95	7mm
DN 70-100	~100	90°	5 cm	5 %	~0.73	0.50-0.60	0.55-0.90	7mm
DN 100-150	~143	90°	5 cm	5 %	~1.01	0.45-0.55	0.50-0.85	7mm
DN 125-175	~178	90°	5 cm	5 %	~1.24	0.40-0.50	0.45-0.70	7mm
DN 150-200	~214	90°	5 cm	5 %	~1.58	0.35-0.45	0.40-0.65	7mm
DN 200-250	~285	90°	5 cm	5 %	~2.08	0.30-0.40	0.35-0.55	7mm
DN 225-275	~320	90°	5 cm	5 %	~2.31	0.30-0.35	0.35-0.45	7mm
DN 250-300	~357	90°	5 cm	5 %	~2.58	0.25-0.30	0.35-0.40	7mm

Additional length *per bend >45° **Approx 5 % loss in length for every 25 % change in dimension

Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06



MULTIline CORE



Multi-knitted hose liner for the trenchless inner lining of pipes.

Product features	
Product name	Lateral Repairs MULTLine CORE
Product code	CORE
Length	50 m; 100 m / 164 feet; 328 feet
Diameter	70, 80, 100, 125, 150, 200, 225, 250.
Wall thickness	4,50* mm / 0,18* inch
Liner undersized	13 %
Heat resistance	Max. 85 °C / 167 °F
Negotiating bends	Max. 90°

Material features	
Material	Multi-knitted fleece with one sided Polypropylene (PP) coating.
Textile	Polyester
Textile weight	550* g/m ²
Coating	One side PP
Coating weight	300* g/m ²
Colour / coating	White / Transparent
Water penetration	≤ 550 mbar / ≤ 7,97 psi
Storage	Protected from light, dry

Features			Length		Resin	Pressure		Roller
Dimension	Flat (mm)	Bend	L + *	L + **	kg / m	Inversion (bar)	3D (bar)	Roller gap
DN 70-100	~95	90°	5 cm	4 %	~0.94	0,50-0,60	0,60-0,75	8mm
DN 100-150	~136	90°	5 cm	4 %	~1.25	0,40-0,55	0,45-0,60	8mm
DN 150-200	~205	90°	5 cm	4 %	~1.90	0,35-0,45	0,40-0,50	8mm
DN 200-250	~273	90°	5 cm	4 %	~2.60	0,30-0,35	0,30-0,40	8mm
DN 250-300	~341	90°	5 cm	4 %	~3.10	0,25-0,35	0,30-0,40	8mm
DN 300-350	~408	90°	5 cm	4 %	~3.80	0,20-0,30	0,25-0,35	8mm

Additional length *per bend >90° **Approx 4 % loss in length for every 25 % change in dimension

Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06



MULTIline FORCE



High-strength, reinforced hose liner for the structural rehabilitation of pipes.

Product features		Material features	
Product name	Lateral Repairs MULTIline FORCE 3.0mm	≈ Material	Polyester needle-punched fleece liner with filament reinforcement and a polypropylene (PP) coating.
Product code	FORCE	# Textile	Polyester
Length	50 m; 100 m / 164 feet; 328 feet	☐ Textile weight	650 g/m ²
⌀ Diameter	100 mm – 300 mm / 4 inch – 12 inch	🌀 Coating	PP
Wall thickness	3,00 mm / 0,12 inch	☐ Coating weight	300 g/m ²
Liner undersized	10 %	🌈 Colour / coating	White / Milky white
Heat resistance	Max. 100 °C / 212 °F	💧 Water penetration	≥ 500 mbar
Negotiating bends	Max. 45°	📦 Storage	Protected from light, dry

Features			Length		Resin	Pressure		Roller
Dimension	Flat (mm)	↷ Bend	L + °	L + °	Ø kg / m	Inversion (bar)	3D (bar)	Roller gap
DN 100	~140	2 x 45	~3 cm	–	~115	0,35-0,40	–	8mm
DN 125	~175	2 x 45	~3 cm	–	~144	0,30-0,45	–	8mm
DN 150	~212	2 x 45	~3 cm	–	~172	0,30-0,50	–	8mm
DN 200	~282	2 x 45	~3 cm	–	~230	0,25-0,40	–	8mm
DN 225	~318	2 x 45	~3 cm	–	~260	0,20-0,40	–	8mm
DN 250	~353	2 x 45	~3 cm	–	~290	0,20-0,40	–	8mm
DN 300	~424	2 x 45	~3 cm	–	~321	0,20-0,40	–	8mm

Additional length *per bend >45°

Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06



MULTIline FORCE RF



High-strength, reinforced hose liner for the structural rehabilitation of pipes.

Product features		Material features	
Product name	Lateral Repairs MULTIline FORCE 4.5mm	≈ Material	Polyester needle-punched fleece liner with filament reinforcement and a polypropylene (PP) coating.
Product code	FORCE	# Textile	Polyester
Length	50 m; 100 m / 164 feet; 328 feet	☐ Textile weight	900 g/m ²
⌀ Diameter	100 mm – 600 mm / 4 inch – 24 inch	🌀 Coating	PP
Wall thickness	4,50 mm / 0,18 inch	☐ Coating weight	300 g/m ²
Liner undersized	10 %	🌈 Colour / coating	White / Milky white
Heat resistance	Max. 100 °C / 212 °F	💧 Water penetration	≥ 500 mbar
Negotiating bends	Max. 45°	📦 Storage	Protected from light, dry

Features			Length		Resin	Pressure		Roller
Dimension	Flat (mm)	↷ Bend	L + °	L + °	Ø kg / m	Inversion (bar)	3D (bar)	Roller gap
DN 100	~140	2 x 45	~3 cm	–	~1.60	0,35-0,40	–	11mm
DN 125	~175	2 x 45	~3 cm	–	~2.00	0,30-0,45	–	11mm
DN 150	~212	2 x 45	~3 cm	–	~2.41	0,30-0,50	–	11mm
DN 200	~282	2 x 45	~3 cm	–	~3.21	0,25-0,40	–	11mm
DN 225	~318	2 x 45	~3 cm	–	~3.61	0,20-0,40	–	11mm
DN 250	~353	2 x 45	~3 cm	–	~4.01	0,20-0,40	–	11mm
DN 300	~424	2 x 45	~3 cm	–	~4.81	0,20-0,40	–	11mm

Additional length *per bend >45°

Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06



MULTiline FORCE UV



High-strength, reinforced hose liner for the structural rehabilitation of pipes.

Product features		Material features	
Product name	Lateral Repairs MULTiline FORCE UV	≈ Material	Polyester needle-punched fleece liner with filament reinforcement and a thermoplastic polyurethane (TPU) coating.
Product code	FORCEUV	# Textile	Polyester
Length	50 m; 100 m / 164 feet; 328 feet	☐ Textile weight	500 g/m ²
⌀ Diameter	100 mm – 600 mm / 4 inch – 24 inch	◇ Coating	TPU
Wall thickness	3,30 mm / 0,13 inch	☐ Coating weight	150 g/m ²
Liner undersized	10 %	⊖ Colour / coating	White / Transparent
Heat resistance	Max. 80 °C / 176 °F	⊖ Water penetration	≥ 500 mbar
Negotiating bends	Max. 45°	⊖ Storage	Protected from light, dry

Features			Length		Resin	Pressure		Roller
Dimension	Flat (mm)	↻ Bend	L + *	L + **	⌀ kg / m	Inversion (bar)	3D (bar)	Roller gap
DN 100	~140	2 x 45	~3 cm	–	~1.15	0,35-0,40	–	7mm
DN 125	~175	2 x 45	~3 cm	–	~1.44	0,30-0,45	–	7mm
DN 150	~212	2 x 45	~3 cm	–	~1.72	0,30-0,50	–	7mm
DN 200	~282	2 x 45	~3 cm	–	~2.30	0,25-0,40	–	7mm
DN 225	~318	2 x 45	~3 cm	–	~2.60	0,20-0,40	–	7mm
DN 250	~353	2 x 45	~3 cm	–	~2.90	0,20-0,40	–	7mm
DN 300	~424	2 x 45	~3 cm	–	~3.21	0,20-0,40	–	7mm

Additional length *per bend >45° **Approx 4 % loss in length for every 25 % change in dimension

Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

Issue: V2026.1 · 2026.06

