

## Calibration Hose Heat Welded MD



PVC-coated polyester fabric with an ultra-flexible high-frequency overlap welded seam — suitable for use with most resin types (Polyester, Vinyl Ester, Epoxy).

### Material & construction

|                                |                                                       |
|--------------------------------|-------------------------------------------------------|
| ≈ Material                     | Heat Welded MD — White                                |
| 🔗 Base fabric                  | PVC-coated polyester                                  |
| # Seam                         | Heat-welded, overlapped and taped seam (medium duty). |
| 🔗 Compatible resins            | Polyester · Vinyl Ester · Epoxy                       |
| 📏 Standard lengths             | Standard roll lengths 50 m, 100 m                     |
| ☀️ Maximum working temperature | 50 °C                                                 |

### Maximum recommended pressure

| Pipe diameter (mm)                 | 100  | 150  | 200  | 250  | 300  | 350  | 400  |
|------------------------------------|------|------|------|------|------|------|------|
| Maximum recommended pressure (Bar) | 1.50 | 1.00 | 0.75 | 0.60 | 0.50 | 0.45 | 0.35 |

### Recommended storage

|                                  |                                                                                                                                                                                                                                                                                                                                                                   |
|----------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| ☀️ Avoid extremes of temperature | <ul style="list-style-type: none"> <li>Freezing may cause the coating structure to degrade locally, especially areas where the coating is in tension or compression – at bends and edges, and immediately adjacent to seam welds.</li> <li>Recommended storage temperature 5 °C – 35 °C.</li> <li>Shelf life at this temperature: in excess of 1 year.</li> </ul> |
| 💧 Recommended humidity           | <ul style="list-style-type: none"> <li>Very high relative humidity (especially at high temperature such as tropical countries) could affect the pigmentation of the hose.</li> <li>Recommended storage humidity 25 % – 65 % rh.</li> <li>Shelf life at 65 %, 35 °C: 1 year.</li> </ul>                                                                            |
| 🚰 Avoid prolonged wet storage    | <ul style="list-style-type: none"> <li>As with high humidity, the coating is more susceptible to degradation at higher temperatures, and even further susceptible if the pH of liquid in contact is significantly above or below 7.</li> <li>Wet storage is not recommended.</li> </ul>                                                                           |
| ☀️ Avoid sunlight / UV           | <ul style="list-style-type: none"> <li>Prolonged exposure to ultraviolet light can affect the pigmentation of the hose.</li> </ul>                                                                                                                                                                                                                                |

### Recommended handling

**Mechanical damage to be avoided.** Ensure that the hose is not placed directly onto grit or gravel floor – sweep and cover the floor first. Handle the hose with care. Ensure personnel are instructed not to walk on the hose.

### Further recommendations

- All hose supplied is recommended as single use only. Multiple use of the material is at customer risk.
- When in use, the hose is to be supported outside the pipe.
- Due to sizing requirements at manufacture, the customer must specify the intended use as calibration hose or pre-liner.

### Notice

- The information in this data sheet corresponds to our knowledge and experience at present and is given without warranty; check the product's suitability for the intended application before use.
- All values are guideline figures determined under laboratory conditions and can differ on industrial job sites.

