

## Glassfiber Complex 1050



E-CR glass-fibre reinforcement complex for structural pipe rehabilitation and CIPP lining.

| Technical data                    |                                                                |
|-----------------------------------|----------------------------------------------------------------|
| ≈ Glass composition               | E-CR Glass                                                     |
| 📦 Weight per unit area            | 1050 g/m <sup>2</sup> ± 8 % (deviation from nominal)           |
| ## 1st layer — Chopped Strand Mat | 500 g/m <sup>2</sup>                                           |
| ## 2nd layer — Woven Roving       | Warp 0°: 150 g/m <sup>2</sup> · Weft 90°: 410 g/m <sup>2</sup> |
| 🔗 Bonding                         | Stitching                                                      |
| ≈ Sewing thread (polyester)       | ≤ 15 g/m <sup>2</sup>                                          |
| 💧 Moisture content                | < 0.15 %                                                       |
| ✂ Edges                           | Trimmed                                                        |
| 📏 Width                           | 125 cm / 250 cm                                                |
| 💧 Coupling agent                  | Silane                                                         |
| ⌀ Tube diameter, internal         | 70 mm                                                          |

### Processing / Storage

The product should be conditioned for 24 hours at room temperature in the application area prior to use.

Store in its original packaging and keep dry. Storage temperature should not exceed 35 °C.

### Delivery form

Rolls are packed in stretch film and supplied on pallets.

\* Other roll widths, tube diameters and lengths available on request.

### Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

### Notice

- The information in this data sheet corresponds to our knowledge and experience at the present time and does not constitute legally binding assurance of properties.
- Before using the product, check its suitability for the intended application. As processing is beyond our control, responsibility rests solely with the user.

Issue: V2026.1 · 2026.06

