

Technical data sheet

MULTIline CORE



Multi-knitted hose liner for the trenchless inner lining of pipes.

Product features		Material features	
Product name	Lateral Repairs MULTILine CORE	≈ Material	Multi-knitted fleece with one sided Polypropylene (PP) coating.
Product code	CORE	# Textile	Polyester
Length	50 m; 100 m / 164 feet; 328 feet	☐ Textile weight	550* g/m ²
⌀ Diameter	70, 80, 100, 125, 150, 200, 225, 250.	🔄 Coating	One side PP
Wall thickness	4,00* mm / 0,16* inch	☐ Coating weight	150* g/m ²
Liner undersized	13 %	🌈 Colour / coating	White / Transparent
Additional length	5%	💧 Water penetration	≤ 550 mbar / ≤ 7,97 psi
Heat resistance	Max. 85 °C / 167 °F	🗑 Storage	Protected from light, dry
Negotiating bends	Max. 90°		

Features			Length		Resin	Pressure	
Dimension	Flat (cm)	↷ Bend	↷ L + bend (cm)	⇄ L + length	⬆ kg / m	Inversion (bar)	Curing (bar)
DN 70	on request	Max. 90°	on request	5%	on request	on request	on request
DN 80	on request	Max. 90°	on request	5%	on request	on request	on request
DN 100	on request	Max. 90°	on request	5%	on request	on request	on request
DN 125	on request	Max. 90°	on request	5%	on request	on request	on request
DN 150	on request	Max. 90°	on request	5%	on request	on request	on request
DN 200	on request	Max. 90°	on request	5%	on request	on request	on request
DN 225	on request	Max. 90°	on request	5%	on request	on request	on request
DN 250	on request	Max. 90°	on request	5%	on request	on request	on request

Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.

For further information visit www.lateralrepairs.com · info@lateralrepairs.com

Issue: V2026.1 · 2026.06