

# Technical data sheet

## MULTIline PRO 4.0 mm



Hose liner for the trenchless inner lining of defective, leaking and statically impaired pipes.

| Product features  |                                            | Material features   |                                            |
|-------------------|--------------------------------------------|---------------------|--------------------------------------------|
| Product name      | Lateral Repairs MULTIline PRO 4.0 mm       | ≈ Material          | Multi (knitted) fleece with one sided TPU. |
| Product code      | PRO                                        | # Textile           | Polyester                                  |
| Length            | 50 m; 100 m / 164 feet; 328 feet           | ☐ Textile weight    | 550* g/m <sup>2</sup>                      |
| ⌀ Diameter        | 70, 80, 100, 125, 150, 200, 225, 250, 300. | 🌀 Coating           | One side TPU                               |
| Wall thickness    | 4,00* mm / 0,16* inch                      | ☐ Coating weight    | 150* g/m <sup>2</sup>                      |
| Liner undersized  | 13 %                                       | ⊙ Colour / coating  | White / Transparent                        |
| Additional length | 5%                                         | ⊙ Water penetration | ≤ 550 mbar / ≤ 7,97 psi                    |
| Heat resistance   | Max. 70 °C / 158 °F                        | 📦 Storage           | Protected from light, dry                  |
| Negotiating bends | Max. 90°                                   |                     |                                            |

| Features     |            |          | Length          |              | Resin      | Pressure        |              |
|--------------|------------|----------|-----------------|--------------|------------|-----------------|--------------|
| Dimension    | Flat (cm)  | ↻ Bend   | ↻ L + bend (cm) | ⇄ L + length | ⊙ kg / m   | Inversion (bar) | Curing (bar) |
| DN 70 → 70   | on request | Max. 90° | on request      | -2 cm/m      | on request | 0,5             | 0,4          |
| DN 70 → 100  | on request | Max. 90° | on request      | 1 cm/m       | on request | 0,6             | 0,6          |
| DN 100 → 100 | on request | Max. 90° | on request      | -2 cm/m      | on request | 0,3             | 0,3          |
| DN 100 → 125 | on request | Max. 90° | on request      | 1 cm/m       | on request | 0,3             | 0,35         |
| DN 100 → 150 | on request | Max. 90° | on request      | 2 cm/m       | on request | 0,3             | 0,4          |
| DN 125 → 125 | on request | Max. 90° | on request      | -2 cm/m      | on request | 0,3             | 0,3          |
| DN 125 → 150 | on request | Max. 90° | on request      | 1 cm/m       | on request | 0,3             | 0,35         |
| DN 150 → 150 | on request | Max. 90° | on request      | -2 cm/m      | on request | 0,3             | 0,2          |
| DN 150 → 200 | on request | Max. 90° | on request      | 1 cm/m       | on request | 0,25            | 0,3          |
| DN 200 → 200 | on request | Max. 90° | on request      | -2 cm/m      | on request | 0,3             | 0,25         |
| DN 200 → 225 | on request | Max. 90° | on request      | 1 cm/m       | on request | 0,25            | 0,3          |
| DN 200 → 250 | on request | Max. 90° | on request      | 2 cm/m       | on request | 0,2             | 0,35         |
| DN 225 → 225 | on request | Max. 90° | on request      | -2 cm/m      | on request | 0,25            | 0,2          |
| DN 225 → 250 | on request | Max. 90° | on request      | 1 cm/m       | on request | 0,2             | 0,25         |
| DN 250 → 250 | on request | Max. 90° | on request      | -2 cm/m      | on request | 0,25            | 0,2          |
| DN 250 → 300 | on request | Max. 90° | on request      | 1 cm/m       | on request | 0,2             | 0,25         |

### Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

### Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.