

Technical data sheet

MULTIline PRO 4.5 mm



Hose liner for the trenchless inner lining of defective, leaking and statically impaired pipes.

Product features		Material features	
Product name	Lateral Repairs MULTIline PRO 4.5 mm	≈ Material	Multi knitted Fleece with One - Sided TPU Coating.
Product code	PRO	# Textile	Polyester
Length	50 m; 100 m / 164 feet; 328 feet	☐ Textile weight	650* g/m ²
⌀ Diameter	70, 80, 100, 125, 150, 200, 225, 250, 300.	🔄 Coating	One side TPU
Wall thickness	4,50* mm / 0,18* inch	☐ Coating weight	150* g/m ²
Liner undersized	13 %	⊙ Colour / coating	White / Transparent
Additional length	5%	⊙ Water penetration	≤ 600 mbar / ≤ 8,70 psi
Heat resistance	Max. 70 °C / 158 °F	📦 Storage	Protected from light, dry
Negotiating bends	Max. 90°		

Features			Length		Resin	Pressure	
Dimension	Flat (cm)	↪ Bend	↪ L + bend (cm)	⇄ L + length	⊙ kg / m	Inversion (bar)	Curing (bar)
DN 70 → 70	on request	Max. 90°	on request	-2 cm/m	on request	0,5	0,4
DN 70 → 100	on request	Max. 90°	on request	1 cm/m	on request	0,6	0,6
DN 100 → 100	on request	Max. 90°	on request	-2 cm/m	on request	0,3	0,3
DN 100 → 125	on request	Max. 90°	on request	1 cm/m	on request	0,3	0,35
DN 100 → 150	on request	Max. 90°	on request	2 cm/m	on request	0,3	0,4
DN 125 → 125	on request	Max. 90°	on request	-2 cm/m	on request	0,3	0,3
DN 125 → 150	on request	Max. 90°	on request	1 cm/m	on request	0,3	0,35
DN 150 → 150	on request	Max. 90°	on request	-2 cm/m	on request	0,3	0,2
DN 150 → 200	on request	Max. 90°	on request	1 cm/m	on request	0,25	0,3
DN 200 → 200	on request	Max. 90°	on request	-2 cm/m	on request	0,3	0,25
DN 200 → 225	on request	Max. 90°	on request	1 cm/m	on request	0,25	0,3
DN 200 → 250	on request	Max. 90°	on request	2 cm/m	on request	0,2	0,35
DN 225 → 225	on request	Max. 90°	on request	-2 cm/m	on request	0,25	0,2
DN 225 → 250	on request	Max. 90°	on request	1 cm/m	on request	0,2	0,25
DN 250 → 250	on request	Max. 90°	on request	-2 cm/m	on request	0,25	0,2
DN 250 → 300	on request	Max. 90°	on request	1 cm/m	on request	0,2	0,25

Resin quantity

Calculate the exact resin amount with the free Lateral Repairs app.



iPhone · App Store



Android · Google Play

Notice

- Given the diversity of installation conditions, application areas and process techniques, the information in this data sheet can only be regarded as non-binding guideline values.
- Length addition: add the stated percentage of the liner length, plus the cm value per 45° bend; calculate the exact resin quantity with the Lateral Repairs app (scan the QR codes).
- The final quality depends on the resin system used, the inversion pressure and the curing pressure. We advise against the use of other resin systems or higher pressures and accept no liability.
- All data were determined at 20 °C / 68 °F and are bench-scale values that can differ on industrial job sites.