

**LAXMI PUMPS PVT. LTD.(UNIT-2)**D-173,Kagal,Hatkanagale, Five Star Industrial Area,
Tal.-Hatkanagale Dist.-Kolhapur 416 216.**Material Test Certificate**

As per IS Std.1865:1991& Customer Specification

Name of the Customer	SHREE RAM FOUNDRY PVT. LTD.		
Discription	MAIN BEARING CAP - CASTING	Date	13/05/24
Drawing No.	F6.182.03.1.00	Quantity	151 Nos
Heat No.	B-26-D-267,268	Inv. No.	B262801/24
Material grade	SG 600/3	Inv. Date	14/05/24

Chemical Composition

Elements	C %	SI %	Mn %	P %	S %	Cu %	Mg %	
Min	3.20	2.20	0.00	0.00	0.00	0.50	0.02	
Max	4.00	3.00	0.50	0.100	0.035	1.50	0.07	
B-26-D-267	3.42	2.42	0.27	0.021	0.014	0.62	0.044	
B-26-D-268	3.50	2.44	0.31	0.021	0.015	0.64	0.044	

Casting Hardness

Specification	190-270 BHN		
Heat No.	B26 D 267	B26 D 268	
Observations	226,241,244	215,229,234	

Microstructure (Location On Face)

	Specification	Observations			
		B26 D 267	B26 D 268		
Graphite Form	Nodularity 80% min.	90.00%	91.00%		
	Nodule Count 150 /mm ² min.	244.00	250.00		
Matrix	Ferrite 20% max	14.00	17.00		
	Pearlite 80% min.	86.00	83.00		
	Carbide/Cementite	NIL	NIL		

Mechanical Properties (On Separately Cast Test Bar)

Properties	U.T.S. N/mm ²	Y.S.N/mm ²	% Elong.
Specification	600 min.	370 min.	3.00 min.
Observation	663	421	5.89

Quality Remarks - Accepted

Prepared By :SUNIL RAUT

Approved By : SATAPPA PATIL

LP/QA/F/01

