

Material Test Certificate

As per IS Std. 1865:1991 & Customer Specification

Name of the Customer	SHREE RAM FOUNDRY PVT. LTD			Date	28/04/24
Description	MAIN BEARING CAP			Quantity	286 Nos
Drawing No.	F6.182.04.00.01			Inv. No.	Eno 736
Heat No.	26-D-1128,1129,1130,1131,1132			Inv. Date	28/04/24
Material grade	SG 600/3				

Chemical Composition

Elements	C %	Si %	Mn %	P %	S %	Cu %	Mg %
Min	3.20	2.20	0.00	0.00	0.00	0.50	0.02
Max	4.00	3.00	0.50	0.050	0.020	1.50	0.07
26-D-1128	3.47	2.42	0.47	0.024	0.009	0.80	0.035
26-D-1129	3.44	2.49	0.46	0.023	0.01	0.81	0.037
26-D-1130	3.46	2.44	0.47	0.021	0.009	0.80	0.036
26-D-1131	3.44	2.47	0.48	0.024	0.009	0.82	0.038
26-D-1132	3.39	2.39	0.45	0.025	0.009	0.80	0.038

Casting Hardness

Specification	190-270 BHN				
Heat No.	26 D 1128	26 D 1129	26 D 1130	26 D 1131	26 D 1132
Observations	224,226,230	232,236,239	228,231,235	231,237,244	245,241,237

Microstructure (Location On Face)

	Specification	Observations				
		26 D 1128	26 D 1129	26 D 1130	26 D 1131	26 D 1132
Graphite Form	Nodularity 80% min.	92.00%	90.00%	91.00%	92.00%	94.00%
	Nodule Count 150 /mm2 min.	244	242	246	250	252
Matrix	Ferrite 20% max	10	18	16	18	15
	Pearlite 80% min.	90	82	84	82	85
	Carbide/Cementite	Nil	Nil	Nil	Nil	Nil

Mechanical Properties (On Separately Cast Test Bar)

Properties	U.T.S. N/mm2	Y.S.N/mm2	% Elon.
Specification	600 min.	370 min.	3.00
Observation	614	450	5.01

Quality Remarks - Accepted

Prepared By : SUNIL RAUT	Approved By : SATAPPA PATIL
--------------------------	-----------------------------

LP/QA/F/01

