

# Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Keisuke Nishioka<sup>1</sup>   Yuta Kojima<sup>2</sup>   Toshiya Saito<sup>3</sup>   Masahito Washiya<sup>3</sup>   Kosuke Kawakami<sup>3</sup>   Mayu Muramatsu<sup>4</sup>

<sup>1</sup>Keio University, Sci. for Open & Environ. Systems   <sup>2</sup>Nagoya University  
<sup>3</sup>JAXA, R&D Directorate   <sup>4</sup>Keio University, Mech. Engineering

17th WCCM / ECCOMAS 2026, Munich   MS090E

2026-06-07

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Keisuke Nishioka<sup>1</sup>   Yuta Kojima<sup>2</sup>   Toshiya Saito<sup>3</sup>   Masahito Washiya<sup>3</sup>   Kosuke Kawakami<sup>3</sup>   Mayu Muramatsu<sup>4</sup>

<sup>1</sup>Keio University, Sci. for Open & Environ. Systems   <sup>2</sup>Nagoya University  
<sup>3</sup>JAXA, R&D Directorate   <sup>4</sup>Keio University, Mech. Engineering

17th WCCM / ECCOMAS 2026, Munich   MS090E


Good morning. I am Keisuke Nishioka, from Keio University and Leibniz Universitaet Hannover, with co-authors at Nagoya University and JAXA. Today I show how we localize hidden delamination in perforated CFRP interstage structures using finite-element analysis and a graph neural network: 61% macro-F1 from surface stress alone, and how we make it robust to measurement noise. About 15 minutes.

## Introduction: CFRP in space transportation

CFRP carries primary load in reusable launch vehicles (high specific strength) [1, 2].

**Interlaminar delamination** around bolt holes critically degrades integrity, especially under repeated use. Reliable *defect localization* is essential.

Conventional NDT — ultrasonic [3], X-ray CT [4], tap testing [5] — is costly and operator-dependent [6].




Perforated CFRP interstage panel (FEM).

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Introduction: CFRP in space transportation

CFRP is the primary structural material in reusable launch vehicles, for its strength-to-weight ratio. Around bolt holes, interlaminar delamination accumulates and is invisible from the outside. Conventional NDT — ultrasonic, X-ray CT, tap testing — is slow, expensive, and operator-dependent. So we need an automated, reliable way to localize these sub-surface defects.




## Infrared stress measurement (DSPSS)

Thermoelastic effect relates a small temperature change to the change in the sum of principal stresses:

$$\Delta T = -k T \Delta \sigma_{\text{sum}}, \quad \sigma_{\text{sum}} = \sigma_1 + \sigma_2 + \sigma_3 = \text{tr}(\sigma).$$

Infrared stress measurement [7–9] thus yields a **full-field surface map** of  $\sigma_{\text{sum}}$  (DSPSS), from which sub-surface defects are inferred.



DSPSS shows a stress valley over the defect.

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

2026-06-07

### Infrared stress measurement (DSPSS)


Our measurable quantity is infrared stress measurement. By the thermoelastic effect, a small temperature change is proportional to the change in the sum of principal stresses. So an infrared camera gives a full-field surface map of the stress sum, which we call DSPSS. A sub-surface defect perturbs this field and creates a local stress valley, as shown on the right.

Infrared stress measurement (DSPSS)

Thermoelastic effect relates a small temperature change to the change in the sum of principal stresses:

$$\Delta T = -k T \Delta \sigma_{\text{sum}}, \quad \sigma_{\text{sum}} = \sigma_1 + \sigma_2 + \sigma_3 = \text{tr}(\sigma).$$

Infrared stress measurement [7–9] thus yields a **full-field surface map** of  $\sigma_{\text{sum}}$  (DSPSS), from which sub-surface defects are inferred.



DSPSS shows a stress valley over the defect.

## Previous study and purpose

- **Previous study** [10, 11]: transfer learning with a CNN estimates defect position/size — but is tied to image grids and struggles on irregular, perforated geometry.
- **This work:** a **Graph Neural Network** (GAT) that consumes FEM-generated DSPSS to predict the *3-D defect location* (in-plane region  $\times$  insertion layer) in perforated CFRP interstage structures.

### Why a graph?

The FEM surface mesh is naturally a graph; a GNN handles the irregular, hole-perforated topology that a CNN grid cannot.

2026-06-07

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

### └ Previous study and purpose

A previous study used transfer learning with a CNN to estimate defect position and size. But a CNN works on a regular image grid and struggles with the irregular, hole-perforated geometry. Our idea is to treat the FEM surface mesh directly as a graph and use a graph attention network. The task is the full 3-D location: both the in-plane region and which layer the delamination sits in.

### Previous study and purpose

- **Previous study** [10, 11]: transfer learning with a CNN estimates defect position/size — but is tied to image grids and struggles on irregular, perforated geometry.
- **This work:** a **Graph Neural Network** (GAT) that consumes FEM-generated DSPSS to predict the *3-D defect location* (in-plane region  $\times$  insertion layer) in perforated CFRP interstage structures.


### Why a graph?

The FEM surface mesh is naturally a graph; a GNN handles the irregular, hole-perforated topology that a CNN grid cannot.

## FEM analysis conditions

- 1/80-scale curved panel ( $R \approx 2$  m,  $L \approx 1.57$  m,  $t = 22$  mm).
- Holes of  $100 \times 100$  and  $200 \times 100$  mm.
- Sandwich laminate; tensile loading.
- Interlaminar delamination modeled explicitly by **Teflon inserts** between selected plies.

Synthetic dataset  $\Rightarrow$  DSPSS fields with known ground-truth defects.




FEM boundary conditions & hole geometry.

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

FEM analysis conditions

### FEM analysis conditions

- 1/80-scale curved panel ( $R \approx 2$  m,  $L \approx 1.57$  m,  $t = 22$  mm).
  - Holes of  $100 \times 100$  and  $200 \times 100$  mm.
  - Sandwich laminate; tensile loading.
  - Interlaminar delamination modeled explicitly by **Teflon inserts** between selected plies.
- Synthetic dataset  $\Rightarrow$  DSPSS fields with known ground-truth defects.



We build the dataset by finite-element analysis: a one-eightieth-scale curved interstage panel, about 2 metres radius, with two rectangular holes. Delaminations are modeled explicitly by inserting thin Teflon sheets between selected plies, under tensile loading. This gives DSPSS fields with exactly known ground-truth defects.


## Input data: normalized / difference DSPSS

Raw DSPSS is dominated by **stress concentration around the hole**, masking the defect signal.

Remedy (paper):

- **Difference** field: damaged – defect-free reference;
- **Z-score normalization** (per node), improving depth-direction discrimination.

⇒ robust localization even near the opening.




Normalized DSPSS isolates the defect.

2026-06-07

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Input data: normalized / difference DSPSS

The raw DSPSS is dominated by the stress concentration around the holes, which masks the defect. So we subtract a defect-free reference to get a difference field, and z-score normalize per node. This isolates the defect signal and, importantly, improves discrimination in the depth direction — that is, which layer the defect is in.



## Stress distribution around the defect

- DSPSS exhibits a clear **stress valley** at the defect centre.
- Depth and width of the valley depend on **ply angle**: 90° plies give sharp narrow valleys; 0°/45° broaden them.
- This ply-angle signature is what the network must learn to separate *which layer* the delamination sits in.

### Implication

Layer discrimination is a *fine spatial-frequency* problem — motivating attention over local neighbourhoods.

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

2026-06-07

### └ Stress distribution around the defect

Looking closer, each defect produces a stress valley at its centre. The depth and width of that valley depend on the ply angle above it: ninety-degree plies give sharp narrow valleys, zero and forty-five broaden them. This ply-angle signature is exactly the cue the network uses to tell which layer the delamination is in. It is a fine spatial-frequency problem, which motivates local attention.

### Stress distribution around the defect


- DSPSS exhibits a clear **stress valley** at the defect centre.
- Depth and width of the valley depend on **ply angle**: 90° plies give sharp narrow valleys; 0°/45° broaden them.
- This ply-angle signature is what the network must learn to separate *which layer* the delamination sits in.

### Implication

Layer discrimination is a *fine spatial-frequency* problem — motivating attention over local neighbourhoods.

## Graph representation & GAT model

- **Nodes** = FEM surface elements; features =  $(x, y, z, \hat{\sigma}_{\text{sum}})$ .
- **Edges** = fixed mesh connectivity (reused across graphs).
- **GAT** [12, 13]: attention weights learn neighbour importance; message passing [14] over the mesh.
- Architecture: 3× GATConv (64→256→256), multi-head, batch-norm + dropout + residual connections.



Graph model on the perforated mesh.

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks


2026-06-07

### Graph representation & GAT model

We represent each surface element as a node, with features being its coordinates and the normalized stress. Edges are the fixed mesh connectivity, reused across all specimens. We use a graph attention network: three GAT layers, sixty-four to two-hundred-fifty-six channels, multi-head, with batch-norm, dropout and residual connections. Attention lets each node weight its neighbours adaptively, which suits the highly non-uniform stress field.

#### Graph representation & GAT model


- **Nodes** = FEM surface elements; features =  $(x, y, z, \hat{\sigma}_{\text{sum}})$ .
- **Edges** = fixed mesh connectivity (reused across graphs).
- **GAT** [12, 13]: attention weights learn neighbour importance; message passing [14] over the mesh.
- Architecture: 3× GATConv (64→256→256), multi-head, batch-norm + dropout + residual connections.





## Output: 3-D defect location as 19-class node labels

- Node classification into **19 classes**: class 0 = defect-free; remaining classes encode *in-plane region*  $\times$  *insertion layer*.
- One-side labelling so prediction needs only single-surface DSPSS.



### Severe imbalance


Defect nodes are < 3% of all nodes — handled by the loss (next slide).

2026-06-07

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Output: 3-D defect location as 19-class node labels

We formulate localization as node classification into nineteen classes: class zero is defect-free, and the other classes jointly encode the in-plane region and the insertion layer. We label only one side, so prediction needs a single surface measurement. Note the severe imbalance — defect nodes are under three percent of all nodes.



Severe imbalance  
Defect nodes are < 3% of all nodes — handled by the loss (next slide).

## Loss function: Focal loss

$$\text{FL}(p_t) = -\alpha_t (1 - p_t)^\gamma \log p_t.$$

- Down-weights easy, abundant defect-free nodes; emphasises rare defect-class nodes [15].
- Crucial because intact regions dominate (> 97%).

Node features normalized; a single fixed edge list reused across all graphs.

2026-06-07

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

└ Loss function: Focal loss

To handle that imbalance we use focal loss, which down-weights the easy, abundant defect-free nodes and focuses learning on the rare defect classes. Without it, the model simply predicts defect-free everywhere.

Loss function: Focal loss


$$\text{FL}(p_t) = -\alpha_t (1 - p_t)^\gamma \log p_t.$$

- Down-weights easy, abundant defect-free nodes; emphasises rare defect-class nodes [15].
  - Crucial because intact regions dominate (> 97%).
- Node features normalized; a single fixed edge list reused across all graphs.

## Results: prediction accuracy

Test-set metrics:

- planar  $R = 0.72$  (mean), depth  $P_{\text{gauss}} = 0.69$ , combined TDPS = 0.70 (best 0.92).
- Best layers: 9–12 (mid-thickness); Layer-10 samples all TDPS  $\geq 0.82$ .
- False-negative rate for defect nodes < 3%.




Predicted vs. true defect regions.

2026-06-07

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Results: prediction accuracy




On held-out test specimens we get a planar score  $R$  of 0.72, a depth score of 0.69, and a combined TDPS of 0.70, up to 0.92 in the best case. The mid-thickness layers, nine to twelve, are localized best. Critically, the false-negative rate on defect nodes is under three percent, so we rarely miss a real defect.

# Overall performance & confusion

## Headline

Macro-F1 = 61% across 19 classes, using surface DSPSS only.

- Dominant diagonal; residual adjacent-layer confusion.
- False positives cluster near the hole edge.
- Robust across defect insertion regions.




Confusion matrix (macro-F1 61%).

2026-06-07

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

### Overall performance & confusion

Overall macro-F1 is sixty-one percent across all nineteen classes, from surface DSPSS alone. The confusion matrix has a strong diagonal; the residual errors are mostly confusion with the adjacent layer, and false positives cluster near the hole edge, where stress gradients are steep.



## Conclusion

- Introduced an **FEM + GAT** framework for 3-D delamination localization in perforated CFRP interstage panels.
- **Difference-normalized DSPSS** suppresses hole stress concentration and enables full-region estimation.
- Achieved **macro-F1 61%** on 19 classes from surface data only, with a very low defect false-negative rate and no false detections in defect-free regions.

### A scalable foundation

toward experimental infrared-stress (TSA) data and practical SHM of aerospace composite structures.

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

2026-06-07

### Conclusion

To summarize the published work: an FEM-plus-GAT framework localizes 3-D delamination in perforated CFRP; difference-normalized DSPSS removes the hole concentration and enables full-region estimation; and we reach sixty-one percent macro-F1 from surface data alone, with very low false negatives and no false detections in healthy regions.

### Conclusion

- Introduced an **FEM + GAT** framework for 3-D delamination localization in perforated CFRP interstage panels.
- **Difference-normalized DSPSS** suppresses hole stress concentration and enables full-region estimation.
- Achieved **macro-F1 61%** on 19 classes from surface data only, with a very low defect false-negative rate and no false detections in defect-free regions.

### A scalable foundation

toward experimental infrared-stress (TSA) data and practical SHM of aerospace composite structures.

## New focus: robustness for real operation


The published model assumes clean FEM fields.

In practice:

- infrared stress measurement carries **acquisition noise** (temperature fluctuation, emissivity, sensor);
- the vast majority of a real structure is **defect-free** — false detections there are costly.

### WCCM contribution

Train for *robustness under experimentally-motivated noise* and explicitly *suppress false detection* on defect-free regions.



Clean vs. noise-injected Z-score input — the defect signature survives.

2026-06-07

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

└ New focus: robustness for real operation

Now the new part for this congress. The published model assumes clean FEM fields. Real infrared measurements carry noise — temperature drift, emissivity, sensor noise. And in practice almost the entire structure is healthy, so false alarms are very costly. So here we focus on robustness under realistic noise and on suppressing false detection. On the right, the input with and without injected noise — the defect signature still survives.

**New focus: robustness for real operation**

The published model assumes clean FEM fields.  
In practice:

- infrared stress measurement carries acquisition noise (temperature fluctuation, emissivity, sensor);
- the vast majority of a real structure is **defect-free** — false detections there are costly.

**WCCM contribution**  
Train for *robustness under experimentally-motivated noise* and explicitly *suppress false detection* on defect-free regions.


## Noise-augmented dataset & defect-free negatives (NDF)

### Defect-free negatives (NDF):

- base field set to zero (no defect);
- additive Gaussian noise (10% of data std);
- 5,000 samples added to training.

### Noise model on defect data:

- line noise along the fibre (z) direction (random intensity/width);
- attenuated noise in x; global white noise.




A defect-free sample (zero field + 10% noise) — teaches “no defect”.

2026-06-07

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks


└ Noise-augmented dataset & defect-free negatives (NDF)



We do two things. First, defect-free negatives: we add five thousand samples that are a zero field plus Gaussian noise at ten percent of the data standard deviation, so the model explicitly learns what no-defect looks like. Second, we add structured noise to the defect data — line noise along the fibre direction, attenuated noise across it, and global white noise — to mimic measurement artefacts.

## Results under noise

- Difference-DSPSS input enables **full-region** defect estimation.
- Prediction stays accurate on **noise-injected** data.
- **No false detection** on defect-free inputs — the NDF negatives remove spurious activations.



Noisy input (left) → correct defect localization (right).


### Takeaway

The framework is robust enough to move toward *experimental* infrared stress data.

2026-06-07

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

### Results under noise



The outcome: with the difference-DSPSS input, the model still estimates defects across the full region; prediction stays accurate on noise-injected data; and the defect-free negatives remove spurious activations, so we get essentially no false detection on healthy inputs. Here, the noisy input on the left still yields the correct target localization on the right. This makes the framework robust enough to move toward real experimental data.



- **Sim-to-real:** apply the noise-robust model to *experimental* infrared-stress (TSA) measurements.
- **Architecture study (preliminary):** extending from attention GNNs to *mesh-physics* GNNs (MeshGraphNet) and layered variants; early results are encouraging and under evaluation with co-authors.
- **Application:** transfer to aerospace payload-fairing SHM.

*Preliminary; not part of the published results.*

2026-06-07

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

### └ Outlook [ongoing, beyond the published paper]

Going forward: first, sim-to-real — applying this noise-robust model to actual infrared stress measurements. Second, and still preliminary, we are extending from attention GNNs to mesh-physics GNNs such as MeshGraphNet and some layered variants; early results are encouraging and under evaluation with our co-authors. And third, transferring the approach to payload-fairing structural health monitoring. I will stop here. Thank you — I am happy to take questions.

- **Sim-to-real:** apply the noise-robust model to *experimental* infrared-stress (TSA) measurements.
- **Architecture study (preliminary):** extending from attention GNNs to *mesh-physics* GNNs (MeshGraphNet) and layered variants; early results are encouraging and under evaluation with co-authors.
- **Application:** transfer to aerospace payload-fairing SHM.

*Preliminary; not part of the published results.*

References I

[1] Y. Hou et al. “On the damage mechanism of high-speed ballast impact and compression after impact for CFRP laminates”. In: *Composite Structures* 229 (2019), p. 111435. DOI: 10.1016/j.compstruct.2019.111435.

[2] D. Kiefel et al. “Quantitative impact characterization of aeronautical CFRP materials with non-destructive testing methods”. In: *AIP Conference Proceedings* 1650 (2015), pp. 591–598. DOI: 10.1063/1.4914658.

[3] S. Joas et al. “CFRP pipe inspection by means of air-coupled ultrasound”. In: *AIP Conference Proceedings* 2055 (2019), p. 120003. DOI: 10.1063/1.5084893.

[4] M. Sultan et al. “On impact damage detection and quantification for CFRP laminates using structural response data only”. In: *Mechanical Systems and Signal Processing* 25.8 (2011), pp. 3135–3152. DOI: 10.1016/j.ymssp.2011.05.028.

[5] P. Cawley and R. Adams. “An Automated Coin-Tap Technique for the Non-Destructive Testing of Composite Structures”. In: *Non-Destructive Testing of Fibre Reinforced Plastics Composites*. Elsevier, 1987, pp. 11–15. DOI: 10.1007/BF00614806.

[6] A. Ngo et al. “Nondestructive Evaluation of Defects in Carbon Fiber Reinforced Polymer (CFRP) Composites”. In: *Proceedings of SPIE – Smart Structures and Nondestructive Evaluation for Health Monitoring and Diagnostics*. Vol. 10169. 6 pages. SPIE, Apr. 2017, 101691P. DOI: 10.1117/12.2260331.

[7] T. Sakagami and S. Kubo. “Applications of pulse heating thermography and lock-in thermography to quantitative nondestructive evaluations”. In: *Infrared Physics & Technology* 43.3–5 (2002), pp. 211–218. DOI: 10.1016/S1350-4495(02)00141-X.

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

2026-06-07

References

References I

[1] Y. Hou et al. “On the damage mechanism of high-speed ballast impact and compression after impact for CFRP laminates”. In: *Composite Structures* 229 (2019), p. 111435. DOI: 10.1016/j.compstruct.2019.111435.

[2] D. Kiefel et al. “Quantitative impact characterization of aeronautical CFRP materials with non-destructive testing methods”. In: *AIP Conference Proceedings* 1650 (2015), pp. 591–598. DOI: 10.1063/1.4914658.

[3] S. Joas et al. “CFRP pipe inspection by means of air-coupled ultrasound”. In: *AIP Conference Proceedings* 2055 (2019), p. 120003. DOI: 10.1063/1.5084893.

[4] M. Sultan et al. “On impact damage detection and quantification for CFRP laminates using structural response data only”. In: *Mechanical Systems and Signal Processing* 25.8 (2011), pp. 3135–3152. DOI: 10.1016/j.ymssp.2011.05.028.

[5] P. Cawley and R. Adams. “An Automated Coin-Tap Technique for the Non-Destructive Testing of Composite Structures”. In: *Non-Destructive Testing of Fibre Reinforced Plastics Composites*. Elsevier, 1987, pp. 11–15. DOI: 10.1007/BF00614806.

[6] A. Ngo et al. “Nondestructive Evaluation of Defects in Carbon Fiber Reinforced Polymer (CFRP) Composites”. In: *Proceedings of SPIE – Smart Structures and Nondestructive Evaluation for Health Monitoring and Diagnostics*. Vol. 10169. 6 pages. SPIE, Apr. 2017, 101691P. DOI: 10.1117/12.2260331.

[7] T. Sakagami and S. Kubo. “Applications of pulse heating thermography and lock-in thermography to quantitative nondestructive evaluations”. In: *Infrared Physics & Technology* 43.3–5 (2002), pp. 211–218. DOI: 10.1016/S1350-4495(02)00141-X.

References II

[8] S. Keo et al. “Defect detection in CFRP by infrared thermography with CO2 Laser excitation compared to conventional lock-in infrared thermography”. In: *Composites Part B: Engineering* 69 (2015), pp. 1–5. doi: 0.1016/j.compositesb.2014.09.018.

[9] T. Sakagami et al. “Application of infrared stress analysis for damage detection in bridge structures”. In: *Procedia Structural Integrity* 2 (2016), pp. 2132–2139. doi: 10.1016/j.prostr.2016.06.265.

[10] Y. Kojima et al. “Inverse estimation method for internal defects based on surface stress of carbon-fiber-reinforced plastics using machine learning”. In: *Advanced Composite Materials* 31.6 (2022). Published online: 30 Mar 2022, pp. 617–629. doi: 10.1080/09243046.2022.2052786.

[11] Y. Kojima et al. “Transfer-learning-aided Defect Prediction in Simply Shaped CFRP Specimens Based on Stress Distribution Obtained from Finite Element Analysis and Infrared Stress Measurement”. In: *Composites Part B: Engineering* 291 (2024), p. 111958. doi: 10.1016/j.compositesb.2023.111958.

[12] P. Veličković et al. “Graph Attention Networks”. In: *International Conference on Learning Representations (ICLR) 2018*. 2018. doi: 10.48550/ARXIV.1710.10903. url: https://arxiv.org/abs/1710.10903.

[13] F. Scarselli et al. “The Graph Neural Network Model”. In: *IEEE Transactions on Neural Networks* 20.1 (2009), pp. 61–80. doi: 10.1109/TNN.2008.2005605.

[14] J. Gilmer et al. “Neural Message Passing for Quantum Chemistry”. In: *Proceedings of the 34th International Conference on Machine Learning (ICML)*. Vol. 70. Proceedings of Machine Learning Research. PMLR, 2017, pp. 1263–1272. doi: 10.48550/arXiv:1704.01212.

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

2026-06-07

References

References II

[8] S. Keo et al. “Defect detection in CFRP by infrared thermography with CO2 Laser excitation compared to conventional lock-in infrared thermography”. In: *Composites Part B: Engineering* 69 (2015), pp. 1–5. doi: 0.1016/j.compositesb.2014.09.018.

[9] T. Sakagami et al. “Application of infrared stress analysis for damage detection in bridge structures”. In: *Procedia Structural Integrity* 2 (2016), pp. 2132–2139. doi: 10.1016/j.prostr.2016.06.265.

[10] Y. Kojima et al. “Inverse estimation method for internal defects based on surface stress of carbon-fiber-reinforced plastics using machine learning”. In: *Advanced Composite Materials* 31.6 (2022). Published online: 30 Mar 2022, pp. 617–629. doi: 10.1080/09243046.2022.2052786.

[11] Y. Kojima et al. “Transfer learning-aided Defect Prediction in Simply Shaped CFRP Specimens Based on Stress Distribution Obtained from Finite Element Analysis and Infrared Stress Measurement”. In: *Composites Part B: Engineering* 291 (2024), p. 111958. doi: 10.1016/j.compositb.2023.111958.

[12] P. Veličković et al. “Graph Attention Networks”. In: *International Conference on Learning Representations (ICLR) 2018*. 2018. doi: 10.48550/ARXIV.1710.10903. url: https://arxiv.org/abs/1710.10903.

[13] F. Scarselli et al. “The Graph Neural Network Model”. In: *IEEE Transactions on Neural Networks* 20.1 (2009), pp. 61–80. doi: 10.1109/TNN.2008.2005605.

[14] J. Gilmer et al. “Neural Message Passing for Quantum Chemistry”. In: *Proceedings of the 34th International Conference on Machine Learning (ICML)*. Vol. 70. Proceedings of Machine Learning Research. PMLR, 2017, pp. 1263–1272. doi: 10.48550/arXiv:1704.01212.

[15] T. Lin et al. “Focal Loss for Dense Object Detection”. In: *Proceedings of the IEEE International Conference on Computer Vision (ICCV)*. IEEE, 2017, pp. 2980–2988. doi: 10.1109/ICCV.2017.324.

2026-06-07

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

References

# Appendix


## Appendix: difference-data construction

Raw DSPSS near a hole is dominated by geometric stress concentration. We remove it by a per-specimen **difference**:

$$\text{Difference} = \underbrace{\text{Original (defect)}}_{\text{damaged}} - \underbrace{\text{Reference (no detect)}}_{\text{pristine}}.$$

With-defect – no-defect reference = difference field (defect localized).


The residual isolates the defect-induced perturbation, independent of the hole’s baseline field.



2026-06-07

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Appendix: difference-data construction




## Appendix: Z-score normalization

The difference field is standardized per node (Z-score):

$$\hat{\sigma} = \frac{\sigma - \mu}{s}.$$

- equalizes magnitude across regions/specimens;
- improves **depth-direction** (layer) discrimination;
- keeps the network NDT-admissible (coordinate/stress only).



Normalized DSPSS input (paper figure).

2026-06-07

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Appendix: Z-score normalization

Appendix: Z-score normalization


The difference field is standardized per node (Z-score):  

$$\hat{\sigma} = \frac{\sigma - \mu}{s}.$$

- equalizes magnitude across regions/specimens;
- improves **depth-direction** (layer) discrimination;
- keeps the network NDT-admissible (coordinate/stress only).

## Appendix: DSPSS profile around the defect

The difference-DSPSS shows a pronounced **stress valley** at the defect centre; its depth and width encode the insertion layer (ply-angle dependence).




Profile of the normalized DSPSS across the defect (paper figure).

## Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

### Appendix: DSPSS profile around the defect

The difference-DSPSS shows a pronounced **stress valley** at the defect centre; its depth and width encode the insertion layer (ply-angle dependence).



Profile of the normalized DSPSS across the defect (paper figure).