

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Keisuke Nishioka¹ Yuta Kojima² Toshiya Saito³ Masahito Washiya³
Kosuke Kawakami³ Mayu Muramatsu⁴

¹Keio University, Sci. for Open & Environ. Systems ²Nagoya University

³JAXA, R&D Directorate ⁴Keio University, Mech. Engineering

17th WCCM / ECCOMAS 2026, Munich MS090E

2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Keisuke Nishioka¹ Yuta Kojima² Toshiya Saito³ Masahito Washiya³
Kosuke Kawakami³ Mayu Muramatsu⁴

¹Keio University, Sci. for Open & Environ. Systems ²Nagoya University

³JAXA, R&D Directorate ⁴Keio University, Mech. Engineering

17th WCCM / ECCOMAS 2026, Munich MS090E

Good morning. I am Keisuke Nishioka, from Keio University and Leibniz Universitaet Hannover, with co-authors at Nagoya University and JAXA. Today I show how we localize hidden delamination in perforated CFRP interstage structures using finite-element analysis and a graph neural network: 61% macro-F1 from surface stress alone, and how we make it robust to measurement noise. About 15 minutes.

Outline

1. Motivation & measurement — defects in CFRP, infrared stress (DSPSS)
2. Method — difference-normalized input & a GAT on the FEM mesh
3. Results — 19-class 3-D localization (macro-F1 61%)
4. New: robustness to measurement noise (defect-free negatives)
5. Outlook

2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Outline

1. Motivation & measurement — defects in CFRP, infrared stress (DSPSS)
2. Method — difference-normalized input & a GAT on the FEM mesh
3. Results — 19-class 3-D localization (macro-F1 61%)
4. New: robustness to measurement noise (defect-free negatives)
5. Outlook

Quick roadmap: motivation and the DSPSS measurement, the method, the published results, the new noise-robustness work, and outlook. About 15 minutes.

Contributions

1. A **graph attention network** localizing 3-D delamination in *perforated* CFRP interstages directly from FEM surface stress (DSPSS).
2. **61% macro-F1** over 19 classes (region $\times$ layer) from *surface data only*, with defect false-negative rate $< 3\%$.
3. **Noise-robust** training (structured noise + defect-free negatives) — a step toward experimental infrared-stress data.

2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Contributions

1. A **graph attention network** localizing 3-D delamination in *perforated* CFRP interstages directly from FEM surface stress (DSPSS).
2. **61% macro-F1** over 19 classes (region $\times$ layer) from *surface data only*, with defect false-negative rate $< 3\%$.
3. **Noise-robust** training (structured noise + defect-free negatives) — a step toward experimental infrared-stress data.


State the three contributions up front, then dive in.

Introduction: CFRP in space transportation

CFRP carries primary load in reusable launch vehicles (high specific strength) [1, 2].

Interlaminar delamination around bolt holes critically degrades integrity, especially under repeated use. Reliable *defect localization* is essential.

Conventional NDT — ultrasonic [3], X-ray CT [4], tap testing [5] — is costly and operator-dependent [6].



CFRP interstage structure of a launch vehicle.

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Introduction: CFRP in space transportation


CFRP is the primary structural material in reusable launch vehicles, for its strength-to-weight ratio. Around bolt holes, interlaminar delamination accumulates and is invisible from the outside. Conventional NDT — ultrasonic, X-ray CT, tap testing — is slow, expensive, and operator-dependent. So we need an automated, reliable way to localize these sub-surface defects.

Introduction: CFRP in space transportation

CFRP carries primary load in reusable launch vehicles (high specific strength) [1, 2].

Interlaminar delamination around bolt holes critically degrades integrity, especially under repeated use. Reliable *defect localization* is essential.

Conventional NDT — ultrasonic [3], X-ray CT [4], tap testing [5] — is costly and operator-dependent [6].




CFRP interstage structure of a launch vehicle.

Infrared stress measurement (DSPSS)

Thermoelastic effect relates a small temperature change to the change in the sum of principal stresses:

$$\Delta T = -k T \Delta \sigma_{\text{sum}}, \quad \sigma_{\text{sum}} = \sigma_1 + \sigma_2 + \sigma_3 = \text{tr}(\sigma)$$

Infrared stress measurement [7–9] thus yields a **full-field surface map** of σ_{sum} (DSPSS), from which sub-surface defects are inferred.




DSPSS shows a stress valley over the defect.

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

2026-06-17

Infrared stress measurement (DSPSS)



Our measurable quantity is infrared stress measurement. By the thermoelastic effect, a small temperature change is proportional to the change in the sum of principal stresses. So an infrared camera gives a full-field surface map of the stress sum, which we call DSPSS. A sub-surface defect perturbs this field and creates a local stress valley, as shown on the right.

Previous study and purpose

Prior work. Kojima *et al.* [10, 11] — a CNN *proof-of-concept* on *non-perforated* CFRP from FEM DSPSS.

This work — harder setting: *perforated* interstage $\times$ 3-D location (region $\times$ layer) $\times$ extreme imbalance ($< 3\%$ defect nodes).

Problem — node classification on the mesh graph $\mathcal{G} = (\mathcal{V}, \mathcal{E})$, node features $\mathbf{x}_i = (x, y, z, \hat{\sigma}_{\text{sum}})_i$; learn $f_\theta : \mathcal{G} \rightarrow \mathbb{R}^{|\mathcal{V}| \times 19}$,

$$\hat{y}_i = \arg \max_{c \in \{0, \dots, 18\}} [\text{softmax } f_\theta(\mathcal{G})]_{i,c}, \quad \theta^\star = \arg \min_\theta \sum_{i \in \mathcal{V}} \text{FL}(p_{i,y_i}),$$

class 0 = defect-free; classes 1–18 = (in-plane region $\times$ insertion layer).

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Previous study and purpose

Kojima et al. gave a CNN proof-of-concept on non-perforated CFRP. Our setting is harder: perforated interstage, full 3-D location (region times layer), and extreme imbalance. Formally we learn a node classifier on the mesh graph, minimizing focal loss; class zero is defect-free, classes one to eighteen encode region times layer.

Previous study and purpose

Prior work. Kojima *et al.* [10, 11] — a CNN *proof-of-concept* on *non-perforated* CFRP from FEM DSPSS.

This work — harder setting: *perforated* interstage $\times$ 3-D location (region $\times$ layer) $\times$ extreme imbalance ($< 3\%$ defect nodes).

Problem — node classification on the mesh graph $\mathcal{G} = (\mathcal{V}, \mathcal{E})$, node features $\mathbf{x}_i = (x, y, z, \hat{\sigma}_{\text{sum}})_i$; learn $f_\theta : \mathcal{G} \rightarrow \mathbb{R}^{|\mathcal{V}| \times 19}$,

$$\hat{y}_i = \arg \max_{c \in \{0, \dots, 18\}} [\text{softmax } f_\theta(\mathcal{G})]_{i,c}, \quad \theta^\star = \arg \min_\theta \sum_{i \in \mathcal{V}} \text{FL}(p_{i,y_i}),$$

class 0 = defect-free; classes 1–18 = (in-plane region $\times$ insertion layer).

Related work: where this work sits

	Kojima '25 (Compos. B)	PIGMID '26 (Compos. B)	This work
Input	surface stress (FEM→IR)	guided waves (PZT×8)	full-field stress (DSPSS)
Model	transfer CNN	physics GNN (wave energy)	mesh-physics GNN
Geometry	simple coupons	instrumented plate	perforated inter- stage, 3-D
Physics	noise-aug. sim pretrain	wave-energy adjacency	FE-mesh topol- ogy + DSPSS
Novelty	sim-to-real transfer	path hetero- geneity	OOD gen. + de- tect/localize split

Unlike guided-wave GNNs (PIGMID) or simple-coupon transfer CNNs (Kojima '25), we learn on the structural FE mesh from full-field DSPSS, and are the first to quantify OOD size/position generalization — **detection transfers, precise localization collapses.**

2026-06-17 Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Related work: where this work sits


Two anchors, both in Composites B. Kojima 2025 is the direct surface-stress lineage we build on (and a co-author). PIGMID 2026 is an adjacent physics-informed GNN, but on guided-wave sensor signals — a different modality. We differentiate on input, structure, the physics prior, and the OOD generalization study.

	Kojima '25 (Compos. B)	PIGMID '26 (Compos. B)	This work
Input	surface stress (FEM→IR)	guided waves (PZT×8)	full-field stress (DSPSS)
Model	transfer CNN	physics GNN (wave energy)	mesh-physics GNN
Geometry	simple coupons	instrumented plate	perforated inter- stage, 3-D
Physics	noise-aug. sim pretrain	wave-energy adjacency	FE-mesh topol- ogy + DSPSS
Novelty	sim-to-real transfer	path hetero- geneity	OOD gen. + de- tect/localize split
Unlike guided-wave GNNs (PIGMID) or simple-coupon transfer CNNs (Kojima '25), we learn on the structural FE mesh from full-field DSPSS, and are the first to quantify OOD size/position generalization — detection transfers, precise localization collapses.			

FEM analysis conditions

- 1/80-scale curved panel ($R \approx 2$ m, $L \approx 1.57$ m, $t = 22$ mm).
- Holes of 100×100 and 200×100 mm.
- Sandwich laminate; tensile loading.
- Interlaminar delamination modeled explicitly by **Teflon inserts** between selected plies.

Dataset: 1 reference + **1386** defect specimens; 5-fold CV (≈ 1110 train / 278 test per fold).



FEM boundary conditions & hole geometry.

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks


FEM analysis conditions

We build the dataset by finite-element analysis: a one-eightieth-scale curved interstage panel, about 2 metres radius, with two rectangular holes. Delaminations are modeled explicitly by inserting thin Teflon sheets between selected plies, under tensile loading. This gives DSPSS fields with exactly known ground-truth defects.

FEM analysis conditions

- 1/80-scale curved panel ($R \approx 2$ m, $L \approx 1.57$ m, $t = 22$ mm).
- Holes of 100×100 and 200×100 mm.
- Sandwich laminate; tensile loading.
- Interlaminar delamination modeled explicitly by **Teflon inserts** between selected plies.

Dataset: 1 reference + **1386** defect specimens; 5-fold CV (≈ 1110 train / 278 test per fold).



Input data: normalized / difference DSPSS


Raw DSPSS is dominated by **stress concentration around the hole**, masking the defect signal.

Remedy (paper):

- **Difference** field: damaged – defect-free reference;
- **Z-score normalization** (per node), improving depth discrimination.

$$d_i = \sigma_i^{\text{dmg}} - \sigma_i^{\text{ref}}, \quad \hat{\sigma}_i = \frac{d_i - \mu_d}{s_d}.$$

⇒ robust localization even near the opening.



Normalized DSPSS isolates the defect.

2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Input data: normalized / difference DSPSS

Input data: normalized / difference DSPSS

Raw DSPSS is dominated by **stress concentration around the hole**, masking the defect signal.

Remedy (paper):

- **Difference** field: damaged – defect-free reference;
- **Z-score normalization** (per node), improving depth discrimination.


$$d_i = \sigma_i^{\text{dmg}} - \sigma_i^{\text{ref}}, \quad \hat{\sigma}_i = \frac{d_i - \mu_d}{s_d}.$$

⇒ robust localization even near the opening.

The raw DSPSS is dominated by the stress concentration around the holes, which masks the defect. So we subtract a defect-free reference to get a difference field, and z-score normalize per node. This isolates the defect signal and, importantly, improves discrimination in the depth direction — that is, which layer the defect is in.

Stress distribution around the defect

- DSPSS exhibits a clear **stress valley** at the defect centre.
- Depth and width of the valley depend on **ply angle**: 90° plies give sharp narrow valleys; $0^\circ/45^\circ$ broaden them.
- This signature tells the network *which layer* the delamination sits in.



Normalized DSPSS profile across the defect.

Implication

Layer discrimination is a *fine spatial-frequency* problem — motivating local attention.


2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Stress distribution around the defect

Stress distribution around the defect

- DSPSS exhibits a clear **stress valley** at the defect centre.
- Depth and width of the valley depend on **ply angle**: 90° plies give sharp narrow valleys; $0^\circ/45^\circ$ broaden them.
- This signature tells the network *which layer* the delamination sits in.



Implication

Layer discrimination is a *fine spatial-frequency* problem — motivating local attention.

Looking closer, each defect produces a stress valley at its centre. The depth and width of that valley depend on the ply angle above it: ninety-degree plies give sharp narrow valleys, zero and forty-five broaden them. This ply-angle signature is exactly the cue the network uses to tell which layer the delamination is in. It is a fine spatial-frequency problem, which motivates local attention.

Detect first, then localize — screening comes for free

Two different jobs. *Detection* (is there / where?) needs **no learning**: every specimen shares one mesh, so healthy fields are a point cloud around *one* template.

The *same* per-node z-score we feed the GNN doubles as an unsupervised screen:

$$s_i = \frac{|x_i - \mu_i|}{\sigma_i}, \quad (\mu_i, \sigma_i) \text{ from } N=2000 \text{ hec}$$

Node-level, label-free, ~30 lines, CPU-minutes.

Node AUROC (clean)

Per-node Mahalanobis / PCA:
0.999 / 0.995 (2×2 / 4×4).

Learned baselines: PaDiM 0.96, PatchCore 0.93, STFPM 0.75, diffusion 0.50–0.66.

SNR: robust, not fragile

Verified on a labelled coupon: detection holds (AUROC ~0.84) at noise $\sigma=0.1$ of field std, failing only near $\sigma \approx 0.7\text{--}1.0$ — not the folklore “0.1 collapse.” Lock-in IR ($\sigma \propto 1/\sqrt{K}$) adds margin.

⇒ detection is cheap; the GNN is for the hard part — **semantic 19-class (region ×**

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

One quick but important point before the network. Detection and localization are different jobs. Detection — is there a defect, and roughly where — needs no learning at all. Because every specimen shares one mesh geometry, the healthy fields form a point cloud around a single template, so the same per-node z-score we already use as input doubles as an unsupervised detector: score each node by how many standard deviations it sits from the healthy mean, with mean and std estimated from two thousand defect-free fields. On clean data this per-node statistic reaches node-level AUROC of about one — it actually beats every learned anomaly detector we tried, including a diffusion model. The one caveat is signal-to-noise, but it is more forgiving than folklore suggests: on a labelled coupon the detector still scores about 0.84 AUROC at noise one-tenth of the field standard deviation, and only falls to chance near seven-tenths to one times the field std — so the often-quoted collapse at sigma equals 0.1 is wrong. Lock-in infrared thermography, where noise falls as one over root-K frames, only adds margin. So screening is cheap. The GNN earns its keep

Detect first, then localize — screening comes for free	
Two different jobs. <i>Detection</i> (is there / where?) needs no learning : every specimen shares one mesh, so healthy fields are a point cloud around <i>one</i> template. The same per-node z-score we feed the GNN doubles as an unsupervised screen: $s_i = \frac{ x_i - \mu_i }{\sigma_i}, \quad (\mu_i, \sigma_i) \text{ from } N=2000 \text{ hec}$ Node-level, label-free, ~30 lines, CPU-minutes. ⇒ detection is cheap; the GNN is for the hard part — semantic 19-class (region ×	Node AUROC (clean) Per-node Mahalanobis / PCA: 0.999 / 0.995 (2×2 / 4×4). Learned baselines: PaDiM 0.96, PatchCore 0.93, STFPM 0.75, diffusion 0.50–0.66. SNR: robust, not fragile Verified on a labelled coupon: detection holds (AUROC ~0.84) at noise $\sigma=0.1$ of field std, failing only near $\sigma \approx 0.7\text{--}1.0$ — not the folklore “0.1 collapse.” Lock-in IR ($\sigma \propto 1/\sqrt{K}$) adds margin. ⇒ detection is cheap; the GNN is for the hard part — semantic 19-class (region ×

Graph representation & GAT model

Nodes = elements ($\mathbf{x}_i$), edges = fixed mesh connectivity. GAT message passing [12–14]:


$$e_{ij} = \text{LeakyReLU}(\mathbf{a}^\top [\mathbf{W}\mathbf{h}_i \parallel \mathbf{W}\mathbf{h}_j]),$$

$$\alpha_{ij} = \frac{\exp e_{ij}}{\sum_{k \in \mathcal{N}(i)} \exp e_{ik}},$$

$$\mathbf{h}'_i = \bigg\|_{m=1}^M \sigma \bigg(\sum_{j \in \mathcal{N}(i)} \alpha_{ij}^{(m)} \mathbf{W}^{(m)} \mathbf{h}_j \bigg).$$

3 layers $64 \rightarrow 256 \rightarrow 256$, M heads, BN + dropout + residual.

GAT: attention-weighted aggregation over neighbours




Attention-weighted aggregation; arrow thickness $\propto \alpha_{ij}$.

2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Graph representation & GAT model

We represent each surface element as a node, with features being its coordinates and the normalized stress. Edges are the fixed mesh connectivity, reused across all specimens. We use a graph attention network: three GAT layers, sixty-four to two-hundred-fifty-six channels, multi-head, with batch-norm, dropout and residual connections. Attention lets each node weight its neighbours adaptively, which suits the highly non-uniform stress field.




Output: 3-D defect location as 19-class node labels

- Node classification into **19 classes**: class 0 = defect-free; remaining classes encode *in-plane region* $\times$ *insertion layer*.
- One-side labelling so prediction needs only single-surface DSPSS.

$$p_{i,c} = \frac{e^{z_{i,c}}}{\sum_{k=0}^{18} e^{z_{i,k}}}, \quad \hat{y}_i = \arg \max_c p_{i,c}.$$


Severe imbalance

Defect nodes are < 3% of all nodes — handled by the loss (next slide).



2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks




We formulate localization as node classification into nineteen classes: class zero is defect-free, and the other classes jointly encode the in-plane region and the insertion layer. We label only one side, so prediction needs a single surface measurement. Note the severe imbalance — defect nodes are under three percent of all nodes.

Loss function: Focal loss

$$\text{FL}(p_t) = -\alpha_t (1 - p_t)^\gamma \log p_t.$$

- Down-weights easy, abundant defect-free nodes; emphasises rare defect-class nodes [15].
- Crucial because intact regions dominate (> 97%).




Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

2026-06-17

Loss function: Focal loss

Loss function: Focal loss

- Down-weights easy, abundant defect-free nodes; emphasises rare defect-class nodes [15].
- Crucial because intact regions dominate (> 97%).



To handle that imbalance we use focal loss, which down-weights the easy, abundant defect-free nodes and focuses learning on the rare defect classes. Without it, the model simply predicts defect-free everywhere.


Results: prediction accuracy

Test-set metrics:

- planar $R = 0.72$ (mean), depth $P_{\text{gauss}} = 0.69$, combined TDPS = 0.70 (best 0.92).
- Best layers: 9–12 (mid-thickness); Layer-10 samples all TDPS ≥ 0.82 .
- False-negative rate for defect nodes $< 3\%$.

R : planar F1. P_{gauss} : Gaussian depth score ($\sigma=2$).


$$\text{TDPS} = \frac{1}{2}(R + P_{\text{gauss}}).$$



Input $\rightarrow$ ground truth $\rightarrow$ prediction (Layer-10 cases).

2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks



On held-out test specimens we get a planar score R of 0.72, a depth score of 0.69, and a combined TDPS of 0.70, up to 0.92 in the best case. The mid-thickness layers, nine to twelve, are localized best. Critically, the false-negative rate on defect nodes is under three percent, so we rarely miss a real defect.


Overall performance & confusion

Headline

Macro-F1 = 61% across 19 classes, using *surface DSPSS only*.


$$F1_c = \frac{2P_cR_c}{P_c + R_c}, \quad \text{macro-F1} = \frac{1}{19} \sum_{c=0}^{18} F1_c.$$

- Dominant diagonal; residual *adjacent-layer* confusion.
- False positives cluster near the hole edge.



2026-06-17 Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Overall macro-F1 is sixty-one percent across all nineteen classes, from surface DSPSS alone. The confusion matrix has a strong diagonal; the residual errors are mostly confusion with the adjacent layer, and false positives cluster near the hole edge, where stress gradients are steep.



Conclusion

- Introduced an **FEM + GAT** framework for 3-D delamination localization in perforated CFRP interstage panels.
- **Difference-normalized DSPSS** suppresses hole stress concentration and enables full-region estimation.
- Achieved **macro-F1 61%** on 19 classes from surface data only, with a very low defect false-negative rate and no false detections in defect-free regions.

A scalable foundation

toward experimental infrared-stress (TSA) data and practical SHM of aerospace composite structures.

2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Conclusion

To summarize the published work: an FEM-plus-GAT framework localizes 3-D delamination in perforated CFRP; difference-normalized DSPSS removes the hole concentration and enables full-region estimation; and we reach sixty-one percent macro-F1 from surface data alone, with very low false negatives and no false detections in healthy regions.

Conclusion

- Introduced an **FEM + GAT** framework for 3-D delamination localization in perforated CFRP interstage panels.
- **Difference-normalized DSPSS** suppresses hole stress concentration and enables full-region estimation.
- Achieved **macro-F1 61%** on 19 classes from surface data only, with a very low defect false-negative rate and no false detections in defect-free regions.

A scalable foundation


toward experimental infrared-stress (TSA) data and practical SHM of aerospace composite structures.

New focus: robustness for real operation

The published model assumes clean FEM fields. In practice infrared measurement carries **acquisition noise**, and almost the whole structure is **defect-free** — false alarms are costly.

WCCM contribution


Robustness under realistic noise *and* explicit suppression of false detection on healthy regions.



Clean vs. noise-injected Z-score input — the defect signature survives.

2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks




Now the new part for this congress. The published model assumes clean FEM fields. Real infrared measurements carry noise — temperature drift, emissivity, sensor noise. And in practice almost the entire structure is healthy, so false alarms are very costly. So here we focus on robustness under realistic noise and on suppressing false detection. On the right, the input with and without injected noise — the defect signature still survives.

Noise-augmented dataset & defect-free negatives (NDF)

Defect-free negatives (NDF): zero field + Gaussian noise (10% of data std), 5,000 samples added to training.

Structured noise on defect data: line noise along the fibre (z), attenuated noise in x , and global white noise.




Left: defect-free + noise (teaches “no defect”). Right: defect + structured noise.

2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks


Noise-augmented dataset & defect-free negatives (NDF)



We do two things. First, defect-free negatives: we add five thousand samples that are a zero field plus Gaussian noise at ten percent of the data standard deviation, so the model explicitly learns what no-defect looks like. Second, we add structured noise to the defect data — line noise along the fibre direction, attenuated noise across it, and global white noise — to mimic measurement artefacts.

Results under noise

- Difference-DSPSS input enables **full-region** defect estimation; prediction stays accurate on **noise-injected** data.
- **No false detection** on defect-free inputs — the NDF negatives remove spurious activations. $\Rightarrow$ robust enough to move toward *experimental* infrared stress data.




Noisy input (left) $\rightarrow$ correct defect localization (right).

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

2026-06-17

Results under noise

- Difference-DSPSS input enables **full-region** defect estimation; prediction stays accurate on **noise-injected** data.
- **No false detection** on defect-free inputs — the NDF negatives remove spurious activations. $\Rightarrow$ robust enough to move toward *experimental* infrared stress data.



Noisy input (left) $\rightarrow$ correct defect localization (right).

The outcome: with the difference-DSPSS input, the model still estimates defects across the full region; prediction stays accurate on noise-injected data; and the defect-free negatives remove spurious activations, so we get essentially no false detection on healthy inputs. Here, the noisy input on the left still yields the correct target localization on the right. This makes the framework robust enough to move toward real experimental data.

Outlook [ongoing, beyond the published paper]

- **Sim-to-real:** apply the noise-robust model to *experimental* infrared-stress (TSA) measurements.
- **Architecture study (preliminary):** extending from attention GNNs to *mesh-physics* GNNs (MeshGraphNet) and layered variants; early results are encouraging and under evaluation with co-authors.
- **Application:** transfer to other perforated / bonded CFRP structures — rocket motor cases, aircraft wing boxes, satellite panels, payload-fairing SHM.

Preliminary; not part of the published results.

2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Outlook [ongoing, beyond the published paper]

Going forward: first, sim-to-real — applying this noise-robust model to actual infrared stress measurements. Second, and still preliminary, we are extending from attention GNNs to mesh-physics GNNs such as MeshGraphNet and some layered variants; early results are encouraging and under evaluation with our co-authors. And third, transferring the approach to payload-fairing structural health monitoring. I will stop here. Thank you — I am happy to take questions.

Outlook [ongoing, beyond the published paper]

- **Sim-to-real:** apply the noise-robust model to *experimental* infrared-stress (TSA) measurements.
- **Architecture study (preliminary):** extending from attention GNNs to *mesh-physics* GNNs (MeshGraphNet) and layered variants; early results are encouraging and under evaluation with co-authors.
- **Application:** transfer to other perforated / bonded CFRP structures — rocket motor cases, aircraft wing boxes, satellite panels, payload-fairing SHM.

Preliminary; not part of the published results.

Acknowledgements

- Conducted in collaboration with **JAXA** (Research & Development Directorate, Research Unit IV).
- Co-authors at **Keio University**, **Nagoya University**, and **JAXA**.
- Built on the FEA-generated CFRP interstage dataset of the prior study [10].

Thank you for your attention — questions welcome.

2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Acknowledgements

Thank the co-authors and JAXA, then invite questions.

Acknowledgements

- Conducted in collaboration with **JAXA** (Research & Development Directorate, Research Unit IV).
 - Co-authors at **Keio University**, **Nagoya University**, and **JAXA**.
 - Built on the FEA-generated CFRP interstage dataset of the prior study [10].
- Thank you for your attention — questions welcome.

References I

- [1] Y. Hou et al. “On the damage mechanism of high-speed ballast impact and compression after impact for CFRP laminates”. In: *Composite Structures* 229 (2019), p. 111435. doi: 10.1016/j.compstruct.2019.111435.
- [2] D. Kiefel et al. “Quantitative impact characterization of aeronautical CFRP materials with non-destructive testing methods”. In: *AIP Conference Proceedings* 1650 (2015), pp. 591–598. doi: 10.1063/1.4914658.
- [3] S. Joas et al. “CFRP pipe inspection by means of air-coupled ultrasound”. In: *AIP Conference Proceedings* 2055 (2019), p. 120003. doi: 10.1063/1.5084893.
- [4] M. Sultan et al. “On impact damage detection and quantification for CFRP laminates using structural response data only”. In: *Mechanical Systems and Signal Processing* 25.8 (2011), pp. 3135–3152. doi: 10.1016/j.ymssp.2011.05.028.
- [5] P. Cawley and R. Adams. “An Automated Coin-Tap Technique for the Non-Destructive Testing of Composite Structures”. In: *Non-Destructive Testing of Fibre Reinforced Plastics Composites*. Elsevier, 1987, pp. 11–15. doi: 10.1007/BF00614806.
- [6] A. Ngo et al. “Nondestructive Evaluation of Defects in Carbon Fiber Reinforced Polymer (CFRP) Composites”. In: *Proceedings of SPIE – Smart Structures and Nondestructive Evaluation for Health Monitoring and Diagnostics*. Vol. 10169. 6 pages. SPIE, Apr. 2017, 101691P. doi: 10.1117/12.2260331.
- [7] T. Sakagami and S. Kubo. “Applications of pulse heating thermography and lock-in thermography to quantitative nondestructive evaluations”. In: *Infrared Physics & Technology* 43.3–5 (2002), pp. 211–218. doi: 10.1016/S1350-4495(02)00141-X.
- [8] S. Keo et al. “Defect detection in CFRP by infrared thermography with CO2 Laser excitation compared to conventional lock-in infrared thermography”. In: *Composites Part B: Engineering* 69 (2015), pp. 1–5. doi: 0.1016/j.compositesb.2014.09.018.
- [9] T. Sakagami et al. “Application of infrared stress analysis for damage detection in bridge structures”. In: *Procedia Structural Integrity* 2 (2016), pp. 2132–2139. doi: 10.1016/j.prostr.2016.06.265.
- [10] Y. Kojima et al. “Inverse estimation method for internal defects based on surface stress of carbon-fiber-reinforced plastics using machine learning”. In: *Advanced Composite Materials* 31.6 (2022). Published online: 30 Mar 2022, pp. 617–629. doi: 10.1080/09243046.2022.2052786.

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

2026-06-17

Defect

References I

- [1] Y. Hou et al. “On the damage mechanism of high-speed ballast impact and compression after impact for CFRP laminates”. In: *Composite Structures* 229 (2019), p. 111435. doi: 10.1016/j.compstruct.2019.111435.
- [2] D. Kiefel et al. “Quantitative impact characterization of aeronautical CFRP materials with non-destructive testing methods”. In: *AIP Conference Proceedings* 1650 (2015), pp. 591–598. doi: 10.1063/1.4914658.
- [3] S. Joas et al. “CFRP pipe inspection by means of air-coupled ultrasound”. In: *AIP Conference Proceedings* 2055 (2019), p. 120003. doi: 10.1063/1.5084893.
- [4] M. Sultan et al. “On impact damage detection and quantification for CFRP laminates using structural response data only”. In: *Mechanical Systems and Signal Processing* 25.8 (2011), pp. 3135–3152. doi: 10.1016/j.ymssp.2011.05.028.
- [5] P. Cawley and R. Adams. “An Automated Coin-Tap Technique for the Non-Destructive Testing of Composite Structures”. In: *Non-Destructive Testing of Fibre Reinforced Plastics Composites*. Elsevier, 1987, pp. 11–15. doi: 10.1007/BF00614806.
- [6] A. Ngo et al. “Nondestructive Evaluation of Defects in Carbon Fiber Reinforced Polymer (CFRP) Composites”. In: *Proceedings of SPIE – Smart Structures and Nondestructive Evaluation for Health Monitoring and Diagnostics*. Vol. 10169. 6 pages. SPIE, Apr. 2017, 101691P. doi: 10.1117/12.2260331.
- [7] T. Sakagami and S. Kubo. “Applications of pulse heating thermography and lock-in thermography to quantitative nondestructive evaluations”. In: *Infrared Physics & Technology* 43.3–5 (2002), pp. 211–218. doi: 10.1016/S1350-4495(02)00141-X.
- [8] S. Keo et al. “Defect detection in CFRP by infrared thermography with CO2 Laser excitation compared to conventional lock-in infrared thermography”. In: *Composites Part B: Engineering* 69 (2015), pp. 1–5. doi: 0.1016/j.compositesb.2014.09.018.
- [9] T. Sakagami et al. “Application of infrared stress analysis for damage detection in bridge structures”. In: *Procedia Structural Integrity* 2 (2016), pp. 2132–2139. doi: 10.1016/j.prostr.2016.06.265.
- [10] Y. Kojima et al. “Inverse estimation method for internal defects based on surface stress of carbon-fiber-reinforced plastics using machine learning”. In: *Advanced Composite Materials* 31.6 (2022). Published online: 30 Mar 2022, pp. 617–629. doi: 10.1080/09243046.2022.2052786.

References II

[11] Y. Kojima et al. “Transfer-learning-aided Defect Prediction in Simply Shaped CFRP Specimens Based on Stress Distribution Obtained from Finite Element Analysis and Infrared Stress Measurement”. In: *Composites Part B: Engineering* 291 (2024), p. 111958. doi: 10.1016/j.compositesb.2023.111958.

[12] P. Veličković et al. “Graph Attention Networks”. In: *International Conference on Learning Representations (ICLR) 2018*. 2018. doi: 10.48550/ARXIV.1710.10903. url: <https://arxiv.org/abs/1710.10903>.

[13] F. Scarselli et al. “The Graph Neural Network Model”. In: *IEEE Transactions on Neural Networks* 20.1 (2009), pp. 61–80. doi: 10.1109/TNN.2008.2005605.

[14] J. Gilmer et al. “Neural Message Passing for Quantum Chemistry”. In: *Proceedings of the 34th International Conference on Machine Learning (ICML)*. Vol. 70. Proceedings of Machine Learning Research. PMLR, 2017, pp. 1263–1272. doi: 10.48550/arXiv:1704.01212.

[15] T. Lin et al. “Focal Loss for Dense Object Detection”. In: *Proceedings of the IEEE International Conference on Computer Vision (ICCV)*. IEEE, 2017, pp. 2980–2988. doi: 10.1109/ICCV.2017.324.

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

2026-06-17

References

References II

[11] Y. Kojima et al. “Transfer-learning-aided Defect Prediction in Simply Shaped CFRP Specimens Based on Stress Distribution Obtained from Finite Element Analysis and Infrared Stress Measurement”. In: *Composites Part B: Engineering* 291 (2024), p. 111958. doi: 10.1016/j.compositesb.2023.111958.

[12] P. Veličković et al. “Graph Attention Networks”. In: *International Conference on Learning Representations (ICLR) 2018*. 2018. doi: 10.48550/ARXIV.1710.10903. url: <https://arxiv.org/abs/1710.10903>.

[13] F. Scarselli et al. “The Graph Neural Network Model”. In: *IEEE Transactions on Neural Networks* 20.1 (2009), pp. 61–80. doi: 10.1109/TNN.2008.2005605.

[14] J. Gilmer et al. “Neural Message Passing for Quantum Chemistry”. In: *Proceedings of the 34th International Conference on Machine Learning (ICML)*. Vol. 70. Proceedings of Machine Learning Research. PMLR, 2017, pp. 1263–1272. doi: 10.48550/arXiv:1704.01212.

[15] T. Lin et al. “Focal Loss for Dense Object Detection”. In: *Proceedings of the IEEE International Conference on Computer Vision (ICCV)*. IEEE, 2017, pp. 2980–2988. doi: 10.1109/ICCV.2017.324.

Appendix


Appendix: difference-data construction

Raw DSPSS near a hole is dominated by geometric stress concentration. We remove it by a per-specimen **difference**:

$$\text{Difference} = \underbrace{\text{Original (defect)}}_{\text{damaged}} - \underbrace{\text{Reference (no defect)}}_{\text{pristine}}.$$


With-defect – no-defect reference = difference field (defect localized).

The residual isolates the defect-induced perturbation, independent of the hole’s baseline field.



2026-06-17 Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Appendix: difference-data construction




Appendix: Z-score normalization

The difference field is standardized per node (Z-score):

$$\hat{\sigma} = \frac{\sigma - \mu}{s}.$$

- equalizes magnitude across regions/specimens;
- improves **depth-direction** (layer) discrimination;
- keeps the network NDT-admissible (coordinate/stress only).



Normalized DSPSS input (paper figure).


Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Appendix: Z-score normalization

Appendix: Z-score normalization

The difference field is standardized per node (Z-score):


$$\hat{\sigma} = \frac{\sigma - \mu}{s}.$$



- equalizes magnitude across regions/specimens;
- improves **depth-direction** (layer) discrimination;
- keeps the network NDT-admissible (coordinate/stress only).


Appendix: DSPSS profile around the defect

The difference-DSPSS shows a pronounced **stress valley** at the defect centre; its depth and width encode the insertion layer (ply-angle dependence).



Profile of the normalized DSPSS across the defect (paper figure).

2026-06-17 Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks



Appendix: evaluation metrics

- R — in-plane (planar) F1 score for defect vs. non-defect at the correct location.
- P_{gauss} — depth-direction score: Gaussian-weighted ($\sigma = 2$ layers) credit for predicting the correct or a near-correct insertion layer.
- **TDPS** (Total Defect Prediction Score) = $\frac{1}{2} (R + P_{\text{gauss}})$.
- **macro-F1** — unweighted mean F1 over all 19 classes (the headline metric).

These quantify in-plane localization (R), depth/layer accuracy (P_{gauss}), and their combination (TDPS), complementing the class-level macro-F1.

2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks


Appendix: evaluation metrics

Appendix: evaluation metrics

- R — in-plane (planar) F1 score for defect vs. non-defect at the correct location.
- P_{gauss} — depth-direction score: Gaussian-weighted ($\sigma = 2$ layers) credit for predicting the correct or a near-correct insertion layer.
- **TDPS** (Total Defect Prediction Score) = $\frac{1}{2} (R + P_{\text{gauss}})$.
- **macro-F1** — unweighted mean F1 over all 19 classes (the headline metric).

These quantify in-plane localization (R), depth/layer accuracy (P_{gauss}), and their combination (TDPS), complementing the class-level macro-F1.

Appendix: what the Stage-0 screen keys on (one case)



Real 4×4 specimens, per-node

$$s_i = |x_i - \mu_i|/\sigma_i:$$

- **Where:** defect nodes rank **top ~0.2%**; per-case **AUROC 0.998** (200 specimens).
- **Which way:** **98–100%** **negative** deviation $\Rightarrow$ a *stress valley* (thermoelastic signature).

Honest limits

|z| magnitudes inflated ($\sigma_i \sim 10^{-3}$) — quote rank/sign, not “ $N\sigma$ ”. precision@K < 1: the hole edge also deviates $\Rightarrow$ the reason we *difference-normalize* before precise localization

2026-06-17

Development of a Defect Estimation Method for CFRP Interstage Structures with Holes using Finite Element Analysis and Graph Neural Networks

Appendix: what the Stage-0 screen keys on (one case)

Backup for a likely question — what does the per-node screen actually respond to. On real 4x4-defect specimens we decompose a case. Two robust facts. First, where: the defect nodes rank in the top about zero-point-two percent by score, per-case AUROC about 0.998, aggregated over two hundred specimens, not cherry-picked. Second, which way: ninety-eight to one hundred percent of the defect-node deviations are negative — the screen keys on a local stress valley, which is exactly the thermoelastic signature of a sub-surface defect. The honest caveats: the absolute z magnitudes are inflated because the per-node sigma is tiny on a z-scored field, so I only quote rank and sign, never N-sigma; and top-K precision is below one because the hole-edge concentration also deviates strongly — which is precisely why we difference-normalize the input before precise localization.

