Customer Name: SAVANNAH TANK & EQUIPMENT CO
Customer PO#: 40299 *NO FRIDAY DELIVER
Shipper No: 224171
Heat Number: 2516600

NUCOR STEEL - BERKELEY
1455 Hagan Avenue
Huger, SC 29450
Phone: (843) 336-6000

CERTIFIED MILL TEST REPORT

11/18/25 9:07:32

100% EAF MELTED AND MANUFACTURED IN THE USA

Structural sections produced by Nucor-Berkeley are cast and hot rolled to a fully killed and fine grain practice. Mercury not intentionally added at any point during manufacturing.

Sold To: CHATHAM STEEL CORPORATION
PO BOX 2567
SAVANNAH, GA 31402

Ship To: CHATHAM STEEL CORP.
501 W BOUNDARY ST
SAVANNAH, GA 31402

Customer #.: 363 - 2
B.o.L. #...: 1869472
MOS: I

SPECIFICATIONS: Tested in accordance with ASTM specification A6/A6M-24b and A370-24a. Tested in accordance with EN10204-2004-3.1. Quality Manual Rev #21 (12-13-24).
AASHTO : M270-50-23
ASTM : A992-22:A36-19/A529-19-50/A572502IT1/A7095021
CSA : G40.2150WM

Description / Part #	Heat# / Grade(s) / Test/Heat JW	Yield/ Tensile Ratio	Yield (PSI) (MPa)	Tensile (PSI) (MPa)	Elong %	C / Cr / ******	Mn / Mo / Ti	P / Sn / Ca	S / B / ******	Si / V / N	Cu / Nb / ******	Ni / ****** / CI	CE1 / CE2 / Pcm
W6X20	2516600	.85	58500	69100	26.00	.07	1.06	.011	.013	.24	.07	.05	.27
020' 00.00'	A992-22		403	476		.05	.01	.0041	.0003	.002	.028		.3114
W150X29.8		.82	57500	70100	29.00		.001	.0010		.0074		2.47	.1392
006.0960m			396	483	23 Pc(s)	9,200 lbs		Customer PO: SAV-38585		BoL#: 1869472			
W6X20	2516606	.83	57200	68900	26.00	.07	1.05	.010	.013	.24	.08	.03	.26
020' 00.00'	A992-22		394	475		.05	.01	.0042	.0003	.002	.030		.3059
W150X29.8		.81	57100	70400	25.00		.001	.0005		.0065		2.58	.1349
006.0960m			394	485	4 Pc(s)	1,600 lbs		Customer PO: SAV-38585		BoL#: 1869472			
W8X21	2515975	.83	57300	68800	28.00	.07	.86	.009	.020	.22	.07	.04	.23
020' 00.00'	A992-22		395	474		.05	.01	.0049	.0002	.002	.027		.2733
W200X31.3		.83	57500	69100	26.00		.001	.0011		.0064		2.35	.1281
006.0960m			396	476	10 Pc(s)	4,200 lbs		Customer PO: SAV-40271		BoL#: 1869472			

Elongation based on 8' (20.32cm) gauge length. 'No Weld Repair' was performed.
CI = 26.01Cu+3.88Ni+1.20Cr+1.49Si+17.28P-(7.29Cu*Ni)-(9.10Ni*P)-33.39(Cu*Cu)
Pcm = C+(Si/30)+(Mn/20)+(Cu/20)+(Ni/60)+(Cr/20)+(Mo/15)+(V/10)+5B
CE1= C+(Mn/6)+((Cr+Mo+V)/5)+((Ni+Cu)/15)

'All mechanical testing is performed by the Quality testing lab, which is independent of the production departments'
CE2 = C+((Mn+Si)/6)+((Cr+Mo+V+Cb)/5)+((Ni+Cu)/15)

Nucor certifies that the contents of this report are accurate and correct. All test results and operations performed by the material manufacturer are in compliance with material specifications, and when designated by the Purchaser, meet applicable specifications.

(State of South Carolina
(County of Berkeley
Sworn and subscribed before me
_____ day of _____

Damdin Munkhbold
Metallurgist/
Quality Control

ACCEPTED
BY JR DATE 12/11/25

DM

Job: 089-25 PO: 40299 Line: 004 HT: 2516600