NUCOR STEEL - BERKELEY — CERTIFIED MILL TEST REPORT — 3702725 20:27:31

1455 Hagan Avenue
Huger, SC 29450
Phone: (843) 336-6000

100% EAF MELTED AND MANUFACTURED IN THE USA

Structural sections produced by Nucor-Berkeley are cast and hot rolled to a fully killed and fine grain practice. Mercury not intentionally added at any point during manufacturing.

Sold To: CHATHAM STEEL CORPORATION
PO BOX 2567
SAVANNAH, GA 31402

Ship To: CHATHAM STEEL CORP.
501 W BOUNDARY ST
SAVANNAH, GA 31402

Customer #.: 363 - 2
Customer PO: SAV-35466
B.o.L. #...: 1854015
MOS: I

SPECIFICATIONS: Tested in accordance with ASTM specification A6/A6M-24b and A370-24a. Tested in accordance with EN10204-2004-3.1. Quality Manual Rev #21 (12-13-24).
AASHTO : M270-50-23
ASTM : A992-22:A36-19/A529-19-50/A5725021I1/A7095021
CSA : G40.2150WM

Description / Part #	Heat# / Grade(s) / Test/Heat JW	Yield/ Tensile Ratio	Yield (PSI) (MPa)	Tensile (PSI) (MPa)	Elong %	C / Cr / ******	Mn / Mo / Ti	P / Sn / ******	S / B / ******	Si / V / N	Cu / Nb / ******	Ni / ****** / CI	CE1 / CE2 / Pcm
W6X20	2511602	.83	58400	70000	27.00	.07	1.03	.008	.016	.22	.08	.03	.25
030' 00.00'	A992-22		403	483		.04	.01	.0053	.0002	.002	.029		.2974
W150X29.8		.83	57700	69200	28.00		.001			.0045		2.41	.1330
009.1440m			398	477	9 Pc(s)	5,400 lbs	Customer PO: SAV-35466			BoL#: 1854015			
W6X25	2511453	.81	55100	68400	26.00	.07	1.06	.009	.020	.26	.08	.04	.26
030' 00.00'	A992-22		380	472		.04	.01	.0048	.0003	.002	.030		.3117
W150X37.1		.80	54800	68400	24.00		.001			.0063		2.64	.1373
009.1440m			378	472	9 Pc(s)	6,750 lbs	Customer PO: SAV-35466			BoL#: 1854015			
W6X25	2511522	.82	56100	68100	25.00	.07	1.04	.009	.019	.23	.08	.04	.26
035' 00.00'	A992-22		387	470		.05	.01	.0054	.0003	.002	.030		.3082
W150X37.1		.82	55700	68200	25.00		.001			.0059		2.59	.1394
010.6680m			384	470	8 Pc(s)	7,000 lbs	Customer PO: SAV-35466			BoL#: 1854015			

Elongation based on 8" (20.32cm) gauge length. 'No Weld Repair' was performed. 'All mechanical testing is performed by the Quality testing lab, which is independent of the production departments'

CI = 26.01Cu+3.88Ni+1.20Cr+1.49Si+17.28P-(7.29Cu*Ni)-(9.10Ni*P)-33.39(Cu*Cu)
Pcm = C+(Si/30)+(Mn/20)+(Cu/20)+(Ni/60)+(Cr/20)+(Mo/15)+(V/10)+5B
CE1= C+(Mn/6)+((Cr+Mo+V)/5)+((Ni+Cu)/15)
CE2 = C+((Mn+Si)/6)+((Cr+Mo+V+Cb)/5)+((Ni+Cu)/15)

Nucor certifies that the contents of this report are accurate and correct. All test results and operations performed by the material manufacturer are in compliance with material specifications, and when designated by the Purchaser, meet applicable specifications.

(State of South Carolina
(County of Berkeley
Sworn and subscribed before me
_____ day of _____

Emma Summers
Metallurgist/
Quality Control

Customer Name: SAVANNAH TANK & EQUIPMENT CO
Customer PO#: 40299 *NO FRIDAY DELIVER
Shipper No: 224171
Heat Number: 2511602

ACCEPTED
BY JR DATE 12/11/25

Emma Summers

Job: 089-25 PO: 40299 Line: 005 HT: 2511602