CERTIFICATE MATERIAL TEST REPORT

(DIN 50049.1 / EN 10204 3.1 / ISO 10474 3.1)

ISO 9001:2015

CAS METAL CO., Ltd.
32, Saenggogsandan 2-ro,
Gangseo-gu, Busan, Korea
Tel : 051-941-1127 Fax : 051-941-1128

CERTIFICATE No. : CAS250605-01
CUSTOMER : NORCA INDUSTRIAL LLC
MATERIAL : ASTM/ASME A/SA182F51/60(2023ED)
ORDER NO. : PO755-005068
PROJECT NAME : P.O. N8150
ISSUED DATE : JUN. 05. 2025.

Heat No.	Spec	CHEMICAL COMPOSITION (%)																Non-destructive examination ⑤		
		C	SI	Mn	P	S	Ni	Cr	Mo	V	Cu	Nb/Cb	Al	N				UT ⑤	N/A	-
	Min.						4.5	22.0	3.0					0.14				MT ⑤	N/A	-
	Max.	0.030	1.00	2.00	0.030	0.020	6.5	23.0	3.5					0.20				PT ⑥	N/A	-
E131792	H.A. ①	0.017	0.45	1.30	0.022	0.001	5.56	22.21	3.04					0.185				Dimension & Visual Inspection	GOOD	
	P.A. ①																			

BLANK

※ Remark

* Country of Origin : KOREA * Country of Melt & Pour : KOREA * NACE MR0175 AND MR0103

* ISO 9001 : 2015 * PED 2014 / 68 / EU. * CORROSION TESTED TO ASTM A262 PRACTICE E : No Defect

ARTICLES	Q'ty	MECHANICAL PROPERTIES	TENSILE TEST ④ (Ø12.5 x 50L)						Hardness Test	CHARPY IMPACT TEST(J)				BEND TEST
			Location ②	Temp.	Y.S.	T.S.	E.L.	R.A.	HBW	Temp. : 40 °F				Radius :
					N/㎟ (MPA)		%			Min. :				
		Lot No.		℃	MIN. 450	MIN. 655	MIN. 25	MIN. 45	MAX 220	Avg. : 1	2	3	AVG	Angle :
01) B16.5 150# SO RF 1/2"	50EA													
02) B16.5 150# SO RF 1"	50EA													
03) B16.5 150# SO RF 1-1/2"	50EA	CAS25-N24	T		491	686	42	63	162, 160	91	89	102	94	
04) B16.5 150# SO RF 2"	20EA													
05) B16.5 150# SO RF 2-1/2"	10EA													
06) B16.5 150# SO RF 3"	25EA		#1											
07) B16.5 150# SO RF 4"	50EA	Simulation P.W.H.T.	#2											
08) B16.5 150# SO RF 6"	25EA		#3											

BLANK

Heat Treament ④											
	Normalizing	°C	HRS		Tempering	℃	HRS		Quenching	℃	HRS
	Solution	1040 °C	6.0 HRS	W.C	Stablization	℃	HRS		Annealing	℃	HRS

☐ **Witnessed By**

☐ **Reviewed By**

We hereby certify that the material herein has been made and tested accordance with the above specification and also with the requirement called for by the above order.

CAS METAL Co., Ltd. QUALITY CONTROL DEPART

Manager of Quality Assurance Dep't

Notes
① - H.A. = Heat Analysis, P.A. = Product Analysis
② - location : L = Longitudinal Tr = Transverse T = Tangential R = Radial Treated S.R. = Stress Relieved
③ - Surface Condition : A.F. = As Forged R.M. = Rough Machined F.M. = Finish Machined
④ - A.C. = Air Cooled, F.C. = Furnace Cooled, W.C. = Water Cooled, O.C. = Oil Cooled
⑤ - UT = Ultrasonic Test, MT = Magnetic Test, PT = Penetrant Test

ACCEPTED

BY JC DATE 1/19/26

Job: 089-25 PO: 40301 Line: 003 HT: E131792