G.F., Survey No. 3009, Sheet No
NA 99, Dangarva Railway Station
Road,Beside Dangarva Railway Bridge,
Dangarva, Mehesana, Gujarat - 384450.
Phone : +91 98256 32757, +91 98198 81321
Email : sales@tubotechinc.com
Website : www.tubotechinc.com

ACCEPTED
BY JR DATE 1/14/26

TUBOTECH STAINLESS INC.

PED 2014/68/EU, ADW / AD 2000 - MERKBLATT W0
AN ISO 9001:2015 CERTIFIED COMPANY
Manufacturer of Stainless Steel Pipes & Tubes, U Tubes, Coil Tubes, Corrugated Tubes

TEST CERTIFICATE AS PER EN10204 3.1

Certificate No. :- TSI/TC/ 2025-26/077 Exp.128 | Date :- 10-04-2025

Work Order No.	128/2024-25 DTD. 13/03/2025	**Customer Order No**	152/005003 DTD: 07/03/2025	**Country of Origin**	India
Customer	M/s. NORCA INDUSTRIAL LLC				
Product	Duplex Cold Finished Seamless Pipes				
REF. QAP / ITP	---				
Supply Condition	Solution Annealed				
Specification	ASTM A790 / ASME SA790 of ASME SEC.II, PART A. EDITION 2024				
Tolerance	ASTM A790/ASME SA790, ASTM A999-24/ASME SA999				**HSN code**
Grade	UNS S32205	**Country of The Raw Material:**	India	**Steel Melting Process**	EAF/AOD 73044100

Sr. No.	Article No.	Customer Article No.	Size	Length	Supply Qty Qty. (Nos.)	FEET	Weight (mt)	End Finish
6	.....	.....	NPS 3 X SCH40S	17-24Feet	11	216.43	---	PLAIN

CHEMICAL COMPOSITION
(In Mass %) Acc: (ACC. TO A790 /ASTM E1086-22)

Sr. No.	Heat No.		C	Si	Mn	P	S	Ni	Cr	Mo	N	Other
		S	0.030 MAX	1.000 MAX	2.000 MAX	0.030 MAX	0.020 MAX	4.500 6.500	22.000 23.000	3.000 3.500	0.140 0.200	-- --
6	SD0113	H	0.022	0.360	1.550	0.020	0.007	4.800	22.140	3.022	0.160	..
		P	0.019	0.380	1.470	0.021	0.004	4.707	22.109	3.015	0.162	..

Sr. No.	Tensile Strength	Yield Strength	% Elongation	Flattening (A370)	Hardness (A370)	Intergranular corrosion	Eddy Current	PMI	Hydro Test (A999) Test Pressure Psi(g)	Holding Time (Sec.)	Visual & Dimensional Inspection
	Mpa	Mpa	G.L. 50mm				--				
	(655 MPa)	(450 MPa Min.)	25% Min.		(30HRC Max.)	--	--				
6	798.22	598.24	33.94	Passed	24,25,26 HRC	--	--	Passed	2500	10	Passed
	810.70	610.38	34.64								

Mechanical tests @ Room temperature (A370) | Non destructive tests

Heat treatement	SOLUTION ANNEALED IN CONTINUOUS FURNACE TEMPRATURE AT 1040-1100°C FOLLOWED BY WATER QUENCHING.
Marking	TUBOTECH NPS ___ X SCH_S X RANDOM LENGTH ASTM A790/ASME SA790 SEAMLESS PIPE UNS S32205 HEAT NO.____ PMI OK MADE IN INDIA
Inspection by	M/s. TUBOTECH STAINLESS INC
Additional Informations	MATERIAL CONFIRMS TO GENERAL REQUIREMENTS AS PER ASTM A999/ASME SA999

NOTE:- S= SPECIFICATION, P= PRODUCT ANALYSIS, H= HEAT ANALYSIS, G.L.= GAUGE LENGTH, LS=LONGITUDINAL SPECIMEN, LSW=LONGITUDINAL STRIP WIDTH

INSPECTOR'S/SURVEYOR'S SIGN	PO.STATUS:- COMPLETED	MANAGER (Q.A.)

TUBOTECH STAINLESS INC QA/QC

We hereby certify that material was manufactured, sampled, tested, and inspected in accordance with the requirements of the material specification and has been found to meet the requirements of the specification and order. Final products are 100% produced from Indian raw materials (Billets or Mother Hollows).

Job : 089-25 PO: 40301 Line: 009 HT: SD0113

Accredited as per ISO/IEC 17025 by NABL
CG METAL LAB LLP ®
Chemical & Mechanical Testing of Metals & Alloys
LLP-IN-ACH-8610
TC-5205
Unit-1 : 51,Shivam Estate, Phase-II, GIDC Chhatral, Ta. Kalol, Dist. Gandhinagar, Gujarat - 382729
M.: +91 96256 44061, 99258 55447 | E-mail : cgmetallab@gmail.com | Web site : www.cgmetallab.com

TEST REPORT

Issued To : Tubotech Stainless Inc.
SURVEY NO. 3009, beside dangarva railway bridge,
Dangarva, Mahesana, Gujarat, 384450

Report No. : ULR-TC520525000002450F
Date of Report : 01/04/2025

Letter Ref. No. & Date : NIL
Description : 3" N8 X SCH 40S, Heat No. SD0113
: Client Name: Norca Industrial LLC, PO No. 152/005003, Dt: 07/03/2025
Material Specification : ASTM/ASME A/SA 790 UNS S32205

Chemical Test Date of Sample Receipt : 01/04/2025 Date of Testing : 01/04/2025

Test Method : ASTM E 1086-22

	C	Si	Mn	P	S	Cr	Mo	Ni	N
Min. (%)						22.000	3.000	4.500	0.140
Max. (%)	0.030	1.000	2.000	0.030	0.020	23.000	3.500	6.500	0.200
Result	0.019	0.380	1.470	0.021	0.004	22.109	3.015	4.707	0.162

End Of Report

Remarks: Above Result Confirm as per Material Specification.

For, C G Metal lab
G.B.Vamaja (Q.M.) / C.R.Patel (T.M.)

Note: Sample(s) not drawn by C.G METAL LAB. This test report refers only to the samples submitted by the customer. The test report shall not be reproduced except in full, without written approval of the laboratory.