ATI
Specialty Rolled Products

500 Green Street
Washington, PA 15301

Certificate of Test

Noreen DeFerrari - Sr. Manager, Quality

Mill Information		Customer Information	
Cert Number	0276500-00	Name	ROLLED ALLOYS INC
Sales Order	50-075-211	PO	0238757-HOU
Cert Date	Aug-27-2025	PO Date	Jul-14-2025

Sold to: ROLLED ALLOYS INC
PO BOX 310
TEMPERANCE, MI 48182

Ship to: ROLLED ALLOYS INC.
9818 E. HARDY ROAD
HOUSTON, TX 77093

Material Information

"ATI 2205" DUPLEX STAINLESS STEEL
PMP HOT ROLLED PLATE ANNEALED PICKLED COMMERCIAL CUT EDGE

NACE MR0175/ISO 15156-3:2020
UNS S32205
ASTM-A-923-23 METHOD B
NACE MR0103/ISO 17945:2015
ASME SEC8-DIV1 UHA51 ED 2023 -58F
G8S-4001-51

UNS S31803
ASTM-A-923-23 METHOD A
ASTM-A-923-23 METHOD C
ASTM-A-240-25A
ASME-SA-240 ED 2023
10/14/20 EXCEPTIONS G8S-4001-51

ACCEPTED
BY JC DATE 12/18/25

Piece Information

Pcs	Gauge (in)	Width (in)	Length (in)	Heat #	Piece ID	Section Id	Lot #	Total Wt (lbs)
Item: 001	Cust-Id: 0010194 Cust-Job:				Govt-Contract-#: ScheduleB:		Govt-DO-Rating:	
1	.2500	96.0000	240.0000	867216	CH88719	0740296US	551187	1786
1	.2500	96.0000	240.0000	867216	CH88721	0740299US	551187	1786
1	.2500	96.0000	240.0000	867216	CH88722	0740300US	551032	1786
1	.2500	96.0000	240.0000	867216	CH88723	0740301US	551032	1786
1	.2500	96.0000	240.0000	867216	CH88724	0740302US	551032	1786
1	.2500	96.0000	240.0000	867216	CH88725	0740304US	551032	1786
1	.2500	96.0000	240.0000	867216	CH88726	0740305US	551032	1786

Chemistry Testing

Element (wt %)	Requirements Min	Requirements Max	Final Heat Analysis 867216	Loc
C	---	.030	.024 ✓	BN
MN	---	2.00	1.72 ✓	BN
P	---	.030	.025 ✓	BN
S	---	.020	< .001 ✓	BN
SI	---	1.00	.48 ✓	BN
CR	22.0	23.0	22.3 ✓	BN
NI	4.50	6.50	5.34 ✓	BN

HEAT # 867216
TRACER # 0740301US

HEAT # 867216
TRACER # 0740300US

HEAT # 867216
TRACER # 0740299US

HEAT # 867216
TRACER # 0740296US

HEAT # 867216
TRACER # 0740305US

HEAT # 867216
TRACER # 0740304US

HEAT # 867216
TRACER # 0740302US

ALC720 08/28/2025 09:25:03

QA-DC-11/4/2025

Receiving Inspection
By: H.V
Date: 9/6/25

Job: 089-25 PO: 40302 Line: 001 HT: 867216

ATI Specialty Rolled Products	Certificate of Test	Noreen DeFerrari - Sr. Manager, Quality
500 Green Street Washington, PA 15301	**Mill Information**	**Customer Information**
	Cert Number: 0276500-00	Name: ROLLED ALLOYS INC
	Sales Order: 50-075-211	PO: 0238757-HOU
	Cert Date: Aug-27-2025	PO Date: Jul-14-2025

Chemistry Testing

Element (wt %)	Requirements Min	Requirements Max	Final Heat Analysis 867216	Loc
MO	3.00	3.50	3.11 ✓	BN
N	.14	.20	.17 ✓	BN
PRW	30.0	40.0	35.5	--

ATI Flat Rolled Products performs chemical analysis by the following techniques for testing locations TC, BN, & LO: C & S by combustion/infrared absorption per ASTM E1019; N & O by inert fusion/thermal conductivity per ASTM E1019; Mn, P, Si, Cr, Ni, Mo, Cu, Cb(Nb), Co, V, W by WDXRF per ASTM E572; Pb, Bi, Ag, Se, Sb by GFAA per ASTM E1184; Al and Ti (>=0.10%) by WDXRF per ASTM E572 otherwise by OES per ASTM E1086; TA, Zn, Mg, Cd, Ce, Ca, Zr, La by ICP per ASTM E1479.

867216 - Material was produced by EF melting with AOD refining.
USA melted, poured and manufactured
Material melted at ATI FRP Brackenridge (FRPB)

FRPB - ATI FRP BRACKENRIDGE 100 River Road Brackenridge, PA 15014

PRW = Cr + (3.3 x Mo) + (16 x N) + (1.65 x W)

Mechanical Testing

		LOT 551032		LOT 551187	
Condition:		ANNEALED		ANNEALED	
Direction:		TRANSVERSE		TRANSVERSE	
Temperature:		ROOM TEMP		ROOM TEMP	
Spec:					
Test Limit	Units	Result	Loc	Result	Loc
YS 0.2% OFFSET	psi	86400. ✓	TC	84200. ✓	TC
TENSILE	psi	110800. ✓	TC	110900. ✓	TC
ELONG. IN 2"	%	34. ✓	TC	32. ✓	TC
RED OF AREA	%	53.	TC	49.	TC
HARDNESS	---	245. ✓ HBW	TC	241. ✓ HBW	TC

When hardness is measured using the Brinell scale, the indentation measuring device is Type A.

ALC720 08/28/2025 09:25:03

ATI Specialty Rolled Products	Certificate of Test	Noreen DeFerrari - Sr. Manager, Quality
500 Green Street Washington, PA 15301	**Mill Information**	**Customer Information**
	Cert Number: 0276500-00	Name: ROLLED ALLOYS INC
	Sales Order: 50-075-211	PO: 0238757-HOU
	Cert Date: Aug-27-2025	PO Date: Jul-14-2025

Mechanical Property Requirements

Condition:		ANNEALED	
Direction:		TRANSVERSE	
Temperature:		ROOM TEMP	
Spec:			
Test Limit	**Units**	**Min**	**Max**
YS 0.2% OFFSET	psi	65000.	---
TENSILE	psi	95000.	---
ELONG. IN 2"	%	25.	---
RED OF AREA	%	---	---
HARDNESS	---	---	270. HBW

Toughness Testing

ID:		LOT 551032		Requirements		LOT 551187		Requirements	
Condition:		ANNEALED		ANNEALED		ANNEALED		ANNEALED	
Direction:		T-L (Y-X)		T-L (Y-X)		T-L (Y-X)		T-L (Y-X)	
Temperature:		-050C		-050C		-050C		-050C	
Spec:		ASTM E23		ASTM E23		ASTM E23		ASTM E23	
Sample Size:		10 mm x 5.0 mm		10 mm x 5.0 mm		STD COMPACT		STD COMPACT	
Test Limit	**Units**	**Test Result**	**Loc**	**Min**	**Max**	**Test Result**	**Loc**	**Min**	**Max**
Impact Energy	ft-lb	47,49,48	PE	26.	---	60,62,54	PE	40.	---
Avg Impact Energy	ft-lb	48	PE	---	---	59	PE	---	---
Lateral Expansion	mils	57,54,58	PE	15.	---	72,68,68	PE	15.	---

Corrosion Testing

Test ID	Result Name	Test Result	Wt Loss	Units	Visual Exam	Pit Depth	Units	Bend	Loc	Requirements
551032 LOT	ASTM A923 ME C	PASS	0.	mdd	---	---	---	---	TC	10. max
551187 LOT	ASTM A923 ME C	PASS	0.	mdd	---	---	---	---	TC	10. max

ALC720 08/28/2025 09:25:03

ATI Specialty Rolled Products	Certificate of Test	Noreen DeFerrari - Sr. Manager, Quality
500 Green Street Washington, PA 15301	**Mill Information**	**Customer Information**
	Cert Number: 0276500-00	Name: ROLLED ALLOYS INC
	Sales Order: 50-075-211	PO: 0238757-HOU
	Cert Date: Aug-27-2025	PO Date: Jul-14-2025

Metallography - General

Test ID	Result Name	Condition	Test Result	Loc	Requirements
551032 LOT	% FERRITE	ANNEALED	48.	PE	40. min 60. max
551187 LOT	% FERRITE	ANNEALED	48.	PE	40. min 60. max
551032 LOT	ASTM A923 ME A	ANNEALED	PASS	TC	---
551187 LOT	ASTM A923 ME A	ANNEALED	PASS	TC	---

Material is free from detrimental intermetallic phases and precipitates.

Certification Statements

Grade verification was performed spectroscopically.

EN 10204:2005 - 3.1 Certificate does not imply that material is an approved PED grade. For a complete listing of approved PED grades, visit our website at www.atimaterials.com.

Material was solution annealed in the range 1950 - 2010F (1066 - 1099C) for a time commensurate with thickness and water quenched or for product under 1/4" thick, rapidly cooled with air or water.

ATI Specialty Rolled Products has complied with all producer requirements of AS6279.

ATI Specialty Rolled Products does not use mercury in the testing or production of its products.

No welds/weld repairs performed.

The following test methods are used by the listed lab: ASTM E8 for all specimens for yield, tensile, and elongation except ISO 6892-1 for 80mm specimens; ASTM E290 for bend (for New Bedford Laboratory - Type 2 Free bend is used), ASTM E112 for grain size; ASTM E10, E18, E92, & E384 for hardness; ASME B46.1 Section3 for surface roughness; AMS 2750 for laboratory heat treatment, ASTM E139 for stress rupture; ASTM E29 for rounding; ASTM E3 and E407 for metallographic preparation and etching.

ATI SRP products have not come in contact with radioactive materials during manufacturing or processing.

EN 10204:2005 3.1 Certificate.

General Statements

The Finishing Location for ALL PIECES is ATI-SRP
The Shipping Location is ATI-SRP WASHINGTON , PA

ATI Specialty Rolled Products	Certificate of Test	Noreen DeFerrari - Sr. Manager, Quality
500 Green Street Washington, PA 15301	**Mill Information**	**Customer Information**
	Cert Number 0276500-00	Name ROLLED ALLOYS INC
	Sales Order 50-075-211	PO 0238757-HOU
	Cert Date Aug-27-2025	PO Date Jul-14-2025

General Statements

TESTING WAS PERFORMED AT THE FOLLOWING LOCATIONS
BN = ATI SRP Brackenridge; 100 River Road; Brackenridge, PA 15014
PE = PRODUCT EVALUATION SYSTEMS; 637 Donohoe Road; Latrobe, PA 15650
TC = ATI SRP Natrona Heights; 1300 Pacific Avenue; Natrona Heights, PA 15065

Knowingly and willfully recording any false, fictitious or fraudulent statement or entry on this document may be punished as a felony under Federal Statutes, including Federal Law, Title 18, Chapter 47.

WARNING: Processing that makes fumes, dust, or solutions may cause lung disease. Please see Safety Data Sheet for further information which has been supplied to your Purchasing Department. For an additional copy, please refer to our website at:
www.atimaterials.com/Products/ati-sds

For access to online Certifications of Test, please register at MyATI.ATIMaterials.com.

This Certified Material Test Report is a true representation of the data on file. The reported results conform to the sales contract and specification(s) as set forth in ATI Specialty Rolled Products order acknowledgement. This Certificate of Test may not be reproduced except in full without the written authorization of the company.

ATI Specialty Rolled Products website contains listing of material produced, general technical and contact information, and current quality and company accreditations including but not limited to ISO-9001, AS-9100, Nadcap, and ISO/IEC 17025. Please visit us at www.atimaterials.com.